

Completely Revised and Updated

UNDERSTANDING WOOD

A CRAFTSMAN'S GUIDE TO
WOOD TECHNOLOGY



UNDERSTANDING WOOD

A CRAFTSMAN'S GUIDE TO
WOOD TECHNOLOGY

"Clearly the best book available on the subject."

—Wooden Boat

Understanding Wood answers every woodworker's question: Why does wood do what it does? Updated to include new information on composite materials, adhesives, and finishes developed in the past 20 years, this completely revised classic has everything you need to know about wood technology. R. Bruce Hoadley, reknowned wood technologist, explores the nature of wood and its properties, the basics of wood technology, and the woodworker's raw materials. You'll learn the best ways to cut, season, machine, join, bend, fasten, and finish wood, and explore the crucial interaction of wood and moisture. You'll also find the latest on wood products and where to buy them.

Everyone who works with wood—craftsmen, builders, engineers, and designers—should own this completely revised version of the classic

Understanding Wood.

UNDERSTANDING WOOD

A CRAFTSMAN'S GUIDE TO
WOOD TECHNOLOGY



UNDERSTANDING WOOD

A CRAFTSMAN'S GUIDE TO
WOOD TECHNOLOGY

*To my family—
my wife, Barbara, and my daughters, Susan and Lindsay—for understanding.*

ACKNOWLEDGMENTS

As I stated in the first edition, the idea and approach for a book of this type came originally from the many students I have worked with over the years, especially those in craft workshops, short courses, and seminars. Their many questions, discussions, reactions, and frequent suggestions to put it all down on paper were the impetus to get me started. For his encouragement to begin the writing and for his support throughout the first edition, I owe special thanks to Dr. Donald R. Progulske, head of the Department of Forestry and Wildlife Management at the University of Massachusetts, Amherst. Twenty years later, in considering a second edition I again was pleased to have the strong support of Dr. William McComb, current head of our department, now renamed the Department of Natural Resources Conservation.

Teaching is in itself an education, and since the first edition, meeting with students in my classes has helped me to rethink, revise, reshape, and update many of the fundamentals of the book and the way I present them. I thank my students once again for their role, even though they may not realize the important feedback they have provided. My faculty colleagues and close friends, Paul Fiset, David Damery, and Dr. Stephen Smulski, have been a continuous source of information, always willing to share their expertise. Emeritus faculty of our department, Dr. Alan A. Marra and Dr. William W. Rice, have also contributed critical information for this second edition related to their respective specialties of wood adhesives and wood drying. Daniel Pepin was invaluable in locating and machining many of the

wood specimens for photography. I am also indebted to Cowls Building Supply, Inc., of North Amherst, Massachusetts, for its contribution of lumber items for photography and for permission to take photographs at its store and mill.

Much of the technical data on physical and mechanical properties of wood as well as some of the illustrations were reproduced or adapted from the *Wood Handbook* and other publications of the U. S. Forest Products Laboratory at Madison, Wisconsin. During visits to the laboratory and in correspondence, members of the staff were always helpful and cooperative.

During the early stages of production, my daughter Lindsay gave me the long hours of assistance needed in proofreading the scanned text of the first edition. She was also my personal editor when I needed help with grammar, when an awkward sentence needed rewriting, or when a complicated paragraph needed rearranging. A major feature of the second edition is the color photography, for which Randy O'Rourke accomplished his camera magic with dedication and patience and brought life to the many wood specimens and objects. Randy's photographs blend nicely with many taken previously by Richard Starr and Brian Gulick. Once again, the electron micrographs by Wilfred Cote are an important piece to understanding wood,

An author discovers that a book could not materialize without extensive professional support. Among the many that made this edition a reality were consulting editors Aime Fraser and Diane Sinitsky, and Jennifer Renjilian, Carolyn Mandarano, and Lynne Phillips at The Taunton Press.



CONTENTS

<i>preface</i>	3
<i>Forword</i>	4

PART ONE THE NATURE OF WOOD AND ITS PROPERTIES

1 The Nature of Wood	6	Bending theory	87
Growth rings	10	The carrying capacity and stiffness of beams	90
Grain	10	Factors affecting strength properties	94
Sapwood and heartwood	11	Compression failures and brashness	99
Structural arrangement of growth		Structural grades	100
rings and rays	12	5 Other Properties of Wood	102
Density and specific gravity	14	Thermal conductivity	103
Systematic classification	16	Effect of temperature on wood	104
Cellular structure	17	Burning of wood	104
Softwoods	18	Fluorescence	105
Hardwoods	20	Psychological properties	107
2 Figure in Wood	24	6 Water and Wood	110
Knots	32	Free water and bound water	112
Abnormal wood	36	Equilibrium moisture content	112
Fungi	40	Green vs. air-dried vs. kiln-dried	114
Insect damage	44	Dimensional change in wood	116
Wood Identification	46	Estimating shrinkage and swelling	118
What to look for	50	Uneven shrinkage and swelling	123
Physical properties	52	PART TWO	
identification techniques	52	BASICS OF WOOD TECHNOLOGY	
Macrophotographs	55	7 Coping with Dimensional Change	
4 Strength Of Wood	74	in Wood	132
Compression parallel to the grain	78	Preshrinking	133
Compression perpendicular to the grain	80	Control of moisture sorption	133
Tension perpendicular to the grain	83	Mechanical restraint	134
Tension parallel to the grain	84	Chemical stabilization	136
Shear perpendicular to the grain	85	Design	139
Shear parallel to the grain	85	Monitoring moisture	141
		The moisture "widget"	145

8 Drying Wood	146	PART THREE	
How wood dries	148	THE WOODWORKER'S RAW MATERIALS	
The dry kiln	149		
Drying your own wood	151	1 3 Lumber	212
Storing lumber	156	Lumber measure	216
		Lumber classification and grading	218
9 Machining and Bending Wood	158	1 4 Veneer and Plywood	224
Machining wood	159	Plywood	229
Bending solid wood	177	Classes of plywood	230
1 0 Joining Wood	180	1 5 Composite Panels	234
The elements of joints	181	Particleboard	235
Basic types of joints	183	Wafer- and strand-based panels	236
Worked joints	183	Fiber-based panels	236
Fastened joints	188	1 6 Engineered Wood	240
1 1 Adhesives and Gluing	192	Finger-jointed lumber	241
Adhesive joints	193	Glulam	242
Gluing fundamentals	194	Structural composite lumber	243
		I-joists	244
1 2 Finishing and Protecting Wood	198	1 7 Finding Wood	246
Surface condition	199	Trees	247
No treatment	202	Recycling used wood	249
Coating treatments	205	Local sawmills	250
Penetrating finishes	206	Lumberyards	251
Combinations and compromise	207	The woodworkers' retail outlets	252
Slowing moisture exchange	207	Industrial arts teachers	253
Evaluation of finished surfaces	209	Magazines	253
Preservative treatment of wood	209	Specialty woods	253
		The Yellow Pages and other listings	253
		Internet	253
		Lumbermen	253
		<i>Afterword: Forests past and future</i>	254
		<i>Appendix 1: Commercial names for lumber</i>	257
		<i>Appendix 2: Finding the specific gravity of wood</i>	260
		<i>Glossary</i>	262
		<i>Bibliography</i>	272
		<i>Index</i>	275

TABLES

Table 1.1	Usages of the word "grain" in woodworking.	11	Table 12.1	Moisture-excluding effectiveness of various finishes on ponderosa pine.	208
Table 1.2	Number of rings in the sapwood of some hardwoods.	12	Table 12.2	Penetration of the heartwood of various softwood and hardwood species.	210
Table 2.1	Comparative resistance of heartwood to decay.	44	Table 13.1	Abbreviations of common lumber terms.	214
Table 3.1	Part of a typical identification key.	54	Table 13.2	Standard American sizes for construction lumber.	217
Table 4.1	Strength properties at 12% MC of some commercially important woods grown in the United States.	79	Table 13.3	Lumber classification based on use, degree of manufacture, and size.	218
Table 4.2	Comparison of highest and lowest average clear wood strength properties among the principal species of southern yellow pine.	101	Table 13.4	Minimum requirements for grading factory hardwood lumber.	219
Table 5.1	Approximate thermal properties for various materials.	103	Table 13.5	Some major lumber-grading associations and the species under their jurisdiction.	221
Table 5.2	Partial list of North American woods exhibiting noteworthy fluorescence under ultraviolet light.	106	Table 13.6	Grades and sizes of dimension yard lumber as designated by the American Lumber Standards Committee.	222
Table 6.1	Average green moisture content of common wood species.	115	Table 14.1	The APA-The Engineered Wood Association classification of plywoods.	230
Table 6.2	Approximate shrinkage as a percent of green dimension, from green to oven-dry moisture content.	117	Table 14.2	Categories of commonly used species for hard wood plywood based on specific gravity ranges for oven-dry weight and volume at 12% moisture content.	231
Table 6.3	Tendency to warp during seasoning of various woods.	123	Table 14.3	Face grades of hardwood plywood.	233
Table 7.1	Suggested soaking time in PEG-1000 for walnut disks.	137	Table 15.1	Standards for particleboard developed by the National Bureau of Standards (Commercial Standard CS 236-66).	236
Table 8.1	Wood dries from the surfaces inward, shrinks differentially, and develops stress.	147	Table 15.2	Strength and mechanical properties of fiberboards.	239
Table 8.2	Approximate time to air-dry 4/4 lumber to 20% MC.	156			
Table 8.3	Suggested salts for controlling relative humidity in closed containers.	157			

FOREWORD

PREFACE TO THE FIRST EDITION

The properties and characteristic qualities of the timber available are so numerous and important, and yet so little understood generally, that I am induced by solicitations of many friends to give, in these pages, information respecting them.

A handy-book on timber is, in the opinion of many, much required. The botanical treatises which are accessible are too strictly scientific in their form and treatment to interest the general reader, and they lack that practical application of knowledge to the wants of the shipwright and carpenter, which is one of the aims of this book to give.

I wish I had written those words, for they summarize perfectly the reasons why I have written this book. But they were, in fact, written in London in the year 1875 by Thomas Laslett, timber inspector to the Admiralty of the British Empire, in his book. *Timber and Timber Trees*.

Like Laslett, I have written my book for woodworkers. but this is not a book about woodworking. Rather, it is about wood itself, surely mankind's first workable material, and an ever-present part of our ever-changing world. We are not likely to run out of wood, because unlike most other materials, we can always grow more. And the more we learn about it, the more there is to know. A look at what else Laslett wrote in his book will make this clear.

Laslett believed, for example, that sap collected between the bark and the wood eventually congealed to form a new growth ring. He could not know about cellular reproduction and the additive formation of new wood cell by cell. Laslett deduced that trees grew taller because the bark squeezed the sap, forcing it upward. Today, with a microscope, we can see cells building sideways in the cambium layer, and twigs growing longer by cellular division. Lest we be tempted to smugness, however, we should imagine how primitive our scientific knowledge might look a hundred years from now.

The main reason I have attempted this book is the realization that a wealth of knowledge about wood has been accumulated by scientists, but almost none of it has been translated and interpreted for the individual craftsman. Working from scientific principles, technology is routinely developed by commercial and academic agencies but mainly shared among themselves in highly technical textbooks and obscure journals. The technology of industrial-scale woodworking has been well developed and widely published. But the same scientific principles have yet to be applied to the small-scale woodworking shop, whether that of the serious amateur, the independent cabinetmaker, or the artist/craftsman. For example, volumes have been written on how to dry lumber in carload quantities, yet it is almost impossible to find guidance when drying the boards cut from a single tree, or when drying a single board,

Much of what has been written about the craft of woodworking is reduced to sets of instructions of directions relative to tools and procedures, without any supporting information about the material itself. These how-to books commonly assume that all conditions relative to the wood are under control, or else they dismiss the point with an airy instruction such as, "Get some suitable hardwood of appropriate quality and dryness." Yet, for a person to pursue a craft with success, knowledge and understanding of the material must develop along with manual skill,

I also feel compelled to attack the mountains of misinformation available and commonly accepted by woodworkers. Most of it comes innocently from the misinterpretation of observations. For example, one book on sculpture states that bright light makes wood check, a conclusion reached when cracks appeared in wood brought up from a dark (and probably damp) cellar into daylight (and drier air). Another says that wood cups because its annual rings try to straighten out as it dries—a correct observation of the direction of cupping, but pure guesswork as to its cause. Tradition carries along such misleading terms as "dry rot" and such misconceptions as "wood has to breathe." Dry wood will not decay, nor does wood breathe in the animal sense. Wood doesn't eat either, and it doesn't require feeding with furniture polish.

My strategy has been to begin with the tree, to examine the wood as the cellular product of the tree's growth. I have given special attention to wood-moisture relationships and dimensional change before going on to physical properties, strength in particular. Then I have tried to analyze such everyday woodworking operations as machining, bending, joining, and finishing in terms of the wood's physical and biological nature. It is my hope that the examples I have given can serve as models for readers in analyzing problems that arise in their own woodworking endeavors.

I also hope that this book will encourage craftsmen to delve further into the literature of wood science and technology, and to help them do so I have included an annotated list of references. Frequently, what makes technical literature opaque to the layman is its terminology. Therefore, against the wishes of some who would have me avoid scientific terms and "say it in simple words," I have tried to present and explain the standard terminology throughout the book, and I have included a detailed glossary. The serious woodworker will find that it is important to know that *rake angle* and *hook angle* have nothing to do with gardening or fishing, and that *terminal parenchyma* is not a horrible disease.

I suppose every author wonders when a book actually began—for me, it goes back more than 50 years. I grew up in the Connecticut countryside where the surrounding woodlands were both playground and the source of material for "making stuff." The cellar of our house had an old workbench and chests of grandfather's tools, worn from years of use but begging for the chance once again to work miracles in wood. My earliest memories include climbing a wobbly stool to get on the workbench to turn on the light, the screech of the huge square-threaded screw of the vise, and lifting the heavy lid of the toolchest to stare at the mysteries within. I recall more trouble than triumph from my early years of woodworking experiments. I remember nails that bent over when driven into oak, saws that bound up tight in green wood, screws twisted off when driven without pilot holes, and planed surfaces ridged by nicks in the iron. But I still "made stuff—my frustrations were nothing compared to my fascination with wood.

I'll never forget the first time I saw a chain saw in operation. It was at a late-summer farm-equipment demonstration, when I was in my early teens. The farmers and loggers all watched in amazement as the saw bar melted through a 12-in. oak log in a matter of seconds, effortlessly taking slice after slice. It was quite a machine.

But I was not watching the raucous machine. I stood transfixed *by* those marvelous disks of wood, a dozen or more, that *la* in the grass and sawdust. The demonstration over, the entire crowd followed the saw operator back to his table to learn more about the machine,

Except me. I was excitedly stacking up as many of the wooden disks as I could carry. They were red oak, creamy sapwood and medium brown heartwood, just tinged with peach. As I staggered through the goldenrod toward my father's car, they were unbelievably heavy. I still recall the vivid pattern of the rings, their pie-crust of bark, the cool dampness of the top disks under my chin, the pungent odor of the wood. The aching in my arms was a tiny price to pay for the unending array of things I would make from such a magnificent product of nature: lamp bases, clock faces, desk sets, picture frames.... I could not believe that woodworkers had not already put this beautiful natural log to better use.

My next recollection is of having the disks safely home and proudly lined up along the wall shelf in our cellar workshop. I probably realized that some sort of drying would be necessary, but that could wait. I was content just to admire my treasure.

I am sure you already know the sad ending. By the following morning, the brilliant end grain had faded to a lifeless sandy color. In the days that followed, my castle of hope crumbled as the first few hairline cracks in the sapwood grew- and reached toward the pith. Soon each disk had a gaping radial crack. In final mockery, even the bark fell off.

But why?

It is easy for me to believe that this one incident was the turning point that eventually led me to pursue my career as a wood technologist, for ever since I have wanted to know why the wood does what it does. I have been lucky enough to make some progress in my quest, and I have been able to share in the classroom some of what I have learned. Now I hope my book helps craftsmen understand wood, too.

— R. Bruce Hoadley, April 1980



Figure 1.1 • For all our familiarity with trees, we are hardly aware of the awesome complexity of their internal structure. Understanding this structure is basic to successful woodworking.
(Photo by R. Bruce Hoadley)

THE NATURE OF WOOD

Wood comes from trees. This is the most important fact to remember in understanding the nature of wood. Whatever qualities or shortcomings wood possesses are traceable to the tree whence it came. Wood evolved as a functional tissue of plants and not as a material designed to satisfy the needs of woodworkers. Thus, knowing wood as it grows in nature is basic to working successfully with it.

Since prehistoric times, man has used the beauty and economic value of trees in commerce and art as well as for shelter and furnishings, and one is tempted to discuss at length the virtues of these noble representatives of the plant kingdom. But since our goal is to understand wood, we will concentrate on the functional and physical aspects of trees rather than on their aesthetic aspects. We must consider the tree on a number of levels—from the entire plant down to the individual cell.

At the microscopic level, understanding cell structure is the key to appreciating what happens when wood is sanded across the grain, why stain penetrates unevenly, and why adhesives bleed through some veneers but not others. But to understand where feather grain is to be found, to visualize a knot's internal structure based on its surface appearance, and to anticipate which boards are susceptible to decay, it is necessary to examine the structure of the entire tree as a living organism (*Figure 1.1*). So this is a logical starting point.

Despite their wide diversity, all trees have certain common characteristics (*Figure 1.5*). All are vascular, perennial plants capable of secondary thickening, or adding yearly growth to previous growth. The visible portion of the tree has a main supporting **stem** or **trunk**. If large enough for conversion into sawtimber or veneer, the trunk is often termed the **bole**. The trunk is the principal source of wood used by woodworkers, although pieces having unusual beauty and utility also come from other parts of the tree. The trunk has limbs, which in turn branch and eventually subdivide into twigs. This subdivision, carrying the leaves or foliage, is collectively termed the **crown**.

But a casual glance hardly reveals the awesome complexity of the internal structure of these impressive plants. One can begin an acquaintance by exposing a crosswise surface of a tree trunk (*Figure 1.2*). At the periphery of the log




Figure 1.2 • Stem cross sections (top) and detail (bottom) show gross and fine structures of a typical softwood, red pine (*Pinus resinosa*), and a typical hardwood, northern red oak (*Quercus rubra*). In red pine, narrow rays are too small to be seen without magnification, while portions of the large rays in the red oak are visible to the naked eye. (Photos by Randy O'Rourke)

surface, the bark layer is easily recognized. Within the bark and comprising the bulk of the stem is the wood, characterized by its many growth rings concentrically arranged around the central pith. Between the bark and the wood is the cambium, a microscopically thin layer of living cells with protoplasm in their cell cavities.

The tree stem parts are accumulations of countless cells. The cell is the basic structural unit of plant material. Each cell consists of an outer cell wall surrounding an inner cell cavity. Within some cells, there is living protoplasm, while others are nonliving and contain only sap or even some air space.

Typically, wood cells are elongated. The proportion of length to diameter varies widely among cell types, from short barrel shapes to long, needlelike cells. The majority of wood is composed of longitudinal cells, whose axes are oriented vertically in the tree stem. The largest cells, as found in woods such as chestnut and mahogany (Figure 1.3), are visible to the unaided eye, but in most species they are too small to be seen without magnification.

Scattered through the wood are groups of cells whose axes are horizontal. These groups extend radially outward from the pith and are therefore called rays. Rays are like flattened ribbons of cells stretched horizontally in the tree, with the plane of the ribbon vertical (Figure 1.4). Rays provide horizontal conduction of sap in the tree, and some ray cells can store carbohydrates until needed by other cells such as newly formed cells in the process of development. The size of rays varies according to the number of cells contained within them. Although individual ray cells and even the smaller rays are not visible to the eye, the largest rays of certain species, as in beech and oak, can be seen easily.



Figure 1.3 • The cells of mahogany are visible to the naked eye. In most species of wood, the cells are not as large and are visible only if magnified with a hand lens or microscope. (Photo by R. Bruce Hoadley)

Cells of similar type or function are collectively referred to as tissue, so we may refer to wood tissue or bark tissue. Bark and wood are both permanent tissues because once formed and matured, their cells retain their shape and size. The cells of certain reproductive tissues (termed meristems or meristematic tissue) can divide to form new cells. The cell division is responsible for elongation of the tree's growing points. The pith cells at the center of the stem left in the path traveled by the apical meristem. All furl growth of the tree is the result of thickness growth produced by division of the cambium, a lateral meristem.

Although apparently static, the tree has an amazingly dynamic internal system during the growing season (Figure 1.5). Water from the soil, carrying nutrients, enters the roots and moves upward through the wood cells to the leaves. Much of this water evaporates through the leaf surfaces; this transpiration helps cool the foliage. In addition, the leaves perform the supreme miracle of plants, photosynthesis whereby water from the soil is combined with carbon dioxide from the atmosphere, catalyzed by chlorophyll, and energized by sunlight. This process has a double dividend. First, it adds oxygen to the air while removing carbon dioxide. and second, it produces a basic sugar ($C_6H_{12}O_6$) for the tree's own use. The sap (i.e., the water in the tree plus any dissolved nutrients or other materials) carries this sugar down through the inner living bark to where it is used to build new cells in the cambium layer.

The cambial cells have extremely thin primary walls and during the growing season their contents are quite watery. As a result, this layer is very fragile, and usually bark can be peeled away quite easily from a freshly cut log.



Figure 1.4 • Rays are formed by groups of cells that are oriented horizontally. They are not visible in most softwoods, but in some hardwoods, such as this oak, they can be striking. (Photo by R. Bruce Hoadley)




Figure 1.5 • Though apparently static, a tree has a dynamic internal system during the growing season. Water from the soil moves up from the roots to the leaves, bringing moisture and nutrients. Much of this water evaporates to cool the foliage through transpiration. Carbon dioxide from the air and water from the leaves combine with chlorophyll to produce sugar (with oxygen as a by-product). The remaining water and nutrients combine with the sugar to form sap, which flows down through the inner living bark.

(Figure 1.6). During the winter dormant season, however, the cell contents thicken. The cambial layer stiffens and becomes less vulnerable to mechanical damage, and if the tree is cut the bark typically remains firmly attached.

This fact may be quite important to woodworkers. If stem cross sections are being prepared for coasters or clock faces, for example, where retaining the bark is desired, the tree should be harvested during dormancy. If, on the other hand, a product such as peeled poles for a log cabin is desired, they best be cut during the growing season to permit easy separation of the bark. The bark might actually have to be carved off if the tree is cut during the dormant season.

In the cambium, "mother" cells reproduce by dividing lengthwise. Of the two "daughter" cells formed, one enlarges to become another cambial mother cell. The other




Figure 1.6 • Bark peels easily from summer-cut wood because the cambial layer is fragile during the growing season. Bark is much harder to remove from wood cut during the dormant winter season. (Photo by Richard Starr)

begins to mature into either a bark cell (if toward the outside of the cambium) or a new wood cell (if formed toward the inside of the cambium). Within about a week, the new wood cells begin to change. The wall of the cell on the inside of the cambium may elongate or enlarge or both, depending on the kind of wood cell it will eventually become.

When the developing daughter cells have attained their ultimate size and shape, a **secondary wall** is added to the inner surface of the fragile primary wall. This wall, which is permanent, becomes the dominant layer of the cell, and its formation fixes forever the cell size and shape: There will never be any change in cell type or dimension or in thickness of the cell walls. The secondary wall is built mainly of **cellulose***, long-chain molecules that are strong and stable. The cellulosic structure of the cell wall is further fortified by **lignin****, the material that characterizes woody plants.

During the last stages of this maturing process, most of the wood cells lose their living protoplasm and have only sap left in them. Some may still perform the function of conducting sap, even though they are no longer living. These cells, whose function is simply to support the tree and in some cases to conduct sap, are sometimes termed **prosenchyma**. In this newly formed **sapwood**, a small percentage of the cells, principally those found in the rays, retain their living protoplasm and can assimilate and store food. Such storage cells are termed **parenchyma**.

GROWTH RINGS

Activity of the cambium (i.e., growth) continues as long as environmental conditions are suitable and the tree is healthy. In the temperate climate that prevails in most of the United States, the characteristic annual cycle includes a growing season and a dormant season. In most trees, the nature of wood cell formation is similarly cyclic, resulting in visible **growth layers**. These increments are also called **growth rings**, or **annual rings**, when formed in association with yearly growth. These rings may vary in width as a charac-

* Cellulose molecules are long-chain polymers, that is, multiples of simpler molecules called monomers that are linked end-to-end. Cellulose has the general formula $C_nH_{10}O_5$, the subscript n indicating the number of monomer units linked together to form the polymer. In wood cellulose, n may be as high as 10,000, which would produce polymer lengths up to $1/\infty$ mm. The orientation of the long-chain cellulose molecules with the long axis of the cells accounts for many of the basic properties of wood. Comparison of chemical formulas suggests that the sugar produced by photosynthesis ($C_6H_{12}O_6$) is converted to the basic monomer of cellulose by the elimination of H_2O per monomer.

Lignin comprises about 25% of the wood's composition, but its exact chemical nature is extremely complex and not fully understood, principally because isolating it from wood changes it chemically.

teristic of the species and as a result of growing conditions (*Figure 1.7*). The distinctiveness of the growth ring in a particular species is determined by its cell structure, usually by the variation of cell diameter or cell-wall thickness or by the distribution of different types of cells.

Where there is visible contrast within a single growth ring, the first formed layer is termed **earlywood**, the remainder **latewood**. The terms **springwood** and **summerwood**, respectively, are also used to indicate these layers, but they are misleading in suggesting a correlation with the calendar seasons of the year. In woods having significant visual contrast between earlywood and latewood, the latewood typically has higher density. The transition from earlywood to latewood may be abrupt or gradual. In some species no separable earlywood and latewood portions are apparent. In some tropical areas, tree growth may continue without the interruption of seasonal dormancy, producing wood without apparent growth rings. However, growth rings may develop from intermittent growth due to variation in rainfall, independent of the yearly calendar.

GRAIN

No discussion of wood can proceed very far without encountering the word **grain**. There are more than 50 ways in which this word can be used in some 10 categories (*Table 1.1*). Each term is defined in the glossary, and each category will be dealt with as appropriate through the text.



Figure 1.7 • Each growth ring in southern yellow pine is distinct, showing a light, soft layer of earlywood followed by a darker, denser layer of latewood. The visual contrast between earlywood and latewood predicts a corresponding difference in hardness of the wood. (Photo by R. Bruce Hoadley)

TABLE 1.1 —Usages of the word "grain" in woodworking.**1. Planes and surfaces**

End grain	Longitudinal grain	Side grain
Face grain	Radial grain	Tangential grain
Long grain		

2. Growth-ring placement

Bastard grain	Plain grain	Side grain
Edge grain	Quarter grain	Slash grain
Flat grain	Radial grain	Tangential grain
Mixed grain	Rift grain	Vertical grain

3. Growth-ring width

Close grain	Dense grain	Narrow grain
Coarse grain	Fine grain	Open grain

4. Earlywood/latewood contrast

Even grain	Uneven grain
------------	--------------

5. Alignment of longitudinal cells

Across the grain	Dip grain	Spiral grain
Along the grain	Grain direction	Steep grain
Against the grain	Interlocked grain	Straight grain
Cross grain	Short grain	Wavy grain
Curly grain	Slope of grain	With the grain

6. Relative pore size

Closed grain	Fine grain	Open grain
Coarse grain		

7. Figure types

Bird's-eye grain	Fiddleback grain	Rift grain
Blister grain	Flame grain	Roey grain
Comb grain	Leaf grain	Silver grain
Crotch grain	Needle-point grain	Stripe grain
Curly grain	Quilted grain	Tiger grain
Feather grain		

8. Machining defects

Chipped grain	Raised grain	Torn grain
Fuzzy grain	Shelled grain	Woolly grain
Loosened grain		

9. Figure imitation

Graining	Woodgrain design
----------	------------------

10. Surface failure

Short in the grain

latewood. If a pronounced difference exists, the wood is said to have **uneven grain** (e.g., southern yellow pine) (*Figure 1.8*). If little contrast is evident, as in basswood, the wood is said to be **even-grained**. Intermediates can be indicated by compound modifiers such as fairly even (e.g., eastern white pine) or moderately uneven (e.g., eastern hemlock).

SAPWOOD AND HEARTWOOD

In twigs and small saplings, the entire wood portion of the stem is involved in sap conduction upward in the tree and is thus termed **sapwood**. Some nonliving prosenchyma cells are active in this conduction, and the living parenchyma cells also store certain components of the sap as food. As the tree develops, the entire trunk is no longer needed to satisfy the leaves' requirements for sap. In the center of the stem, nearest the pith, the prosenchyma cells cease to conduct sap and the parenchyma cells die. The sapwood is thus transformed into **heartwood**. The transition to heartwood is also accompanied by the formation in the cell wall of material called **extractives**.

To the woodworker, the most significant aspect of heartwood extractives is color, for the sapwood of all species ranges from whitish or cream to perhaps yellowish or light



Figure 1.8 • Uneven-grained woods like southern yellow pine (right) have visually prominent rings. In fairly even-grained woods like eastern white pine (left), the contrast between earlywood and latewood is not as pronounced. (Photo by Randy O'Rourke)

The term grain alone often describes the direction of the dominant longitudinal cells in a tree. Substituting the term grain direction adds clarification, because the word grain alone can be meaningless without an accompanying context. For example, the meaning is hardly clear in the statement, "The grain of this piece of wood is unsatisfactory."

It is appropriate here to introduce the word grain as used to indicate the degrees of contrast between earlywood and

tan (Figure 1.9). The dark, distinctive colors we associate with various woods—the rich brown of black walnut, the deep purple red of eastern redcedar or the reddish to black striping of rosewood—are the result of heartwood extractives. However, not all extractives are dark in color. Some trees, such as spruces, do not have pigmented extractives associated with heartwood formation. Colorless or nearly colorless extractives may nevertheless provide decay resistance, as in northern white-cedar.

Sapwood is not generally resistant to fungi, so any noteworthy decay resistance of a species is due to the toxicity of the extractives to fungi. Fungal resistance is therefore restricted to the heartwood portion of the tree.

Heartwood extractives may change the properties of the wood in other ways as well. In some species, they reduce the permeability of the wood tissue, making the heartwood slower to dry and difficult or impossible to impregnate with chemical preservatives. Extractives often make the heartwood a little denser than the sapwood and also a little more stable in changing moisture conditions. (Though when green, sapwood sometimes contains up to five times as much moisture as heartwood, and it may shrink more than heartwood because of its lack of extractives.) Extractive materials in the heartwood of some species may be so abrasive that they dull cutting tools, and they may contribute to the wood's surface hardness. But as sapwood becomes heartwood, no cells are added or taken away, nor do any




Figure 1.9 • Heartwood contains extractives, which are pigmented to some degree in most woods. The definite color change in this yellow-poplar clearly shows the heartwood/sapwood division. (Photo by Randy O'Rourke)

cells change shape. The basic strength of the wood is not affected by sapwood cells changing into heartwood cells.

As the girth of the tree increases with the addition of new sapwood, the diameter of the heartwood zone also expands proportionately (Figure 1.10). The width of the sapwood is characteristic for some species or at least relatively consistent (Table 1.2). For example, catalpa retains only 1 or 2 growth rings of sapwood. Black tupelo, on the other hand, retains 80 to 100. In mature tree stems of 3 ft. to 4 ft. dia., sapwood is commonly 1 1/2 in. to 2 in. wide in mature trees of eastern white pine and cherry but may be up to 6 in. wide in aspen, birch, and maple.

STRUCTURAL ARRANGEMENT OF GROWTH RINGS AND RAYS

Because of the arrangement of the layers of growth in the tree, as well as the vertical or horizontal orientation of the individual cells, it is appropriate to consider the structure of wood in three-dimensional terms (Figure 1.11).

One plane is perpendicular to the stem axis and is termed the **transverse plane**, or **cross-sectional plane**, typically observed at the end of a log or stump.

Because the tree cross section is analogous to a circle, a plane passing through the pith of the wood (as a radius of the circle) is called a **radial plane** or surface.

A plane parallel to the pith, but not passing through it, forms a tangent to the circular growth-ring structure and is termed a **tangential plane** or surface. The curvature of the

TABLE 1.2—Number of rings in the sapwood of some hardwoods.

Common name of tree	Scientific name of tree	Number of rings in sapwood
Northern catalpa	<i>Catalpa speciosa</i>	1-2
Black locust	<i>Robinia pseudoacacia</i>	2-3
American chestnut	<i>Castanea dentata</i>	3-4
Black cherry	<i>Prunus serotina</i>	10-12
Honeylocust	<i>Gleditsia triacanthos</i>	10-12
Black walnut	<i>Juglans nigra</i>	10-20
American beech	<i>Fagus grandifolia</i>	20-30
Sugar maple	<i>Acer saccharum</i>	30-40
Flowering dogwood	<i>Cornus florida</i>	30-40
Silver maple	<i>Acer saccharinum</i>	40-50
Sweet birch	<i>Betula lenta</i>	60-80
Southern magnolia	<i>Magnolia grandiflora</i>	60-80
Black tupelo	<i>Nyssa sylvatica</i>	80-100



Figure 1.10 • The relative width of the sapwood varies according to species; heartwood (dark area) is small in white ash (A) and wide in catalpa (B). Heartwood/sapwood growth may also vary tremendously within a species, according to growing conditions. Both discs (C) were cut from eastern redcedar trees. The sample on the left was shaded by the larger trees around it reducing its crown. The one on the right grew normally in an open meadow with a full crown of foliage and greater need for sap conduction. (Photos by Randy O'Rourke)




Figure 1.11 • This block of Douglas-fir was cut to show three planes: the transverse or cross-sectional surface (X), the radial surface (R), and the tangential surface (T). (Photo by Randy O'Rourke)

growth ring is not geometrically regular, and the surface in question is most ideally tangential where the plane is perpendicular to a radial plane. In practice, any slabbed log surface is usually accepted as a tangential surface. On a small cube of wood, the curvature of the rings is negligible, so the cube can be oriented to contain quite accurate transverse (cross-sectional), radial, and tangential faces (*Figure 1.11*).

Thin slices or sections of wood tissue, as commonly removed from the surfaces for study, are termed transverse, radial, and tangential sections depending on where they came from. These planes or sections are often designated simply by the letters **X**, **R**, and **T**, respectively.

In describing lumber or pieces of wood, the term **end-grain surface** (or simply **end grain**) refers to the transverse surfaces. By contrast, any plane running parallel to the pith is either **side grain** or **longitudinal surface**.

With lumber or veneer, additional terminology is used for various longitudinal surfaces (*Figure 1.12*). For example, pieces whose broad face is more or less in the radial plane are termed **radial grain**, **edge grain**, or **vertical grain**, since the edges of the growth rings emerge at the surface, with the growth rings appearing as vertical lines when viewed from the end-grain surface. One method of producing such pieces is first to saw the log into longitudinal quarters and then to saw each quarter radially. Pieces so pro-




Figure 1.12 • In a flatsawn or flat-grained board (T), the growth rings are roughly tangential to the wide face of the board. In an edge-grained or quartersawn board (R), the rings are roughly perpendicular to the wide face.

duced are said to be **quartersawn** and their surfaces are **quarter-grain** (see *Figure 2.2* on p. 25). These terms are flexible and may be applied to pieces in which the growth rings form angles of anywhere from 45 degrees to 90 degrees with the surface. The terms **comb grain** and **rift grain** indicate surfaces intermediate between 45 degrees to 90 degrees, especially when describing oak.

Lumber and veneer whose face orientation is approximately tangential are said to be **flatsawn, flat-grained, or tangential-grained**. **Plain grain** and **slash grain** are sometimes used synonymously with flatsawn. The term **side grain** sometimes means flat-grained. All these terms can include growth-ring orientations from 0 degrees to 45 degrees with the surface. The term **mixed grain** refers to quantities of lumber having both edge-grain and flatsawn pieces. **Bastard grain** typically refers to growth rings oriented between 30 degrees and 60 degrees to the surface.

DENSITY AND SPECIFIC GRAVITY

Density (weight per unit volume) is the single most important indicator of strength in wood and may therefore predict such characteristics as hardness, ease of machining, and nailing resistance. Dense woods generally shrink and swell more and usually present greater problems in drying. The densest woods also make the best fuel.

Specific gravity is the ratio of the density of a substance to the density of a standard substance (water, in the case of wood and other solids). Specific gravity is often called the

density index. In measuring density and specific gravity, it is customary to use oven-dry weight and current volume. Because of volumetric shrinkage and swelling, the volume of wood may vary slightly with moisture content.

Density is expressed as weight per unit volume, customarily as pounds per cubic foot or grams per cubic centimeter. Water has a density of 62.4 lb./ft.³ or 1 g/cm³. A wood weighing 37.44 lb./ft.³ or 0.6 g/cm³ is thus six-tenths as heavy as water and has a specific gravity of 0.6.




Figure 1.13 • Specific gravity is a good indicator of strength; the values in this table are the average for each species, based on oven-dry weight and volume at 12% moisture content.




Figure 1.14 • Specific gravity (or relative density) is an important guide to wood properties—these blocks of domestic and imported species all weigh the same, despite their great differences in size. At the extremities of the range, a big block of balsa (on the left scale pan) precisely balances a small block of rosewood. (Photo by Brian Gulick)

- | | |
|--------------------------|----------------------|
| 1. Beech | 17. Teak |
| 2. Tulipwood | 18. Eastern redcedar |
| 3. Spanish-cedar | 19. Rosewood |
| 4. White pine | 20. Western redcedar |
| 5. Hickory | 21. Eastern spruce |
| 6. Sumac | 22. Douglas-fir |
| 7. Purpleheart | 23. Red oak |
| 8. Black locust | 24. White ash |
| 9. Redwood | 25. Catalpa |
| 10. Balsa | 26. Obceche |
| 11. Walnut | 27. Basswood |
| 12. Butternut | 28. Yellow-wood |
| 13. Ebony | 29. Myrtle |
| 14. Southern yellow pine | 30. Sugar maple |
| 15. Lignumvitae | 31. Goncalo alves |
| 16. Barberry | |




Figure 1.15

Figure 1.13 gives the average specific gravity of some familiar woods (Figure 1.14 and Figure 1.15). There is a twelvefold range from balsa to lignumvitae. *The Guinness Book of World Records* lists black ironwood, also known as South African ironwood (*Olea laurifolia*), as the heaviest at 98 lb./ft.³ and acknowledges *Aeschynomene hispida* of Cuba is the lightest, weighing only 23/4 lb./ft.³ The respective specific gravities are 1.49 and 0.044.

A vital message conveyed by the density chart is how misleading the familiar terms **hardwood** and **softwood** really are. There are indeed differences between hardwoods and softwoods, but, as will be discussed in the next section, the terms hardwood and softwood simply distinguish the two broad groups of related trees within the plant kingdom. The terms are inaccurate as indicators of softness or hardness of the wood.

SYSTEMATIC CLASSIFICATION

A woodworker typically reacts to the idea of scientific classification and naming of woods with distaste and discouragement because gaining a mastery of the subject seems impossible. This need not be the case, for the woodworker does not need to become an expert in taxonomy (plant classification according to natural relationships) to become familiar with the field. Familiarity with scientific names is important for two reasons. First, there is often a difference between the common name used for a tree and the lumber that comes from it. Second, there is a great deal of inconsistency among common names.

The **plant kingdom** is composed of several major divisions. The one that includes all seed plants, **spermatophytes**, is further divided into two broad groups (separated according to how the seeds are borne). The **gymnosperms** (naked seeds) include all trees producing softwood lumber, and the **angiosperms** (covered seeds) include all trees yielding hardwood lumber. These groups are subdivided into orders, families, genera (singular genus), and species (singular species).

Within the gymnosperms (softwoods), trees of North America that provide commercial softwood timber are classified into four families of the order *Coniferales*. The term **conifer** thus indicates softwood trees. These trees are characterized by needlelike or scalelike foliage (usually evergreen) and have an **excurrent** tree form (a straight and dominant main stem with subordinate lateral branching) (*Figure 1.16*). Familiar examples are pines, spruces, firs, hemlocks, and cedars.

Conifers range from about 0.30 to 0.55 average specific gravity. Were they lighter, like balsa, they would be too soft




Figure 1.16. Dendritic form characteristic of hardwoods, left, contrasts with the excurrent form typical of softwoods, right.

for many building uses. If they were heavier, like oak or hickory, they could not be worked easily with hand tools, nor could they be nailed easily without preboring. This density range, the wide distribution of conifers in our temperate zone, and the excurrent stem form (yielding long straight planks and boards) explain the dominant use of softwoods for structural lumber. (Hardwoods can also be used structurally if they are of suitable form and workable. Chestnut and yellow poplar have both attributes and have been widely used.)

Another order of gymnosperms, *Ginkgoales*, has but a single species, *Ginkgo biloba*, the ginkgo or maidenhair tree of China and Japan. It is thought to be the oldest surviving tree, often referred to as a living fossil, since geological evidence indicates its existence more than 200 million years ago. The ginkgo has finally disappeared in the wild, but the species was perpetuated through cultivation in oriental temple gardens, and as early as the 18th century, seeds were brought to North America for propagation as an ornamental. The ginkgo is widely planted as a street tree because of its tolerance to air pollution as well as its graceful form and elegant foliage. However, its wood has had little use.


The angiosperms (hardwoods) include some 22 families in the United States. Hardwood trees are mostly **deciduous**, that is, their leaves drop in autumn. Their form tends to be **dendritic** or **deliquescent** (characterized by branching and rebranching of the main stem). The higher density range of some species and the attractive heartwood color and figure have earned them a favored place among woodworkers.

Using conventional taxonomy, eastern white pine would be classified as follows: Kingdom: plant; division: spermatophytes; subdivision: gymnosperms; order: *Coniferales*; family: *Pinaceae*; genus: *Pinus*; species: *strobus*. A particular species of wood is designated by the combination of the **genus** (generic name) and **species** (specific epithet)—*Pinus strobus* for eastern white pine. This designation is adequate in most cases, but a full scientific designation includes the name (or abbreviated name if well known) of the botanist who classified the species. Eastern white pine would be written *Pinus strobus* L., indicating that the Swedish botanist Linnaeus classified it. Italics are used for the genus and species because they are Latin names. The genus is capitalized, but the species is not. Where the genus is obvious, as in a discussion exclusively about pines, it is sometimes abbreviated—*P. strobus* for eastern white pine, *P. resinosa* for red pine, *P. ponderosa* for ponderosa pine. When a piece of wood can be identified as to genus but not to exact species, it is designated by the genus name followed by the abbreviation sp., as in, for example, southern yellow pine. *Pinus* sp. or red oak, *Quercus* sp. The notation spp. indicates plural.


A single species may have several common names, especially in different localities. For example, the preferred common name for the species *Liriodendron tulipifera* is yellow-poplar. The tree is locally called tuliptree or tulip poplar and its wood is known as whitewood, tulipwood, hickory poplar, white poplar, or simply poplar—and even popple. But poplar and popple commonly describe cottonwoods and aspens in the genus *Populus* and whitewood is used for several other species. Ironwood is another common name that keeps popping up. Among tropical species, designation by scientific names is especially important. Several excellent reference books of scientific names are listed in the bibliography on p. 272. Also see Appendix 1 on p. 257.

CELLULAR STRUCTURE


Although the average woodworker need not have a detailed familiarity with the cell structure of every species, an acquaintance with anatomical detail will increase understanding of the broad differences between softwoods and hardwoods and the reasons for differences among species (*Figure 1.17*). Within a species, anatomical structure also reveals the extent of variability and helps pinpoint locations of relative hardness and softness. It may also show sites of potential splitting, critical to every phase of woodworking from carving and finishing to drilling, nailing, and gluing. Understanding cell structure is also vital to appreciating the



BLACK CHERRY




BLACK WALNUT




RED OAK

Figure 1.17 • Characteristic cell structure and the differences between hardwoods and softwoods is visible in these photos made with a scanning electron microscope. Cross-sectional surface is uppermost, radial plane is lower left, and the tangential plane is lower right. (Photos by Wilfred Cote)



EASTERN WHITE PINE



SOUTHERN YELLOW PINE




Figure 1.18 • Some coniferous cell types. Tracheid (A, enlarged view A) comprise more than 90% of the wood volume. The remainder is mostly ray tissue, either ray parenchyma cells (B) or ray tracheids (C). Some species also have a very small percentage of epithelial cells (D, E), which line resin canals, or longitudinal parenchyma cells (F).

permeability of wood, which affects, among other things, drying and stain absorption and especially the inequality of properties in different directions in wood.

SOFTWOODS

Though it seems complicated at first, the structure of softwoods (*Figure 1.18*) is relatively simple compared with that of hardwoods. Most of the cells found in coniferous wood are **tracheids**, which comprise 90% to 95% of the volume of the wood. Tracheids are fiberlike cells about 100 times longer than they are in diameter. Among different species, their average lengths range from about 2 mm to about 6 mm. In an average coniferous species, a cubic inch of wood contains some four million tracheids. These fibers are excellent for making paper.

Average tracheid diameters range from 20 to 60 micrometers [1 **micrometer (um)** equals 0.001 mm]. This gives a basis for classifying **texture** among softwoods. Redwood has the largest-diameter tracheids and is termed coarse-textured; eastern redcedar has the smallest-diameter tracheids and is fine-textured. With a 10-power hand lens, texture can be estimated as coarse, medium, or fine on the basis of how clearly individual tracheids can be seen in cross section. Texture, a valuable aid in wood identification, is also related to surface smoothness and finishing qualities.

The functions of conduction and support of the tree are carried out by the nonliving (prosenchymatous) tracheids. A trade-off between these two functions seems to take place from earlywood to latewood: In earlywood the tracheids are larger in diameter and thin walled, well suited for conduction; in latewood the thicker-walled, smaller-diameter tracheids are less suited to conduction but give more support to the tree. This overall variation in tracheids from earlywood to latewood determines the evenness of grain. In white pine the grain is quite even, for example, but in southern yellow pine there may be as much as a threefold difference in density from earlywood to latewood (the approximate specific gravity of the earlywood is 0.3, the latewood 0.9).

One typical consequence of uneven grain in conifers is the color reversal that results from staining (*Figure 1.19*). Another common problem develops when flatsawn pieces are used for stair treads or flooring. The earlywood wears away at a faster rate, leaving raised ridges of latewood.

Some coniferous species also have **resin canals**, tubular passageways lined with living parenchyma (epithelial) cells, which exude resin or "pitch" into the canals. Resin canals are found in four genera of the conifers, all within the family *Pinaceae*: *Pinus* (pine), *Picea* (spruce), *Larix* (larch), and *Pseudotsuga* (Douglas-fir). (*Figure 1.20*). Resin canals




Figure 1.19 • Earlywood of Douglas-fir (A) is lighter in color than latewood but more porous. Thus it retains satin more readily and finishes darker in color. Large earlywood pores of red oak (B) already appear darker than those of latewood, and the effect is accentuated as the stain accumulates in them. (Photos by Randy O'Rourke)



Figure 1.20 • Unless resins are solidified or set by high temperatures in kiln-drying, droplets of resin may exude from the canals as on the surface of this turned baluster of eastern white pine. Resin droplets remain sticky for some time but then harden. Careful scraping or sanding will remove them. (Photo by R. Bruce Hoadley)




Figure 1.21 • Pitch pockets in a spruce board. Pitch pockets are lens-shaped voids filled with resin, which sometimes occur in woods having resin canals. (Photo by R. Bruce Hoadley)

are largest and most numerous in pines, usually distinct to the naked eye. In other species, magnification may be necessary to locate them.

In sapwood the resin in the canals is quite fluid, and it may be years before it eventually solidifies in the wood. On new millwork the resin often flows to the surface of the wood, forming a droplet where each resin canal intersects the wood surface (Figures 1.20, 1.21). Kiln-drying schedules that

include final temperatures above 175°F are necessary to set the resin adequately and to minimize bleed-out problems. Tiny resin spots tend to bleed through paint films, resulting in a yellowish speckling of the surface of painted carvings of pine. Because hardwoods don't have resin canals, low-density hardwoods such as basswood avoid the resin-spot problem.




Figure 1.22 • Thin sections of eastern white pine magnified about 100 times. The cross-section (transverse) view is dominated by rows of tracheids (A); also visible are the narrow rays (B) and a single resin canal (C). In the radial view, elongation of the tracheids is apparent, and the rays (B) appear as bricklike bands of cells. In the tangential section, the rays are seen in end view. One ray, called a fusiform ray (D), has a horizontal resin canal through its center. (Photos by R. Bruce Hoadley)

Pitch from resin canals has been traditionally harvested from southern yellow pine by gashing the trees and collecting the resin that oozes out. Processing the pitch yields such products as turpentine, rosin, and pine tar oil, which are often called naval stores because of their original importance in shipbuilding.

The rays in softwoods are narrow, usually one cell wide (except for occasional rays with horizontal resin canals in some species). They may be 40 or more cells high in some species, but they are essentially invisible even with the use of a 10-power hand lens. Microscopic examination is needed to see them (Figure 1.22). Most of the living parenchyma cells in coniferous woods are found in the rays. In addition to those in the rays, a few parenchyma cells occur elsewhere in some species, but a microscope is necessary to detect them.

HARDWOODS

In comparing the anatomy of the hardwoods with that of the softwoods, several general differences are immediately apparent. Most hardwoods lack resin canals (although some tropical hardwoods have gum ducts). Rays in hardwoods vary widely in size, well into the range of visibility with the unaided eye. Many more types of cells are present in hardwoods, and there is more variation in their arrangement. It is believed that the hardwoods evolved much later than the softwoods. Most notable is the degree to which hardwoods have evolved cells specialized by function. The noteworthy difference in this respect is the degree to which the functions of conduction and support are accomplished by the evolu-




Figure 1.23 • Hardwood cell types are extremely varied. This illustration indicates their relative size and shape.




Figure 1.24 • Red oak, a ring-porous hardwood, magnified about 100 times. Large, thin-walled pores (A) are concentrated in the earlywood and are many times the diameter of the thick-walled fibers (B) abundant in the latewood. The pores are surrounded by small-diameter, thin-walled tracheids (C). Large, multiseriate rays (D), easily visible to the naked eye, are a distinctive feature of oaks. Uniseriate rays (E), seen only with a microscope, are also numerous. (Photos by R. Bruce Hoadley)

tion of specialized cells; **vessel elements** represent the ultimate in functional specializations (Figure 1.23).

Vessel elements are relatively large in diameter but have *thin* walls. They form in end-to-end arrangements in the tree. Their end walls disappear as a final stage in their development, thus forming continuous pipelines, or **vessels**, ideal for sap conduction. Vessels vary in size among and within species. Some are seen easily with the naked eye. Others require hand-lens magnification but are distinguishable from other cell types because they are slightly larger. **Fibers**, by contrast, are smallest in diameter, with closed ends and thick walls and therefore poorly suited for conduction. They contribute strength to the wood.

When a vessel is cut transversely (across the end grain), exposed open end is referred to as a **pore**. Because all hardwoods possess vessels, they are sometimes called **porous** woods (softwoods are therefore called **nonporous** woods).

The size, number, and distribution of vessels and fibers determining factors in the appearance and uniformity of hardness of a particular wood. In some woods (oak, ash, elm chestnut, catalpa), the largest pores are concentrated in the earlywood. Such woods are said to be **ring-porous** (figure 1.24). This structure usually causes pronounced uneven grain, and typically these woods have distinct figures and patterns (Figure 1.25). The uneven uptake of stain makes these ring-porous layers even more pronounced

(Figure 1.19). But these planes of weakness may be used advantageously, as in ash, where the layers can be separated for basket strips (Figure 1.26). Some species, such as hickory, have an obvious earlywood concentration of pores and are classed as ring-porous, although there is not much noticeable variation in wood density. Other hardwoods (such as maple, birch, basswood, and yellow-poplar) have pores distributed fairly evenly and are termed **diffuse-porous** woods. Most domestic diffuse-porous woods have relatively small-diameter pores (Figure 1.27), but among



Figure 1.25 • Catalpa carving by the author displays the pronounced figure typical of ring-porous hardwoods. (Photo by R. Bruce Hoadley)




Figure 1.26 • When pounded on the tangential surface, the earlywood layers of freshly cut black ash will buckle. This makes it easy to peel the growth rings apart for making baskets. (Photos by R. Bruce Hoadley)

tropical woods some diffuse-porous woods (e.g., mahogany) have rather large pores. In some woods, the pores are large in the earlywood and get smaller toward the latewood but with no distinct zoning. These woods are called semi-ring-porous or semi-diffuse-porous. Examples are black walnut and butternut. Some species that are usually diffuse-porous may sometimes tend toward semi-ring-porous structure—black willow and cottonwood are two examples.

In hardwoods, pore size is used as a measure of texture. Red oak, with its large pores, is coarse-textured; sweetgum is fine-textured because of its small-diameter pores.

In some hardwoods, as the transition from sapwood to heartwood takes place, bubblelike structures appear in the cavities of the vessel elements. These structures are known

as tyloses and if present can usually be seen in large-diameter pores with a hand lens (Figure 1.28). In some species they are sparse or absent (red oaks) or unevenly distributed (hickory, chestnut). In others they are numerous (white oak). In some species (black locust, Osage-orange) the vessel elements are densely packed with tyloses. Because liquid passage is difficult in white oak, it is the obvious choice over red oak for making barrels and other tight cooperage.

Besides the vessels, the other types of longitudinal cells in hardwoods (fibers, tracheids, and parenchyma cells) are of uniformly small diameter, so even with a hand lens they cannot be seen individually. But because of their difference in cell-wall thickness, masses of them are distinguishable. Fiber masses typically appear darker; tracheids and parenchyma cells are lighter. Such characteristic arrangements are valuable in identification.

Hardwood rays vary widely in size and therefore in appearance. The smallest rays are only one cell wide and may be visible only with a microscope, as in chestnut or aspen. At the other extreme, rays up to 40 cells wide and thousands of cells high are quite conspicuous to the unaided eye. Single rays 4 in. or more in height have been measured in white oak (Figure 1.4).

The pronounced ray structure in some woods is important to the woodworker. The rays, consisting totally of parenchyma cells, represent planes of structural weakness in the wood. In drying wood, stresses often create checks in the plane of the rays. The weakness of the rays may provide a natural cleavage plane to assist in splitting firewood, roughing out furniture parts from green wood, and riving shingles. However, in attempting to machine a smooth radial surface,




Figure 1.27 • Black cherry, a typical diffuse-porous wood, has uniformly sized vessels (A) evenly distributed among the fibers. The rays (B), up to six cells wide, are distinct when the transverse surface is viewed with a hand lens. (Photos by R. Bruce Hoadley)




Figure 1.28 • In some hardwoods, the transition between sapwood and heartwood contains spheres. In some species, these spheres are packed with tyloses, which prevent conduction. (Photo by R. Bruce Hoadley)



Figure 1.29 • Ray fleck is characteristic of the radial surface and is quite pronounced in some woods, such as in this sycamore. (Photo by R. Bruce Hoadley)

rays may be an impediment. Because the plane of the rays seldom coincides perfectly with the surface and because chip formation tends to follow the plane of the rays, minute tearouts may result. As expected, such problems are related to ray size.

On the other hand, rays may add noteworthy figure to the edge-grain surface of wood. When ray appearance is distinct on the radial surface, it is termed ray fleck (*Figure 1.29*). Ray fleck is characteristic of certain woods, for example, sycamore, oak, and beech. In lacewood, also called silky oak (*Cardwellia sublimis*), the prized figure is produced by slicing the veneer just off true radial to produce an attractive ray fleck (see *Figure 2.4* on p. 26). In some species, such as cherry and yellow-poplar (see *Figure 3.2, A* on p. 47), the ray fleck appears lighter than the background wood, whereas in others, such as maple and sycamore, it is darker. Together with ray size, this feature is quite helpful in identification.



Figure 2.1 • Spectacular pigment figure in ziricote is seen in this life-size sculpture named Cape Lady II by David Hostetler. (Photo by David Hostetler)

FIGURE IN WOOD

Appearance is one of the principal values of wood to the woodworker, so this subject deserves special attention. To fully appreciate figure, the woodworker must have an understanding of the anatomical structure and physiological functions of the tree (*Figure 2.1*).

The layman often refers to distinctive surface appearance of wood, especially that resulting from growth-ring structure, as "grain." How many times have we heard such statements as, "Oh, look at the beautiful grain in that table"? To avoid continued confusion with that already overworked word, the term **figure** is used to refer to distinctive or characteristic markings on longitudinal or side-grain surfaces of wood. In commercial parlance, the term figure is generally reserved for the more decorative woods. Figure in wood results from a combination of particular anatomical features

(from normal growth structure to various abnormalities and extractives) plus the orientation of the surface that results from cutting.

Lumber is sawn to produce all surface orientations, from flatsawn to edge grain (*Figure 2.2*). Veneer can likewise be cut in any plane relative to the growth rings, from flat-slicing to quarter-slicing. Veneer can also be "peeled," that is, cut using the rotary process whereby a log is rotated against a gradually advancing knife—a continuous sheet of veneer is removed, as one would unwind a roll of paper towels. Figure arises from the visual variabilities of normal wood structure, namely growth rings and rays. The more uneven the grain and the larger and more conspicuous the rays, the more distinctive the figure.




Figure 2.2 • The method of manufacture determines the appearance of grain on a board or veneer.

In quartersawn lumber or quarter-sliced veneer, the plane of cut is more or less 90 degrees to the growth rings. Depending on the unevenness of the grain, the figure will be a parallel-line pattern on the face of the board (*Figure 2.3*). The distinctive appearance of the rays, which is known as **ray fleck**, may vary from the intricate cross-striping of cherry to the large, showy and lustrous rays of oak, known as **silver grain**. To reduce the size of the ray flecks and yet produce an interesting pattern, woods such as lacewood and oak



Figure 2.3 • Quarter-sawn surfaces of uneven-grained conifers such as this Douglas-fir board have parallel-grain figure. (Photo by Randy O'Rourke)



Figure 2.4 • Lacewood with ray fleck figure. This piece was rift-cut just off the true radial to produce interesting figure while reducing the size of the flecks. (Photo by Randy O'Rourke)

are sometimes cut just off the true radial in order to produce **rift-cut** or **rift-sawn** surfaces (*Figure 2.4*).

If a log were a perfect cylinder with uniformly thick growth layers, the figure on the surfaces of boards cut in tangential planes would be parallel markings. Fortunately, every tree grows with enough irregularity to distort the otherwise static markings (*Figure 2.5*). On flatsawn surfaces, then, the growth rings intercept the surface, forming ellipses or U-shaped or V-shaped markings down through the area of closest tangent to the rings (*Figure 2.6*).






Figure 2.5 • Quartersawn surfaces of perfectly straight logs reveal uninteresting parallel lines (A). A log with severe sweeps has ellipsoid figure on the flatsawn belly surface (B) and parabolic figure on the back surface (C). (Photo A by Randy O'Rourke; photos B and C by Richard Starr)



Figure 2.6 • FLATSAWN FIGURE IS CHARACTERIZED BY OVAL, U-SHAPED, and V-SHAPED PATTERNS. BOARDS (LEFT TO RIGHT) ARE ASH, CHERRY, SOUTHERN YELLOW PINE, CHESTNUT, WHITE BIRCH, AND EASTERN SPRUCE. PHOTO BY R. BRUCE HOADLEY)

Toward the edges of a flatsawn board, depending on how wide the board is and how much curvature is in the growth rings, the figure approaches edge grain. Where growth rings are fluted slightly, as in butternut, basswood, and sometimes black walnut, an irregular but interesting figure results (Figure 2.7). Rotary veneer cutting produces a continuous, repetitively merging series of tangential figure (Figure 2.8).

Cone cutting, which is a method of removing a circular layer of veneer analogous to sharpening a pencil, produces interesting circular pieces bearing cone figure.

The grain direction (that is, the direction of the longitudinal cells) of the average tree trunk is more or less straight, with some normal variation from strict geometric form.

Wood from other parts of normal trees may exhibit interesting figure resulting from grain distortion. Crotches, for example, where a somewhat equal forking of the trunk has occurred, develop an unusually twisted and intergrown structure where the two stems merge (Figure 2.9). A cut passing through the center of the crotch produces

crotch figure. If the cut is toward the outside of the crotch, a swirl crotch figure results. The term moonshine crotch is also applied to crotch figure. The stump region of the tree also produces interesting figure.

In some species, deviation from normal structure may occur either as a common feature or as a rare exception.

which produces interesting and attractive figure in the wood. Curly figure results when longitudinal cell structure forms or curly grain. A split radial surface looks like a




Figure 2.7 • INDENTED RINGS IN SITKA SPRUCE (A) PRODUCE BEAR-SCRATCH FIGURE. THE JAGGED CONTOURS OF THE BUTTERNUT IN B COME FROM FLUTED GROWTH RINGS. (PHOTOS BY RANDY O'ROURKE)



Figure 2.8 • The continuous tangential figure of Douglas-fir plywood is typical of rotary-cut veneer. (Photo by Randy O'Rourke)



Figure 2.9 • Crotch-figure in mahogany. (Photo by R. Bruce Hoadley)

washboard (*Figure 2.10*). When this surface is smoothly machined to a flat plane, a cross-barred effect is produced by the variable light reflection of the cell structure intersecting the surface at various angles (*Figures 2.11, 2.12*). In maple this is termed tiger maple, or fiddleback, because it is preferred for violin backs. Some of the most remarkable pieces of curly figure can be seen in old Kentucky long-rifle stocks.



Figure 2.10 • Curly figure results when longitudinal cell structure forms a wavy pattern. When the wood is split, a washboard surface results. Curly figure is most pronounced when cut radially, as in this sugar maple. (Photo by Randy O'Rourke)




Figure 2.11 • The curly figure in this red maple board is produced largely by the changing angle of light reflection. (Photo by Randy O'Rourke)

Ribbon or stripe figure is produced when wood that has interlocked grain is cut radially. Interlocked grain is the result of repeated cycles of spiral growth, varying back and forth from left- to right-hand spirals (*Figure 2.13*). Except for short pieces, such wood is virtually impossible to split (*Figure 2.14*), these reversing spirals create a characteristic visual effect, due in part to the variation in the length of the severed vessels at the surface. The lines are long where the




Figure 2.12 • Fiddleback mahogany. (Photo by R. Bruce Hoadley)




Figure 2.13 • If spiral grain in a tree cycles one way and then the other, interlocked grain results. If a log from such a tree were turned down on a lathe, the reversing angle of the spiral grain would result as shown.

grain direction is parallel to the surface but reduced nearly to pore diameter where the vessels intersect the surface at a considerable angle. The varying light reflectiveness of the fiber tissue also contributes to the overall appearance (Figure 2.15) Figure that shows short stripes is often called **roe figure** and the interlocked grain referred to as **roey grain**. Where wavy grain occurs in combination with interred grain so the ribbon figure is interrupted at intervals, the figure is termed **broken stripe** (Figure 2.16): when curly figure predominates, a **mottled** figure results (Figure 2.17).

The cambium sometimes has localized indentations, bumps, or bulges that leave behind wood of characteristic **figure**. In ponderosa pine, lodgepole pine, and Sitka spruce, dimpling sometimes occurs as numerous small, conical



Figure 2.14 • Interlocked grain is revealed on the split radial surface of tupelo. The top edge, where the wood was split, is straight. The bottom edge shows the degree of interlocking. (Photo by Randy O'Rourke)




Figure 2.15 • Ribbon or stripe figure in mahogany veneer. Varied vessel lengths and light reflection create the pattern. (Photo by R. Bruce Hoadley)



Figure 2.16 • Broken-stripe figure in Ceylon satinwood, sometimes referred to as bee's-wing figure. (Photo by R. Bruce Hoadley)



Figure 2.17 • Mottled figure occurs when the curly figure predominates in a piece with a combination of wavy and interlocked grain. (Photo by R. Bruce Hoadley)



Figure 2.19 • Localized swirl in the grain of sugar maple produces bird's-eye figure. (Photo by R. Bruce Hoadley)




Figure 2.18 • Localized depressions in the growth rings, called dimples, are obvious on the split tangential surface of this piece of lodgepole pine. (Photo by Randy O'Rourke)




Figure 2.20 • Closely crowded bulges in the growth layer produce blister figure and the grain deviation associated with it. (Photo by Brian Gulick)

indentations of the plane of the growth ring (*Figure 2.18*). In occasional trees of sugar maple, localized small swirls of grain direction produce **bird's-eye** figure (*Figure 2.19*), so called because each swirl looks like a tiny eye.

Large, closely crowded bulges in the growth layers produce **blister figure** (*Figure 2.20*), which is also called **quilted figure** (*Figure 2.21*) if the mounds are elongated. When finished smoothly, the variation in light reflectiveness because of grain distortion creates a very unusual three-dimensional effect, so that the figure seems to roll when the

piece is moved. Quilted and blister figures are usually associated with bigleaf maple but are occasionally formed in other species as well.

Burls (*Figure 2.22*) are large, knoblike projections or bulges formed along the trunks (or sometimes limbs) of trees. The wood tissue within the burl is extremely disoriented and often contains numerous bud formations. The resulting figure is quite attractive and traditionally has been used in small articles such as bowls and turnings.



Figure 2.21 • When the bulges of blister figure are elongated, quilted figure results. When smooth, the grain distortion creates an unusual three-dimensional effect that seems to roll when the piece is moved. (Photo by Richard Starr)



Figure 2.22 • A burl on a red oak stem. The wood tissue within a burl is distorted and often contains numerous bud formations. (Photos by Randy O'Rourke)

Veneers cut from burls also display the fascinating figure (*Figure 2.23*).

Figure also may be produced by irregular coloration. In hardwoods especially, the heartwood coloration is preferred and the sometimes lighter sapwood may be considered a defect and discarded. However, a striking effect in single and multiple pieces can be created by joining boards of such species as rosewood, black walnut, and eastern redcedar where sapwood is prominent.

Within the heartwood alone, the term pigment figure refers to distinctive patterns formed by uneven extractive deposits. Some examples are rosewood, zebrawood, and figured sweetgum (*Figure 2.24*). It is interesting to note that the layering effect of pigmentation may be quite independent of the growth-ring layering (*Figure 2.1*).



Figure 2.23 • Walnut burl figure is prized. (Photo by R. Bruce Hoadley)



Figure 2.24 • Pigment-figured sweet gum. (Photo by R. Bruce Hoadley)

KNOTS

While some irregularities in wood may increase value, as when a distinctive figure is produced, others decrease value. By tradition, any irregularities that decrease value are branded as defects. Although some of the features described below seem to be negative in woodworking, the woodworker is urged to reserve judgment on nature's irregularities. These were indeed defects when hand tools could not deal with them, but now many of these irregularities can be easily machined using power tools.

Knots are a case in point. The commercial hardwood lumber-grading system assumes that every knot is a defect

and bases grade on the size and number of clear areas among the knots (and other blemishes). On the other hand, many beautiful works of craftsmanship and art have been produced using, or even featuring, knots.

The woodworker should first understand what knots are and how their structure relates to the rest of the wood. Knots are simply the parts of limbs that are embedded in the main stem of the tree (*Figure 2.25*, *Figure 2.27*).

As the tree grows, branching is initiated by lateral bud development from the twig (*Figure 2.26*). The lateral branch thus was originally connected to the pith of the main stem. Each successive growth ring or layer forms continuously over the stem and branches, although the growth ring is




Figure 2.25 • A knot is the basal portion of a branch whose structure becomes surrounded by the enlarging stem. Since branches begin with lateral buds, knots can always be traced back to the pith of the main stem.



Figure 2.26 • Coniferous trees are characterized by their excurrent form. They have a dominant stem from which whorls of lateral branching occur at regular intervals, or nodes. (Photo by R. Bruce Hoadley)

thicker on the stem than on the branches and the branch diameter increases more slowly than the trunk (*Figure 2.25*). As the girth of the trunk increases, a cone of branch wood—the **intergrown knot**—develops within the trunk. Such knots are also termed **tight knots** because they are intergrown with surrounding wood, or **red knots**, especially in conifers where they often have a distinct reddish tinge.

At some point the limb may die, perhaps as a result of overshadowing by limbs higher up. The limb dies back to approximately the trunk surface, its dead cambium unable to add further girth. So subsequent growth rings added to the main stem simply surround the dead limb stub, which may

begin to rot. A number of years of growth may be added to the main stem, surrounding the branch stub. The dead part of the stub becomes an **encased knot** (*Figure 2.25*). It is not intergrown and therefore is called a **loose knot**, often with bark entrapped. A **knothole** results when an encased or loose knot falls out of a board (*Figure 2.29*).

Encased knots also are called **black knots** because they are commonly discolored by stain and decay. In time the stub may become weakened by decay and fall or be broken off, or it may be pruned back flush with the trunk. Further growth layers will cover the stub, and eventually the cambium will form a continuous layer. From this point on, solid layers of wood and bark will be formed beyond the overgrown knot. But as the cambium moves outward, the knot-scarred bark layers persist for an amazing number of years, providing a clue to the buried blemish.





Figure 2.27 • In a board or veneer, knots in clusters indicate the whorls, separated by the clear wood of the internodes (A). Knotty rotary-cut veneer from a tree with numerous limbs (B) Photo A by Randy O'Rourke; photo B by R. Bruce Hoadley)



Figure 2.28 • A spike knot showing an intergrown portion (top) and an encased portion (bottom). (Photo by Randy O'Rourke)



Figure 2.29 • A knothole results when an encased loose knot falls out. (Photo by Randy O'Rourke)

Knots **may** be classified by how they are cut from the tree. If **they** are split by radial sawing and extend across the face of the board, they are termed **spike knots** (*Figure 2.28, Figure 2.30*). On flatsawn boards, they typically appear round or oval and are called **round knots** (*Figure 2.31*). Knots smaller than 1/4 in. dia. are called **pin knots** (*Figure 2.32*).

Understanding knots can be useful to the woodworker. Nothing is more devastating to a carver than to work halfway through a block of wood only to uncover an interior knot flaw. Yet the trained eye can usually predict such a blemish. If a pie-shaped section is taken from a log and the first few growth rings near the pith are removed, any branches will be seen at least as tiny knots. If none are present, there will be no knot-related defects in the piece. If any are located, the bark should be carefully examined for scars.



Figure 2.30 • These spike knots show the origin of limbs at the pith. (Photo by Randy O'Rourke)

Experience can tell much about the size and depth of such defects (*Figure 2.33*).

It should be noted that since every knot originates at the pith, every knot that appears on the bark side of a flatsawn board will also appear on the pith side of that same board. On the other hand, some knots on the pith side may have ended and grown over before reaching the bark surface. Therefore, the bark side is often the clearer, higher-quality face.

There are a variety of reasons why knots are commonly considered defects. The wood of the knot itself is different in density (usually higher), and its grain orientation is more or less perpendicular to the surrounding wood. Because shrinkage is greater across the knot than in the surrounding wood, encased knots may loosen and drop out. Although



Figure 2.31 • Tight round knots. (Photo by Randy O'Rourke)




Figure 2.32 • Pin knots. (Photo by Randy O'Rourke)




Figure 2.33 • A carving chunk may appear flawless at first glance (A). Removing wood adjacent to the pith (B) will locate internal knots (C). Scars in the bark (at X) may be a sign of knots large enough to ruin the block for carving.

intergrown knots remain tight, they may develop radial cracks. Encased knots are usually considered worse defects because of the discoloration and the entrapped bark associated with them (*Figure 2.34*). From the standpoints of strength and machining properties, the disorientation of grain direction is troublesome not only because of the knot itself but also because the entire area is influenced by the knot. For example, a spike knot extending across a board may cause it to break in half under small loads.

Knots may also be an asset and can be valuable features of figure in many ways. Knotty pine is often thought to be characteristic of early American decor, although in reality knots were mostly avoided, plugged, or painted over by colonial cabinetmakers. Knotty pine as wall-boarding seems to be a 20th-century invention to use the increasing stocks of common grades of lumber. Other species that exhibit knots with some degree of regularity, such as spruce, cedar, and other western softwoods, have been successfully marketed to feature their knots. Individual pieces of wood with knots are increasingly fashioned into masterpieces of cabinetry and sculpture.



Figure 2.34 • Included bark adjacent to a knot in red oak. This defect may also result from an injury to the growing tree. (Photo by Richard Starr)

ABNORMAL WOOD

The first few growth rings added around the pith may not be typical of the mature wood formed by the tree. This core of atypical tissue is termed juvenile wood (*Figure 2.35*). It is prevalent among conifers, especially plantation-grown trees, which grow rapidly until eventual crown closure. Then competition with other trees slows the growth to a more normal rate. Juvenile wood is characterized by wider growth rings of lower-density wood and less strength. It may also have abnormal shrinkage properties, which result in greater

tendency to warp, especially by twisting. Pieces of wood including (or very near) the pith should be suspect. Some trees and species show little or no juvenile-wood abnormality.

Reaction wood is a term applied to abnormal wood formed in tree stems and limbs that are other than erect, that is, parallel to the pull of gravity. The principal concern to woodworkers is the occurrence of reaction wood in leaning trunks (*Figure 2.36*) from which otherwise defect-free wood might be expected. Stems can lean because of partial uprooting by storms, severe bending under snow or ice, and tree



Figure 2.35 • Wide growth rings surrounding the pith (left) are juvenile wood, which is lighter and weaker than narrow-ringed mature wood. In the photo on the right, needle scars appearing as dots on the wood also indicate juvenile wood. (Photos by Randy O'Rourke)



Figure 2.36 • Reaction wood forms in trees that lean (A). The curving sweep of this hemlock tree, although picturesque, means unpredictable compression wood will be found within as shown in the cross section (B). The section of spruce (C) shows severe compressive wood formation. (Photo A by R. Bruce Hoadley; photos B and C by Randy O'Rourke)

growth toward sunlight available from only one direction. Reaction-wood formation seems to include a mechanism for redirecting stem growth to the vertical, resulting in a bowing of the stem. Therefore boards or pieces from a log with noticeable bow should be suspected of containing reaction wood and should be examined very closely for it.

Reaction wood has different traits in softwoods and hardwoods. In softwood species, reaction wood forms principally toward the underside of the leaning stem. Because the pull of gravity presumably puts the lower side of the leaning trunk into compression, reaction wood in conifers is termed compression wood. Several visual features aid in its detection (*Figure 2.37*).

The part of the growth ring containing reaction wood is usually wider than normal, resulting in an eccentrically shaped stem with the pith offset toward the upper side. The abnormal tracheids typically appear to form wider than nor-

mal latewood. Even-grained woods, such as eastern white pine, therefore appear uneven-grained. However, in woods that are notably uneven-grained, such as southern yellow pine, the latewood is duller and more lifeless and tends to even out the contrast.

The two main disadvantages of compression wood for the woodworker are its effects on strength and shrinkage. Since reaction-wood tracheids are thick-walled, the wood is typically denser than normal. But because the wood contains less cellulose than usual and the cellulose chains are not as parallel to the long direction of the cells, the wood is weaker than normal. The woodcarver is especially aware of the abnormally hard but brittle qualities of compression wood. In finishing, compression wood may not stain uniformly with normal wood. The carpenter notices the difficulty in driving nails and the greater tendency to split. For structural uses where load-bearing capability is vital, as in ladder rails, unknowing use of reaction wood has resulted in




Figure 2.37 • Compression wood in pine may appear as a dark streak on a flatsawn board (A) or as an abrupt change from normal light-colored sapwood to dark (B) on a quartersawn board. The abnormal appearance (C) of earlywood and latewood on this flatsawn surface indicates compression wood. (Photos by Randy O'Rourke)

fatality because the wood breaks suddenly when bent and at lower than expected loads (*Figure 2.38*).

The second major problem with compression wood is its abnormal longitudinal shrinkage. Normal wood shrinks so slightly along the grain that it is usually negligible. Compression wood shrinks longitudinally 10 to 20 times the normal amount. What's more, because reaction-wood formation is nonuniform in a given board, the shrinkage is uneven, resulting in greater problems. Drying of reaction wood or changes in moisture content creates uneven shrinkage stresses in the wood, often resulting in warp (*Figure 2.39*). This, along with juvenile wood, is a major cause of warp in framing lumber. Most distortions that

develop in stud walls probably result from reaction wood. In woodworking, attempts to rip saw pieces containing reaction wood may result in the wood's pinching against the saw or its splaying widely apart as the cut progresses (*Figure 2.40*).

In hardwood trees, reaction wood forms predominantly toward the upper side of the leaning stem. Because gravity causes the upper side to be in tension, it is termed tension wood. In hardwoods, however, there is less tendency than in softwoods for the pith to be off-center in the stem, and tension wood may develop irregularly around the entire stem. Tension wood is often quite difficult to detect. Sometimes it looks silvery (*Figure 2.41*), other times dull and lifeless, and




Figure 2.38 • Brash failure in compression wood. (Photo by Randy O'Rourke)



Figure 2.39 • Severe crook in roughsawn lumber caused by compression wood. (Photo by R. Bruce Hoadley)




Figure 2.40 • Excessive longitudinal shrinkage of compression wood created enough stress to split away the edge of this board. Ripping such lumber on a table saw would be troublesome. (Photo by Randy O'Rourke)



Figure 2.41 • In hardwoods, the reaction wood is on the upper side of the sweep in the tree and is called tension wood. Tension wood looks silvery (A) as shown in the left section after smooth sanding. Tension wood may result in eccentric growth rings in trees (B, C). (Photos A and B by Randy O'Rourke; photo C by Richard Starr)

in some cases there is little if any visual difference. Indications of crookedness or sweep in the log are signals of possible tension wood. The abnormal fibers of tension wood actually contain a greater than normal amount of cellulose. This wood is commonly stronger than normal. Of concern to the woodworker is the way this wood machines. Fiber structure does not sever cleanly but leaves a fuzzy or woolly surface (Figure 2.42). Aside from the immediate problem of machining tension wood, seemingly successful efforts to smooth the wood leave a microscopic woolliness on the surface. Upon finishing, stain is absorbed irregularly and the surface appears blotchy. As with compression wood, longitudinal shrinkage in tension wood is both irregular and greater than normal, resulting in warping and machining problems.



Figure 2.42 • The abnormal fibers of tension wood can leave a woolly surface, as on this cottonwood board when it was sawn from the log. (Photo by Randy O'Rourke)

Figure 2.43 • Wood damaged by marine borers. (Photo by Randy O'Rourke)



Figure 2.44 • Severe blue-staining on this white pine board indicates the presence of sapstain fungi. Staining affects the appearance of wood but not its strength. (Photo by Randy O'Rourke)



FUNGI

Wood kept under favorable conditions apparently lasts indefinitely—artifacts in excellent condition have been recovered from ancient Egyptian tombs. However, it is equally important to note that wood is biodegradable, that is, subject to deterioration by natural agents. Elimination of dead wood by decay is as necessary to the continuation of a forest as is the sprouting of the seed, for if fallen trees and limbs remained, there would eventually be no open ground for new reproduction.

Biodegradation of wood is accomplished in part by insects and marine borers (*Figure 2.43*), but the greatest degree of deterioration is the work of **wood-inhabiting fungi**.

Fungi are low forms of plant life. Incapable of producing their own foods as do green plants, these parasites derive their sustenance from a host plant. Fungi that inhabit wood

are classified as molds, stains, or decay. Molds live mainly on the surface of the wood, while stains invade the cell structure. Both principally live off carbohydrates stored in parenchyma cells. Because their work is confined essentially to sapwood, they are termed **sapstains**. Since they commonly produce a bluish-gray discoloration, the term **blue stain** is often applied. The main problem with sapstains is this discoloration (*Figure 2.44*), not structural cellular damage.

Decay fungi invade the cell structure, not only consuming any available stored materials but also by actually dissolving the cell-wall material by enzyme action. The early stages of infestation, called **incipient decay**, are characterized mainly by discoloration—strength may not be significantly altered. Eventually, proliferation of fungi results in **advanced decay**, wherein discoloration is accompanied by obvious softening of the wood. Wood thus affected is termed **rot**, but the result varies somewhat according to the species



Figure 2.45 • Infection with brown rot (A) eventually results in cubical breakup of the wood (B). (Photos by Randy O'Rourke)




Figure 2.46 • This Douglas-fir 2x4 is infected with white speck, a white pocket rot that invades the heartwood of living trees. It ceases to develop once the wood is cut. (Photo by Randy O'Rourke)

of fungi involved. **Brown rots** principally attack cellulose, leaving a brown powdery residue, often characterized by cross-checks similar in pattern to charred wood (Figure 2.45).

White rots consume both lignin and cellulose, leaving a whitish, sometimes stringy residue. Certain fungi concentrate in localized areas or pockets, as in **pecky cypress**, a brown pocket rot. **White speck**, which occurs in softwoods, is characterized by small pockets filled with whitish residue (Figure 2.46).

Although wood with decay is generally considered defective or worthless, decay may sometimes be a valued feature. The rot pockets in both pecky cypress and white-speck-infected lumber are often displayed decoratively, mainly in wall boarding. Such infested wood is especially attractive if the rot pockets are reasonably uniform in size and distribution.

In some wood attacked by certain white rots, the development of decay is accompanied by attractive dark brown or black staining (Figure 2.47). Thin layers of stain are



Figure 2.47 • As certain white rots develop, dark zone lines form, as on this piece of sugar maple (A). This type of decay is called spalting. The turned bowl of spalped maple was made by Mark Lindquist (B). (Photo A by Randy O'Rourke; photo B by Richard Starr)

apparently formed at intervals indicating successive advances of the incipient decay in the wood. When the wood is machined, the layers are exposed as thin lines on the surface and are called **zone lines**. Between the zone lines, wood in varying stages of decay may range from normally hard to punky. The term **spalped wood** is commonly used to describe wood with zone-lined decay. Items of unusual beauty such as bowls or plaques can be made from spalped wood, as long as the wood is firm enough to be machined and finished.

Dealing with fungi requires understanding their life cycle and their requirements for development (*Figure 2.48*). Fungi propagate by tiny single-celled spores. A spore, carried by the winds, is brought into contact with a wood surface. If conditions are favorable, the spore develops a threadlike filament called a **hypha**. The hyphae proliferate by branching

and rebranching. A mat of hyphae, which is called a **mycelium**, may appear as a cottony mass on wood surfaces.

As invasion of the hyphae continues, fruiting bodies may form. In blue-stain fungi, these are tiny structures bearing spores, which appear as dark specks to the unaided eye. In other fungi, these fruiting bodies, sometimes called **conks**, appear as knoblike or shelflike projections on the decayed wood. Spores develop within crevices or holes in the under-surface of the fruiting body. The life cycle is thus perpetuated. Spores are produced in such excessive numbers that it is estimated that our every breath contains fungal spores. We must assume that the air always contains fungal spores and that they will inoculate any wood surface in a condition favorable to decay.

There are four basic requirements for wood-inhabiting fungi to thrive. Rendering any one of these unsuitable can control fungi.

Temperature is the first condition—between 75°F and 90°F is optimum. Beyond the extremes of 40°F and 105°F, growth essentially stops. Unfortunately, humans also thrive at temperatures favorable to fungi, so regulating temperature is not a practical way to prevent attack. However, temporary storage in refrigerators or freezers is a most effective, albeit expensive, way to prevent deterioration, especially for green wood.

Fungi also need oxygen. Waterlogged wood does not decay because of the absence of oxygen. Approximately 20% air volume in the wood is needed for fungal development. If green wood of high moisture content is kept from drying out, fungi can be held in check. But again, most wood we use cannot be kept in this manner.

Moisture content is also a factor. The optimum level is at or slightly above the fiber saturation point (about 30% moisture content), in which the cell walls are saturated but the cell cavities are essentially empty. Fungi can develop in wood with average moisture content as low as 20%. Drying wood quickly down to below 20% moisture content and keeping it dry is the principal way to prevent fungal deterioration, and one of the main reasons for drying wood is to prevent fungi from developing.

In dealing with moisture requirements, as with oxygen and temperature, making the conditions unsuitable merely causes a fungus to go into dormancy, in which state it can survive for many years. If favorable conditions are restored, development may resume. This is perhaps the explanation for the fallacy about **dry rot**—there is really no such thing. A few species of fungi capable of infecting wood of low moisture content are called **dry-rot fungi**. Although they are capable of transporting moisture to the areas of infection, these fungi cannot develop in wood with total lack of




Figure 2.48 • The life cycle of a typical wood-inhabiting fungus: Microscopic airborne spores (A) are carried by winds and air currents to potential hosts (B), such as logs, lumber, and wood products. If conditions are suitable, the spores produce filament-like hyphae, which elongate and branch (C), then multiply, spreading through the wood (D) or forming a cottony surface mat or mycelium. Advanced stages of the fungus produce fruiting bodies, often appearing as shelflike or bractlike conks (E) on wood surfaces. In tiny crevices on the undersides of the conks, myriad spores are produced, which, when mature, are released into the air and carried to the next potential host.

moisture. Wood must be moist to decay. However, sometimes wood that undergoes intermittent wetting and decay is inspected during a dry period. The rotted wood, now powdery dry, is interpreted as dry rot.

Food is the fourth requirement. The sapwood of most species is suitable, both because it lacks extractives and because it contains carbohydrates stored in parenchyma cells. The heartwood may be naturally decay-resistant if

extractives are toxic or repellent to fungi. Woods vary considerably in decay resistance or durability (*Table 2.1* on p. 44). Where it is impossible or impractical to keep wood below 20% moisture content, the next best approach is to choose a durable wood or wood that has been impregnated with a chemical preservative. The subject of fungal control will be further discussed in connection with drying wood and with finishing and treating it.

TABLE 2.1—Comparative resistance of heartwood to decay.

Resistant or very resistant	Moderately resistant	Slightly or nonresistant
Baldcypress (old growth)	Baldcypress (young growth)	Alder
Catalpa	Douglas-fir	Ashes
Cedars	Honeylocust	Aspens
Cherry, black	Larch, western	Basswood
Chestnut	Oak, swamp chestnut	Beech
Cypress, Arizona	Pine, eastern white	Birches
Junipers	Pine, longleaf	Buckeye**
Locust, black*	Pine, slash	Butternut
Mesquite	Tamarack	Cottonwood
Mulberry, red*		Elms
Oak, bur		Hackberry
Oak, chestnut		Hemlocks
Oak, gambel		Hickories
Oak, Oregon white		Magnolia
Oak, post		Maples
Oak, white		Oak (red and black species)**
Osage-orange*		Pines (most other species)**
Redwood		Poplars
Sassafras		Spruces
Walnut, black		Sweetgum**
Yew, Pacific		Sycamore
		Willows
		Yellow-poplar

*These woods have exceptionally high decay resistance.

**These species, or certain species within the groups shown, have higher decay resistance than most of the other woods in their respective categories.

INSECT DAMAGE

Many different insects cause damage to wood; some in living trees as they grow, some in harvested logs and in sawn lumber, others in finished products. Here are a few of the familiar types of damage that are encountered by woodworkers.

Pith flecks, which occur in living trees, are caused by larvae of tiny flies (*Diptera*) belonging to the genus *Agromyza*. These flies burrow downward in the tree stem along the cambial layer during the growing season. The tunnels damage the cambium and become occluded with scar tissue. When the wood eventually is machined, the tunnels are revealed on exposed surfaces as dark brown blemishes. They appear as an oval or oblong spot in cross section but as a somewhat irregular or intermittent streak along longitudinal surfaces (*Figure 2.49*).

At first glance, these defects may resemble the pith of some woods—hence, the name **pith flecks** or **medullary spots**. Pith flecks commonly occur in a number of species, notably in gray, river, and paper birches and in red and silver maples. They also occur sporadically in other maples and birches and in many other hardwoods, including basswood, willow, cherry, and aspen. Because pith flecks are small in size and well distributed, their structural damage is insignificant—and whether they should be considered visual defects or simply visual characteristics is arbitrary.

Bore holes in various sizes are mainly the work of beetles. While many attack logs after harvest or sawn lumber during air-drying (and may inadvertently be included in processed material), some will attack the dry wood in finished products. In the latter case, **powder-post beetles** are one of the most common types. These small, cylindrical beetles lay their eggs in minute seasoning checks or in open



Figure 2.49 • Pith flecks on the tangential surface of this paper birch plank were formed by larvae of tiny flies that burrowed down the tree stem along the cambial layer. (Photo by Randy O'Rourke)

pores, especially in coarse-textured hardwoods such as ash, oak, and chestnut. The larvae burrow through the wood in quest of the carbohydrates stored in parenchyma cells, hence their damage is concentrated in sapwood. Their presence usually goes undetected until the adults emerge from the surface and small amounts of the powdery frass sift out of the exit holes. If the adults reinfest the same piece of wood repeatedly, the interior of the wood eventually becomes a maze of tunnels packed with powdered wood.

Infected wood should not be used, for once established, the beetles are difficult to exterminate. Control measures should therefore focus on prevention. For most products, a continuous film of finish or paint is highly effective in sealing the pores or checks in which the eggs can be laid. Attacks are most common in unfinished hardwoods used in structural members, farm implements, and tool handles.

Two additional insects, **termites** and **carpenter ants**, deserve mention in view of the devastating damage they cause in stored lumber and wood structures. Both insects are

social, and their colonies have a preference for moist wood. In fact, the most common species of termites (**subterranean termites**) must maintain contact with the soil. Termites live in complete seclusion and remain unseen except when some winged adults emerge and swarm in flight, usually in the spring, to establish an outpost colony. Termites actually consume wood for sustenance, and where conditions are favorable, damage will continue to spread. Carpenter ants, on the other hand, do not eat wood, but excavate galleries to provide shelter. As an ant colony becomes large, the galleries can become extensive enough to cause serious structural damage, usually in a concentrated location. The large black adults can often be seen scavenging for food in the vicinity of an active colony.

For both termites and carpenter ants, the key to prevention is keeping wood dry and isolated from the ground. Wooden parts of buildings should be well above soil surfaces, and construction should be properly designed, constructed, and maintained to avoid leakage of rainwater.




Figure 3.1 •To examine the surface of a wood sample, hold the lens close to the eye, then bring the sample toward the lens until the surface comes into focus. Maintain focus by butting the hands together and bracing them against the cheek. (Photo by R. Bruce Hoadley)

WOOD IDENTIFICATION

Because of the wide range of woods, success in identification is quite unpredictable. The beginner in this fascinating game should be forewarned that although some species can be identified accurately at a glance, others defy final separation even by experts using the most sophisticated equipment. Happily, the vast majority occupy a middle ground where systematic examination and comparison with known wood features are usually successful, and it's possible to attain a satisfying level of skill in identification. By diligent examination of wood features, particularly those found on end-grain surfaces, any woodworker can learn the distinguishing characteristics of commonly encountered woods (*Figure 3.1*).

It is tempting to take the "looks-like" approach, where you simply look at a piece of wood and decide what it resembles. I have known old, experienced lumbermen who

could plod through a drying yard and identify nearly every board at a glance, but they weren't always right. And when they were wrong they were often off by a mile. The other problem with the "looks-like" method is that you usually don't know when you're looking at a wood you've never seen before. Every wood is apt to look like another wood once in a while (*Figure 3.2*). A far better approach is to study anatomical features. Identification by gross features (visible to the unaided eye) is usually possible only after considerable experience and knowledge gained through study under magnification.

The most reliable approach is based on minute or microscopic features, which means observing thin sections of wood under a microscope. Microscopic examination is most important with softwoods, where visual features are characterized more by similarity among woods than differences; in




Figure 3.2 • Identification by easily visible features can be quite unreliable. For example, in A, the similar appearance of a light-colored ray fleck against a darker background can lead to confusion between yellow-poplar (top) and black cherry (bottom), especially when the original heartwood color has been changed by staining and aging. When viewed in cross section (B), the light line of terminal parenchyma will easily distinguish yellow-poplar (C). (Photo A by Randy O'Rourke; photos B and C by Richard Starr)

many instances the only basis for separation is minute features (*Figure 3.3*). Considerable study is required to gain skill in using the microscope and sufficient acquaintance with all the necessary features, as well as with the extent of variation to be expected among individual pieces of the same species (*Figure 3.4*). Many excellent references on the subject are listed in the bibliography on p. 272.




Figure 3.3 • Three species of pine common in New England antiques are easily differentiated by microscopic examination of the radial sections at 400x power. The definitive features are the appearance of the ray tracheids and the nature of the pits in the ray parenchyma cells. (Photos by R. Bruce Hoadley)

As a compromise, however, identification based on macroscopic features (those discernible under slight magnification) is perhaps best suited to the needs of the average woodworker. This method has the advantage of requiring only simple equipment, and yet the number of woods that can be identified far surpasses what can be mastered with the naked eye. The consistent and unique combinations of anatomical features in hardwoods make macroscopic identification quite effective. In addition to the end-grain "cellular fingerprint," other obvious features such as color, luster, density, and hardness are also considered.

The standard magnifier used for macroscopic identification is the 10-power (10x) lens. The most common types are shown in *Figure 3.5*. Hold the lens close to the eye in good light, then move the piece of wood toward the lens until it comes into focus. By butting hand to hand and hand to cheek, you'll be able to hold the eye, the lens, and the wood sample in constant position with maximum visibility of the cell structure (*Figure 3.1*).




Figure 3.4 • Spiral thickenings on the inner walls of earlywood tracheids, the most definitive identification feature of Douglas-fir, appear under the microscope as fine coil springs. Even a tiny sliver can be positively identified by this constant feature. (Photo by R. Bruce Hoadley)



Figure 3.5 •Tools for macroscopic identification are few and simple: a 10x hand lens and a means of cutting wood surfaces cleanly. A very sharp knife or an industrial single-edged razor blade is satisfactory (A). Some lenses have built-in lights (B). (Photos by Randy O'Rourke)

The most common pitfall in identification work is not producing a cleanly cut surface. In order to see cell structure clearly, the end grain must be severed by a flat, clean slice and be as free of cellular disturbance as possible (*Figure 3.6*). In principle, any sharp tool that can make a slicing cut will suffice. An ordinary pocketknife, if keenly sharpened, will do nicely. Few of us, however, routinely sharpen that well.

My favorite routine is to whittle down the wood so the area to be cut forms a small plateau of perhaps $3/16$ in. square. I then make a pass or two with a single-edge razor blade for the final surface. In most woods, the area to be cleaned up need be only a small area within a single growth ring. In other cases, as when looking for resin canals, a larger area of the sample may have to be surfaced.




Figure 3.6 •The cleaner the cut, the more detail is revealed. Compare these cross sections of red oak that were cut with a saw (A), a dull knife (B), and a razor blade (C). (Photos by R. Bruce Hoadley)

The best razor blades to use are those sold for industrial purposes such as slicing leather or scraping; the edge on blades sold for shaving is too fragile for any but the softest woods. By holding the wood with fingers well below the surface to be cut and by butting the knuckles of the third, fourth, and fifth fingers against the piece, you can safely slide the single-edge blade across the wood surface (*Figure 3.7*). Transverse surfaces are the most difficult to cut cleanly; radial and tangential surfaces are much easier.

On uneven-grained woods, it is important to orient the blade edge perpendicular to the growth rings so that at any moment of cutting, the blade edge engages equal amounts of earlywood and latewood. If the blade is held parallel to the rings, it will advance unevenly as the blade alternately encounters earlywood and latewood, and a washboard sur-




Figure 3.7 • When slicing a sample, hold the wood with the fingers well below the surface to be cut. (Photo by Randy O'Rourke)




Figure 3.8 • For the cleanest cut, hold the blade firmly and move it in the direction of the arrow. This produces a slicing cut. Make a thin cut on a very small area. Moistening the surface of the wood will improve cutting, especially in very hard woods.

face will result. The secret is sliding the edge (Figure 3.8). Most woods can be cut as they are, although it helps to moisten some woods. Soak the hardest, most difficult-to-cut woods in hot water first.

WHAT TO LOOK FOR

In learning to identify woods, first gain an acquaintance with the pertinent structural features, both gross and macroscopic. These features are discussed below, with summary review of those I've already described. The features described are pointed out in photos of representative species on pp. 55-73.

SAPWOOD/HEARTWOOD If a piece has both heartwood and sapwood, the combination is usually discernible. If only one is present, a distinct or dark color may indicate heartwood; a light, neutral color may be sapwood. Heartwood color is important in identification.

GROWTH RINGS The width of growth rings is sometimes a salient characteristic. For example, rings are typically narrow in ponderosa pine and wide in willow. Wide variation may exist within some species, such as redwood, and wood samples used for identification should avoid extremes where possible because their anatomical features may be atypical.

The degree of evenness of grain is usually characteristic for a species. Where reasonable unevenness exists, the nature of the transition from earlywood to latewood may also be significant. An **abrupt transition** indicates a sharp delineation between the larger, thin-walled cells of the earlywood to the smaller, thick-walled cells of the latewood. The term **gradual transition** indicates no clear delineation between earlywood and latewood.

Special features of growth rings, such as the fluted contours typical of butternut, American hornbeam (Figure 3.9), and basswood, may be important.




Figure 3.9 • Fluted or wavy growth rings are characteristic of butternut (A) and American hornbeam (B). (Photos by Randy O'Rourke)

TEXTURE Texture refers to the relative tracheid diameters in softwoods or the relative pore size in hardwoods. As a macrofeature for classification, fine, medium, and coarse texture are the customary terms.

RESIN CANALS Resin canals are present in four genera of softwoods—pines, spruces, larches, and Douglas-fir. The number, distribution, and size of resin canals are characteristics used for identification (*Figure 3.10*).

PORES In hardwoods, pore size, distribution, arrangement, and abundance are important identification aids. Distribution of pores within the growth rings—i.e., ring-porous, semi-ring-porous, or diffuse-porous—is the customary initial consideration. As seen in cross section, localized groupings can also have characteristic arrangements.

Solitary pores appear singly, bounded entirely by other cell types. **Wavy bands of pores**, as in elm or hackberry, form undulating concentric lines in the latewood and are a most convenient identification feature. **Pore multiples**, common in hickories and birches, refer to two to several pores in close radial arrangement. **Pore chains** are long radial rows in actual contact or apparent close arrangement, as in holly. Less specific radial arrangements appearing as flame- or fan-shaped groupings or irregular lines (oaks, chestnut, chinkapin) may likewise be characteristic.

PARENCHYMA Because of their small size, parenchyma cells are individually indiscernible even with a hand lens. In cross section, numbers of parenchyma cells arranged as lines or characteristically shaped patches may show up as lighter-colored tissue in contrast with the darker fiber masses. (Tracheids, which are of about the same diameter and cell-wall thickness, may also be intermixed with parenchyma in lighter-colored tissue in oaks, ashes, and chestnut.)




Figure 3.10 • Numerous, uniformly distributed resin canals are easy to see in this piece of eastern white pine. (Photo by Randy O'Rourke)

Terminal parenchyma designates formation of this tissue at the end of the growth ring. Yellow-poplar, for example, is the epitome of diffuse-porous structure, and growth rings in this wood might not be recognizable were it not for the distinct line of terminal parenchyma. This feature is also present in true mahogany (*Swietenia* spp.).

Lines of parenchyma within the growth ring are termed **banded parenchyma**. These are clearly visible in all species of hickory. Shorter or less distinct lines of banded parenchyma are features of some species, such as oaks. Light-colored tissue associated with pores (paratracheal parenchyma) is said to be **paratracheal vasicentric** if it encircles a single pore. In some cases, the parenchyma that encircle adjacent pores merge, forming **confluent** parenchyma, as in the latewood of white ash. The distinction between latewood pores joined by confluent parenchyma and the wavy bands of pores (as in elm) should be noted as an identification aid.

RAYS In softwoods, rays are not distinctive macroscopic features. In hardwoods their appearance is important in all three planes. In cross section their size (especially in relationship to pore size), apparent number and spacing, and visual distinctiveness (they range from distinct to the naked eye to invisible even with a lens) are important. In some species, the apparent straightness of the rays versus a tendency to weave through the pores may be characteristic. Ray height and the relative distribution of rays can best be judged on a tangential surface (*Figure 3.11*). On radial surfaces, **ray fleck** may be distinctive (*Figure 3.2, A*).

TYLOSES The presence or absence of tyloses as well as the relative abundance of tylosis formation is usually a consistent feature of hardwood pores.




Figure 3.11 • The distinctive ray patterns identify these rulers as being made of maple (top), beech (center), and sycamore (bottom). (Photo by Randy O'Rourke)

PHYSICAL PROPERTIES

Several physical properties that can be perceived with the naked eye or by unsophisticated methods are sometimes unique, either alone or in combination with other features, and can aid greatly in identification.

COLOR In terms of both hue and shade, color should routinely be noted in examining wood. It is sometimes unique for a particular species. In eastern redcedar, for example, the purple hue and deep shade of the heartwood make identification quite easy. Similarly, the heartwood color of redwood, black walnut, amaranth (purpleheart), and padauk (vermillion) are renowned. In some species, wide variation may be normal. Yellow-poplar has a fairly broad layer of creamy white sapwood. The heartwood is commonly medium to deep green, although variations ranging from pinkish or purplish to almost inky black are sometimes encountered.

In some species, the color, although consistent, is common to a host of other species and therefore not distinctive. It should also be noted that surface color is greatly affected by exposure to daylight and air and may change drastically with time. For example, the deep purple of eastern redcedar ages rapidly upon exposure to daylight to a nondistinct medium brown.

LUSTER Light reflectivity or sheen is occasionally distinctive for a particular species. The side-grain surfaces of spruce are considered lustrous in relation to those of redwood, which by comparison are dull.

ODOR Although distinctive for only a few woods, odor may be a most useful feature. Species for which it is an especially noteworthy trait include eastern redcedar, Douglas-fir, sassafras, teak, and incense-cedar. The ability to detect odor varies, but some people find the more subtle odors of basswood, baldcypress, and catalpa distinctive enough to be helpful in identification. Odor is most pronounced in freshly cut material and may be strengthened by moistening the wood. Unfortunately, it can also be transferred to adjacent wood by close contact. Many a wood identification student is dismayed to find that all assorted wood samples packed in a tightly closed box smell like the one eastern redcedar sample.

DENSITY AND HARDNESS These physical properties relate to the relative weight of wood and its surface compressive strength properties, respectively. Specific numerical data on these properties are available (see *Figure 1.13* on p. 14), but they are also helpful in a grossly general sense. A close correlation exists between density and hardness, and if a numerical rating of density is known for a species, hard-

ness can often be estimated. Running one's thumbnail perpendicular to the grain direction across a side-grain surface gives a surprisingly meaningful measure of hardness. The difference in hardness between butternut and black walnut, for example, can usually be detected with a little practice.

IDENTIFICATION TECHNIQUES

There is no best or single technique for identifying wood. The most useful technique in any situation does depend on the degree of difficulty of the particular wood and the experience and skill of the individual doing the identification. The available aids include known samples of wood, manuals and photographs of wood characteristics, and identification keys. Each has advantages and disadvantages.

Collections of known samples are extremely valuable, for they allow direct viewing of features that may be difficult or impossible to describe accurately in words. Samples can be used for direct visual comparison by holding them side-by-side with the unknown being considered. They offer a palpable sense of the wood's physical properties. But collections of single samples are risky because the observer has no way of measuring how typical each sample is. Still, it's a good idea to save small pieces of stock, drill holes in them, and string them together. Accumulating such multiples will aid immeasurably in sensing the variation within a species.

Good photographs of wood structure taken at an appropriate magnification are nearly as helpful as actual samples. An advantage is that the woods photographed were probably chosen to typify the species.

Verbal descriptions of the anatomical features of particular species appear in various texts and identification books. They may include general information, physical properties and source, and gross, macroscopic, and microscopic features. They are commonly accompanied by macro- and microphotographs of wood surfaces or sections. The information is systematically arranged for convenient comparison with the sample in question. Such material is most useful in confirming a tentative identification or in comparing two possible choices. The difficulty is in narrowing down the choices enough to locate the definitive description.

The use of keys is another approach to identification. An identification key can be thought of as an information tree (*Figure 3.12*). The tree always branches into forks, and the identity of a particular species is found at the tip of one of the twigs.

To use the key, you start at the bottom and proceed upward. At the first fork, you decide which limb to take by considering the two choices given, each a statement of wood characteristics. You take the limb that correctly describes the




Figure 3.12 • An identification key is like a branching tree. As one climbs, successive limbs lead to a definitive twig.

wood in question and ascend to the next fork. And so on until you eventually reach a twig where the identity of your wood is given.

Keys typically appear as paired, numbered statements (*Table 3.1*). Based on the features of the wood being examined, the user of the key chooses the appropriate statement in each pair. This choice in turn leads to another choice and so on until a species is reached. The portion of a typical key reproduced on p. 54 indicates their general form. (Several excellent keys are mentioned in the bibliography on p. 272.)

If you follow a key through either forward or backward, you can compile a list of wood features for a particular species. Some keys are based -solely on macroscopic features, some solely on microscopic features, and others on a combination of both.

There are two serious drawbacks to keys, however. The first is that if a wrong choice is made, you can proceed on an incorrect path to an incorrect solution without realizing it. The novice often goes astray because many of the necessary

choices are based on subjective considerations and judgment developed through previous acquaintance with wood anatomy. The second pitfall is trying to identify a wood that isn't even on the key being used. This can happen, especially with a totally unknown wood.

Choose keys carefully. Try to find fairly detailed ones that include the woods of a given geographic area. Beware of keys that are abbreviated or cover a small number of species. A key for the "10 most common woods of the United States" would surely invite trouble, since you would be quite likely to encounter a wood that isn't included.

After considerable practice in identification and after becoming familiar with routine wood features, you can usually tell when a wood "isn't keying out right" because it isn't in the key. But this further suggests that keys are better for the advanced than for beginners. As you get more and more practice with common woods, you quickly recognize an exotic wood when you encounter it.

Identification is important in the woodshop. A woodworker may want to identify a piece of scrap or need to

TABLE 3.1—Part of a typical identification key. Enter the key at the top and make a choice between the two options. That choice will lead you to another, and so on.

Identification Key

1. Wood without pores; rays not distinct without using lens 2
1. Wood with pores; rays sometimes visible to the naked eye 14
2. Resin canals visible as light- or dark-colored dots on **cross** section or as tiny interrupted streaks on radial or tangential surface 3
2. Resin canals not easily visible to the naked eye or with a hand lens 7
3. Wood rather hard to cut across grain, latewood usually prominent on cross section 4
3. Wood softer, easier to cut, latewood not as prominent 5
4. Numerous resin canals, wood shades of yellow brown southern yellow pine
4. Resin canals not numerous, wood with an orange-red cast; when moistened, wood has a distinct odor Douglas-fir
5. Latewood distinct, sharp boundary with earlywood in the same growth ring, latewood clearly contrasted on tangential surface. Wood frequently dimpled (appear as indentations). Resin canals appear as pale dots, not holes, on cross section ponderosa pine
5. Latewood indistinct, gradual boundary with earlywood in the same growth ring, not contrasty on tangential surface. Resin canals appear as open holes on cross section 6
6. Resin canals large and numerous, appearing as brown streaks on radial or tangential surfaces sugar pine
6. Resin canals smaller and less numerous, not as prominent on radial or tangential surfaces western or eastern white pine
7. Heartwood a dark shade of brown, red brown, or purplish brown 8
7. Heartwood a light shade of tan or cream 11
8. Purplish to rose-brown, frequently with small spots of cream-colored wood enclosed. Cells small, wood smooth-cutting. Distinctive cedar-chest odor eastern redcedar
8. Dull brown to reddish brown, cells larger; or if orange-brown, more resistant to cutting 9

know the identity of a broken chair part for a correct replacement. Perhaps the species of wood in an antique must be determined. We must assume the woodworker is acquainted with gross and macroscopic anatomical features and with the woods he has used before. When the piece is examined, certain features should be noted immediately—hardwood or softwood, evenness of grain, tyloses in the pores, parenchyma arrangements, size of rays, and so on. Certain species are automatically eliminated as the list of possibilities is mentally narrowed down. The exercise usually concludes at one of these three points:

1. The wood appears to be species A, based on features familiar to the observer from previous experience and that are clearly definitive of the species. Comparison with a known sample and review of a written description help confirm the choice—or reject it.
2. The wood is probably species A or B or C, or might even be species D. Again, samples of the possible choices should be examined and descriptions reviewed, being especially alert for distinguishing features. In both of these cases, the person's experience has in effect mentally traversed most of the keys, arriving at or near the end. Plowing through a key would have been a tedious waste of time.
3. The features observed do not suggest any answer. The wood is definitely unfamiliar. At this point the keys are the things to use. When an answer is reached, the choice should be carefully compared with check samples if available or with written descriptions or photographs. Extreme care must be taken in deciding whether the identification is indeed correct or whether the wood might in fact be a species not even included in the key.


The importance of circumstantial evidence cannot be overemphasized. For example, in the identification of timber excavated from the site of an early 19th-century sawmill in western Massachusetts, the half-decayed fragments could be identified only as hemlock (*Tsuga* sp.). Because of where the wood was found, it was easy to conclude that it was eastern hemlock (*T. canadensis*) rather than western hemlock (*T. heterophylla*). Likewise, under similar circumstances, the sections shown in *Figure 3.3* could be narrowed to eastern white pine (*Pinus strobus*) rather than western white pine (*P. monticola*), red pine (*P. resinosa*) rather than Scots pine (*P. sylvestris*), and pitch pine (*P. rigida*) rather than other hard pines (*Pinus* spp.).

MACROPHOTOGRAPHS

Presented in the following pages are macrophotographs of 54 common species. Although inclusion of a complete wood identification manual and keys is beyond the scope of this book, this section should give the reader a survey of basic macroscopic anatomical features, which are critical to the

identification and understanding of wood. The reader is urged to use the photos along with known or unknown samples viewed with a 10x hand lens as a practice exercise. Photos approximate the resolution possible with such a lens. The accompanying descriptions cover both gross and macroscopic features and properties. (All photos in this section are by R. Bruce Hoadley.)

DOMESTIC SOFTWOODS



Eastern white pine (*Pinus strobus*)


Moderately soft and light (average specific gravity 0.35). Heartwood creamy white to light brown, often with a reddish tinge, aging to a much darker color. Pleasant resinous odor. Medium texture. Fairly even grain, growth rings indistinct to distinct. Earlywood (A) occupies majority of growth ring with gradual transition to narrow band of latewood (B). Resin canals (C) medium-sized, visible to the naked eye, numerous, and uniformly distributed but confined mainly to outer portion of growth rings. Rays of two sizes: narrow rays visible with hand lens and rays containing horizontal resin canals (D) sometimes visible without lens.


Sugar pine (*Pinus lambertiana*)

Moderately soft and light (average specific gravity 0.36). Heartwood buff or light brown, sometimes with a reddish tinge.

Faint resinous odor. Texture medium-coarse to coarse. Fairly even grain with gradual transition from earlywood (A) to narrow latewood (B), growth rings distinct. Resin canals (C) numerous, uniformly distributed, largest among coniferous species, clearly visible to naked eye; contents migrating onto wood surfaces or into adjacent cell structure often make resin canals even more conspicuous. Rays of two widths: larger rays containing transverse resin canals visible with unaided eye.

Transverse resin canals usually appear as distinct dark specks on tangential surface.







Southern yellow pine (*Pinus* spp.)

Moderately hard and heavy (average specific gravity 0.48 to 0.59). Heartwood ranging from shades of light or yellow brown to orange or reddish brown. Wood resinous and with distinct resinous odor. Texture medium. Extremely uneven grain; annual rings distinct and prominent on all surfaces. Abrupt transition from earlywood (A) to very dense latewood (B), which commonly occupies one-third to one-half the annual ring. Resin canals (C) numerous, medium-large, visible to naked eye, and uniformly distributed through latewood portions of growth rings. Rays of two widths: larger rays containing transverse resin canals visible to unaided eye.

Douglas-fir (*Pseudotsuga menziesii*)
 Moderately hard and heavy (average specific gravity 0.48). Heartwood orange-brown to deep reddish brown or sometimes yellowish brown. Characteristic resinous odor. Texture medium to medium-coarse. Uneven grain, earlywood (A) usually wider than latewood (B), with abrupt transition. Resin canals (C) indistinct to visible to unaided eye but distinct with hand lens, sporadically distributed, frequently in tangential groups (D) in the latewood. Rays of two widths: those with transverse resin canals (E) barely visible to naked eye.





Tamarack (*Larix laricina*)

Moderately hard and heavy (average specific gravity 0.53). Heartwood yellowish brown to reddish or russet brown. Wood has a somewhat waxy or greasy feel. Texture medium. Uneven grain, abrupt transition from earlywood (A) to latewood (B). Resin canals small, inconspicuous or invisible to naked eye, sparse or sporadically distributed, mainly in latewood, solitary (C) or in tangential groups (D). Rays of two sizes visible with hand lens.

Eastern spruce (*Picea* spp.)

Moderately soft and moderately light (average specific gravity 0.40). Wood creamy white or pale yellowish brown (sapwood not distinct from heartwood), lustrous. Texture medium-fine.

Moderately even grain, growth rings fairly distinct, transition gradual from earlywood (A) to narrow latewood (B). Resin canals very small, usually not visible to unaided eye, appearing as pale yellow or whitish dots with hand lens, unevenly distributed, solitary (C) or in small tangential multiples. Rays of two widths: narrow rays visible only with hand lens and larger rays with resin canals (D) barely visible to the unaided eye.


**Eastern hemlock** (*Tsuga canadensis*)


Moderately hard but moderately light (average specific gravity 0.40). Wood buff or pale brown, sometimes with a faint reddish or purplish tinge. Sapwood not always distinct from heartwood. Texture medium. Fairly uneven grain. Latewood (A) distinctly dense, occupying one-third or less of the ring; transition variable, semi-abrupt to abrupt. Normal resin canals absent. Rays very fine, not visible to the unaided eye.

Western (true) fir (*Abies* spp.)

Moderately soft and light (average specific gravity 0.35). Wood pale buff to light brown, the darker latewood portion of the growth ring having a purplish cast (sapwood not distinct from heartwood). Texture medium-coarse, moderately even to moderately uneven grain, growth rings distinct, transition generally gradual to latewood (A). Normal resin canals absent.

Rays very fine, indistinct to the unaided eye.







Eastern redcedar (*Juniperus virginiana*)

Moderately hard and moderately heavy (average specific gravity 0.47). Heartwood vivid purplish red when freshly cut, fading to drab reddish brown with exposure; heartwood often with streaks or pockets of included creamy light sapwood. Characteristic fragrant odor. Texture very fine. Even grain, growth rings evident due to slightly denser latewood. Transition from earlywood (A) to latewood (B) gradual to semi-abrupt. Parenchyma with dark contents numerous, forming one or more dark zones (C) approaching false rings within the growth ring, sometimes visible to the unaided eye or distinct with hand lens. Rays very fine.

Western redcedar (*Thuja plicata*)
 Relatively soft and light (average specific gravity 0.32). Heartwood medium to dark coffee-brown. Characteristic cedar odor. Medium texture. Moderately uneven grain, growth rings distinct. Abrupt transition from earlywood (A) to narrow latewood (B). Parenchyma not visible or barely visible with hand lens, sometimes appearing as an indistinct tangential line in latewood. Rays (C) fine, inconspicuous without hand lens.




Redwood (*Sequoia sempervirens*)


Moderately soft and light (average specific gravity 0.37). Heartwood variable in color from light cherry to deep reddish brown. Very coarse texture; individual tracheids clearly visible with hand lens on cleanly cut cross-sectional surfaces. Ring width variable from wide to very narrow; grain fairly uneven to moderately even. Transition from earlywood (A) to latewood (B) abrupt. With hand lens, parenchyma visible on longitudinal surface as strands of dark reddish specks. Rays (C) distinct as light lines against darker background on cross section.

Baldcypress (*Taxodium distichum*)


Medium soft and medium light (average specific gravity 0.46). Heartwood variable in color from light or dark yellowish brown to medium reddish brown. Wood has a greasy or waxy feel, sometimes with a rancid odor. Very coarse texture; individual earlywood tracheids clearly visible with hand lens on cleanly cut cross sections. Growth-ring width variable (extremely narrow in old-growth trees); grain fairly uneven in wider rings of second-growth timber. Transition from earlywood (A) to latewood (B) fairly abrupt. With hand lens, parenchyma visible on longitudinal surfaces as short lines of dark reddish specks. Rays (C) distinct as light lines across darker background on cross sections.



DOMESTIC HARDWOODS

**Red oak** (*Quercus* spp.)



Hard and heavy to very heavy (average specific gravity 0.63). Heartwood light reddish brown, often with a pinkish or flesh-colored tinge. Ring-porous, with distinct earlywood (A), up to four pores in width, transition from earlywood to latewood abrupt. Earlywood pores distinct to the naked eye, usually lacking tyloses (B) and surrounded by lighter tissue (C). Latewood pores (D) distinct with hand lens, few enough to be countable, and arranged in single or branching radial rows, surrounded by lighter tissue (E). Tangential lines of parenchyma often visible against darker fiber mass in latewood (F). Extremely large rays (G) visible easily to the naked eye; small rays (H) just discernible with hand lens. On tangential surfaces, large rays average 3/8 in. to 3/4 in. in height, tallest only occasionally more than 1 in.

**White oak** (*Quercus* spp.)

Hard and heavy to very heavy (average specific gravity 0.67). Heartwood light to dark brown, often with grayish cast. Ring-porous with distinct earlywood (A) up to three pores wide, transition to latewood usually distinct. Large earlywood pores (B), usually with abundant tyloses in heartwood and surrounded by lighter-colored tissue (C). Latewood pores (D) from distinct to indistinct, too numerous to count, arranged in radial groups intermingled with lighter tissue (E). Tangential lines of parenchyma (F) usually visible against darker fiber mass in latewood. Extremely large rays (G) visible to naked eye; narrow rays (H) barely discernible with hand lens. On tangential surfaces, rays commonly exceed 1 in. in height, tallest may be several inches.

American chestnut (*Castanea dentata*)



Moderately soft and moderately light (average specific gravity 0.43). Heartwood light to medium or grayish brown. Wood ring-porous. Earlywood zone several pores wide (A), pores distinct to unaided eye, typically oval in the radial direction, with abundant tyloses (B). Latewood pores numerous, small, barely discernible with hand lens, and arranged in more or less radial (C) or wandering around earlywood (D) and latewood pores (C). Rays all fine, barely discernible with hand lens.

**American elm** (*Ulmus americana*)

Moderately hard and heavy (average specific gravity 0.50). Heartwood brown or reddish brown. Interlocked grain common. Ring-porous, earlywood comprises the largest pores usually in a single row (A); pores usually have abundant tyloses (B). Transition to latewood abrupt. Latewood pores small and numerous, arranged in wavy bands (C). Rays not distinct to the unaided eye but visible as uniformly narrow light lines with hand lens (D).

White ash (*Fraxinus americana*)


Moderately hard and heavy (average specific gravity 0.60). Sapwood creamy white, usually wide. Heartwood medium to grayish brown, often streaked or blotchy. Wood ring-porous, pores distinct. Earlywood zone two to four pores wide, pores surrounded by lighter-colored tissue (A). Abrupt transition from earlywood to latewood. Latewood pores solitary (B) or in multiples of two or three (C). Lighter parenchyma encircles latewood pores and unites them into lateral groups, especially in the outer latewood (D). Rays appear as fine light lines with hand lens (E).


**Shagbark hickory (*Carya ovata*)**

Very hard and heavy (average specific gravity 0.74). Sapwood creamy white to tan, heartwood pale to medium brown, sometimes blotchy or streaky with darker color. Wood ring-porous, earlywood pores visible to naked eye, largest pores in a single row (A) interrupted by areas of fiber tissue (B). Transition from earlywood to latewood abrupt. Latewood pores smaller, solitary (C) or in multiples of two to four (D). Rays not visible to the naked eye. With hand lens, rays appear as distinct radial lines, forming a meshlike pattern with equally distinct tangential lines of banded parenchyma (E).

Northern catalpa (*Catalpa speciosa*)

Moderately soft and moderately light (average specific gravity 0.41). Heartwood grayish brown to medium brown, with a distinctive odor, somewhat musty or spicy. Usually ring-porous, earlywood zone usually wide, up to several pores in width (A), with abrupt transition to latewood. Sometimes semi-ring-porous, with gradual earlywood to latewood transition. Latewood pores small solitary (B), grouped in small radial multiples (C) and clusters, tending to form longer clusters (D) and merging into bands (E) toward outer margin or ring. Rays (F) indistinct to unaided eye but visible as fine bright lines with hand lens in the latewood.





**Black locust** (*Robinia pseudoacacia*)

Very hard and heavy (average specific gravity 0.69). Heartwood yellowish or golden brown, often with a greenish cast. Ring-porous, the earlywood zone two or three pores wide (A). Latewood pores small, arranged in nested clusters (B), joined laterally into loosely defined bands toward the outer margin of the growth ring (C). All pores densely packed with tyloses, giving an overall flat yellowish appearance to the pores and making adjacent pores indistinct from one another. Rays (D) distinct as sharp yellow lines against the darker brown fiber mass of the latewood.

Blackwalnut (*Juglans nigra*)



Moderately hard and heavy (average specific gravity 0.55). Heartwood light to deep chocolate brown, occasionally with a purple tinge; heartwood color may be variable in shade. Semi-ring-porous, pores grading in size from large and distinct to unaided eye in the earlywood (A) to small and visible only with hand lens in the outer latewood (B). Pores solitary (C) or in radial multiples (D). Tyloses present but variable in abundance (E). Parenchyma barely visible with hand lens as faint, fine, somewhat irregular tangential lines (F). Rays (G) indistinct to unaided eye, visible as fine lines with hand lens.

**Butternut** (*Juglans cinerea*)


Moderately soft and light (average specific gravity 0.38). Heartwood light to medium chestnut or ginger brown. Semi-ring-porous; pores grading in size from large and distinct (A) to small and indistinct (B), solitary (C), or in radial multiples (D). Tyloses variable in abundance. Parenchyma visible with hand lens as faint tangential lines (E). Rays (F) uniformly fine, visible with hand lens.

American beech (*Fagus grandifolia*)


Hard and heavy (average specific gravity 0.64). Heartwood light to medium brown or reddish brown. Diffuse-porous, pores small and distinct only with hand lens, evenly distributed through first-formed portion of growth ring (A); at outer margin of ring a zone of denser cell structure (B) with very small pores, indistinct even with hand lens. Rays variable in size, the largest (C) easily visible to the eye, the smallest (D) visible only with hand lens. Large rays are noded (swollen) at growth-ring boundary (E). (Rays appear on tangential surfaces as characteristic, variable-sized lines.)

**Sycamore** (*Platanus occidentalis*)

Moderately hard and moderately heavy (average specific gravity 0.47). Heartwood light to medium brown, often with orange or reddish tinge. Diffuse-porous; pores small and uniformly distributed through first-formed portion of growth ring (A), very small, scattered and indistinct in outer zone of growth ring (B), which appears lighter in color. Rays (C) visible to the unaided eye, uniformly large and evenly spaced, noded (swollen) at growth-ring boundary (D). On tangential surfaces, rays appear as uniform-sized lines somewhat closely but uniformly spaced.

**Red alder** (*Alnus rubra*)



Moderately soft and moderately light (average specific gravity 0.41). Wood light brown with reddish or peach hue. (No sapwood/heartwood distinction.) Diffuse-porous, with growth rings distinctly delineated by a fine line of contrasting (usually lighter) tissue (A). Pores numerous, small, solitary (B) or in multiples (C). Rays of two distinct sizes: numerous fine rays visible only with hand lens; large rays (D) few in number and irregularly distributed, easily visible to unaided eye.



Sugar maple (*Acer saccharum*)

Hard and heavy (average specific gravity 0.63). Heartwood light to medium reddish brown. Sapwood usually wide, near white or very light, with pale brown or reddish tinge. Diffuse-porous, pores solitary (A) or in radial multiples (B), indistinct without hand lens. Growth rings delineated by darker tissue (C) at growth-ring boundary. Rays of two sizes: small rays barely perceptible even with hand lens; large ones (D) visible to naked eye, as wide as or wider than largest pores. On tangential surfaces, rays usually appear as very fine but distinct lines, uniformly spaced but clearly smaller than in beech or sycamore. Pith flecks occasionally present.

Red maple (*Acer rubrum*)
 Medium hard and medium dense (average specific gravity 0.54). Heartwood pale to light brown, sometimes similar in color to light creamy sapwood, but often with a soft or distinct grayish cast. Diffuse-porous, pores solitary (A) or in radial multiples (B), indistinct without hand lens. Growth rings delineated by darker latewood tissue (C) at growth-ring boundary. Rays (D) variable in width, the widest visible to the naked eye and with hand lens appearing about as wide as the largest pores (but slightly narrower than widest in *A. saccharum*). On tangential surfaces, rays appear as uniformly spaced, short fine lines (but not as distinct as in *A. saccharum*). Pith flecks (E) common.





Black cherry (*Prunus serotina*)

Moderately hard and heavy (average specific gravity 0.50). Heartwood light cinnamon brown to dark reddish brown, sometimes variable. Diffuse-porous, pores small, distinct with hand lens, uniformly distributed, solitary (A) and in multiples and small clusters (B). A row of pores in the earlywood (C) delineates the growth rings. Rays (D) are distinct to naked eye, appearing as sharp light lines against the darker cell mass.

Yellow-poplar (*Liriodendron tulipifera*)

Moderately soft and moderately light (average specific gravity 0.42). Heartwood commonly green or greenish brown, occasionally shaded with purple, blue, black, yellow, or with streaks of various colors. Sapwood flat, creamy or grayish white ("white-wood"). Diffuse-porous, pores small, solitary (A) and in multiples (B). Growth ring distinct due to whitish or pale-yellow line of terminal parenchyma (C), clearly visible to naked eye.

Rays (D) also visible to naked eye (about as distinct as terminal parenchyma), often swollen (noded) at growth-ring boundary (E).


**American basswood (*Tilia americana*)**


Moderately soft and light (average specific gravity 0.37). Heartwood pale brown or creamy light brown. Freshly cut or moist wood has a characteristic musty odor. Diffuse-porous, pores fairly small, uniformly distributed, solitary (A) or in tangential or radial multiples (B). Growth rings delineated by terminal parenchyma (C). Rays (D) distinct with hand lens.

Yellow birch (*Betula alleghaniensis*)

Hard and heavy (average specific gravity 0.62). Heartwood light to medium brown or reddish brown. Sapwood often quite wide. Diffuse-porous, growth rings often indistinct. Pores barely visible to the unaided eye (vessel lines visible on longitudinal surfaces), solitary (A) or in radial multiples (B), many having whitish contents (C). Large pores clearly larger than widest rays.



Rays fine (D), generally not visible without hand lens.



**Paper birch** (*Betula papyrifera*)

Medium hard and medium heavy (average specific gravity 0.55). Heartwood light to medium brown or reddish brown. Sapwood creamy white or pale yellow. Diffuse porous growth rings often indistinct. Pores inconspicuous on cross-sectional surfaces, but vessel lines usually visible on longitudinal surfaces. Pores solitary (A) or in radial multiples (B), some appearing as whitish spots (C). Largest pores clearly larger in diameter than width of rays. Rays (D) fine, generally not visible without lens. Pith flecks (E) common.



Cottonwood (*Populus* spp.)
 Relatively soft and light to moderately light (average specific gravity *P. balsamifera* 0.34, *P. deltoides* 0.40). Heartwood light brown to grayish brown. Green wood often has a sour, unpleasant odor. Wood generally diffuse-porous, sometimes semi-diffuse-porous. Pores numerous, densely but uniformly distributed, solitary (A) or in radial multiples (B). Largest pores barely visible to unaided eye. Terminal parenchyma form a fine light line along the growth-ring boundary (C). Rays very fine, indistinct even with hand lens.

**Quaking aspen** (*Populus tremuloides*)

Moderately soft and light (average specific gravity 0.39). Sapwood near white, heartwood very pale brown. Wood generally diffuse-porous, sometimes tending toward semi-ring-porous appearance. Pores numerous, uniformly and densely distributed, solitary (A) or in radial multiples (B). Pores usually not visible to unaided eye. Terminal parenchyma forms a very fine light line along growth-ring boundary (C). Rays (D) very fine, indistinct even with hand lens.


Sweetgum (*Liquidambar styraciflua*)

Moderately hard and heavy (average specific gravity 0.52). Heartwood grayish brown or reddish brown, often streaked with lighter and darker shades. Diffuse-porous, growth rings scarcely discernible. Pores very small, barely visible even with hand lens, solitary (A) or in radial multiples (B). Rays numerous, visible as fine lines (C) with hand lens.

**Tupelo** (*Nyssa* spp.)



Moderately hard and heavy (average specific gravity 0.50). Heartwood grayish white or with greenish or brownish cast. Normally with interlocked grain. Diffuse-porous, growth rings only faintly visible. Pores very small, barely visible even with hand lens, evenly distributed, solitary (A) or in radial multiples (B). Rays (C) visible with hand lens as fine, closely spaced lines, in some cases only one pore-width apart.

TROPICAL HARDWOODS





Padauk (*Pterocarpus* spp.)—vermillion, red narra, maidou
Hard and heavy (specific gravity 0.77). Color variable from yellowish brown to bright orange to reddish brown or blood red, often with darker streaks. Grain usually interlocked but sometimes straight. Growth rings indistinct or may be distinct due to terminal parenchyma. Texture medium to moderately coarse. Vessels distinct without hand lens. Mostly diffuse-porous, pores solitary (A) and in radial multiples of two to ten (B). Parenchyma visible without hand lens, as tangential lines independent of pores (C), connecting pores (D), or extending laterally (E) from pores. Rays (F) fine, not visible without lens.

Purpleheart (*Peltogyne* spp.)—amaranth
Hard and heavy (average specific gravity 0.83). Heartwood brown when freshly cut, becoming deep violet-purple with exposure. Grain straight to interlocked. Growth rings sometimes delineated by light lines of terminal parenchyma (A). Texture fine, pores barely visible without lens, numerous and evenly distributed, solitary (B) and in radial multiples of two to four (C). Parenchyma aliform (D) and confluent (E). Rays (F) distinct on cross sections with hand lens.

**Indian rosewood** (*Dalbergia latifolia*)

Hard and heavy (specific gravity averages 0.80). Heartwood light to dark violet-brown with near black pigment layering that resembles growth rings. Anatomical growth rings indistinct, grain irregular to roey. Pores variable in size, medium-large to small, irregularly distributed, solitary (A) and in radial multiples (B) of two to four. Parenchyma aliform (C) to confluent (D) and in tangential lines (E). Rays (F) fine, not visible without hand lens. Ripple marks distinct on tangential surfaces.


Teak (*Tectona grandis*)—Burma teak, genuine teak
Hard and heavy (average specific gravity 0.66). Golden brown darkening to brown or almost black with age and exposure. Characteristic spicy odor and waxy feel. Grain straight, sometimes wavy. Ring-porous, growth rings distinct. Texture coarse. Earlywood (A) one to three vessels wide, latewood pores solitary (B) and in radial multiples of two or three (C). Parenchyma terminal and surrounding pores. Rays (D) distinct without hand lens on cross section.




Central American mahogany (*Swietenia* spp.)—genuine mahogany, Honduras mahogany
Moderately light to heavy (specific gravity 0.40 to 0.83). Color variable from pale or yellow brown to dark red or dark reddish brown, often with a pinkish cast. Darkens on exposure. Grain straight, interlocked, or irregular. Growth rings distinct due to concentric lines of terminal parenchyma (A). Texture medium-coarse. Vessels distinct to the naked eye, numerous, evenly distributed, may have white (B) or gum deposit. Pores solitary (C) or in radial multiples of two to ten (D). Rays (E) barely visible to the naked eye on cross section; distinct on radial surface, darker than background.

Spanish-cedar (*Cedrela* spp.)

Moderately soft and light (average specific gravity 0.44). Heartwood light to dark brown with an orange or reddish tinge. Characteristic spicy or cedarlike odor (most familiar by its use in cigar boxes). Straight grained to mildly interlocked. Growth rings usually distinct, delineated by thin line of terminal parenchyma and by predominance of largest pores along earlywood in ring-porous specimens. Pores large to medium-small, not numerous but evenly distributed, solitary (A) and in radial multiples (B). Parenchyma terminal (C) and vasicentric (narrow band around pore) (D). Rays (E) visible without hand lens on cross section. Vessels with red gum.







African mahogany (*Khaya* spp.)

Moderately hard and heavy (average specific gravity 0.63). Heartwood pale rosy red to dark reddish brown, sometimes with a purplish cast. Grain is typically interlocked, producing an even stripe figure when cut radially. Growth rings usually indistinct, terminal parenchyma occasionally present, but only weakly defined. Pores medium to medium-large, visible without hand lens, evenly distributed as solitary (A) or in radial multiples of two to eight (B). Some pores with red gum (C) (but no white deposits, as in *Swietenia* spp.). Rays (D) distinct on cross-sectional surfaces without hand lens.

White lauan (*Shorea* spp.)—white meranti
 Medium hard and medium dense (average specific gravity 0.46). Heartwood pale grayish or yellowish brown with a pinkish cast and silvery sheen. Grain usually roey. Diffuse-porous with coarse texture. Pores large to very large, conspicuous to the eye, evenly distributed or forming scattered short diagonal rows, solitary (A) or in multiples (B). Growth rings are indistinct, but gum ducts embedded in bands of parenchyma present as conspicuous tangential lines (C). Lighter parenchyma vascentric (surrounding pores), sometimes aliform (extending tangentially from pore) (D). Rays (E) barely visible on cross sections but distinct with hand lens. (Note: Some 22 species of *Shorea* are included in the white lauan group.)





Yellow meranti (*Shorea* spp.)—yellow seraya

Medium hard and medium dense (average specific gravity 0.50). Heartwood light yellowish brown with a cinnamon or sometimes greenish cast and golden luster. Grain usually roey. Diffuse-porous with medium-coarse texture. Pores medium to large, visible without hand lens, evenly distributed, solitary (A) or in radial multiples of two to several (B). Growth rings indistinct but gum ducts (often with white contents) embedded in bands of parenchyma, present as conspicuous tangential lines (C). Rays (D) barely visible on cross sections but distinct with hand lens. (Note: Some 33 species of *Shorea* are included in the yellow meranti group.)

Balsa (*Ochroma* spp.)


Extremely light (average specific gravity 0.10-0.20). Color white, cream to pale brown, occasionally having a pink tinge. Straight-grained. Growth rings not apparent. Texture coarse. Diffuse-porous. Vessels large, distinct to naked eye; pores solitary (A) and in multiples of two to three (B). Parenchyma not distinct. Rays (C) distinct to naked eye. Extreme lightness in weight and softness of wood are valuable identification features.


**Obeche** (*Triplochiton scleroxylon*)

Moderately soft and light (average specific gravity 0.38). Color uniformly pale yellow to creamy white or pale buff. Grain characteristically interlocked, producing ribbon figure on radial surfaces. Growth rings indistinct or distinct due to change in fiber density. Texture medium to moderately coarse. Vessels distinct to eye, pores solitary (A) or in small radial multiples (B), sometimes irregularly distributed, commonly with tyloses (C). Parenchyma visible only with lens as short, fine tangential lines (D). Largest rays (E) visible on cross section; on radial surface, rays are distinct, appearing lighter than background.

Jelutong (*Dyera costulata*)

Moderately soft and light (average specific gravity 0.38). Wood is pale straw to creamy white, with no color difference between heartwood and sapwood. Its clear appearance interrupted by conspicuous latex slits at regular intervals of about 3 ft. along longitudinal surfaces. Straight grained and fine textured. Growth rings visible due to tangential bands of denser tissue (A). Wood diffuse-porous, pores occasionally solitary (B) but mostly in radial multiples (C) visible to the unaided eye. Rays (D) faintly visible on cross sections. Parenchyma in fine tangential lines, forming reticulate pattern (E) with rays on cross section.







Ramin (*Gonystylus* spp.)—melawis

Hard and heavy (average specific gravity 0.67). Color pale yellow to buff. Grain usually straight, sometimes slightly interlocked. Growth rings not apparent or delineated by lighter-colored tissue (tracheids). Texture moderately fine, wood evenly diffuse-porous. Vessels (pores) distinct with hand lens, solitary (A) or in radial pairs (B). Parenchyma aliform (C) and confluent (D) (connecting pores) and in tangential lines independent of pores (E). Rays (F) fine, distinct with hand lens.

Avodire (*Turraeanthus africanus*)

Medium hard and medium dense (average specific gravity 0.52). Heartwood pale yellow to nearly white with a satiny luster. Grain usually roey. Growth rings indistinct, wood diffuse-porous. Pores medium in size, barely visible without hand lens, numerous and evenly distributed, many solitary (A), the remainder in radial multiples (B). Parenchyma not visible with hand lens. Rays (C) distinct with hand lens, but inconspicuous on cross sections to unaided eye.





Mansonia (*Mansonia altissima*)—African black walnut, ofun, aprono, opruno


Hard and heavy (specific gravity 0.60 to 0.68). Color ranging from grayish brown to dark chocolate or walnut brown, sometimes with a purplish tinge and occasionally with lighter and darker bands. Grain itself usually straight but sometimes mildly interlocked. Growth rings distinct due to lines of terminal parenchyma (A). Texture fine and even. Diffuse-porous, pores indistinct without hand lens, solitary (B) and in radial multiples of two to eight (C), numerous. Rays (D) not distinct to naked eye but appear as fine crowded lines with hand lens.

Satinwood (*Chloroxylon swietenia*)—

East Indian satinwood, Ceylon satinwood
Hard and heavy (average specific gravity 0.84). Color light yellow or golden tallow and lustrous, sometimes with darker streaks or dark gum veins. Grain narrowly interlocked producing a narrow ribbon figure, often mottled. Growth rings distinct to the naked eye, owing to thin lines of terminal parenchyma (A). Texture fine and even. Diffuse-porous. Vessels small but distinct with hand lens, pores mostly in radial groups of two to six (B) or solitary (C). Parenchyma terminal and in short tangential lines (D). Rays (E) fine, distinct with hand lens.

**Lignumvitae** (*Guaiaecum officinale*, *G. sanctum*)

Very hard and very heavy (average specific gravity 1.15 to 1.30). Color variable from light olive green to dark greenish brown, usually with dark streaks. Grain strongly interlocked, producing closely spaced ribbon stripe pattern on radial surfaces. Growth rings indistinct. Texture very fine. Vessels indistinct without lens, solitary (A) or in radial rows (B); gums and resin deposits abundant. Parenchyma not visible. Rays invisible to the naked eye; with hand lens rays appear as very fine lines (C) on cross section.

**Ebony** (*Diospyros* spp.)

Very hard and heavy (average specific gravity 0.90). Heartwood uniformly jet black, or sometimes with lighter streaks, and with metallic luster. Grain straight to irregular or wavy. Growth rings indistinct, wood diffuse-porous. Pores very small, barely visible with hand lens, evenly distributed, solitary (A) or in radial multiples (B). Parenchyma usually not visible with hand lens, but sometimes apparent as faint, uniformly spaced fine tangential lines. Rays (C) very fine, visible only with hand lens.




Figure 4.1 • This is a universal testing machine set up in Hoadley's laboratory to measure the bending strength of a wooden beam under static loading. The machine has accessory components to apply stress in various modes, with the amount of force indicated by the large dial as well as by a running printout.

(Photo by Randy O'Rourke)

STRENGTH OF WOOD

A caller once asked, "How strong is oak?" Puzzled by the question and wondering where to begin to answer I replied simply, "Oh, it's *very* strong." "That's good to know because I'm going to build a table and I want it to be good and strong, so I guess I'll use oak." He seemed content and went on to discuss something else.

My answer was not much use to him. I really didn't say anything about oak, and when I hung up the phone I felt a little ashamed that I hadn't taken the time to try to unscramble the whole subject and discuss it thoroughly. But the whole subject of **strength** or **mechanical properties** of wood is far more complicated than meets the eye. A good answer to even an innocent question such as "How strong is oak?" is nothing you can whisk up quickly or easily. For one thing, the mechanics of materials is in itself a complex field of science, even for "simple" materials that are **homogeneous** (uniform in composition) and **isotropic** (having equal properties in all directions), such as steel. But wood is neither; it is an **anisotropic, heterogeneous** material, subject to species differences, biological variability, and a wide array of natural irregularities and defects. Moreover, there are many kinds of strengths and many kinds of stresses and strains, and materials respond to them in varying degrees.

As for the caller's question, I would rather have been asked, "What's involved in building a strong table?" Then I could have given a simple answer. First, you must have a good design, one that will anticipate the probable load to be imposed and efficiently carry and transfer the stresses among the components. Second, the table must be well fabricated and assembled, especially with regard to joints and fasteners. Third, a wood must be chosen that is strong enough for the design, or preferably, the design would have been developed with the strength of the wood in mind. These three points are of course inseparable, but this section is about the strength of wood, not design or fabrication.

Of all the properties of wood, strength is probably of most concern to woodworkers. It not only determines the mechanical performance of a finished piece but also is an important factor in drying, machining, bending, gluing, and fastening. In considering strength, it is important to recall that the structure of wood is anisotropic, for its properties may be strikingly different in the longitudinal, radial, and

tangential directions. Familiarity with basic wood-moisture relationships is also critical (see chapter 6).

A thorough discussion of strength properties could fill a thick textbook all by itself. Here I will highlight some principles that I think will aid the woodworker.

The study of strength is a numerical science, and in order to discuss the subject properly, it is necessary to introduce mathematical formulas and symbols. To the uninitiated, the physics and engineering notation used may seem imposing, but even if all the details are not comprehended at the first reading, the basic principles given are meaningful. It will become apparent in this chapter that practical design or engineering with wood is not a numerically exact science but rather more often depends upon judgment and intuition. Nevertheless, such judgment is best developed with some understanding of basic engineering principles.

In exploring the subject of strength, the terms **stress** and **strain** must first be defined.

Stress is **unit force**, that is, the amount of force or load acting on a unit of area. It is determined by dividing the load, P , by the area, A (*Figure 4.2*). To illustrate, assume we have a piece of eastern white pine, 2 in. by 2 in. by 10 in. long, at 12% moisture content, straight-grained, and free of defects. We place it in a press and apply a load of 2,000 lb. on the ends. The total force of 2,000 lb. acts on 4 sq. in. and develops a stress of:

$$\frac{P}{A} = \frac{2,000 \text{ lb.}}{4 \text{ in.}^2} = 500 \text{ lb./in.}^2$$

(Pounds per square inch is usually abbreviated **psi**.)

Strain is **unit deformation**, that is, deformation per unit of original length. In the white pine block, suppose we precisely measure the amount by which the column was compressed while subjected to 500 psi stress and found it to be 0.004 in. The strain would be:

$$\frac{\text{deformation}}{\text{length}} = \frac{0.004 \text{ in.}}{10 \text{ in.}} = 0.0004 \frac{\text{in.}}{\text{in.}}$$

Strain is expressed in inches per inch, without canceling the units.




Figure 4.2 • STRESS, OR FORCE PER UNIT AREAS, IS CALCULATED BY DIVIDING THE LOAD (2,000 LB.) BY THE AREA (4 SQ. IN.), EQUALING 500 PSI. THE STRAIN, OR UNIT DEFORMATION, IS CALCULATED BY DIVIDING THE DEFORMATION OF THE BLOCK (0.004 IN.) BY ITS ORIGINAL LENGTH (10 IN.), EQUALING 0.0004 IN./IN.

Strength is often defined as the ability to **resist** applied stress, and the strength of the material is synonymous with the **resistance** of the material. In this sense, we are interested not simply in the total load or stress the material can resist but also in how much deformation or strain results from a given level of stress. In considering the strength of wood, the relationship between stress and strain is of primary concern.

Going back to our block of eastern white pine, let's apply regular and equal increments of load or stress and with each increase measure the resulting deformation or strain. We can then accumulate a series of stress and strain measurements all the way from minimum stress to failure of the block, and we can plot them in graph form (Figure 4.3).

The data show that the maximum load carried by the block was 17,600 lb. and the maximum stress was 4,400 psi. The test data reveal another important trait of the wood. Up to a stress level of 3,250 psi, stress and strain are proportional, that is, each increment of stress produces a proportional




Figure 4.3 • IN A STANDARD STRESS/STRAIN GRAPH, PAIRS OF LOAD (LB.) AND DEFORMATION (IN.) VALUES TAKEN DURING A DESTRUCTIVE COMPRESSION TEST ARE PLOTTED TO SHOW MAXIMUM CRUSHING STRENGTH, PROPORTIONAL LIMIT, AND MODULES OF ELASTICITY.

increment of strain. This characteristic proportionality of certain materials is known as **Hooke's Law**, after Robert Hooke, who discovered this behavior in 1678. Beyond the **proportional limit**, additional increments of stress result in increasingly larger increments of strain as the maximum stress, and ultimately failure, is approached. Figure 4.4 shows typical failure in compression parallel to the grain.

In wood, the proportional limit commonly occurs at between one-half and two-thirds of the maximum stress. The importance of Hooke's Law is that wood is **elastic** up to the proportional limit, that is, strains are recoverable upon removal of stress. As indicated by Figure 4.5, a piece of wood subjected to a stress level x less than the proportional limit stress (σ') produces strain y . When the stress is removed, the strain returns to zero. If the piece is stressed beyond the proportional limit, however, to stress level X , then removal of the stress recovers only part of the strain. Thus, strain equal to $O-Y$ will remain. This remaining strain is called **permanent set**.




Figure 4.4 • Failures in compression parallel to the grain. (Photo by Randy O'Rourke)




Figure 4.5 • Wood stressed within its elastic range to some value (x) and unloaded recovers from the resulting strain. Wood stressed to some value (X) beyond the proportional limit and unloaded does not recover; some of the strain remains a permanent set (O-Y).

These fundamental mechanics are easily demonstrated with a hammer. Tap the surface of a board gently with a hammer, and no damage is apparent. The wood actually depresses under the mild force of the hammer but returns immediately as the hammer bounces back. But strike a hard blow—as when you miss in driving a nail—and the wood is permanently dented. A deeper dent occurs as the hammer strikes, but only partial elastic recovery takes place as the hammer rebounds. The remaining dent reflects the permanent set.

A wooden archery bow must be designed to keep deformation and bending stresses within the elastic limit, so that when the bowstring is drawn to arrow length

and released, the bow springs back to its original position. Drawing the bowstring back too far might stretch the wood fibers beyond proportional limit. Thus, when unstrung, the bow would not spring back to shape because it had taken on set.

As Hooke's Law states, the ratio of stress to strain for a given piece of wood within the elastic range is a constant. This ratio is called the modulus* of elasticity. Also known as Young's Modulus and usually abbreviated as MOE or simply E , this ratio equals the stress divided by the resulting strain. It can be calculated by choosing any set of values of stress and resulting strain, although the stress and strain

*The word modulus means simply "measure."

values at the proportional limit are conventionally used. For our white pine block, we would calculate:

$$E = \frac{\text{stress}}{\text{strain}} = \frac{3,250 \text{ psi}}{0.0026 \text{ in./in.}} = 1,250,000 \text{ psi}$$

The units representing strain (inches/inch) mathematically cancel out, and although the modulus of elasticity is simply expressed in psi, it is not an actual stress in the wood. We most often see E written as 1.25×10^6 psi, or simply abbreviated as $1.25E$, as on a lumber-grade stamp. It is useful in making comparisons. Wood with a value of $2.2E$ (that is, 2.2×10^6 psi) is twice as stiff as wood with a value of $1.1E$.

The relative **slope** of the stress-strain curve, as indicated by the modulus of elasticity, E , gives a measure of relative **stiffness**; the steeper the slope, the higher the E value and the stiffer the wood. Moreover, the higher the E value, the lower the deformation under a given load. Thus, under a given load, a floor framed with joists rated at $2.2E$ will sag only half as much as one using joists rated $1.1E$.

We often think of the word strength in terms of failure, or maximum stress, and are satisfied to use maximum load values to rate one piece or species against another. At the same time, we depend upon the performance of the wood, not just at the failure level or slightly below it, but in fact well below the proportional limit, since we are depending on the elastic performance of the wood. Imagine a diving board or a baseball bat that remained slightly bent after use. Think of the consequences if the living-room floor joists didn't straighten up when the crowd went home after a party.




Figure 4.6 • Compression, tension, and shear are the primary forms of stress, and all three develop when a beam bends: compression (σ_c) along the upper portion, tension (σ_t) along the lower portion, and shear throughout, maximum (T_{\dots}) near the ends.

We are usually well aware of instances where the proportional limit has been exceeded—those dents near a nail head left by errant blows of a hammer, chair rungs loose in their mortises, and loose heads on hammer handles. Sometimes we intentionally make use of the plastic range (i.e., the nonelastic range beyond the elastic limit). A good example is in steam-bending wood, where heating in order to produce a permanent set lowers the elastic limit.

We can now characterize the compressive resistance ("strength") of our white pine block in terms of three important features of stress/strain behavior: maximum crushing strength, strength or fiber stress at proportional limit, and modulus of elasticity.

Our white pine block under compression is an example of only one of the three kinds of primary stress that can be applied to an object (*Figure 4.6*). **Compression stress** shortens or compresses an object. **Tensile stress** elongates or expands the dimensions of an object. Tensile and compressive stresses are referred to as **axial stresses** because they cause shortening or elongation along a common line of action. By convention, the Greek letter sigma (σ) is used to denote axial stress. (Sometimes σ_c designates compression, and σ_t , tension.) **Shear stress** causes portions of an object to move or slide in parallel but opposite directions. Shear is conventionally indicated by the Greek letter tau (τ).

Some strength properties are simply resistance to primary stresses, as in the example of the white pine block, where compression alone was involved. In other cases, the manner of loading causes combinations of stresses, wherein each type of stress must be sorted out and analyzed. An example of this is the bending strength of wood.

Since wood is anisotropic, each stress will be resisted differently according to growth-ring placement and grain direction. To determine relationships, an infinite number of tests of different wood-structure orientations could be done, but to minimize this array, the American Society for Testing and Materials (ASTM) has adopted standardized tests for the most important ones. The ASTM standards define the physical dimensions of the test pieces and specify conditions of moisture content, grain direction, growth-ring orientation, and how free the piece is from defects. The tests are conducted in a standard testing machine (*Figure 4.1*) capable of holding pieces in appropriate fixtures, of applying force at prescribed rates of loading, of indicating the resistance, and of measuring deflection. Not all strength behavior is routinely recorded for every test. *Table 4.1* shows strength properties for selected species.

COMPRESSION PARALLEL TO THE GRAIN

When wood is stressed in a manner that shortens its fibers lengthwise, it is under compression parallel to the grain, as

TABLE 4.1—Strength properties* at 12% MC of some commercially important woods grown in the United States.

	Compression			Tension	Shear	Static bending		
	to grain	to grain	⊥ to grain	⊥ to grain	to grain	FSPL	MR	E
	PSPL (σ') PSI	MCS (σ_{max}) PSI	PSPL (σ') PSI	MTS (σ_{max}) PSI	MSS (τ_{max}) PSI	(σ') PSI	(σ_{max}) PSI	(σ/E) 10 ⁶ PSI
Hardwoods								
Alder, red (<i>Alnus rubra</i>)	4,530	5,820	540	420	1,080	6,900	9,800	1.38
Ash, white (<i>Fraxinus americana</i>)	5,790	7,410	1,410	940	1,950	8,900	15,400	1.77
Basswood, American (<i>Tilia americana</i>)	3,800	4,730	450	350	990	5,900	8,700	1.46
Beechwood, American (<i>Fagus grandifolia</i>)	4,880	7,300	1,250	1,010	2,010	8,700	14,900	1.72
Birch, paper (<i>Betula papyrifera</i>)	3,610	5,690	740	—	1,210	6,900	12,300	1.59
Birch, yellow (<i>B. alleghaniensis</i>)	6,130	8,170	1,190	920	1,880	10,100	16,600	2.01
Butternut (<i>Juglans cinerea</i>)	4,200	5,110	570	440	1,170	5,700	8,100	1.18
Cherry, black (<i>Prunus serotina</i>)	5,960	7,110	850	560	1,700	9,000	12,300	1.49
Chestnut, American (<i>Castanea dentata</i>)	3,780	5,320	760	460	1,080	6,100	8,600	1.23
Cottonwood, eastern (<i>Populus deltoides</i>)	3,490	4,910	470	580	930	5,700	8,500	1.37
Elm, American (<i>Ulmus americana</i>)	4,030	5,520	850	660	1,510	7,600	11,800	1.34
Elm, rock (<i>U. thomasii</i>)	4,700	7,050	1,520	—	1,920	8,000	14,800	1.54
Hackberry (<i>Celtis occidentalis</i>)	3,710	5,440	1,100	580	1,590	5,900	11,000	1.19
Hickory, pecan (<i>Carya illinoensis</i>)	5,180	7,850	2,130	—	2,080	9,100	13,700	1.73
Hickory, shagbark (<i>C. ovata</i>)	6,605	9,210	2,170	—	2,430	10,700	20,200	2.16
Honeylocust (<i>Gleditsia triacanthos</i>)	5,250	7,500	2,280	900	2,250	8,800	14,700	1.63
Locust, black (<i>Robinia pseudoacacia</i>)	6,800	10,180	2,260	640	2,480	12,800	19,400	2.05
Magnolia, southern (<i>Magnolia grandiflora</i>)	3,420	5,460	1,060	740	1,530	6,800	11,200	1.40
Maple, red (<i>Acer rubrum</i>)	4,650	6,540	1,240	—	1,850	8,700	13,400	1.64
Maple, sugar (<i>A. saccharum</i>)	5,390	7,830	1,810	—	2,330	9,500	15,800	1.83
Oak, black (<i>Quercus velutina</i>)	4,750	6,520	1,150	—	1,910	7,900	13,900	1.64
Oak, northern red (<i>Q. rubra</i>)	4,580	6,760	1,250	800	1,780	8,500	14,300	1.82
Oak, post (<i>Q. stellata</i>)	3,700	6,600	1,760	780	1,840	7,600	13,200	1.51
Oak, southern red (<i>Q. falcata</i>)	2,910	6,090	1,080	510	1,390	6,000	10,900	1.49
Oak, white (<i>Q. alba</i>)	4,760	7,440	1,070	800	2,000	8,200	15,200	1.78
Sweetgum (<i>Liquidambar styraciflua</i>)	3,670	6,320	660	760	1,600	6,600	12,500	1.64
Sycamore, American (<i>Platanus occidentalis</i>)	3,710	5,380	860	720	1,470	6,400	10,000	1.42
Tupelo, black (<i>Nyssa sylvatica</i>)	3,470	5,520	1,150	500	1,340	7,300	9,600	1.20
Walnut, black (<i>Juglans nigra</i>)	5,780	7,580	1,250	690	1,370	10,500	14,600	1.68
Yellow-poplar (<i>Liriodendron tulipifera</i>)	3,730	5,540	560	540	1,190	6,200	10,100	1.58
Softwoods								
Baldcypress (<i>Taxodium distichum</i>)	4,740	6,360	900	270	1,000	7,200	10,600	1.44
Cedar, Alaska (<i>Chamaecyparis nootkatensis</i>)	5,210	6,310	770	360	1,130	7,100	11,100	1.42
Cedar, incense (<i>Libocedrus decurrens</i>)	4,760	5,200	730	270	880	5,900	8,000	1.04
Cedar, western red (<i>Thuja plicata</i>)	4,360	5,020	610	220	860	5,300	7,700	1.12
Douglas-fir (<i>Pseudotsuga menziesii</i>)	5,850	7,430	870	340	1,160	7,800	12,200	1.95
Fir, balsam (<i>Abies balsamea</i>)	3,970	4,530	380	180	710	5,200	7,600	1.23
Fir, white (<i>A. concolor</i>)	3,590	5,350	600	260	930	6,500	9,300	1.38
Hemlock, eastern (<i>Tsuga canadensis</i>)	4,020	5,410	800	—	1,060	6,100	8,900	1.20
Hemlock, western (<i>T. heterophylla</i>)	5,340	6,210	680	310	1,170	6,800	10,100	1.49
Larch, western (<i>Larix occidentalis</i>)	5,620	8,110	980	430	1,410	8,300	13,900	1.96
Pine, eastern white (<i>Pinus strobus</i>)	3,670	4,800	440	310	900	5,700	8,600	1.24
Pine, jack (<i>P. banksiana</i>)	3,550	5,660	600	420	1,170	5,800	9,900	1.35
Pine, lodgepole (<i>P. contorta</i>)	4,310	5,370	750	290	880	6,700	9,400	1.34
Pine, ponderosa (<i>P. ponderosa</i>)	4,060	5,270	740	400	1,160	6,300	9,200	1.26
Pine, red (<i>P. resinosa</i>)	4,160	6,070	650	460	1,210	7,000	11,000	1.63
Pine, longleaf (<i>P. palustris</i>)	6,150	8,220	950	470	1,500	9,300	14,300	1.93
Pine, shortleaf (<i>P. echinata</i>)	5,090	7,270	750	470	1,390	7,700	13,100	1.76
Pine, sugar (<i>P. lambertiana</i>)	4,140	4,770	590	350	1,050	5,700	8,000	1.20
Pine, western white (<i>P. monticola</i>)	4,480	5,620	540	—	850	6,200	9,500	1.51
Redwood [old-growth] (<i>Sequoia sempervirens</i>)	4,560	6,150	860	240	940	6,900	10,000	1.34
Spruce, engelmann (<i>Picea engelmannii</i>)	3,580	4,770	540	350	1,030	5,500	8,700	1.28
Spruce, Sitka (<i>P. sitchensis</i>)	4,780	5,610	710	370	1,150	6,700	10,200	1.57
Spruce, white (<i>P. glauca</i>)	3,700	5,470	540	360	1,080	6,500	9,800	1.34
Tamarack (<i>Larix laricina</i>)	4,780	7,160	990	400	1,280	8,000	11,600	1.64

in a column supporting a porch or our introductory test on eastern white pine.

In a standard ASTM test for compression parallel to grain (Figure 4.7), the specimen is 8 in. long and fitted with a special deflection gauge that measures compression of the central 6 in. By taking load/deformation data beyond the proportional limit, fiber stress at the proportional limit (σ'), maximum crushing strength (σ_{max}), and modulus of elasticity (E) can be computed.

For its weight, wood is surprisingly strong in compression parallel to the grain. Take, for example, a hickory chair I once saw whose four legs were each 1 1/4 in. dia. The chair looked quite graceful and not at all overdesigned, but let's make a few quick calculations. The four legs have a total cross-sectional area of:

$$A = 4(\pi)r^2 = 4(\pi)(0.625 \text{ in.})^2 = 4.91 \text{ in.}^2$$

From Table 4.1, we see that air-dry hickory has an average proportional limit strength of 6,605 psi. The four legs could support a total load of about 32,430 lb. Thus, compression parallel to the grain is hardly a structurally limiting factor. This is common; even calculations of supporting members of buildings typically show a wide margin of overdesign in compression parallel to the grain. I cannot remember ever seeing a structural failure or even hearing of one due purely to compression stress parallel to the grain. If




Figure 4.7 • In the standard test for compression parallel to the grain, the testing machine applies a load to the ends of the column. A deflection gauge fastened to the specimen measures shortening of the column. (Photo by Randy O'Rourke)

compression were the only factor, a 250-lb. person could be supported by four hickory dowels, each one only 1/8 in. dia. We see this in the formula:

$$A = 4(\pi)(1/16 \text{ in.})^2 = 0.0491 \text{ in.}^2$$

$$\sigma = \frac{P}{A} = \frac{250 \text{ lb.}}{0.049 \text{ in.}^2} = 5,102 \text{ psi}$$

Clearly, this load is well within the proportional-limit compression strength of hickory.

But we can hardly conceive of sitting on a seat supported by four 1/8-in. dowels. Our intuition alone would warn us of the danger, but we can also calculate the fault in the design.

First, the dowels will buckle, since columns having an l/d ratio (l/d = length, d = least dimension) of greater than 11 will buckle at less than full load (if our dowel legs were 17 in. long, the l/d ratio would be $17/0.125 = 136$).

As in a building, the supporting frame must be stabilized by lateral connection to prevent buckling. Even if our dowel legs were stabilized by a multitude of small rungs, any sideways thrust against the chair would cause bending. So the legs of a chair must be thick enough to be more than just supporting posts. However, the bottoms of the 1 1/4-in. chair legs could be tapered down like sharpened pencils to 1/8-in.-dia. tips and be more than adequate to sustain a 250-lb. person sitting with all four chair legs squarely on the floor.

COMPRESSION PERPENDICULAR TO THE GRAIN

When heavy objects rest upon the surface of a wooden table or on a wooden floor, they apply loads equal to their weights that stress the wood in compression perpendicular to the grain. To determine the strength of wood in compression perpendicular to the grain, a standard test piece 6-in.-long, 2-in. by 2-in. cross section is supported horizontally and loaded over its central 2 in. (Figure 4.8). Load/deflection data are recorded until the proportional limit is reached. Beyond this limit, as the piece is compacted more and more, the resistance increases and no meaningful maximum load is reached (Figure 4.9). Therefore the only strength value routinely determined is the fiber stress at proportional limit (FSPL). Typical values for fiber stress at proportional limit in compression perpendicular to the grain range from something like 440 psi for eastern white pine to 2,170 psi for hickory. In general, values are drastically lower for compression perpendicular to the grain than for compression parallel to the grain.

Compression perpendicular to the grain is very often a limiting strength. Go back to our example of the hickory chair with legs tapered to A_s in. Although the 5,102 psi

developed at the tips could be carried by the chair legs, it would easily punch into the surface of an eastern white pine floor board whose FSPL is listed at only 440 lb. In fact, a 120-lb. woman placing her full weight on a shoe with a 1/2-in. by 1/2-in. heel will develop a stress as high as:

$$\frac{120 \text{ lb.}}{1/2 \text{ in.} \times 1/2 \text{ in.}} = 480 \text{ psi}$$

Eastern white pine obviously is not a logical choice for flooring, but the 2,170-psi perpendicular-to-grain strength of hickory would comfortably resist heel denting.

Published values for strength properties commonly list a single value for perpendicular-to-grain compression strength that is the average of both radial and tangential




Figure 4.8 • In the standard test for compression perpendicular to the grain, the probe of a freestanding deflectometer automatically records the deformation as the test proceeds. (Photo by Randy O'Rourke)

properties. In some species, there may be insignificant differences between the two, but in others the anatomical structure causes noteworthy radial and tangential differences. For example, in ring-porous hardwoods such as ash or catalpa and in uneven-grained softwoods such as southern yellow pine or Douglas-fir, a piece stressed in the radial direction will be no stronger than the weakest layer of earlywood. This fact is used to advantage when pounding loose strips of ash for basket-making.

Hitting a baseball against the tangential face of an ash bat (that is, stressing the wood radially) deadens the impact by crushing the earlywood layers (*Figure 4.10*). For this reason, the trademark is always imprinted on the tangential face of the bat, and the batter is instructed at an early age not to hit the ball on the trademark. This leaves many a ballplayer




Figure 4.9 • When measuring compression perpendicular to the grain, there is no meaningful maximum load because after reaching proportional limit, the piece is compacted more and resistance increases.

Figure 4.10 • Hitting a baseball on the tangential surface of this white ash bat has caused "chipping" or separation of the growth layers by compression failure in the weaker earlywood. (Photo by Randy O'Rourke)



with the notion that printing the trademark has weakened the bat. Ash and other similar woods support greater loads when loaded tangentially (i.e., against the radial face) because the layers of stronger latewood share the stress equally. Interestingly, compression strength is usually least when applied perpendicular to the grain, at a 45-degree angle to the growth rings.

In internal-external joints such as a mortise and tenon, where racking is involved, strength in compression perpendicular to the grain can be especially critical (Figure 4.11). The side-grain strength (compression perpendicular) of the tenon is no match for the end-grain strength (compression parallel) of the mortise when the same species is used for both.




Figure 4.11 • In a mortise and tenon subject to racking, as in a chair, the strength of the tenon in compression perpendicular to the grain is critical.

sion parallel) of the mortise when the same species is used for both.

A particularly critical situation develops when wood is restrained from swelling, as in the end of a hammer, handle inserted into the hammer head or even in a mortise-and-tenon joint. As will be discussed further in chapter 6, the amount of swelling perpendicular to the grain that takes place as a result of natural humidity changes may be substantial. If swelling is restrained, the effect is that of compressing the wood. However, the elastic limit strain is less than 1%, as can be seen in Figure 4.12. Therefore, compression set may develop. Upon redrying, the piece "unloads" itself by shrinking to a smaller than original diameter, thus loosening the joint (Figure 4.13).




Figure 4.12 • In response to normal humidity variation, wood may swell as much as 3% perpendicular to the grain. Restrained swelling is similar to compression, and it may cause wood to load itself beyond the proportional limit, thereby causing permanent shrinkage, or compression set.




Figure 4.13 • This experiment demonstrates the development of compression shrinkage. Three sections were cut from a board at 7% moisture content, then each was mounted in a steel frame, attached at the lower end by a woodscrew. The third section was free to swell, but the first and second sections were restrained by the upper part of the frame, and the first section was also fastened at the top with another woodscrew. The humidity was slowly raised until the moisture content of the wood reached 18% or more. The third section swelled; the first and second confined to the frame developed internal stress beyond their proportional limits. Although no damage was apparent, they took on permanent compression set. The moisture content was then restored to 7%, and the results can be seen in this photo. The third section shrank back to its original size; the second became shorter due to compression shrinkage; and the first, restrained from shrinking, developed internal tension sufficient to break it apart. (Photo by Randy O'Rourke)

► TENSION PERPENDICULAR TO THE GRAIN

Perpendicular-to-grain tensile failures occur when we split firewood, when nails are driven into unyielding wood, when cupped boards are forced flat, when a karate student breaks a board, and when we plane a long, curling shaving from the edge of a board. But we are generally aware of the weakness of wood in this regard and have pretty much learned to design and use wood to avoid unwanted failures.

Perhaps the most common and misunderstood tensile failures are due to self-induced tension from uneven dimensional change. As will be elaborated in subsequent chapters, end-checking, surface-checking, and internal honeycomb checks during the drying process are classic examples of this kind of failure, as are the radial cracks developed in pieces embracing the pith.

The standard ASTM test for tension perpendicular to the grain (*Figure 4.14*) makes no provision for measuring strain. Only stress at maximum load is determined, and this is the only extensively published strength property in tension perpendicular to the grain. Typical values for maximum tensile strength range from 310 psi for eastern white pine to 1,010 psi for American beech. Such values are important when comparing resistance to splitting among various woods.

Fortunately, some testing has been done on specimens that are fitted with gauges to measure strain (*Figure 4.15*). As indicated in *Figure 4.16*, the elastic behavior is similar to that of compression perpendicular to the grain, with approximately the same proportional-limit strain. Above the pro-




Figure 4.14 • In the standard test for tension perpendicular to the grain (resistance to splitting), a piece of wood is pulled apart until it splits. Only maximum stress can be determined with this test. (Photo by Randy O'Rourke)




Figure 4.15 • In Youngs'test for strength of wood in tension perpendicular to the grain, a gauge is attached to a sample of standard form and dimension. The gauge measures strain as the wood, gripped at its ends, is put under tension.

proportional limit we find a striking difference, in that tensile failure occurs totally and abruptly at strains of less than 2%, at a maximum stress about double the proportional-limit stress. It is unfortunate that more extensive data is not available for more species because this information would give us valuable insight into strain limits. If the moisture content of one portion of a piece of wood drops 8% to 10% lower than an adjacent portion, the drier portion will attempt to shrink by about 2% of its tangential dimension. Our strength information suggests that it will probably crack wide open.




Figure 4.16 • A typical stress/strain graph of tension perpendicular to the grain. The proportional limit is reached at less than 1% strain, and failure occurs at less than 2% strain.


TENSION PARALLEL TO THE GRAIN

Wood is strongest in tension parallel to the grain, but this fact does us little good. A typical test specimen (*Figure 4.17*) suggests why. In order to make wood fail in tension parallel to the grain, it must be increased in dimension on each end where it is being held. To put it another way, if you just try to grip or clamp a strip of wood at each end and pull it apart in tension parallel to the grain, the grips or clamps will simply slip or rip off the ends. When a structural member is designed to be large enough so its attachment fastenings can safely transmit the required loads to other members, the cross section of the piece turns out to be far greater than needed along its entire length to carry tensile loads. Except for uses such as in aircraft, where weight is a critical factor, it is usually cheaper to leave the material full size than to machine the excess away.

Ultimate tensile strength for eastern white pine (specific gravity 0.36) has been measured at about 13,000 psi; for hickory (specific gravity 0.81) 30,000 psi. Compared with structural steel, which has a specific gravity of 7.8 and ultimate tensile strength in the range of 60,000 psi, it can easily be argued that on a weight-for-weight basis, wood is stronger than steel—at least in tension parallel to the grain.

Strength in tension parallel to the grain has been of somewhat academic importance in most products, with some

Figure 4.17 • ASTM test for tension parallel to the grain.



exceptions such as roof trusses. In fact, because of the difficulty of machining specimens and conducting tests and the limited use for such data, this property has been largely ignored. However, with our developing technology in composite and assembled products, it may be possible to design structural members that can take advantage of the superior strength of wood in tension parallel to the grain.

SHEAR PERPENDICULAR TO THE GRAIN

Wood is extremely resistant to shearing perpendicular to the grain because of the alignment and structure of its longitudinal cells. Thin veneers can be cut perpendicular to the grain with scissors or with a paper cutter, but when any appreciable thickness is involved, no meaningful shear plane develops and the wood simply crushes or tears. As a result, no standard test has been developed to define or measure shear perpendicular to the grain.

SHEAR PARALLEL TO THE GRAIN

Along the grain, wood separates in shear more readily. A common example of shear failure is where fasteners or interlocking joints shear out to the nearest end-grain surface (*Figure 4.18*).

The ASTM test for shear is performed on a notched block (*Figure 4.19*) held in a special shear tool (*Figure 4.20*) because it is important to prevent rotation of the block as load is developed. The shear strength per square inch is determined by dividing the maximum load, P , by the shear area, A . Typical values are 900 psi for eastern white pine and 2,330 psi for sugar maple.

As with tension perpendicular to the grain, shear strength parallel to the grain may be drastically affected by anatomical features such as large rays or earlywood-latewood varia-




Figure 4.18 • Shear failure occurs where fasteners shear out to the nearest end-grain surface.




Figure 4.19 • A standard specimen for testing shear parallel to the grain.




Figure 4.20 • The standard test for shear parallel to the grain is performed on a notched block (Figure 4.19) held in a special tool that keeps the sample from rotating while a blade (returned by springs) pushes straight down, shearing the block at the inside edge of the notch. (A) The sample is ready for testing. (B) The sample has failed in shear parallel to the grain. (Photos by Randy O'Rourke)





Figure 4.21 • Bending a plywood panel develops shear forces in the plies, causing rotation of small bundles of fibers separated by knife checks. This is called rolling shear. The checks are closed on the right, open on the left. To demonstrate the difference in shear resistance, shear specimens with a central veneer layer are tested to open the checks (O) or close the checks (C). (Photo by R. Bruce Hoadley)

tion. As will be discussed later, shear may become critical in bending, especially in short beams and composite products.

When the shear plane is developed parallel to the grain but produced by stresses perpendicular to the grain, rolling shear may result (Figure 4.21). This behavior is characteristic of fibrous materials and results in groups or bundles of fibers separating and rotating. This type of failure commonly develops in the core ply of plywood, and it is initiated by knife checks, which often occur in thick veneers. This is discussed further in chapter 9.

A special shear test is the mainstay for evaluating wood adhesives. In the standard block shear test for adhesives, the double-notched shape of the specimen (*Figure 4.22*) prevents rotation and directs the stress along the plane of the glue line. Sugar maple is the standard designated species for the test, and the quality of bonding is judged on the combination of stress developed and the percentage of wood failure versus glue failure along the shear plane (*Figure 4.23*).




Figure 4.22 • The standard test specimen for measuring shear strength of a glue line is made of sugar maple. A special fixture holds the specimen in the testing machine in such a way as to direct the force along the plane of the glue line and prevent rotation of the block.




Figure 4.23 • Failed glue joints may show that the glue broke, the wood broke, or both. Glue failure before wood failure may be acceptable if the specimen resists stress equal to the normal shear strength of solid wood parallel to the grain. (Photo by R. Bruce Hoadley)

BENDING THEORY

No chapter on the strength of wood would be complete without a discussion of **bending** or **flexural** behavior. Nature evolved the tree to be a combination column and cantilever beam, and it is not surprising that wood is so beautifully efficient when loaded in compression parallel to the grain or in bending. We take greatest advantage of the strength of wood when we use it to make beams. Understanding beam mechanics is fundamental to structural design, and it is somewhat complicated. Let's try a brief overview, step-by-step.

A **beam** is defined as an elongated member, loaded perpendicular to its long axis. Many examples of beams come quickly to mind. A **simple beam** is one supported at the ends and loaded in between, such as the joists in a floor, the seat of a child's swing and the treads of open stairs. Even a seesaw is a simple beam, although the reverse of the ones above, since it's supported in the middle and loaded on the ends. There are more complicated types, such as **continuous beams** (supported and loaded in several places), **fixed-end beams** (like the rungs of a chair), and **cantilever beams** (fixed on one end, such as a tree limb or, for that matter, the tree). Here, we'll stick with simple beams.

Let's consider a center-loaded, simply supported beam (*Figure 4.24*). The bending resulting from the load tends to shorten or compress the upper surface and to stretch the lower surface. The stresses developed are axial stresses: compression along the upper surface, tension along the bottom. Both stresses are maximum at the very surface and diminish to zero at the central horizontal plane of the beam, which is called the **neutral axis**. The surface axial stresses are greatest at midspan and decrease to zero at each end of the beam. These axial tension and compression stresses are called **bending stresses**, or **fiber stresses**. In materials such as steel, which have equal resistance in compression and tension, the bending stresses at the upper and lower surfaces are equal.

A classic engineering formula, the **flexure formula**, is used to determine the magnitude of bending stresses based on the known load or loads (P) and the length (l), the width (b), and the depth (d) of the beam. In wood, axial strength is greater in tension than in compression and so the flexure formula does not strictly apply. It is nevertheless assumed to be valid. The apparent axial stresses are determined by subjecting wood beams to a bending load, collecting the appropriate load data, and applying the flexure formula. In the standard ASTM static bending test, a 2-in. by 2-in. by 30-in. beam of wood is supported at both ends over a 28-in. span and center-loaded (*Figure 4.25*). The test is called a static test because the center load is applied at a fairly slow rate of speed (0.1 in. per minute). (In an impact bending test, load-




Figure 4.24 • This simple beam is supported at the ends and loaded in the middle. The bending that results shortens the upper surface and stretches the lower surface, while the neutral axis stays the same length. The associated axial stresses are compression along the upper surface and tension along the lower.




Figure 4.25 • ASTM static bending test: As the bearing head descends at 0.1 in. per minute, a sensor measures simultaneous deflection. This measurement is printed as a graph similar to that shown in *Figure 4.26*. (Photos by Randy O'Rourke)

ing is almost instantaneous.) With a standard testing machine and suitable instruments, simultaneous measurements of load and deflection of the neutral axis are taken continuously throughout the test.

A typical load/deflection graph (*Figure 4.26*) was recorded in testing a beam of eastern white pine. Prior to testing, the beam, measured at midspan, had a width (b) of 2.01 in. and a depth (d) of 2 in. The graph shows a maximum load (P_{\max}) of 1,590 lb., a proportional limit load (P') of 990 lb. and a deflection at proportional limit (y') of 0.28 in. The relative slope of the curve within the elastic range indicates the stiffness of the beam. (A special formula, given below, is used to convert the load/deflection ratio to stress/strain or modulus of elasticity.) In a typical bending failure (*Figure 4.27*), the beam's upper part fails first in compression, forming buckled layers of cells, while the lower portion shows typical splintering tension failure.

When adapted to a simply supported, center-loaded beam of rectangular cross section, the flexure formula becomes:

$$\sigma = 1.5 \frac{Pl}{bd^2},$$

where σ = bending stress at midspan, upper and lower surfaces of beam, psi; P = load on beam, lb.; l = span of beam, in.; b = width of beam, in.; d = depth of beam, in. (1.5 is a constant for simple beams with center load).

To calculate the maximum bending stress, referred to as the modulus of rupture, or MR (also abbreviated as MOR or simply R), we use the maximum load, P_{\max} :

$$\begin{aligned} \sigma_{\max} &= MR = 1.5 \frac{P_{\max} l}{bd^2} \\ &= 1.5 \frac{(1,590 \text{ lb.})(28 \text{ in.})}{(2.01 \text{ in.})(2.0 \text{ in.})^2} = 8,306 \text{ psi.} \end{aligned}$$




Figure 4.26 • A load/deflection graph for a white pine beam tested in static bending.





Figure 4.27 • Typical splintering tension failure on a standard bending specimen of sugar maple (A). The nail is located at the neutral axis, which runs lengthwise through the beam. In a spruce beam tested to failure, compression failures are visible in the upper half and tension failures in the lower half (B). (Photo A by Randy O'Rourke; photo B by R. Bruce Hoadley)

The bending stress at proportional limit load, called **fiber stress at proportional limit** or **FSPL**, is calculated by using the proportional limit load, **P'**:

$$\begin{aligned} \sigma' = FSPL &= 1.5 \frac{P'l}{bd^2} \\ &= 1.5 \frac{(990 \text{ lb.})(28 \text{ in.})}{(2.01 \text{ in.})(2.00 \text{ in.})^2} = 5,172 \text{ psi.} \end{aligned}$$

MR and **FSPL** are the values of stress along the upper and lower surfaces of the beam at midspan, which are the points of maximum stress in the beam.

ticity, **E**, as follows:

$$E = \frac{1}{4} \frac{P'l^3}{y'bd^3}$$

$$= \frac{1}{4} \frac{(990 \text{ lb.})(28 \text{ in.})^3}{(0.28 \text{ in.})(2.01 \text{ in.})(2.00 \text{ in.})^3} = 1,206,716 \text{ psi}$$

where **y'** = the center deflection of the beam at proportional limit load, **P'**. (1/4 is a constant for center-loaded simple beams.)

E measures the apparent ratio of stress to strain of fibers along the upper and lower surfaces of the beam, which of course would be related to how much deflection or "sag" would result in a beam under load.

Although **P'** and **y'** (the values of load and deflection at proportional limit) are used by convention, any pair of values could be used because the ratio of load to deflection (**P** to **y**) is constant over the entire elastic range. (The importance of this fact will be emphasized in discussing nondestructive structural grading.)

The average values of bending strengths, MR, FSPL, and E are given in *Table 4.1* on p. 79 for various woods.

In structural engineering with wood, modifications of the above formulas are used for different placement or distribution of loads. The formulas can be used in various ways by rearranging them algebraically. For example, for a given structural design, the load-carrying capacity, P, or expected deflections, y, can be determined. Given a requirement for load-carrying capacity or deflection limit, the necessary design specifications (dimensions, species, grade) can be established. In practice, especially for standard framing systems using stock lumber sizes of established grades, structural design is accomplished in cookbook fashion, using tables of values that have been worked out for relating practically all combinations of spans, dimensions, loads, and deflection. It would be an awesome task, even for an engineer, to analyze from scratch the stress on every stick in a structure.

THE CARRYING CAPACITY AND STIFFNESS OF BEAMS

A tremendous amount of insight into the strength of wood members subject to bending can be gained by rearranging the two formulas used to indicate strength and stiffness of beams.

The two general formulas for bending stress and modulus of elasticity are:

$$\sigma = k \frac{Pl}{bd^2} \quad \text{and} \quad E = K \frac{Pl^3}{ybd^3}$$

(k and K are constants according to the placement and distribution of loads. For the center-loaded beam, we have been considering k = 1.5, K = 0.25.)


The woodworker, however, is not involved in determining the strength of wood but rather in assessing the performance of objects made of wood for which strength information is already available. The two most relevant questions facing the woodworker are how much the beam will carry and what factors influence its carrying capacity, as well as how much the beam will deflect and what factors influence its deflection.

To answer the first question, it is convenient to rewrite the first equation:


$$P = \frac{1}{k} \frac{\sigma bd^2}{l} = \frac{l}{k} \frac{F_b bd^2}{l}$$

(For C we have substituted F_b , the commonly used symbol for allowable bending stress, as designated in stress-grade tables or grade stamps.)


This allows us to calculate the load P that the beam can carry (*Figure 4.28*). It also allows us to see that load-bearing capacity will vary.




—inversely as the length (if you double the length, you'll cut the load-bearing capacity in half (*Figure 4.29*);




—directly as the allowable fiber stress, F_b (if you select a lumber grade that is twice as strong, the beam will carry twice as much) (*Figure 4.30*);



—directly as the width (if you make the beam twice as wide, it will carry twice as much) (*Figure 4.31*);




—directly as the *square* of the depth (if you double the depth, it will carry *four times* as much) (*Figure 4.32*).




Similarly, we rewrite the second equation:

$$y = K \frac{P l^3}{E b d^3}$$


The deflection, y , of a beam varies (Figure 4.33):




—directly as the load (if you double the load on a beam, it will deflect twice as much) (Figure 4.34):




—inversely as the modulus of elasticity, E (if you select a grade with double the E , the deflection will only be half as much) (Figure 4.35);




—inversely as the width (if you use two beams side by side, the deflection will only be half as much) (Figure 4.36). However, the deflection also varies:



—directly as the *cube* of the span (if you double the span, the beam will deflect *eight times as much*) (Figure 4.37);



—inversely as the *cube* of the depth (if you double the depth, you reduce the deflection to *one-eighth*) (Figure 4.38).



A few points are worth emphasizing. Carrying capacity and stiffness are each affected directly according to the numerical value of the strength property involved. Likewise, varying the width has its expected proportional effect, so two beams are "twice as strong" as one.

In many cases, little can be done to manipulate the span. If you want a 16-ft.-wide living room, the joists must be 16 ft. long; the length of bed rails is fairly well fixed by our average height; a canoe paddle has to be long enough to dip into the water; and the rails of a ladder must be far enough apart for ease of climbing and the stability of the ladder. But where the span can be shortened, the effect on strength, deflection in particular, can be amazing. A good rule of thumb: Cut the span by one-fifth and you just about double the stiffness ($0.8 \times 0.8 \times 0.8 = 0.512$); increase the span by one-quarter, and you double the deflection ($[1.25]^3 = 1.95$)**.

Another hypothetical case: As you plan to finish off your basement into a game room, workshop, or utility room, suppose it is possible to position a partition wall directly under the middle of your living-room floor system. Cutting the span of the joists in half will make your living-room floor seem eight times as rigid.

But it is the depth of a beam that typically can be manipulated to best advantage in influencing strength. Another excellent case in point of deflection mechanics is the structural advantage of using a board as a joist (loaded edgewise) rather than as a plank (loaded flatwise). Consider the standard 2x10, which has actual dressed dimensions of 1 1/2 in. by 9 1/4 in. The original carrying capacity is given by

$$P = \frac{1}{k} \frac{F_b b d^2}{l}$$

(where the board is loaded as a plank, so $b = 9.25$ in., $d = 15$ in.).

** $0.8^3 = 0.512$; $1.25^3 = 1.953125$. **L**, $0.8^3 = 0.512$; $1.25^3 = 1.953125$.
I N S T E A D O F G I V I N G I N S T R U C T I O N S .

Now if we rotate the board to its edgewise position to be loaded as a joist, the relative value of b is reduced to:

$$\frac{1.5}{9.25} b = 0.162b$$

compared with the original b , but the depth has been increased to:

$$\frac{9.25}{1.5} d = 6.167d.$$

Carrying capacity now equals:

$$\frac{1}{k} \frac{(0.162b)(6.167d)^2}{l} = \frac{6.16}{k} \frac{F_b b d^2}{l} = 6.16P.$$

The carrying capacity is more than six times as great for a 2x10 joist than for a 2x10 plank. Now let's consider deflection.

$$y = K \frac{P l^3}{E b d^3} \quad \text{becomes}$$

$$K \frac{P l^3}{E(0.162b)(6.167d)^3} = \frac{K}{38.00} \frac{P l^3}{E b d^3} = \frac{y}{38.00}.$$

The 2x10 joist will deflect only 1/38 as much as the 2x10 plank.

The fact that depth has a more drastic influence on deflection than on carrying capacity is extremely important in framing flooring systems because deflection rather than carrying capacity is the key performance criterion. Common design guidelines are 40 lb. per sq. ft. load and 1 in 360 deflection limit (i.e., 1-in. deflection in 360 in. of span). We have no way of sensing (or caring) what critical stress levels are as long as they are never reached, and usually when the 1 in 360 deflection limit is met, the stress developed is well below that which would cause failure. But deflection becomes increasingly apparent to our senses. I have never heard of a floor actually failing, although I have heard many a complaint about floors being too "bouncy" or "springy."

Under the provision of 40 lb. per sq. ft. load and 1 in 360 deflection limits, the "allowable span" tables tell us that a 2x8 with stress rating of $E = 1,000,000$ psi is adequate for a 12-ft. span. This, however, is marginal and although it satisfies the load and deflection requirements, it may not be as rigid as the homeowner wants. You may wish to overdesign for added satisfaction.

I once knew a builder who proudly revealed that he had doubled all the flooring joists (obviously at twice the cost)

in a condominium to give better quality and increased satisfaction to the occupants. While commendable from the consumer's point of view, it was a questionable design choice from the cost standpoint. Instead of doubling 2x8s (at double the cost), 2x10s might have been used. Since 2x10s of the same species and grade were selling at the same price per board foot, this would have required a material cost increase of only 25%. By increasing the depth from 7.25 in. to 9.25 in., or an increase from d to 1.276 d , we find:

$$K \frac{P l^3}{E b (1.276d)^3} = \frac{y}{2.077}$$

So by using 2x10s in place of 2x8s, performance could have been doubled for 259% more cost.

There are countless applications where the principles of beam mechanics can be applied generally, without getting into precise calculations, to improve the mechanical performance of a wood member. For example, in building stairs we realize the importance of firmly fastening the risers to the treads, so the risers will serve as very deep "joists" and stiffen the treads.

A canoe paddle is a modified simple beam that develops maximum bending stress along the shaft at the point of the lower handhold (*Figure 4.39*). In making a canoe paddle, you want the maximum strength for the least weight. In shaping the critical area of the paddle, then, you would want to make the shaft elliptical in cross section, with the long axis of the ellipse oriented in the loading direction, in other words, perpendicular to the plane of the paddle blade. The elliptical shape will of course be stronger (that is, it will develop less axial stress for a given loading or will enable a greater loading to develop the same level of maximum stress) than a round one of equal cross-sectional area (and therefore equal weight).

I sometimes think of a simple beam as two cantilever beams attached to one another. Put another way, a cantilever beam can be thought of as half of a simple beam (*Figure 4.40*). The same mechanical principles that govern the relationship of simple beam depth to midspan axial stresses can be applied to attachment stresses on a cantilever beam.

This suggests further application to certain joints. For example, when you lean back in a chair, the seat apron is cantilevered onto the back posts (*Figure 4.40*). Here we see the importance of the depth of the apron member (or the height of the connecting mortise) in determining the magnitude of stresses in the joint. Similarly, where such joints are doweled, the distance between the dowels, as controlled by the depth of the apron, also determines stress levels in the dowels.

There is a practical limit to how much a beam can be improved by increasing the depth in comparison with the




Figure 4.39 • A canoe paddle is a simple beam. The elliptical shaft is stronger in bending than is a round one of the same cross-sectional area.




Figure 4.40 • In a cantilever beam, the maximum board stresses vary inversely with the square of the depth of the beam.

width, for just as the stability of columns is limited by their relative length, joist-type beams may become unstable or difficult to fasten. In floor systems, diagonal crossbracing must be installed to ensure stability as well as to help distribute concentrated loads.

Shear strength may also be critical in bending. A beam may be thought of as consisting of horizontal layers that attempt to slide past one another as the beam bends under load (*Figure 4.42*). The internal stress that causes sliding, called horizontal shear, is greatest near the ends of the beam along the neutral axis, and it is zero through the midspan of a center-loaded beam. In beams that are fairly long relative to their depth, axial bending stresses become critical long before shear stress becomes very great. However, in beams that have a relatively small length-to-depth ratio (i.e., beams that are short), shear stresses may reach critical levels before axial stresses, resulting in horizontal shear failure. Although they are not too common.




Figure 4.41 • The seat of a chair is cantilevered onto the back posts. When you lean back, the depth of the apron determines the magnitude of stresses in the joint.

instances of such failures come to mind. When you attempt to use a wooden pole as a lever to raise a heavy object, the tip of the pole may broom over. When bulldozers push against tree stumps, the stumps sometimes broom over rather than uproot or break off.

Horizontal shear failures in bending are also likely in woods with natural planes of weakness, such as the early-wood pore zones in white ash, where the weak layer of structure coincides with the plane of maximum horizontal shear. This is an additional reason for not hitting a baseball on the trademark side of the bat.

Horizontal shear can be especially critical in composite products having relatively weak internal layers. The classic case in point is thick plywood, where the perpendicular grain direction of interior plies represents weaker layers, often further weakened by knife checks in the veneer, so rolling shear develops (*Figures 4.43, 4.21*). Such failures often result when plywood is used in place of solid wood to







Figure 4.42 • Horizontal shear in a beam is illustrated in the drawing and photos above by subjecting to bending a stack of free-sliding slats arranged as a beam. The stiffness that would be gained by gluing the layers together suggests the role of shear resistance in a solid beam. (Photos by Richard Starr)

construct a short cantilevered overhang, such as a tabletop. Heavy loading of the overhang may cause failure in horizontal rolling shear, even though the surface plies have not failed from axial bending stress. This separation of the plies is often incorrectly regarded as delamination and therefore blamed on adhesive failure, but close inspection will usually identify the real problem as horizontal shear.

Various types of particleboard may also be prone to horizontal shear failure due to their low internal bond strength. This is especially true in boards having a stratified density or varied particle type from face to center.

FACTORS AFFECTING STRENGTH PROPERTIES

Much of the previous discussion has been aimed at the basics of strength properties, and for simplicity we made some assumptions and generalizations that would seldom apply in reality. For example, calculations of stress in chair parts were made with average static strength test results, without considering variability or defects in the wood, moisture content, time under load, or safety factors. In the real world, however, lumber can have defects, and we must have dependable, "allowable" stress values that take into account the possible effects of defects or uses that affect strength. It is important for the woodworker to understand the extent to which various factors affect strength, so that intelligent judgment can be made in the many cases where one can't go




Figure 4.43 • Horizontal rolling shear, induced by lathe checks, develops when a 12-in. plywood beam is loaded in the center. This is analogous to putting weight on the edge of an overhanging plywood tabletop. (Photo by Randy O'Rourke)

by the book. Some factors reflect environmental conditions in which the wood is used, some reflect natural characteristics or abnormalities inherent in trees, while others are defects inflicted upon the wood during the process of converting trees to wood products.

MOISTURE CONTENT The change in tear resistance and flexibility of paper in response to wetting and drying dramatizes the influence of moisture content on the strength of wood substance. Although less striking, the increase in the strength of wood as moisture content decreases below the fiber saturation point, which is the condition where cell walls are fully saturated but cell cavities are free of water, is nevertheless obvious. Many woodworkers and carvers have discovered the relative ease with which green, or freshly cut, wood can be worked with hand tools. In cases where a partially shaped piece can be dried without defect, the rough work is often easiest to accomplish in the green state. Nails easily driven through many hardwoods while green would bend over if the wood were dry.

The strength of wood increases as the wood gets drier, although the rate of strength improvement is not directly related to loss of bound water (as is the case with the shrinkage rate) (*Figure 4.44*) property. For example, maximum crushing strength in compression parallel to the grain and fiber stress at proportional limit in compression perpendicular to the grain is approximately tripled in drying from green to oven-dry. Modulus of rupture in bending is more than doubled in the process, but the stiffness is increased by only about half.




Figure 4.44 • Wood weakens as its moisture content increases.

TIME UNDER LOAD The test results listed in *Table 4.1* on p. 79 were obtained from static strength tests in which specimens were under load only for a matter of minutes. If loaded more rapidly, they would show higher strength, while if loaded more slowly they would show lower strength. For example, wood loaded to failure in bending within one second (rather than the standard 5- to 10-minute duration of the static bending test) would show about 25% higher strength. If held under sustained load for 10 years, it would show only 60% of the static bending strength. To put it another way, if a beam must support a load for 10 years, it can carry only 60% as much load as it carries in the static bending test. This reveals that in addition to the immediate elastic response, which is apparent upon loading, there is additional time-dependent deformation called creep. At low to moderate loads, creep is imperceptible. Over extremely long periods of time or when loads approach maximum, creep may result in objectionable amounts of bending or even failure, such as sagging timbers in old buildings. The sagging of shelf boards loaded with books is perhaps a more familiar example. The study of time-dependent stress and strain behavior is called rheology.

Since most structures are built for an anticipated life of many years, long-term loading is an important consideration in determining allowable stress ratings for lumber. Wood performs well under repeated short-term or cyclic loads without fatigue failure or becoming brittle, unlike certain metals and concrete.

TEMPERATURE Strength in wood responds immediately to changes in temperature, increasing as the temperature drops, decreasing as the temperature rises. Through the range of temperatures found in nature, air-dry wood changes in strength by an average of 2% to 5% for every 10°F change in temperature. Such changes are reversible. That is, when returned to room temperature, the wood returns to its original strength. High temperatures may result in some permanent loss of strength, the extent depending on the temperature reached, the duration of heating, the heat source, and the moisture content of the wood. For example, wood of some species at low moisture content that is heated momentarily in dry air to near ignition temperatures and immediately recooled shows no strength loss. However, sustained heating of moist wood in hot water at temperatures near 212°F can cause some permanent loss of certain strength properties. However, exposure of wood to extremes of low temperatures cannot induce permanent increase in strength.

CROSS GRAIN In most wooden items—boards, beams, posts, turnings, and so forth—it is intended or assumed that the grain direction is parallel or virtually parallel to the long axis of the piece. Wood with such ideal grain orientation is said to be straight-grained. Deviation of the grain from the

direction of the longitudinal axis to an extent as to cause measurable effect on properties is termed **cross grain**.

Cross grain that is a deviation from the edge of a flatsawn board is called **spiral grain**, the result of helical grain direction in the tree (*Figure 4.45*). Spiral grain may also result from misaligned sawing. **Diagonal grain** is cross grain resulting from deviation of the plane of the growth ring from the longitudinal axis, resulting from failure to saw boards parallel to the bark of the log.

Cross grain is measured as **slope of grain**, taken as the ratio of unit deviation across the grain to the corresponding distance along the grain (*Figure 4.46*). The slope of grain is expressed as 1:12, one-twelfth, or 1 in 12 (in any case, it is read as "1 in 12"). When the grain deviates from two adjacent faces, the **combined slope of grain** must be calculated by geometric methods (*Figure 4.47*).

Visual determination of grain direction can be most deceiving. Except on true radial surfaces, the temptation to use growth rings as an indicator of grain direction should be avoided. Except on tangential surfaces, rays also should not

be relied upon. Linear anatomical features visible to the eye, such as softwood resin canals or hardwood vessels, are quite helpful. It may also help to mark the wood with ink or dye using a felt-tipped pen. The grain direction then will be indicated by hairline extensions of the ink along longitudinal elements. There are also scribing tools that follow the grain when drawn along the surface of a board. It is good practice to test your ability to analyze slope of grain on short scraps of wood, then split them apart to check your evaluation.

Straightness of grain is important because of the effect it has on strength properties. Limitations on permissible grain deviation are therefore often specified in structural lumber, particularly in ladder stock. It is assumed that stresses induced by loads on the wood, when developed parallel to the axis of a piece, will coincide with the grain direction of the wood and be resisted by the superior parallel-to-grain strength of wood in tension or compression. The consequence of cross grain depends on the extent to which a corn-




Figure 4.45 • Striations in the bark of this eastern hophornbeam stem indicate spiral grain. (Photo by Randy O'Rourke)




Figure 4.46 • This round-edge red maple board first appears normal, but pith flecks indicate spiral grain. The split shows the slope is 1 in 6. (Photo by Randy O'Rourke)




Figure 4.47 • In simple cross grain, as in the diagonal grain A, the slope of the grain is easily measured by observing the growth rings on the surface. Here the slope is 1 in 8. The example shown in B is more common, where the growth-ring appearance on the surface does not coincide with the grain direction (X). The slope is 1.5 in 12 (or 1 in 8). Note that the slope must be calculated from end grain and edges.

ponent of weaker perpendicular-to-grain strength is brought into play (Figure 4.48).

Compression strength appears least affected by this characteristic. Slopes of grain no worse than 1:10 have a negligible effect, and a slope of 1:5 shows only about a 7% reduction in strength. Bending and tensile strengths are more drastically affected. Modulus of rupture, for example, is reduced by about 20% by a slope of 1:10 and by 45% by a slope of 1:5.

VARIABILITY In chapter 1, and particularly in Figure 1.14 on p. 15, the twelvefold range of density among species was discussed. This variation among species is evident when we consider the relative proportions of different cell-type dimensions and cell-wall thicknesses (Figure 4.49). The average specific gravity of a species is perhaps the best possible single predictor of strength.

Within a species there is considerable variation in density and strength, and the strongest piece of wood (among straight-grained, defect-free pieces) of a species typically has at least double the strength of the weakest. For example, if the average maximum crushing strength in compression parallel to the grain for a given species is 4,500 psi, individual pieces of that species could be expected to have

strengths ranging from about 3,000 psi to about 6,000 psi. Most of this strength range is associated with a density variation and can therefore be sensed by the weight of a piece. However, some is due to subtle differences in cell structure and cannot be predicted.

In certain species, some of this variability is predictable based on growth rate. In conifers, especially uneven-grained species such as Douglas-fir, the width of the denser, stronger latewood is least affected by changes in growth rate. As a tree grows faster, the wider rings have a greater proportion of earlywood; as the growth rate slows down, the earlywood is narrower (Figure 4.50). The wider rings of fast-grown softwoods therefore have a greater percentage of earlywood and the wood will be weaker on the average. Growth rate, usually measured in rings per inch, is extremely valuable in visually stress-grading structural softwood lumber.

In ring-porous hardwoods such as oak and ash, the width of the large-pored earlywood doesn't vary much, so the rate of growth is reflected in the amount of denser latewood. Therefore, fast growth produces denser material (Figure 4.51). Among diffuse-porous hardwoods, growth rate has no predictable relationship to strength. Beyond these few indications, variability in strength of clear wood is difficult to detect.




Figure 4.48 • Cross-grain failure in a chair stretcher (A). Bending failure due to cross grain (B). (Photo A by Randy O'Rourke; photo B by R. Bruce Hoadley)




Figure 4.49 • The denser the cell structure, the stronger the wood. Contrast rosewood (A) with balsa (B). (Photos by R. Bruce Hoadley)



Figure 4.50 • In softwoods, the slower the growth, the stronger the wood. The variable rate of growth in red pine is shown here by the spacing of growth rings. The narrower the earlywood band, the stronger the wood. (Photo by Randy O'Rourke)

There is no significant difference in the strength of sapwood and heartwood per se within a given species. In some cases, heartwood may be preferred because of its decay resistance and its natural ability to retain strength longer. On the other hand, sapwood takes preservative better and can therefore be treated to retain its strength even longer.

LOCALIZED DEFECTS The word defect is a risky term to use without qualification. In this section it refers to irregularities or features affecting strength. A knot, for example, may be a visual asset, but it is clearly detrimental to strength.

Knots are unquestionably the most commonly encountered defects, since all trees have some form of branching system. Knots reduce strength in two ways. The knot itself has abnormal cell structure that runs at an angle to the surrounding grain direction, and an encased knot is not connected to the surrounding tissue. Furthermore, the area around the knot typically contains cross grain that results in severe strength reduction. The degree of weakening caused by knots is quite variable and unpredictable—ranging from negligible in the case of small, round pin knots to total in the case of large, loose spike knots that actually cause a board to fall apart. To be on the safe side, one should assume that the knot has the same effect as physically cutting out the entire knot and the surrounding distorted tissue from the piece. In judging the strength of a piece of knotty lumber, imagine all the knots cut away, then ask yourself whether what is left will be strong enough.

Checks, shakes, and splits are voids and discontinuities in the wood tissue. They should always be suspected of extend-




Figure 4.51 • In ring-porous hardwoods, fast growth produces harder wood. Compare slow-growth red oak (left and center) with fast growth (right). (Photo by Randy O'Rourke)

ing farther than their obvious visual appearance. Seasoning checks may have partially closed, for example. Although reclosed checks or hidden checks may be visually acceptable, their effect on strength will always be present. Failures in tension perpendicular to the grain or shear parallel to the grain can occur by the extension of preexisting checks at much lower stress than would cause failure in undamaged wood.

Defects must be carefully evaluated according to the manner of loading. For example, a ring check, totally enclosed within a boxed heart timber, would affect strength if the timber were used as a beam but would not if it were used as a short column. In bending, the placement of a defect can be profoundly important. A large round knot along the neutral axis of a joist would have little effect, since stresses are minimal in this area. But if the same knot were along the edge of the beam, the rule of assumed physical removal would have to be applied, which would reduce the apparent depth of the joist. Our previous discussion pointed out that reducing the depth of a beam also reduces its load-bearing capacity as the square of the depth. Exactly where you notch or bore a joist is therefore critical. A hole bored through the neutral axis of a joist to pass a wire or pipe will have negligible effect compared with the same-sized notch at the beam surface.

Decay, even in the early stage, has an effect on the impact strength of wood. As decay progresses, every other strength property is in turn affected, and eventually a total loss of strength may result. It is safest to assume that when any sign of decay is visually apparent, the wood is already weakened.

Although stain fungi do not reduce strength, fungal stain indicates that conditions exist or did exist that favor decay and therefore the wood should be suspect. Once dried and kept dry, stained wood can be used without fear of loss of strength.

A list of miscellaneous small defects in wood could be impressively long. The most common defects include insect holes, pitch pockets, bark pockets, pith, wane, bird peck, and nail holes. For these and most other small defects, a close examination will tell you how badly strength is compromised. Look for physical damage, tissue failure, and associated grain distortion, and use your common sense to draw a conclusion about its usability.

COMPRESSION FAILURES AND BRASHNESS

During severe windstorms or under heavy snow load, the bole of a tree may bend excessively. This can also occur during a blowdown or in felling a tree. When the bole of a tree is bent like a giant beam, the wood in the concave side can fail in compression without tension failure developing in the convex side. Thus, the compression damage to the tree might go unnoticed. The result is irregular planes of buckled longitudinal cells, called compression failures, which generally run crosswise to the grain. In rough lumber they are virtually impossible to detect, but on planed or sanded longitudinal surfaces, they are usually visible, appearing as wrinkles across the grain (*Figure 4.52*).

Compression failures are extremely detrimental to members stressed in bending, for the buckled cell structure fails



Figure 4.52 • Compression failures appear as wrinkles across the grain on the longitudinal surfaces of dressed lumber. Photo by Randy O'Rourke)

readily in tension, resulting in sudden beam failure at lower than normal stress levels. I recently bought a lawn rake with a ramin handle to attack the autumn leaves. On the very first stroke, the handle snapped in half as a clean cross break. An area 6 in. to either side of the break had several almost imperceptible compression failures, probably accrued in the felling of the tree. I hadn't done a very good job of shopping. Critical structural members, such as ladder rails, scaffolding, aircraft parts, and boat spars, must be carefully inspected to exclude material with compression failures. Wood containing compression failures is also unsuitable for steam-bending work.

Normal wood is characteristically tough. When it breaks in bending, the cell structure progressively separates as splintering fractures. Audible cracking and creaking accompany the gradual failure of the wood. There is considerable deformation, well beyond the elastic limit, before total failure finally takes place.

Under certain conditions, wood fails abruptly, with minimal deflection and at lower than expected loads. These failures are characterized by cross breaks that lack the usual evidence of fibrous or splintering separation. Such brittle and weak behavior in wood is called brashness (*Figure 4.53*). The fibrous breaking of normal wood might be compared to the breaking of a stringy stalk of celery, while the brash failure of wood would be analogous to the abrupt snapping of a carrot, as did the rake handle mentioned above.

As described above, wood damaged by compression failures will exhibit brashness when stressed in bending. Reaction wood in conifers (compression wood) also shows brashness, even though its density is greater than normal




Figure 4.53 • Normal gradual splintering failure in catalpa beam (left) contrasts with abrupt, brash failure in white pine beam that contains reaction wood (right). (Photo by Randy O'Rourke)

wood. Extreme growth rates may also produce brashness. In ring-porous hardwoods, extremely slow growth results in low-density wood because of the large percentage of earlywood vessels. This wood is characteristically brash and is especially troublesome in steam-bending. Among conifers, moderately slow but healthy growth produces dense, strong wood. Extremely slow growth, as in stunted or overmature trees (wood with 3.5 or more rings per inch), may also produce brash wood. Extremely fast growth in conifers, reflecting the low density of the dominant earlywood, also tends to be brash. The wide-ringed growth of pronounced juvenile wood is especially prone to brashness. Prolonged exposure to high temperature and fungal decay are other causes of brashness in wood.

STRUCTURAL GRADES

After reviewing the many factors that can affect the strength of wood, it is obvious that few (if any) pieces of real-world structural lumber have the same properties as straight-grained, defect-free pieces and that the ordinary conditions of use are unlike short-duration testing under controlled conditions. The differences can be striking.

Allowable stress ratings have been established for safe and reliable structural uses of wood. This is done by stress grading, which grades lumber into categories within which all pieces can be relied upon to have prescribed minimum strength properties. Starting with the strength properties of small, clear specimens, adjustments are then made for normal variability, duration of load, moisture content, and a safety factor. The traditional system of visual grading sorts the pieces into groupings based on visible characteristics, such as rate of growth, latewood percentage (indicating density), knots, slope of grain, reaction wood, shake, wane, and other defects. The groups are usually designated by unique grade names, as well as by allowable stress values for as many as six properties: extreme fiber stress in bending (F_b), modulus of elasticity (E), tension parallel to grain (F_t), compression parallel to grain (F_c), compression perpendicular to grain (F_{cp}), and horizontal shear (F_v).

As an example of the contrast between average strength, values for small, clear, straight-grained specimens and the allowable stresses assigned to graded lumber of the same woods, *Table 4.2* shows values for southern yellow pine. The test values are the averages for six major species of southern yellow pine, adjusted to 12% moisture content (MC). The allowable stress values are for structural joists and planks, kiln-dried to 15% MC.

First let's compare fiber stress in bending (F_b). For small, clear specimens, the test averages range from 16,300 psi down to 12,600 psi for modulus of rupture (MR). However, the allowable design stress in structural material is reduced to the

range of 2,250 psi to 800 psi among the various grades. This indicates the extent to which defects and other allowances affect the strength of clear wood and must be accounted for in designing structures against the chances of failure.

But for modulus of elasticity (E), relatively minor reductions are made, even in the lowest grades. In fact, it is apparent that visual sorting is capable of successfully selecting the stiffest pieces, since the best allowable stress value is 2.0×10^6 psi, which is higher than the strongest species average of 1.98×10^6 psi. This brings out an interesting point about modulus of elasticity. It senses the performance of the entire piece because under load all areas of the piece, weak and strong, make a representative contribution to resisting strain. However, in the case of breaking strength, defects may act as the weak link in the chain and severely reduce load-carrying capacity. The percentage reduction in E therefore is less over the range of grades than is the reduction in bending strength.

This suggests an important strategy in design of framing where deflection is a controlling factor. Many times it is advantageous to use a low grade of high modulus of elasticity species, such as Douglas-fir or southern yellow pine, rather than a high grade of a low E species, such as spruce. For example, in one case a house design calls for 14-ft. spans, for which 2x10s of grade No. 2 and better eastern spruce with an allowable E of 1.0 would marginally satisfy the deflection requirement. But consider No. 3 2x12 Douglas-fir. Its allowable fiber stress value is lower, but the deeper beam reduces the stress enough to remain safe. No. 3 Douglas-fir is rated $E = 1.5$. Let's look again at the formula for beam deflection:

$$y = K = \frac{Pl^3}{Ebd^3}$$

When we raise E from 1.0 to 1.5 and d from 1.0d to:

$$\frac{11.25}{9.25} = 1.216d,$$

$$K \frac{Pl^3}{(1.5E)b(1.216d)^3} = \frac{K}{2.69} \frac{Pl^3}{Ebd^3} = \frac{y}{2.69} = 0.370y.$$

We see that deflection is reduced by 60%, meaning that the joists are more than twice as rigid.

The increase in lumber board footage is 20%. But the cost of Douglas-fir No. 3 is currently only 59% of the cost of No. 2 and better spruce. Therefore, the 20% additional Douglas-fir still costs only 71% as much as the spruce. In summary, the floor system framed with No. 3 Douglas-fir 2x12s would cost 29% less but would be twice as rigid and would still be safe enough.

TABLE 4.2—Comparison of highest and lowest average clear wood strength properties among the principal species of southern yellow pine (longleaf, shortleaf, loblolly, and slash) with equivalent allowable design stress values of various grades of structural lumber.

Average clear wood strength properties of wood tested at 12% moisture content (values in psi).

Test	Static bending	Compression parallel to grain	Shear parallel to grain	Compression perpendicular to grain	Static bending
Property	Modulus of rupture	Maximum crushing strength	Maximum shear strength	Fiber stress at proportional limit	Modulus of elasticity
Highest average	16,300	8,260	1,680	1,010	1,980,000
Lowest average	12,600	6,940	1,390	750	1,750,000

Allowable stress ratings of joists and planks, surfaced at 15% moisture content and used at a maximum of 15% moisture content (values in psi).

Design stress	Extreme fiber in bending	Compression parallel to grain	Horizontal shear	Compression perpendicular to grain	Modulus of elasticity
Designation	F_b	F_c	F_v	F_{cp}	E
Commercial Grade					
Dense Select Structural	2,250	1,900	95	475	2,000,000
Select Structural	1,950	1,650	95	405	1,900,000
No. 1 Dense	1,900	1,700	95	475	2,000,000
No. 1	1,650	1,450	95	405	1,900,000
No. 2 Dense	1,550	1,450	95	475	1,800,000
No. 2 Medium Grain	1,350	1,350	95	405	1,700,000
No. 2	1,150	1,050	80	345	1,500,000
No. 3 Dense	925	875	95	475	1,600,000
No. 3	800	750	80	345	1,500,000

In the above examples involving calculations of strength behavior in floor systems, only the joists were considered for the sake of simplicity. In reality, the subflooring, finish flooring, and cross-bridging are integral parts of the total floor system and will be involved in the total performance. Effects, as demonstrated for different joist depths and species properties, must be taken as approximate, but comparisons are nevertheless valid.

MACHINE STRESS GRADING In recent years, machines have taken over some of the grading. Rather than sorting pieces visually, each piece is flexed in a machine with enough load (but well below the proportional limit [P']) to establish the slope of the elastic curve. In this way, E - determined directly. This results in an actual modulus of elasticity for the piece, not an estimated one. Based on thousands of previous tests carried to failure, closer prediction of MR can be made from these E values, so that

more precise F_b (extreme fiber stress in bending) values can be assigned.

Although such a nondestructive and accurate method of stress rating should be welcomed, it has caused an interesting reaction. It has created a case of what I call "the baker's dozen syndrome." Some of us can still remember when the baker gave you 13 cupcakes when you bought 12. We can also remember the day when we bought a dozen and got 12. In shock we thought, "Hey, where's my other cupcake? I paid for a dozen and I got only 12!" Likewise, builders and homeowners had been getting extra F_b and E . But now the more precise is recognized as something less. In particular, boards that don't *look* strong are a special cause for concern. So regrettably, machine stress rating, although seemingly a major advancement in lumber quality control, was slow to become accepted but is now a fairly well-established technology for grading structural lumber.




Figure 5.1 • A fluorescent response under ultraviolet light is one of the unusual properties exhibited by certain woods. (Photo by Randy O'Rourke)

OTHER PROPERTIES OF WOOD

So far we've been concerned with the biological nature of wood and with wood's mechanical properties. I'd like to digress briefly into some lesser-known aspects of wood—its thermal properties, the little-known property of fluorescence, and what I call wood's psychological properties (*Figure 5.1*).

THERMAL CONDUCTIVITY

The concept of wood being "warm" is understandable on the basis of thermal conductivity. The sensation of hot or cold depends not only on the temperature of the object touched but also on the rate at which it conducts heat away from or into our skin. For example, if you touch cool pieces of wood and metal, heat is conducted out of your skin and into the metal hundreds of times faster than into the wood. Although they are at the same temperature, the wood feels warmer. Consequently, wood has long been preferred for gunstocks, tool handles, and seating.

So, perhaps without knowing it, we are all familiar with the thermal conductivity of wood, or rather, the relative non-conductivity of wood. Wood is more noteworthy as an insulator than as a conductor of heat. Comparative values of conductivity are listed in *Table 5.1*. The coefficient of thermal conductivity, **K**, indicates the relative rate of heat flow through the various materials listed.

Since the **K value** indicates relative conductivity, its reciprocal, $1/K = R$, measures relative insulating value. The higher the **R value**, the better the insulator. R values are commonly used to designate the insulating value of building materials such as insulation batts and wall sheathing.

As given in *Table 5.1*, the values for oven-dry wood are meaningful only to the extent that they show the range represented by different species. This is because wood is seldom used in its oven-dry condition. The thermal conductivity for any species depends on both specific gravity and moisture content and can be calculated by the formula:

$$K = 5(1.39 + 0.028 MC) + 0.165,$$

where **K** = the coefficient of thermal conductivity in Btu/ft.²/°F/hr./in.; **S** = specific gravity; and **MC** = moisture content in %. Thus, both increasing specific gravity and increasing moisture content will result in higher conductivity because it lowers the insulating value.

For most species of softwood structural lumber at commonly encountered moisture contents, the **K** value will generally be about 1 or slightly less, the **R** value about 1 or slightly above. For example, in spruce structural lumber having a specific gravity of 0.40 and an average moisture content of 10%,

$$K = 0.40(1.39 + 0.028[10]) + 0.165 = 0.833.$$

TABLE 5.1—Approximate thermal properties for various materials.

Material	K*	R**
Air	0.16	6.25
Water	4	0.25
Ice	15	0.07
Glass	5	0.2
Brick	4.5	0.22
Concrete	7.5	0.13
Marble	17	0.06
Steel	310	0.003
Aluminum	1,400	0.0007
Building insulation (foam rock wool, fiberglass)	0.2 to 0.3	3.3 to 5
Wood (oven-dry perpendicular to grain)	0.4 to 1.2	0.8 to 2.5

*K = Coefficient of thermal conductivity, expressed as the number of British thermal units (Btu) that will flow through a material per hour, per inch of thickness, per square foot of surface area, per degree Fahrenheit difference in temperature from the warmer to the cooler side.

**R = 1/K, referred to as the resistivity of a material, represents the relative insulation value for a material.

Given the high cost of energy and concern for the condition of our energy resources, heat loss in buildings is of the utmost concern. Table 5.1 makes it clear that wood is a better thermal insulator than most other structural materials. It is more than seven times more effective than concrete, 300 times more effective than steel, and 1,400 times more effective than aluminum of comparable thickness. At the same time, materials produced specifically for insulation, such as glass fibers, rock wool, and foam products, are three to four times better insulators than solid wood. In many cases where strength, beauty, and insulating value are desirable, wood is an appropriate compromise and therefore a logical choice.

Noting from the table that water has a K value of 4 and ice has a K value of 15, it is obvious that keeping wood (or any other insulating material) dry is vital to maintaining its insulating potential. In cold climates, vapor barriers should be provided as close as possible to the interior walls of buildings. This prevents condensation from accumulating within the walls, which will lower the R value and encourage decay.

In most cases where thermal conductivity is critical, the direction of heat movement is perpendicular to the grain, so the values mentioned are calculated for that situation. Thermal conductivity parallel to the grain is two to three times greater than across the grain.

EFFECT OF TEMPERATURE ON WOOD

Like any other material, wood expands when heated and contracts when cooled. This change is referred to as linear thermal expansion or contraction. The unit amount by which a material expands (per unit of original length per degree rise in temperature) is called its **coefficient of thermal linear expansion**.

In the grain direction, wood changes dimension by only about 2 millionths of its length per Fahrenheit degree change in temperature. This means that if an 8-ft. Douglas-fir framing stud were to experience a temperature change from 90°F to -10°F, it would become only 0.018 in. shorter, slightly more than 1/64 in. Over the same temperature range, steel rods of the same length shrink by more than three times this amount and aluminum more than seven times. Perpendicular to the grain, the coefficient of thermal expansion for wood is as much as ten times larger than the coefficient for wood parallel to the grain direction.

When extreme changes in temperature occur in the environment, the associated humidity changes will probably produce shrinkage or swelling of the wood that far overshadows the insignificantly small thermal expansion or contraction. For routine uses of wood, changes in dimension caused by changes in temperature are negligible.

While expansion is not usually significant, the effect of temperature on the strength of wood is extremely important. As will be considered later in discussing strength and steam-bending of wood, elevated temperature may cause both temporary and permanent strength reductions, the net effect depending on such factors as the species and moisture content, the heat source, and the level and duration of the heat.

BURNING OF WOOD

When the temperature of wood is raised well above the boiling point of water, chemical degradation begins to take place. At higher temperatures or with prolonged heating, the wood will darken or char. In the presence of ample oxygen, wood ignites when the temperature reaches 500°F to 550°F. If oxygen is excluded, gases are driven off without combustion. This process is called **destructive distillation** or **pyrolysis**, and the eventual product is charcoal. When oxygen is present, the gases and charcoal burn together. However, all the gases do not burn until temperatures reach 1,100°F. Once ignited, those burning gases may develop temperatures up to 2,000°F.

The molecules forming the wood's major constituents were originally synthesized by taking energy from the sun to drive the necessary chemical reactions to produce nourishment for the tree's cells to grow. As these components break down in combustion, this energy is released as heat, up to 9,000 Btu per pound of dry wood. Although a thorough discussion of wood as a fuel is beyond the scope of this book, those who work wood will probably want to use their waste wood as fuel at some point.

The most popular unit of measure of fuel wood is the **standard cord**, defined as a pile of 4-ft.-long wood stacked 4 ft. high and 8 ft. wide. Although it occupies 128 cu. ft. of space, an average cord contains about 80 cu. ft. of solid wood. Depending upon species and moisture content, a cord weighs from one to two tons.

Firewood is commonly cut to short lengths and sold in units called **face cords**. A face cord is a stack 4 ft. high and 8 ft. wide whose depth is equal to the length of the pieces in the stack. A 16-in. face cord is a 4-ft. by 8-ft. stack of pieces 16 in. long. It would occupy one-third of the space of a standard cord but would probably contain slightly more wood than one-third of a standard cord because wood stacks more tightly when cut to shorter length. A 4-ft. face cord equals a standard cord.

I have yet to discover a wood that I cannot use satisfactorily for fuel (provided it has been adequately dried). Among the various species, however, I have undeniable favorites—some for their flame color, some for their aroma, some for their ability to produce cooking coals, some for

their slow burning rate. But heating value is closely related to dry weight, so specific gravity is the most reliable predictor of thermal value.

For example, eastern white pine has a fuel potential of 12,000,000 Btu per cord, while hickory has a fuel value of 24,000,000 Btu per cord. In determining whether fuel wood is an economically attractive alternative, calculations have shown that a cord of white pine has the heating value of about 100 gallons of No. 2 fuel oil; a cord of hickory, 200 gallons. But these calculations are based on two important considerations: the stove efficiency and the moisture content of the wood. Modern airtight or "high-efficiency" woodstoves have a conversion efficiency of 50% to 60%. an assumption included in the above calculations. By contrast, a standard box stove has only about 25% efficiency and an open fireplace less than 10%.

The calculations further assume that the wood has been air-dried, or seasoned, to 20% MC or less. If the wood is too wet, a great deal of heat is lost in heating and evaporating the excess moisture. Another consequence of burning wet wood is that the moisture driven off condenses in the flue along with other materials, forming a layer of creosote, a flammable substance that may later support a chimney fire.

In cities and suburban areas, burning wood for heat is an expensive luxury, justified only for the aesthetic and psychological pleasure it brings. In most rural areas, the cost of conventional fuels compared to available cordwood makes wood a logical choice. It is estimated that in Vermont, the amount of timber that decays and disintegrates by neglect represents far more fuel than would be needed to satisfy the entire energy budget of the state. Although the reaction rate is drastically different, the breakdown of wood by burning and by biological deterioration is similar. The principal products in both cases are thermal energy, carbon dioxide, and water. Thankfully, burning wood produces only negligible amounts of sulfuric pollutants, in contrast to many other common fuels.

The burning of wood is also used as a craft technique. Carvers of birds use fine wood-burning pencils to create delicate veining of feathers. Sculptors and other craftsmen use blowtorches to decorate surfaces by charring, which achieves an attractive effect because of differences in the relative density of earlywood and latewood.

FLUORESCENCE

Anyone who has not yet witnessed the strange response of woods under ultraviolet light has a delightful surprise in store. Certain woods, when viewed under "black light," emit a mysterious glow or fluorescence, which is almost sure to

inspire ideas in woodcraft. This is a rather unfamiliar property of wood and is a fascinating visual phenomenon, well worth investigating.

Fluorescence is the absorption of invisible light energy by a material capable of transforming it and emitting it at wavelengths visible to the eye. Sir George Stokes, who first observed the response in the mineral fluorite, gave the term fluorescence to this phenomenon in 1852.

The human eye can see light over the spectrum of wavelengths varying from about 8,000 Angstrom units (red) down to about 3,800 Angstrom units (violet). (Angstrom units, which equal about 4 billionths of an inch, are used to measure wavelengths of light.) Above 8,000 Angstroms is invisible infrared light; below 3,800 is invisible ultraviolet light. The black light commonly used for visual effects is in the 3,800 to 3,200 Angstrom range and is referred to as long-wave or near ultraviolet light. It won't harm the eyes. Light in the 3,200 to 2,900 Angstrom range includes rays that cause tanning and sunburn. Below 2,900 Angstroms is short-wave or far ultraviolet. This light is used to kill bacteria and is very dangerous to the eyes. Sterilization units or other sources of short-wave ultraviolet should never be used to view fluorescent materials.

The commercially available long-wave or black-light lamps emit light averaging about 3,700 Angstroms. However, the light may range from as low as 3,200 up to about 4,500 Angstroms, well into the visible range. We therefore often see a purple glow, although most of the light emitted is invisible.

Chemicals in a fluorescent material absorb this invisible light but transform the energy, so that the light emitted from the material is within the visible range and is seen as a particular color. Many domestic species of wood exhibit some fluorescence. *Table 5.2* lists the principal species, although there are doubtless others. Fluorescence is of obvious value in identification, and many otherwise confusing species are easily separated on the basis of fluorescence.

Fluorescence is scarcely recognizable in some species and strikingly brilliant in others. The colors listed are typical for each species, but variation of both hue and brilliance occur among individual samples. Countless other species from around the world, too numerous to list, also show fluorescent properties. Some 78 genera, 45 of which are in the family *Leguminosae*, yield fluorescent woods. However, our native species are as attractive as those found anywhere in the world.

Yellow is the predominant color, and also the most brilliant, as in black locust, honeylocust, Kentucky coffeetree, and acacia. Barberry, a lemon-yellow wood under normal light, is also among the most brilliant yellows, but because it is a shrub it is difficult to locate pieces large enough for anything but small items, such as jewelry.

TABLE 5.2—Partial list of North American woods exhibiting noteworthy fluorescence under ultraviolet light.

Scientific name	Common name	Color of fluorescence
<i>Acacia greggii</i>	Catclaw acacia	Deep yellow
<i>Annona glabra</i>	Pond-apple	Dull yellow
<i>Asimina triloba</i>	Pawpaw	Faint yellow-green
<i>Berberis thunbergii</i>	Japanese barberry	Bright yellow
<i>Cercidium floridum</i>	Blue paloverde	Yellow-green
<i>Cercidium microphyllum</i>	Yellow paloverde	Yellow
<i>Cercis canadensis</i>	Eastern redbud	Bright yellow
<i>Cladrastis kentukea</i>	Yellowwood	Pale yellow-light blue
<i>Cotinus obovatus</i>	American smoketree	Deep yellow
<i>Gleditsia aquatica</i>	Waterlocust	Pale yellow
<i>Gleditsia triacanthos</i>	Honeylocust	Bright yellow
<i>Gymnocladus dioicus</i>	Kentucky coffeetree	Deep yellow, bright
<i>Ilex verticillata</i>	Common winterberry	Light blue
<i>Magnolia virginiana</i>	Sweetbay	Faint pale yellow
<i>Mangifera indica</i>	Mango	Pale orange
<i>Piscidia piscipula</i>	Florida fishpoison-tree	Dull yellow
<i>Rhus copallina</i>	Shining sumac	Bright yellow
<i>Rhus glabra</i>	Smooth sumac	Bright yellow
<i>Rhus ovata</i>	Sugar sumac	Yellow
<i>Rhus typhina</i>	Staghorn sumac	Bright yellow, greenish yellow to pale blue
<i>Robinia neomexicana</i>	New Mexico locust	Bright yellow
<i>Robinia pseudoacacia</i>	Black locust	Bright yellow
<i>Robinia viscosa</i>	Clammy locust	Bright yellow
<i>Torreya taxifolia</i>	Florida torreya	Dull yellow
<i>Yucca brevifolia</i>	Joshua-tree	Yellowish gray
<i>Zanthoxylum clava-herculis</i>	Hercules-club	Sapwood pale yellow to light blue, heartwood bright orange

Perhaps the most interesting is staghorn sumac. The sapwood has a pale lavender-blue fluorescence (Figure 5.2). In the heartwood, each growth ring repeats a yellow, yellow-green, lavender-blue sequence. Many species show less spectacular but nevertheless interesting colors. Yucca and holly have a soft bluish to gray fluorescence. Purpleheart emits a dim coppery glow. Badi exhibits a mellow pumpkin orange.

In addition to normal sapwood and heartwood fluorescence, certain anatomical features such as resin canals, oil cells, vessel contents, bark, fungal stains, and pigment streaks can also show selective fluorescence. In aspen, for example, a brilliant yellow fluorescence usually occurs at the margins of areas stained by fungi.

The unusual effects of fluorescing woods suggest interesting applications for the craftsman, especially in carving

and marquetry (Figure 5.3). Inspiring sculpture and religious statuary can have moving effects when viewed in darkness or in subdued light with hidden ultraviolet lamps. Desk-set bases or light-switch covers can be given unusual effects. Fluorescence can add extra excitement to wooden jewelry and personal accessories. An African mask or Polynesian tiki carved in a fluorescent species makes an unusual pendant or pin.

Fluorescent woods can be used in combination by laminating or inlaying. Menacing fluorescing teeth can be set in the mouth of a carved dragon. Spooky yellow eyes that "light up" can be inlaid into a carved owl. Laminated woods can be carved or turned into unusual lamp bases—especially for black lights. And don't throw away carving chips and planer shavings—children delight in gluing chips and sawdust to cardboard to create fluorescing designs and pictures.




Figure 52 • Different woods exhibit various degrees of fluorescence. Photo A shows 4-in.-dia. cross-sectional slices of eastern redcedar and staghorn sumac under normal light. Photo B shows them under ultraviolet light. The sumac is fluorescent, the redcedar is not. (Photos by Randy O'Rourke)

The fluorescent response of wood is subject to surface chemical degradation, however, apparently associated with the familiar darkening or aging effect. The brilliance of fluorescent wood is most rapidly faded by exposure to daylight, especially direct sunlight. The original brilliance of a carving will remain for years if it is kept in a dark place. In normal indoor daylight conditions, a year's exposure will fade the fluorescence to about half its original brilliance. This dulling effect is at the very surface, and a light recarving or sanding will renew the original fluorescence.

Most finishes reduce the brilliance of fluorescence but in the long run may help maintain it by minimizing aging. Clear paste wax seems to have the least dulling effect.

PSYCHOLOGICAL PROPERTIES

The word "properties" usually suggests scientific information about physical, mechanical, chemical, or anatomical characteristics. We commonly express properties such as moisture content, density, strength, and thermal conductivity in standardized units of length, volume, mass, or degrees. This book has so far dealt closely with these scientific prop-

erties because they allow us to work out so many of the routine technical problems encountered in woodworking. For all that, this book would be incomplete if it did not acknowledge what I call the psychological attributes of wood.

Wood has values or powers that cannot be quantified in scientific terms. These aspects of wood, without being well-understood or even explainable, may well be among the most important and powerful. However difficult they are to describe or define, we can at least demonstrate their certain existence.

Part of what we are dealing with here might be termed *sensual properties*, where there is a close relationship to our senses of touch, sight, hearing, smell, and taste. These properties include color, odor, resonance, and so forth, and are in part explainable and describable in scientific terms. For example, the somewhat emotional reference to the warmth of wood is largely the physical reality that wood feels warm to the touch (especially when compared to ceramics and metals), which we understand scientifically in terms of dry wood's low coefficient of thermal conductivity. But there remains an aura of warmth suggestive of "friendliness."

In considering psychological properties, we need not strive for (nor expect) much agreement among people.



Figure 5.3 • Seated figure, 6 in. high, carved by the author from staghorn sumac. Under normal light (left), the large area of sapwood along the upper arm and body is a pale grayish-cream color; heartwood is a drab yellow-green to olive green. Under ultraviolet light (right), the sapwood fluoresces to pale lavender-blue, and the heartwood repeats a luminescent lavender/yellow-green/bright yellow sequence in each growth ring. (Photos by R. Bruce Hoadley)

Unlike physical and even sensual properties, which can be described by the universal language of science and thereby be conveyed to others, psychological properties are subjective. A psychological feature may exist for one person and be totally meaningless to the rest of humanity. Similarly, an individual piece of wood may have meaning that does not attend other pieces of the same species or even the same tree. For example, deep sentimental value may be attached to an object made from the wood of a familiar or famous tree. Souvenirs carved of wood that is native to a particular place are treasured because of the memories they evoke. If you have ever made a thing of wood taken from a particular tree and presented it to someone who had special attachment to that tree or its locale, you know how precious such a thing can be. A similar attachment to something made of synthetic materials is improbable. Of my entire collection of a hundred or more pieces of wood earmarked for carving, I know the exact place and the very tree from which each came. It is extremely important to the meaning and satisfaction I derive from carving to be familiar with the "roots" of each piece of wood.

I suggest that the psychological appeal of wooden objects develops through the interaction of two vital elements working together: nature and mankind. That wood is a direct and unchanged product of nature undeniably attracts us. In contrast, we bemoan the aesthetic loss in particleboard and hardboard or in products such as rayon carpets or molded egg cartons, which are made of wood but are so transformed from the tree as to be unrecognizable.

Subconsciously (if not consciously) many people today resist being pushed gradually into a synthetic environment, further and further removed from nature, and they seek to retain every possible remnant of the natural world. The importance of wood in interior decoration and the continued importance of leather, wool, and stone testify to the aesthetic and psychological value of natural materials.

Closely related to the value of natural wood in an object is the element of human involvement. Wood was originally used because it was the most appropriate, available, and logical material to satisfy functional needs, but along with production skill and aesthetic appreciation. The fact that our large-scale

commodity production has lost much of this sensitivity is one of the reasons why real wood, especially when hand-crafted, remains so meaningful.

It is not easy to analyze and understand the value of working in wood by hand, nor of the products made thereby. Some people want information about wood to become better technicians, the better to satisfy some of their own commodity needs themselves—the "do-it-yourself-and-save-a-buck" outlook. But I believe that just as many people begin woodworking with an interest in the material itself, rather than any need or desire to make something out of it. Of course, many people begin as technicians and upon "discovering" wood become devoted artisans.

Let me try to illustrate my point by recounting an "experiment" I have repeated with several groups of wood technology students at the University of Massachusetts. In our department seminar room, we have a long walnut conference table. It is handsomely proportioned, with slightly-bowed edges so the top is narrower at each end than in the middle. The table is expertly built, with a top of figured sliced walnut veneers, carefully matched. The ends and edges are neatly banded with deep strips of solid walnut, giving a plank effect to the whole.

With a group of students seated around the table, I call attention to its features from the overall appearance and design, the figure on the top and the well-fitted construction down to its general heft and resonance. I ask for a consensus on the table's merits, and the students enthusiastically approve. Then I ask, "If this is such a beautiful table, aesthetically pleasing and well crafted, does it really matter that it isn't real wood? You all *do* realize that it's actually plastic, don't you?"

The utter shock on every face reveals that indeed it does matter. The bewilderment deepens as I extol the sophistication of modern technology, which can precisely imitate the physical properties of the material and of photographic methods capable of imitating the fine cellular detail of the wood.

When I feel that the point has been driven home, I reveal my prank with the assurance that the table really is genuine walnut. After a short period of emotional confusion, the students forgive me when they realize the purpose of my deception. The group then agrees that "all other things being equal" (as textbooks like to put it), there is indeed a difference between a real wooden table and a synthetic look-alike. That difference, whatever it is, is the mystique of wood.




Figure 6.1 • Sap—mostly free water—flows from the cell cavities as this block of freshly cut red pine sapwood is squeezed by the jaws of the vise. Sapwood in red pine trees can have a moisture content of more than 200%. A similar-size block is shown at lower right. (Photo by Randy O'Rourke)

WATER AND WOOD

Someone once quipped that more than 90% of all problems with wood involve moisture. For those who ignore basic wood-moisture relationships, that is a conservative estimate.

Everyone has been introduced to the interaction of water and wood, for everyone has seen the problems that result when wood shrinks and swells. The bureau drawer that slides freely in January but sticks tightly in August is an all too familiar example of the dimensional response of wood to changes in atmospheric humidity. Warp and surface checks in lumber, loose tool handles, and out-of-round turnings are also common symptoms. Although other consequences of moisture—such as fungal discoloration or gluing failures—can plague the woodworker, dimensional problems are by far the most common and troublesome.

Wood in trees is wet. Very wet. The cell structure contains excessive water (sap) and is fully swollen (*Figure 6.1*). But under conditions where wood is commonly used, much of this water will dry out and the wood will partially shrink. In time, the dryness of the wood and the humidity of its environment reach a fluctuating moisture balance. As woodworkers, we have two goals when dealing with these facts. First, we must dry wood (and thereby preshrink it) to a moisture content consistent with its eventual environment, and second, we must control any subsequent gain or loss of moisture in order to minimize dimensional change. To achieve these goals, we must understand the initial drying of sap from freshly cut wood, as well as the continuing exchange of moisture between the wood and the surrounding atmosphere.

In a nutshell, the atmospheric humidity determines the moisture content of wood, and the moisture content, in turn, determines the dimension of wood. A working knowledge of wood-moisture relationships—the interrelationship of humidity, moisture content, and dimension—is best gained step-by-step. Let's start with the **moisture content of wood** and the **relative humidity of the atmosphere**.

MOISTURE CONTENT The moisture content (MC) of wood is measured as the ratio of the weight of water in a given piece of wood to the weight of the wood when it is completely dry. The water-free weight of wood is usually

referred to as the oven-dry weight because drying in an oven is a common method of obtaining it. This ratio is traditionally expressed as **percent moisture content**.

Suppose a piece of wood weighs 30 lb. If it weighs only 25 lb. after drying in an oven, 5 lb. of water have been driven off. The moisture content would be $5/25 = 0.20$, usually expressed as 20% moisture content. If the same piece had originally weighed 60 lb. and dried to 25 lb., 35 lb. of water would have been driven off. The wet wood had a moisture content of 140% ($35/25 = 1.40 = 140\%$).

RELATIVE HUMIDITY **Humidity** is a general term referring to water or moisture in vapor form in the atmosphere. **Absolute humidity** refers to the actual quantity of moisture present in air. This is typically expressed in grains per cubic foot (1 grain = 1/7,000 lb.) or in grams per cubic meter. **The** amount of water the air can hold varies with temperature (*Figure 6.2*). At 70°F, for example, the air can hold a maximum of 8 grains of moisture per cu. ft.




Figure 6.2 • The relationship between temperature and moisture content of saturated air. The maximum moisture that the air can hold depends on how warm it is; as the temperature rises, so does the saturation point.

Relative humidity (RH) is the ratio of the amount of moisture in the air at a certain temperature to the maximum amount it can hold at that temperature. If the air at 70°F held 4 grains of water per cu. ft., the RH would be 50% because the air is capable of holding 8 grains at that temperature. If the absolute humidity were 6 grains per cu. ft., the RH would be 75%.

The **dew point** is the temperature at which water vapor condenses from the air. Air at 70°F and 50% RH (with 4 grains per cu. ft.) has a dew point of 49.3°F. That means that at 49.3°F the air can hold no more moisture and the relative humidity is 100%. Were that air cooled further, to say 41°F, it could hold only 3 grains of moisture per cu. ft., so 1 grain per cu. ft. would condense out as precipitation.

Nature determines our atmospheric humidity. Weather systems bring air masses having a certain absolute humidity. The actual humidity in any given locale can differ significantly from that absolute humidity due to local influences such as moist vegetation or surface evaporation from nearby bodies of water. Air can never contain more moisture than associated with its dew point, which is why the absolute humidity is low in the cold of winter and high in the summer.

In buildings we routinely manipulate nature's air by heating it up when it is too cold, by cooling it, and sometimes by adding or subtracting moisture from it. It is important for woodworkers to understand the effect of heating and cooling the air in buildings without also adding or subtracting water from it.

Heating air increases its ability to hold moisture. If we increase the temperature of air while the **absolute** humidity is unchanged, the **relative** humidity will be lowered. In sub-zero winter weather, outdoor air has a low absolute humidity as it seeps into our homes and shops. When we heat it to near 70°F without adding moisture, the relative humidity drops very low. Conversely, summer air usually holds an abundance of moisture because of its high temperature. If we cool the air, thus reducing its capacity to hold moisture, the relative humidity (which may be high to begin with) rises even higher.

FREE WATER AND BOUND WATER

The liquid content of the living tree, called **sap**, is primarily water but also contains dissolved minerals, nutrients from the soil, and sugars manufactured by the foliage. For our purposes, we can consider moisture or water in wood to mean both the original sap of the tree and the water from other sources that even previously dried wood can pick up. Water can return to wood from countless sources, ranging from rain to the moisture in humid air.

To visualize the condition of moisture in the wood of a standing tree, imagine a sopping-wet sponge just pulled from a pail of water. The sponge is analogous to growing wood in that the cell walls are *fully saturated* and swollen and the cell cavities contain water. If we squeeze the sponge, the water pours forth. Similarly the water in wood cell cavities, called **free water**, can be squeezed from wood (see *Figure 6.1*). As many carpenters know, when you hit green lumber with a hammer (depending on the species), you may see water spurt out.

Now imagine thoroughly wringing out the wet sponge until no further water is evident. The sponge remains full-sized, flexible, and damp to the touch. In wood, the comparable condition is called the **fiber saturation point** (FSP). In this state, the cell cavities are emptied of free water, but the cell walls are still saturated and thus still in their weak-

est condition. Only when water leaves the cell walls does the wood begin to shrink and increase in strength.

This water remaining in the cell walls is called **bound water**. In contrast to free water, which is held in cell cavities in liquid form, like water in a tumbler, bound water is held within the cell walls in molecular form by physical forces of attraction. Just as a sponge must be left to dry—and shrink and harden—so must the bound water be removed by placing the wood in a relatively dry atmosphere. How much of the bound water is lost (and therefore how much shrinkage takes place) will depend on the RH of the atmosphere. If the air is at 100% RH, no bound water will be lost. To remove all the bound water, the wood would have to be placed in an oven or desiccator or in a vacuum where the RH is zero. We use wood where the RH is somewhere between 100% and zero, so only part of the bound water is lost.

EQUILIBRIUM MOISTURE CONTENT

Wood always remains hygroscopic, which means that it responds to changes in atmospheric humidity. As the RH drops, it loses bound water; as the RH increases, the wood regains bound water. For a given RH level, a balance is eventually reached at which the wood is no longer gaining or losing moisture. When this balance of moisture exchange is established, the amount of bound water eventually contained in a piece of wood is called the **equilibrium moisture content** (EMC) of the wood.

The relationship between the amount of bound water in wood and the RH is shown in *Figure 6.3*. *In my estimation, this is the most important item in this book.* Although I'm not much for memorizing, I think every woodworker should have a few basic points clearly in mind. A good starting point is to remember that 50% RH gives an approximate 9% EMC. Then note that 25% RH gives about 5% EMC, and




Figure 6.3 • This may be the most important information in this book. Hang a copy of this graph on your shop wall and look at it every day. The amount of bound water in wood is determined by the relative humidity (RH) of the surrounding atmosphere; the amount of bound water changes as the RH changes. The moisture content of the wood when a balance is established at a given RH is its equilibrium moisture content (EMC). The solid line on the graph represents the relationship between EMC and RH for white spruce, a typical species with a fiber saturation point (FSP) of about 30% EMC. It is a fair approximation of the relationship for most common woods.

75% RH gives about 14% EMC and you know the essentials. The lower end point always originates at 0% RH and 0% EMC, and 100% RH always gives total fiber saturation. Reproduce this graph poster-size and hang it on your shop wall. Look at it every day. It's *that* important.

Everything, of course, has its qualifications, a few of which must be mentioned here regarding this graph. First, the curve is for white spruce, a typical species, shown as having an FSP of about 30% MC. The FSP varies among different species. In species having a high extractive content (example, redwood and mahogany), the FSP will be noticeably lower, around 22% to 24%. For those low in extractives, such as birch, the FSP might range as high as 75%. For most purposes, the relationship for spruce will serve as a satisfactory example of most woods.

Temperature also has an effect upon EMC. The curve shown is for 70°F, but the EMC is about one percentage point lower for every 25°F to 30°F elevation in temperature. The EMC curves always converge at 0% RH and 0% EMC, so variation due to extractives or temperature will therefore be most pronounced toward the fiber-saturation-point end of the curve.

In addition, when wood is losing moisture (desorbing), the EMC curve is slightly higher than when the wood is picking up moisture (adsorbing) because of the slight difference in the ease with which molecules are released or reattached to the cell wall structure. This is called the hysteresis effect. Under usual room conditions of slightly fluctuating RH, however, the average or oscillating curve (as shown in *Figure 6.3*) is applicable most of the time.

Depending on the degree of environmental control, especially the extent to which we heat during the winter, humid-

ity can vary widely indoors. In summer, with doors and windows open, interiors may approach outdoor conditions. In winter, when buildings are heated, we reach the low extreme. For example, imagine a night in late January when the thermometer outside drops to 0°F. Figure 6.2 shows that nature is supplying air that can carry a maximum of one-quarter grain of moisture per cu. ft. As this air diffuses into homes, it is heated to about 70°F, at which temperature it could hold 8 grains. Its RH drops to 6%. Checking Figure 6.3, we see that the surfaces of unprotected wood or thin veneers would drop to below 2% MC. Undoubtedly, humidifiers and the domestic activities of cooking, washing, and even breathing add some moisture to the air, not to mention the moisture being released by the wood itself. But under average living conditions, without intentional humidification, it is not uncommon during January and February for the conditions in my shop to hover below 25% RH.

In summer the situation is reversed. In July and August the temperature may reach the 90s. With late afternoon thundershowers, the RH may stay above 85% for days. We are talking about air with 12 or more grains of moisture per cu. ft. The foundation of my house rests on bedrock, so in the summer the cellar rarely gets above 70°F. Thus for every cu. ft. of muggy August air that enters my cellar, 4 grains of moisture will be lost either as condensation onto cool surfaces or in raising the interior humidity even higher. In time, the humidity could approach 100%. I am amused to remember how, when I was a child, we used to open the cellar in such summer weather "to dry it out." It's little wonder we had a damp cellar.

By actual measurements on spruce wafers, I have recorded an MC of 23% in August in the same cellar location where I found 5% to 6% readings in January. This is probably typical of many areas of the country where summers are warm and humid and winters are bitter cold. It is important to realize that if the absolute humidity of air is unchanged, lowering the temperature of the air raises the RH, while heating the air lowers the RH.

As will be emphasized again when discussing shrinkage and finishing, such seasonal extremes must be averaged (see *Figure 7.3* on p. 135). The low moisture conditions associated with winter, spring, and fall weather seem to outweigh the effects of short-term, high-humidity summer extremes. Thus 7.5% to 8% MC is an appropriate average for this kind of area. To bring wood to such low levels, it must either be stored indoors or dried in a kiln. Since the latter is the usual practice, the term **kiln-dried** typically means dried to a level appropriate for interior use. To the cabinetmaker, then, kiln-dried suggests an MC of below 10%.

In structural lumber, however, **air-dried** levels of MC are considered adequate. In this context, kiln-dried may mean 19% or less. In some cases, structural lumber is kiln-dried

mainly to reduce its weight for more economical shipping, to control fungi or other wood-destroying organisms, or simply to speed up the drying process, even though the final MC may be scarcely below the FSR. So the term kiln-dried alone should not be blindly interpreted to indicate any particular MC.

One of the more unfortunate yet common fallacies is that kiln-drying leaves wood irreversibly dry and that once dried the wood somehow becomes dimensionally stable. In reality, if dry wood is stored under relatively moist conditions, bound water will be reabsorbed to the equilibrium moisture condition. Tests have shown that even larger packages of 1-in. pine kiln-dried to 7% to 8% MC attain an MC of 13% to 14% after sheltered outdoor storage for six months. More rapid gain of moisture to even higher MC can result from exposure to weather or storage in damp indoor conditions.

When we deal with modified wood products, such as particleboard, hardboard, or decorative laminates, the adhesives and additives used as well as the heat applied during manufacture may influence the EMC considerably. For example, at an RH of 40%, where wood might come to an EMC of about 7.5%, particleboard might average 7%, hardboards 5%, and decorative laminates as low as 3.5%. Even among different species, the EMC at 40% RH may vary from 6.5% to 8.5% MC.

Someone once suggested the concept of thinking of an **equilibrium relative humidity (ERH)** rather than an EMC to emphasize the fact that RH determines EMC, not the other way around. It is prudent to think that "my lumber should be at equilibrium with 40% relative humidity" rather than that "my lumber should be at 7.5% moisture content."

GREEN VS. AIR-DRIED VS. KILN-DRIED

Let's elaborate on these fundamentals of moisture content because we will encounter them in our work. The amount of water in the living tree is quite variable. *Table 6.1* gives some average values of moisture content in trees for a number of species.

In general, the hardwoods have initial moisture contents in the 60% to 100% range. Notable exceptions are white ash, on the low side, and cottonwood, on the high side. In general, heartwood and sapwood have similar levels of MC but sometimes sapwood is higher, sometimes heartwood is higher. In softwood species, the general case seems to be that the heartwood has a fairly low MC, often scarcely above the FSP, while the sapwood is considerably higher. Among the lower-density species such as balsa or even pine, the sapwood MC often exceeds 200%.

In some species, MC shows seasonal variation. A pronounced rise in MC of 30% or more about the time of leaf

TABLE 6.1—Average green moisture content of common wood species.

	Moisture content	
	Heartwood	Sapwood
	%	%
Hardwoods		
Apple	81	74
Ash, white	46	44
Aspen	96	113
Basswood, American	81	133
Beech, American	55	72
Birch, yellow	74	72
Cherry, black	58	—
Cottonwood, black	162	146
Hackberry	61	65
Hickory, bitternut	80	54
Magnolia	80	104
Maple, sugar	65	72
Oak, California black	76	75
Oak, northern red	80	69
Oak, southern red	83	75
Oak, white	64	78
Sweetgum	79	137
Sycamore	114	130
Tupelo, black	87	115
Walnut, black	90	73
Yellow-poplar	83	106
Softwoods		
Cedar, Alaska-	32	166
Cedar, eastern red-	33	—
Cedar, incense-	40	213
Cedar, Port-Orford-	50	98
Cedar, western red-	58	249
Douglas-fir (coast type)	37	115
Fir, grand	91	136
Fir, white	98	160
Hemlock, eastern	97	119
Hemlock, western	85	170
Pine, loblolly	33	110
Pine, lodgepole	41	120
Pine, longleaf	31	106
Pine, ponderosa	40	148
Pine, red	32	134
Pine, shortleaf	32	122
Pine, sugar	98	219
Pine, western white	62	148
Redwood (old growth)	86	210
Spruce, eastern	34	128
Spruce, Engelmann	51	173
Spruce, Sitka	41	142

emergence and lasting a month or two has been noted in birch and ash. In many species, MC decreases in late summer and increases again when the leaves fall. In other species, such as beech, there is little year-round variation. Fluctuations in conifers also differ among species. In all cases, however, water content varies principally in the sapwood. Because of the inconsistent behavior among species, there are no general recommendations regarding the best time of year to cut wood to facilitate drying; each species must be considered individually.

There is considerable confusion over the meaning of the word green in reference to wood. It is often used to indicate the condition of freshly cut wood from a living tree. But because most properties of wood are unchanged regardless of the amount of free water it contains, we consider any wood above the FSP as green, even when the condition has been restored by wetting previously dried wood.

Most people underestimate the amount of water that can be contained in a piece of wood and especially the amount of free water that must be removed before shrinkage begins to take place. *Figure 6.4* shows the surprising amount of free water that can be contained in an average piece of wood.

Exposed to outdoor conditions, wood will lose its free water and eventually become air-dry. This term is used in many confusing ways but should generally be taken to mean that the MC is in equilibrium with the outdoor atmosphere of a particular area. The amount of time to air-dry depends on the species, the thickness, the weather conditions, and so forth. In New England, for example, where the RH averages in the 70% to 80% range, lumber stored outdoors will air-dry to 12% to 15% MC. Every woodworker should know about local conditions, and a call to the nearest weather bureau will usually provide information about RH. Outdoors, the average EMC is typically rather uniform, subject to only a moderate fluctuation in seasonal conditions, such as spring winds or late-summer high humidity.

Once I was curious about the progress of a couple of houses being built on a new road nearby. It was a typical rainy summer day, wet but pleasant for a walk under an umbrella. The foundation of the first house was capped off and the framing partially completed. Framing lumber had been unloaded carelessly along one side of the driveway, which had become a veritable lake. A pile of 2x8s had toppled over so the ends of one-third of them were dunked in the big puddle. As the rain pelted down between the pieces in the loosened pile, I noticed the proud grade stamp on each piece boasting "KILN-DRIED." It was like having the delivery boy hang your dry-cleaning in the apple tree next to the lawn sprinkler. Ironically, two pallets of bricks were protected from the weather by a polyethylene covering; I supposed the mason would have to hose them down before he could lay up the fireplace.

In summary, two points of caution are in order here. First, structural lumber is dried in a kiln for efficiency, to reduce its shipping weight, and to bring it down to levels that are suitable for construction, say 15% to 19%. Furthermore, even though lumber is kiln-dried, it can still gain or lose moisture depending on how it is stored. *Figure 6.5* summarizes the pertinent MC values.




Figure 6.4 • This piece of catalpa had a moisture content of 114% and weighed almost 60 lb. when cut. When dried to 8% MC (for carving), it weighed only 30 lb. The gallon jugs show the amount of free water (F) and bound water (B) that was lost in drying. Some bound water (equivalent to B') still remains in the wood at 8% MC. (Photo by Randy O'Rourke)




Figure 6.5 • Moisture-content values.

DIMENSIONAL CHANGE IN WOOD

Shrinkage and swelling need little introduction for woodworkers. Wood shrinks or swells due to loss or gain of bound water from the cell walls. The amount of movement varies according to the orientation of the wood cells and is typically measured separately in the three principal directions: tangential, radial, and longitudinal. The total amount of linear shrinkage that takes place in a given direction from the green to the oven-dry condition is customarily expressed as a percentage of the green dimensions. This total shrinkage is figured as follows:

$$S = \frac{(D_g - D_{od})}{D_g} \times 100,$$

where S = the total shrinkage, in percent (S_t = tangential shrinkage, S_r = radial shrinkage, S_l = longitudinal shrinkage); D_g = green dimension, D_{od} = oven-dry dimension.

Tangential shrinkage, for example, is expressed by the formula:

$$S_t = \frac{(D_g - D_{od})}{D_g} \times 100.$$

Figure 6.6 illustrates this formula for tangential shrinkage in a flatsawn board.

The orientation of the long-chain cellulosic structure in the cell wall is nearly parallel to the long axis of the cells. As water molecules enter and leave the cell walls, the resulting swelling or shrinkage is mainly perpendicular to the cell walls and does not influence their length. Similarly, pushing marbles into a straw broom would make the broom head wider but would have little effect on the overall length of the broom head.




Figure 6.6 • The percent shrinkage (in this case tangential shrinkage, S_t) is the change in dimension after oven-drying divided by the original dimension (D_g).


Total shrinkage of wood along the grain is normally only about 0.1%. An 8-ft. wall stud that is installed green and allowed to dry to an average 8% MC would shrink only about 1/16 in. along its length. In normal wood, longitudinal shrinkage is considered negligible. In juvenile wood or in reaction wood, however, longitudinal shrinkage can be as

much as 2%, about 20 times that of normal wood. Abnormal wood usually develops unevenly in severity and distribution, and the resulting uneven longitudinal shrinkage may cause severe warping. In practice, however, we typically ignore the longitudinal shrinkage of normal wood.


TABLE 6.2—Approximate shrinkage as a percent of green dimension, from green to oven-dry moisture content.

Hardwoods	Tangential	Radial	T/R	Softwoods	Tangential	Radial	T/R
Alder, red	7.3	4.4	1.7	Baldcypress	6.2	3.8	1.6
Ash, black	7.8	5.0	1.6	Cedar, Alaska-	6.0	2.8	2.1
Ash, white	7.8	4.9	1.6	Cedar, eastern red-	4.7	3.1	1.5
Aspen, quaking	6.7	3.5	1.9	Cedar, incense-	5.2	3.3	1.6
Basswood, American	9.3	6.6	1.4	Cedar, northern white-	4.9	2.2	2.2
Beech, American	11.9	5.5	2.2	Cedar, western red-	5.0	2.4	2.1
Birch, paper	8.6	6.3	1.4	Douglas-fir (coastal)	7.8	5.0	1.6
Birch, yellow	9.2	7.2	1.3	Douglas-fir (inland)	7.6	4.1	1.9
Buckeye, yellow	8.1	3.6	2.2	Fir, balsam	6.9	2.9	2.4
Butternut	6.4	3.4	1.9	Fir, white	7.1	3.2	2.2
Catalpa	4.9	2.5	2.0	Hemlock, eastern	6.8	3.0	2.3
Cherry, black	7.1	3.7	1.9	Hemlock, western	7.9	4.3	1.8
Chestnut	6.7	3.4	2.0	Larch, western	9.1	4.5	2.0
Chinkapin, golden	7.4	4.6	1.6	Pine, eastern white	6.1	2.1	2.9
Cottonwood, eastern	9.2	3.9	2.4	Pine, loblolly	7.4	4.8	1.5
Dogwood, flowering	11.8	7.4	1.6	Pine, lodgepole	6.7	4.3	1.6
Elm, American	9.5	4.2	2.3	Pine, longleaf	7.5	5.1	1.5
Elm, rock	8.1	4.8	1.7	Pine, pitch	7.1	4.0	1.8
Hackberry	8.9	4.8	1.9	Pine, ponderosa	6.2	3.9	1.6
Hickory, pecan	8.9	4.9	1.8	Pine, red	7.2	3.8	1.9
Hickory, shagbark	10.5	7.0	1.4	Pine, shortleaf	7.7	4.6	1.7
Holly, American	9.9	4.8	2.1	Pine, slash	7.6	5.4	1.4
Honeylocust	6.6	4.2	1.6	Pine, sugar	5.6	2.9	1.9
Hophornbeam, eastern	10.0	8.5	1.2	Pine, western white	7.4	4.1	1.8
Hornbeam, American	11.4	5.7	2.0	Redwood (old growth)	4.4	2.6	1.7
Locust, black	7.2	4.6	1.6	Redwood (young growth)	4.9	2.2	2.2
Madrone, Pacific	12.4	5.6	2.2	Spruce, Engelmann	7.1	3.8	1.9
Magnolia, southern	6.6	5.4	1.2	Spruce, red	7.8	3.8	2.1
Maple, red	8.2	4.0	2.0	Spruce, Sitka	7.5	4.3	1.7
Maple, sugar	9.9	4.8	2.1	Tamarack	7.4	3.7	2.0
Oak, black	11.1	4.4	2.5	Yew, Pacific	5.4	4.0	1.4
Oak, live	9.5	6.6	1.4				
Oak, northern red	8.6	4.0	2.2	Imported woods			
Oak, overcup	12.7	5.3	2.4	Apitong	10.9	5.2	2.1
Oak, red	8.9	4.2	2.1	Avodire	6.5	3.7	1.8
Oak, southern red	11.3	4.7	2.4	Balsa	7.6	3.0	2.5
Oak, white	10.5	5.6	1.8	Banak	8.8	4.6	1.9
Persimmon	11.2	7.9	1.5	Cativo	5.3	2.3	2.3
Sassafras	6.2	4.0	1.6	Greenheart	9.0	8.2	1.1
Sweetgum	10.2	5.3	1.9	Khaya	5.8	4.1	1.4
Sycamore	8.4	5.0	1.7	Lauan	8.0	3.8	2.1
Tupelo, black	8.7	5.1	1.7	Limba	5.4	4.4	1.2
Walnut, black	7.8	5.5	1.4	Mahogany	5.1	3.7	1.4
Willow, black	8.7	3.3	2.6	Obeche	5.3	3.1	1.7
Yellow-poplar	8.2	4.6	1.8	Parana pine	7.9	4.0	2.0
				Primavera	5.2	3.1	1.7
				Ramin	8.7	3.9	2.2
				Spanish cedar	6.3	4.1	1.5
				Teak	4.0	2.2	1.8
				Walnut, European	6.4	4.3	1.5


RED OAK (GREEN)




RED OAK (AIR-DRY)



RED OAK (OVEN-DRY)



RED PINE (OVEN-DRY)



AMERICAN BEECH (OVEN-DRY)



Figure 6.7 • Each photo shows a longitudinal (top), radial (center), and tangential (bottom) strip of wood, equal in length when green. (Photos A and B by R. Bruce Hoadley; photos C, D, and E by Randy O'Rourke)

Transverse shrinkage, on the other hand, is significant. The shrinkage values in *Table 6.2* show considerable difference among different species. Tangential shrinkage (perpendicular to the grain and parallel to the growth rings) is always greater than radial (perpendicular to growth rings).

Tangential shrinkage ranges from 4% in teak to 12.7% in overcup oak, with an overall average of 7.95%. Radially, shrinkage values range from 2.2% for teak or redwood to 8.5% for eastern hophornbeam, averaging 4.39%. It is reasonable to think of wood as having roughly 8% tangential shrinkage and 4% radial shrinkage.

The difference between tangential and radial shrinkage is caused by anatomical structure, principally the restraining effect of the wood rays, whose long axes are radially oriented. The magnitude of the differential shrinkage is critical to development of certain forms of warp and defects. The woodworker soon learns the importance of the ratio of tangential to radial shrinkage. *Table 6.2* reveals that the tangential shrinkage/radial shrinkage ratio averages 1.8, but individual species range from 1.1 (greenheart) to 2.9 (eastern white pine).

Over the entire range of MC—from FSP to oven-dry—shrinkage is approximately proportional to moisture loss. Typical relationships between tangential, radial, and longitudinal shrinkage and moisture loss are shown in *Figure 6.7* and *Figure 6.8*.

This listing of shrinkage values suggests why some species, such as teak, mahogany, northern white-cedar, redwood, and catalpa, have a reputation for being woods that are quite stable. The values also suggest that others, such as beech, certain oaks, and hickories, can be potentially troublesome.




Figure 6.8 • Shrinkage vs. moisture content in northern red oak, a typical species.

ESTIMATING SHRINKAGE AND SWELLING

There are many ways in which dimensional change in wood can affect the woodworker, and the following discussion considers some typical examples. In most cases, the mere change in dimension is noteworthy or troublesome. In others, uneven or unequal shrinkage is responsible for the problem.

Let's look at shrinkage from a quantitative point of view. Can we estimate how much a piece of wood will shrink under a given set of circumstances? Assume that a rough workbench was constructed out of freshly cut northern red oak (Figure 6.9). Suppose the top were formed by spiking down 10-in.-wide flatsawn planks laid edge-to-edge, as in the illustration. If the bench were left in an unheated garage, how wide would the cracks between the planks eventually become? In other words, how much would each plank shrink across its width as the wood dried out?

First, recall what we considered in Figure 6.3 and Figure 6.8. In the curve relating EMC to shrinkage, the tangential shrinkage is given as 8.67c. We can now construct a composite graph for northern red oak that will relate RH to MC and MC to shrinkage (Figure 6.10).

If the average RH in the garage (unheated but generally open to the outside air and sheltered from the direct sun and rain) is about 75%, we can follow the broken lines on the chart and see that an RH of 75% will give an EMC of about 13%, resulting in about 4.6% shrinkage. On a 10-in. board, this means 0.46 in., so each of the planks would be expected to shrink almost 1/2 in. in width.

Another way to estimate this shrinkage, once we know the EMC, is by this formula:

$$\Delta D_i = DS \left(\frac{\Delta MC}{fsp} \right)$$




Figure 6.9 • Freshly cut 10-in.-wide red oak planks on a workbench top would shrink as the wood dried, leaving cracks.

where ΔD = change in dimension due to shrinkage
 D_i = initial dimension
 S = total shrinkage percentage—from Table 6.2, use S_t (tangential shrinkage) for flatsawn lumber, S_r (radial shrinkage) for edge-grain lumber
 ΔMC = change in moisture content*
 fsp = fiber saturation point (average value = 28%).

(In using the formula, remember that 8.6% means 8.6/100 = 0.086; 28% is similarly written as 0.28, etc.)

For our example, then,

$$\Delta D = (10 \text{ in.})(0.086) \left(\frac{0.28 - 0.13}{0.28} \right) = 0.46 \text{ in.}$$

The boards are now 9.54 in. wide. Suppose we move our bench into the house where the RH is 40%, giving an EMC of about 7.5%. How much more will the boards shrink? We can get an estimate** (see p. 120) by again using the formula:

$$\Delta D = (9.54 \text{ in.})(0.086) \left(\frac{0.13 - 0.075}{0.28} \right) = 0.161 \text{ in.}$$




Figure 6.10 • This composite graph shows the relationship of relative humidity to moisture content and moisture content to radial and tangential shrinkage in northern red oak. At 75% RH, the wood will shrink 4.6% in the tangential direction.

*SINCE THE FORMULA APPLIES ONLY TO MOISTURE GAIN OR LOSS BELOW THE FIBER SATURATION POINT, NO VALUES ABOVE THE FSP SHOULD BE CONSIDERED. FOR EXAMPLE, IF THE ORIGINAL MOISTURE CONTENT OF A BOARD WERE 86% AND IT DRIED TO 9%, DMC WOULD BE COMPUTED AS 0.28 TO 0.09 = 0.21, SINCE NO SHRINKAGE WOULD TAKE PLACE IN DRYING FROM 86% DOWN TO THE FSP, 28%.

Each board will shrink another 0.16 in. to an estimated final width of 9.38 in.

Calculations using the above formulas are extremely valuable in accommodating dimensional change to allow swelling space for panels or the clearance allowance for doors and drawers. A typical shop problem might be as follows: You are constructing a chest with drawers such as the one shown in *Figure 6.11* using flatsawn sugar maple. How much allowance will ensure clearance of each drawer front in the frame?

Table 6.2 indicates that the tangential shrinkage (S) for sugar maple is 9.9%. Assume that shop conditions put your lumber at an EMC of 8%, but your experience has determined that with the light oil finish you plan to use, the EMC of the finished piece could go as high as 12% in summer weather. The height of the drawer front (F) should be no greater at 12% MC than the vertical drawer opening (D/O). Therefore the question becomes "how much shorter than the

opening should the drawer front be at the current moisture content of 8%?" An estimate would be:

$$\begin{aligned} \Delta D &= (D/O) (S_t) \left(\frac{\Delta MC}{fsp} \right) \\ &= (D/O)(0.099) \left(\frac{0.12 - 0.08}{0.28} \right) \\ &= (D/O)(0.0141). \end{aligned}$$

For a 9-in. drawer opening,

AD = 9 in. (0.0141) = 0.1272 in., about 1/8 in., so the drawer front (F) should be finished to a height of 87/8 in.

In the dead of winter, if the EMC drops to 5%, the gap for a drawer that is 9 in. at 12% MC will be

$$\begin{aligned} \Delta D &= 9 \text{ in.} (0.099) \left(\frac{0.12 - 0.05}{0.28} \right) \\ &= 0.223 \text{ in.}, \text{ or more than } \frac{7}{32} \text{ in.}! \end{aligned}$$

If the dividers between drawers are large enough for their shrinkage and swelling to be taken into account, D/O' (the centerline spacing of the dividers) should be used. The shrinkage, AD, will therefore account for the dividers too.

**THE SHRINKAGE PERCENTAGES ARE ACCURATE ONLY FOR SHRINKAGE FROM THE GREEN CONDITION. FOR SHRINKAGE OF WOOD STARTING AT A PARTIALLY DRY CONDITION, THE ABOVE FORMULA WILL INTRODUCE AN AVERAGE ERROR OF ABOUT 50% OF THE CALCULATED CHANGE IN DIMENSION. FOR MOST PURPOSES SUCH ERROR IS INSIGNIFICANT IN VIEW OF OTHER INHERENT SOURCES OF ERROR. HOWEVER, WHERE A MORE REFINED ESTIMATE IS DESIRABLE, THE FOLLOWING FORMULA SHOULD BE USED:

$$\Delta D = \frac{D_i(MC_i - MC_f)}{\frac{fsp}{S} - fsp + MC_i}$$

where MC = initial moisture content
MC_f = final moisture content

(As noted above, neither MC, nor MC_f, can be greater than the FSP.)
Therefore, our last example would be computed as follows:

$$\Delta D = \frac{9.54 \text{ in.}(0.13 - 0.075)}{\frac{fsp}{s} - fsp + MC_i}$$

Thus our previous estimate of 0.1612 in. was off by 4.6%.

The formula can be used to estimate the swelling, which is indicated by a negative value of AD.

Note that when MC_f is at or above the FSP, the formula becomes

$$\begin{aligned} \Delta D &= \frac{D_i(fsp - MC_f)}{\frac{fsp}{S} - fsp + fsp} \\ &= \frac{D_i S (fsp - MC_f)}{fsp} \end{aligned}$$

$$= D_i S \left(\frac{\Delta MC}{fsp} \right), \text{ as originally introduced.}$$




Figure 6.11 • In designing a chest, dimension F must not exceed the drawer opening (D/O) when the wood swells in summer humidity. Dimension D/O' is the centerline spacing of the drawer dividers.

A point usually overlooked in drawer design is the difference in future wood movement between two species worked at about the same EMC. Suppose we want to make a drawer 10 in. deep by lap-dovetailing flatsawn beech sides to quartersawn mahogany fronts. Can we expect the sides and the front to stay the same width while the RH varies with the seasons?

Assume that the drawer is made during the summer, with both species at an EMC of 10%, which drops to 6% in winter. The calculation would be the same the other way around, from winter to summer.

For the mahogany drawer front, $S_f = 3.7\%$.

$$\begin{aligned}\Delta D &= (10) (0.037) \left(\frac{0.10 - 0.06}{2.8} \right) \\ &= 0.052 \text{ in.}, \text{ or about } \frac{1}{20} \text{ in.}\end{aligned}$$

For the beech drawer side, $S_t = 11.9\%$.

$$\begin{aligned}\Delta D &= (10) (0.119) \left(\frac{0.10 - 0.06}{0.28} \right) \\ &= 0.170 \text{ in.}, \text{ or about } \frac{1}{6} \text{ in.}\end{aligned}$$

Thus the width of the drawer front changes a mere 1/20 in., while the side changes almost 1/6 in., which is three times as much. This change could have been predicted from the ratio between shrinkage coefficients, S , of 11.9% for the beech and S , of 3.7% for the mahogany. The choice of woods is

extreme for the sake of illustration, but the amount of seasonal variation is not.

The importance of dimensional change in making furniture is generally known, but we may be tempted to assume it has no consequence in carpentry. Two examples will illustrate that even in building construction, dimensional change must be seriously considered.

The first instance came to my attention while visiting a partially completed home. The house was closed in, rough floors were down, and the interior drywall was installed. In the kitchen, 2x4s had been placed on the floor, approximately where they were to be used as base framing for the counters. They were sad-looking specimens of lumber, badly weathered and warped. Nudging one piece with my foot, I noticed that the floor underneath showed a wet spot, indicating that the MC was probably near or above the FSR. Sensing my concern over the quality of the material, the builder assured me that he used such pieces only where they would be nailed down securely, as in this case, so that the condition of the material was of no consequence. I did not pursue the matter, but I immediately recognized the ingredients of a potential problem.

It is customary to frame cabinets in place as shown in *Figure 6.12*. A cleat anchored to the vertical studs of the wall supports the rear edge of the countertop. The forward edge is supported by the cabinet front, which in turn is supported by the base frame. Any shrinkage in the base frame is reflected by a drop in the *front* edge of the counter.




Figure 6.12 • When built as shown, the front edge of the counter will not remain level. Built this way, the base framing along the front (B) shrinks, and the front edge ends up lower than the back. If this shrinkage is accounted for in the design, the countertop will be level when the lumber reaches the moisture equilibrium point.

How much? Let's consider the extreme. The piece in question had tangential grain across its 3 1/2-in. dimension. It was probably red spruce, for which *S*, (tangential shrinkage) is 7.8%. Assuming it was originally green but would eventually dry to 7.5% MC, AMC = 28 - 7.5 = 20.5%. Using the formula to estimate shrinkage:

$$\Delta D = 3.5 \text{ in.} (0.078) \left(\frac{0.205}{0.28} \right) \\ = 0.200 \text{ in.}, \text{ or a shade more than } \frac{3}{16} \text{ in.}$$

I had occasion to check the counter a few years later, and the front appeared to have just about that amount of pitch, which was enough so that an egg would roll across the Formica top and over the edge. I know the builder's work well enough to believe that it was level when he finished the job. I have since checked other counters and find the problem to be common. (I secretly check by rolling a marble or ping-pong ball when I don't have the nerve to ask to measure with a level.) I've never found a counter that slopes back to the wall.

How does shrinkage affect an entire structure? Let's consider as an example a two-story house of typical platform construction, such as the one shown in *Figure 6.13*. It shows a stacking of some 37.75 in. of framing members whose transverse shrinkage would take place vertically. What is the effect in the framing of MC change that takes place after the structure is occupied and heated?

To assess the original MC in such cases, I have made extensive moisture measurements on framing lumber, both in lumberyards and in houses under construction. Readings can range between 11% and 26%, but the average is about 18%.

Using moisture meters with insulated pin electrodes, I have also measured the MC of comparable interior framing lumber in a number of houses that had been occupied for at least three years. These readings were then checked against spruce wafers placed in indoor locations and allowed to reach equilibrium. Accounting for variations due to seasons of the year and to location, overall average moisture comes out to about 8%. The average moisture content change (AMC) then would be approximately 18% - 8% = 10%.

Common woods for framing are Engelmann and eastern spruce, western hemlock, and western fir. Because pieces vary from quartersawn to flat-grained, we arrived at the compromise species/growth-ring-orientation shrinkage value for the total shrinkage (*S*) of 5.8%. Applying the shrinkage formula once again:

$$\Delta D = 37.75 \text{ in.} (0.058) \left(\frac{0.10}{0.28} \right) = 0.782 \text{ in.} ***$$




Figure 6.13 • This wall-framing diagram of a typical two-story dwelling shows 37.75 in. of framing members stacked vertically. Using the shrinkage formula given in the text, the potential vertical shrinkage of the house is a little more than 3/4 in.

The top of the house would be expected to drop by more than 3/4 in. due to shrinkage. If green lumber were used, the shrinkage would be about twice as great. If the entire house were to shrink all over, the result would doubtless be quite insignificant. But problems are likely where rigid vertical plumbing or masonry structures are involved. I have seen countless broken joints along roof-chimney junctions apparently due to the shrinkage of the building. When framing is anchored to the chimney system, sloping floors, racked walls, and separated corner and ceiling joints may result.

These consequences are often referred to as the "settling" of a house. To me, this is unfair to the builder because it implies that the building components were so loosely

*** IF WE ALSO CONSIDER THE LONGITUDINAL SHRINKAGE (*S*₁ = 0.1%) IN THE UPPER AND LOWER STUDS, FOR EACH 7 FT. 6 IN. OR 90 IN. IN LENGTH, $\Delta D = (2 \times 90) (0.001 \times 0.10 / 0.28) = 0.064 \text{ in.}$, AN ADDITIONAL 1/16 IN. SOME ADDITIONAL COMPONENT FOR THE ROOF RAFTERS WOULD ALSO BE PRESENT, DEPENDING ON THE ROOF PITCH.

assembled that they eventually settled more compactly together, like so many crackers in a box. We should recognize "settling" as just another manifestation of the shrinkage of wood.

UNEVEN SHRINKAGE AND SWELLING

Change in dimension is only one consequence of shrinkage or swelling. Even more serious effects may result when shrinkage or swelling is uneven throughout the piece, even though it is very small in magnitude. Warp, which is the distortion of a piece from its desired or intended shape, usually results from variable shrinkage in different directions or from uneven shrinkage that causes stress in the piece

(Figure 6.14). Cup is a form of warp that is characterized by deviation from flatness across the width of a board. Bow is deviation from lengthwise flatness in a board. Crook is departure in end-to-end straightness along the edge of a board. Twist signifies that the four corners of a flat face do not lie in the same plane. Kink describes a localized crook due to a knot. Table 6.3 lists a number of woods by their tendency to warp during seasoning.

When uneven shrinkage causes stress that exceeds the perpendicular-to-grain strength of the wood, separation of cells occurs along the grain. Such failures are termed checks. Although most common on the surfaces and ends of pieces, they may also occur internally.




Figure 6.14 • Principal forms of warp in boards.

TABLE 6.3—Tendency to warp during seasoning of various woods.

Low	Intermediate	
	Softwoods	
Cedars	Baldcypress	
Pine, ponderosa	Douglas-fir	
Pine, sugar	Firs, true	
Pine, white	Hemlocks	
Redwood	Larch, western	
Spruce	Pine, jack	
	Pine, lodgepole	
	Pine, red	
	Pine, southern	
	Hardwoods	
Alder	Ash	Beech
Aspen	Basswood	Cottonwood
Birch, paper and sweet	Birch, yellow	Elm, American
Butternut	Elm, rock	Sweetgum
Cherry	Hackberry	Sycamore
Walnut	Hickory	Tanoak
Yellow-poplar	Locust	Tupelo
	Magnolia, southern	
	Maples	
	Oaks	
	Pecan	
	Willow	




Figure 6.15 • Various shapes of red pine have been dried and placed in their relative original positions on a diagram of a log. The fact that tangential shrinkage is greater than radial shrinkage causes squares to become diamond-shaped and cylinders to become ovals. Quartersawn boards seldom warp, but flatsawn boards cup away from the pith. (Photo by Randy O'Rourke)

TANGENTIAL VS. RADIAL SHRINKAGE *Figure 6.5* illustrates how flatsawn boards cup with the concavity away from the pith as a result of greater tangential than radial shrinkage. The severity of this effect is greatest in boards with one face intersecting the pith. That face—a radial face—will shrink only half as much as the other (*Figure 6.16*). Some woodworkers say that the "rings tend to flatten out," which is an easy way to remember which way the board will cup but has little to do with the reason why. Cup is reversible upon swelling (*Figure 6.17*).

If lumber cut against the pith is restrained from cupping, it may crack itself open. Furthermore, any attempts to flatten by force a board that has cupped in drying will typically produce a crack (*Figure 6.18*).

A square or rectangular piece with diagonally oriented growth rings will shrink twice as much across one diagonal than the other, distorting the board into a diamond—the term *diamonding* designates the effect. This has its counterpart in turnings, since the greater tangential shrinkage will turn a round cross section into an oval. Holes bored lengthwise in wood also show this behavior, since a hole in a piece of wood reacts the same as a piece of solid wood of the same shape.

The classic problem of nonuniform thickness change in boards is often traceable, at least in part, to the difference between radial and tangential shrinkage. The typical case in point emerges in quartersawn boards. If one edge of a board



Figure 6.16 • The severity of cupping in a board is related to its position in the log. (Photo by R. Bruce Hoadley)




Figure 6.17 • Strips were cut in sequence from the end of an air-dry red oak board. As shown by the middle strip, it measured $9\frac{1}{2}$ in. wide at 14% MC. The top strip was then dried to below 4% MC—it both shrinks and cups. The bottom strip was allowed to reabsorb moisture to more than 20% MC. It expands and cups in the opposite direction. (Photo by Richard Starr)




Figure 6.18 • Half of a cupped elm board (top) was flattened and cracked by the pressure of the rollers in a thickness planer. The other half exhibits the original cup. (Photo by Randy O'Rourke)




Figure 6.19 • The difference between radial and tangential shrinkage can be quite noticeable along a glue joint (A), where quartersawn boards are butted bark side to pith side. The problem can be minimized by matching bark to bark and pith to pith (B).

is located near the pith in a tree, the growth rings within it will have sharp curvature, and shrinkage in its thickness will be essentially radial (r), as at A in *Figure 6.19*. At the opposite edge, the growth-ring orientation is more truly edge-grained and will have tangential shrinkage (t) through the thickness of the board along the edge toward the bark. Although slight, such differences may be quite noticeable along a glue joint if adjacent edges have bark edges butted to pith edges. The problem can be minimized by matching bark edges to bark edges and pith edges to pith edges, as in B.

Probably the most familiar—or notorious—manifestation of shrinkage is the radial cracking**** of logs or log sections caused by the stress resulting from greater tangential shrinkage, which cannot be accommodated by distortion alone. The stress eventually becomes great enough to crack the wood radially. It's interesting to compare the effect of bandsawing a radial cut into disks before drying begins (*Figure 6.20*, *Figure 6.21*). In the red pine disks used, the heartwood begins to shrink first, doubtless because of its lower MC (41% in contrast to 206% for the sapwood). In





Figure 6.20 • The results of drying cross-sectional disks of red pine. When a green disk (A, left) dries, the greater tangential shrinkage results in a radial crack (A, right). As a disk dries, the crack may open first near the pith (B) because the hardwood has a lower moisture content and shrinks first. (It would later open as in A, right). If a disk first has a radial slot sawn in it, the slot may open first in the heartwood (C), and eventually the unrestrained disk opens the slot wide (D). (Photo A by R. Bruce Hoadley; photos B, C, D by Richard Starr)

• in pieces containing the pith, the large radial failures due to dominant tangential shrinkage are often called cracks rather than checks.




Figure 6.21 • Results of drying cross-sectional disks of northern red oak. This disk had a radial slot sawn in it (A). Because of heartwood extractives, the sapwood dries first and shrinks more, resulting in radial sapwood checks. When the heartwood dries, the slot opens wide (B). A disk without a slot (C) also forms sapwood cracks in early stages of drying. Eventual shrinkage stress opens a radial crack (D). (Photos by Richard Starr)




Figure 6.22 • This star-patterned red pine disk remained crack-free for three years. Then the humidity bottomed out during a bitter cold spell, and the hidden stresses were revealed. The disk cracked. (Photo by Randy O'Rourke)

oak (Figure 6.21), the preslotted piece begins to open before any dominant crack occurs in the unsawn disk, suggesting that stress is developing in the unsawn one while it is being relieved by the saw slot in the other. In each species the crack in the sawn disk is obviously wider than in the uncut disk.

Sometimes a disk can be dried without cracking. Success is favored by a number of factors. Species with low shrinkage percentages and low tangential-to-radial shrinkage ratios are better prospects. Catalpa, for example, develops only a slight tendency to crack because of its low shrinkage percentage. I have dried many catalpa logs and disks up to about a foot in diameter without cracking merely by drying slowly. But the slowest drying in the world wouldn't bring a 12-in. red pine disk through without a crack. Every once in a while I get cocky and think I have succeeded, but the fact remains that the stress is there and usually exhibits itself by eventual cracking. I had a disk of unfinished red pine cut near a branch whorl, giving it an attractive star effect. It sat around my office for three years without defect. Finally one day during a bitter cold spell the humidity bottomed out and did the job. The result is shown in Figure 6.22.

A friend of mine once turned a pedestal from a green cherry log. He took it into the kitchen to admire during dinner and *listened* to it crack.

On one occasion I was asked to give a talk, on rather short notice, on the subject of stabilizing wood with polyethylene glycol-1000 (PEG). I found I had no samples available to illustrate the results. With only five days to get ready, I sawed two red oak disks about 9 in. in diameter. For four days I soaked one disk in PEG, the other in water. The day

before the lecture, I popped them both in the oven, sure that the untreated one would crack. The next day, about two hours before the lecture, I opened the oven. To my horror neither had a crack. I knew the untreated disk must be loaded with shrinkage stress, but who can see stress? In disgust, I slammed the disks down on a benchtop. A crack suddenly appeared in the untreated disk, and within a minute or two opened up to more than 1/4 in. I had my lecture props on time.

Low-density woods seem favorable to disk drying, apparently because of their ability to deform internally to relieve the shrinkage stress. Here again catalpa is a winner because of its moderately low density.

Size also has an important effect on drying. I've been able to dry only a few species of wood in disk diameters more than 8 in., mostly low-density species. However, I have a set of coasters of 27 different species that are cross-sectional disks of 3 in. to 3 1/4 in. in diameter. To make them, I cut lengths of tree stem about 18 in. long in the winter (so the bark will be tight), coat both ends with paraffin, and put them aside. If the logs crack, they join my fuel supply. If not, I bandsaw them into disks 3/8 in. thick after the logs have stopped losing weight. Then I wait another several months, sand them smooth, and apply a few rubbed coats of urethane. Of the hundreds I have made, I know of only one that cracked in use. But I know they all have some stress because of greater tangential than radial shrinkage.

PERPENDICULAR TO GRAIN VS. PARALLEL TO GRAIN

A second type of dimensional behavior that causes problems is the wide discrepancy between perpendicular-to-grain dimensional movement and the nearly negligible longitudinal instability. A classic problem is the mitered joint, which is shown in *Figure 6.23*. The joint opens on the outside in summer humidity and on the inside in the low humidity of winter.

Opened miter joints are easy to evaluate since they're typically in plain sight. A hidden example of the same problem is the all-too-common wobbly chair. It somehow seems absurd that although men have walked on the moon and heart transplants succeed, we still have wobbly chairs.

Wobbly chairs are caused principally by the difference between the dimensional change of a mortise and the dimensional change of a tenon. The simplest variation of this joint is a round tenon in a drilled hole or mortise, as in the insertion of a chair rung into a chair leg. Since the rung is perpendicular to the grain direction of the chair leg, the tenon and the hole shrink and swell by about the same amount in diameter.

In the direction of the grain, the hole in the leg is virtually stable; the rung, however, will have pronounced dimensional response, especially if the growth-ring orientation of the rung is vertical in the joint. The allowable elastic compression and tension strains are smaller than the amounts of swelling and shrinkage that develop in response to seasonal humidity fluctuation. The result will be overcompression of




Figure 6.23 • These demonstration sugar maple frame corners were tightly mitered when originally assembled. The upper one was dried, and the lower one was exposed to high humidity. Wood is stable along the grain but shrinks across the grain, opening the joint on the inside corner, or swells across the grain, opening the joint on the outside corner. (Photo by Randy O'Rourke)

the rung when it tries to expand in the vertical direction. Upon redrying to its original moisture content, it will shrink to a smaller diameter than the original. Glue is only partially successful in preventing this compression-set loosening. With or without glue, extreme moisture variation can cause looseness of the joint.

In dowel or mortise-and-tenon joints, good gluing can help in restraining some of the compression-set shrinkage that would ordinarily open a joint. However, as the tensile strain limit is approached, the failure usually occurs at or near the glueline (*Figure 6.24*). Failure adjacent to the glueline is probably due to a number of things, especially the machining damage to the surfaces of the mortise and tenon as well as the perpendicular grain direction conflict involved. I have never seen a tenon fail internally, such as with a honeycomb check, because the glue wouldn't let it shrink. It is always the glueline or a layer of cells adjacent that fails first.

I once did some research with round mortise-and-tenon joints. I made half with regular tenons, and in the other half




Figure 6.24 • After moisture cycling, a dowel joint without glue (A) takes on compression-set and shrinks away from the mortise at the top and bottom. This particular dowel has the growth rings oriented vertically. With a glued dowel (B), only one side of the joint opens, usually tearing some tissue from the wall of the mortise. But the remaining glueline is no match for racking stress and quickly fails in tension. (Photos by Randy O'Rourke)

I took a chisel and split the tenons radially as far down as the length of their insertion into the mortise. After moisture cycling severe enough to break gluelines in the regular joints, the split tenons had opened up internally, and the gluelines were largely intact (*Figure 6.25*). This approach of creating a plane of failure (and therefore strain relief) where it won't do any harm is worth a great deal of further research. I suspect that various wedged tenons are successful because of this mechanism. I have seen through-wedged tenons in plank benchtops where the tenon remained tight around the outer edge, but there was an obvious opening in the middle along the wedge.

Another experiment involved putting brand-new chairs through moderately severe moisture cycles (90%-30%-90%-30% RH). The joints in the chairs loosened so much you could hear the rattle without even sitting upon them.

When contemplating problems such as internal/external joints where restrained swelling is likely, remember that the elastic limit of wood under compression perpendicular to the grain is on average less than 1%, so that restrained swelling of the magnitude of 1% may be setting up a problem.




Figure 6.25 • When the tenon is split before assembly, the crack will open under moisture cycling, but the glueline is likely to remain intact. This is probably what happens when tenons are wedged. (Photo by Randy O'Rourke)

To amplify this concept, imagine a hickory handle conditioned to 7% MC in a heated shop and then fitted and tightly wedged into the eye of a hammer head. The hammer is then moved to a garage where the handle reaches an EMC of 14%. Recalling the shrinkage formula:

$$\Delta D = D_i S \left(\frac{\Delta MC}{f_{sp}} \right)$$

and noting from Table 6.2 that $S_t = 10.5\%$ for Shagbark hickory,

$$\Delta D = D_i(0.105) \left(\frac{0.07 - 0.14}{0.28} \right) = -0.026D_i.$$

The handle will try to swell tangentially by 2.6% of its dimension. Perpendicular-to-grain compression tests on hickory have shown a proportional limit strain of about 17c. Thus we might expect more than 15% of set to occur. If the hammer is then brought back to its original 7% EMC environment, we might expect it to shrink tangentially to about 15% less than its original dimension at that same MC (Figure 6.26).

Suppose that the hammer is left out in the rain, where the handle might absorb moisture to virtual FSP.

$$\Delta D = D_i(0.105) \left(\frac{0.07 - 0.28}{0.28} \right) = -0.079D_i.$$




Figure 6.26 • Moisture cycling, not pounding, is the usual cause of loose tool handles as demonstrated with this commercially manufactured hammer. When the hammer head was originally cut apart, the hickory handle was tightly wedged into the eye. After storage in a damp place, the section was then moved to drier conditions, and the joint loosened as shown here due to compression shrinkage in the handle. (Photo by Randy O'Rourke)

The handle will try to swell the full 7.9% but it would be restrained by the head, so about 6.9% compression-set could be expected.

To check out these predictions, I ran some controlled tests in which shagbark hickory disks were restrained in stainless-steel rings. The disks were carefully machined to slip snugly into the rings at 7% MC. They were allowed to absorb moisture until fiber saturation was attained. Then they were redried to original weight and remeasured. They showed an average loss in diameter of 7.5% tangentially and 5.4% radially. Similar experiments with beech (Figure 6.27) and other species also showed that results could be approximately predicted. Little wonder tool handles loosen when moved from place to place.

Incidentally, I now keep my adze, axes, and sledgehammers in the garage with plastic trash bags wrapped around the heads. This has ended my handle-loosening problems, since the average EMC in the garage is more uniform than cyclic indoor conditions.

Another problem related to moisture and opposing grain orientation occurs when boards are restrained at their edges and then undergo shrinkage due to moisture loss. These kinds of problems occur in items constructed of air-dry lumber at 14% or 15% MC that eventually reach equilibrium at 67c or 7% indoors. The resulting shrinkage in a flatsawn board averages at least 2% and the board may split in tension perpendicular to the grain.

Oddly, they also occur when things are made of wood at an appropriate moisture content, say 7%. A typical example




Figure 6.27 • American beech disks illustrate the effect of cyclically varying MC on wood under restraint. The disk on the left is shown as originally turned at 7% MC and fitted snugly in the ring. The disk on the right was moistened to fiber saturation, then reconditioned to original weight. The wood (in compression-set) has shrunk away from the restraining ring. (Photo by Randy O'Rourke)




Figure 6.28 • The ends of logs dry first, and the resulting shrinkage causes end-grain checks, as shown here in cherry. (Photo by R. Bruce Hoadley)

of this involves a design in which wide boards or panels are fastened at their edges to a fixed frame. The side panels of a carcass built with the longitudinal-grained drawer runners fastened at each end to the panel edges is one case in point. If exposed to high humidity (such as furniture stored in the cellar or a cool basement game room), it cannot swell, and up to 3% compression-set may be developed. No problem may be visible, but when it returns to the "correct" moisture content, the piece cannot shrink to its earlier shape, again due to edge restraint by the drawer runners. This is when things begin to pop. The result is a check as soon as the attempted shrinkage exceeds the tensile-strain limit. The mechanism responsible was discussed in chapter 4 and is illustrated in *Figure 4.14*.

The misinterpretation of this problem is often something like, "Oh, we never have any trouble with high humidity; it's low humidity that causes all our problems." The unfortunate conclusion is that wood should be kept at high humidity or that dryness, per se, is detrimental to wood.

UNEVEN DRYING A third cause of dimensional troubles is uneven shrinkage due to uneven drying. A familiar case is when a pile of air-dry lumber is brought into a heated building. Cupping soon develops on the top boards as the exposed faces dry and shrink first. The cupping back and forth of a tabletop finished only on the upper face is another common example. But perhaps the most universal problem is end-checking. Water moves longitudinally through wood 10 to 15 times faster than it moves perpendicular to the grain. Therefore, end-grain surfaces rapidly lose their moisture and are first to drop below FSP and begin to shrink. If the shrinkage exceeds about 1.5%, tension failures in the form of end-checking may occur (*Figure 6.28*, *Figure 6.29*).



Figure 6.29 • Because drying is more rapid along the grain than across, boards dry first near the ends. The ends shrink before the rest of the board and end checks result. (Photo by Randy O'Rourke)

Here's another way to look at it: Let's assume that moisture moves, on the average, 12 times faster along the grain than across it. Suppose a board is 1 in. thick. Up to 6 in. from either end, water molecules at the mid-thickness of the board have a better chance to escape through the end-grain surface than through the side-grain surface. Except for the 6 in. near the ends, drying from the board should be uniformly slow because most molecules will escape through the side grain. The objective of end-coating boards with sealers is to prevent rapid end-drying and create uniform side-grain drying right to the end of the board.

Stresses are ever-present in drying because there must be differential drying in a piece of wood to make the moisture move. If the moisture gradients are great enough, serious defects will develop.

VARIATION IN SHRINKAGE PROPERTIES A fourth category of troublesome uneven shrinkage results when shrinkage properties vary within a given piece of wood—a characteristic of juvenile and reaction wood (*Figure 6.30*). These abnormal woods shrink more along the grain than normal wood. That might not be a problem if the degree of abnormality were uniform, but it never is. Typically, the severity of reaction wood varies within a given piece, or it may even be combined in the piece with normal wood. Bow and crook are commonly traceable to such variable longitudinal shrinkage.

Twist is sometimes the result of uneven reaction wood formation, but most pronounced twist is associated with spiral grain. Those boards that form veritable propellers are usually caused by spiral grain.

In some cases, the reaction wood may shrink so powerfully that it crushes adjacent normal wood in compression




Figure 6.30 • Reaction wood is typically to blame when boards bow or crook, as in this piece of shiplap log-cabin siding (A). Reaction wood may also cause twisting, as shown in the Japanese fir (B). (Photo A by Richard Starr; photo B by Randy O'Rourke)




Figure 6.31 • These flaws are the result of differential shrinkage in eastern white pine boards containing reaction wood. In A, compression wood predominates, and its greater longitudinal shrinkage caused compression failures in the adjacent normal wood on the right. The ridge indicates reaction wood that shrank less across the grain than the normal wood. In B, normal wood predominates, and the greater longitudinal shrinkage of reaction wood has pulled it apart. (Photo A by Richard Starr; photo B by R. Bruce Hoadley)

parallel to the grain (*Figure 6.31*). At the same time, if the reaction wood is a small portion of the board, it may pull itself apart by failing in tension parallel to the grain (see *Figure 6.31B*).

I once lived in a house that was framed in native hemlock, which runs heavy to reaction wood. One night I heard what sounded like a gunshot coming from the cellar. Racing down the stairs, I found nothing alarming. However, in one corner there was a concentration of dust particles in the air. Looking up, I discovered the source of the noise. The lower face of one of the hemlock joists, with obvious reaction wood, had a gaping cross-break. The dryness of furnace heat

was the final increment of unbearable shrinkage tension, causing the beam to fail abruptly.

In some species, extractives may significantly reduce shrinkage of heartwood as compared to sapwood. Such differences between dimensional change as noted in *Figure 6.21* may also produce troublesome results in boards. The sapwood/heartwood shrinkage difference is also likely responsible in part for the uneven thickness variation noted in *Figure 6.19*. In any case, the practice of matching sapwood to sapwood and heartwood to heartwood is a logical one.



Figure 7.1 • Repeating the same measurement of a board at monthly intervals for a year will reveal startling dimensional variation in the wood over the seasons. (Photo by Randy O'Rourke)

COPING WITH DIMENSIONAL CHANGE IN WOOD

The examples mentioned in the previous chapter describing the ways that moisture-related instability of wood can cause problems suggest that the woodworker must not only understand basic wood-moisture relationships but also must know the alternatives that can be considered in dealing with dimensional instability (*Figure 7.1*).

As I see it, there are five fundamental approaches to coping with dimensional change in wood: (1) preshrinking by drying prior to use, (2) control of moisture adsorption and desorption, (3) mechanical restraint, (4) chemical stabilization, and (5) design. Alone or in combination, each has its individual merits in dealing with a particular woodworking situation.

PRESHRINKING

As obvious as it is, preshrinking wood by seasoning is too important to pass over lightly. Although wood is dried for many other reasons (to reduce weight, to prevent deterioration by fungi, to increase strength, to permit gluing and finishing), the principal objective is to have shrinkage take place *before* rather than *after* the final product is completed. The key to this approach is drying the wood to a moisture content consistent with the average relative humidity of the place where the finished piece will be used. Ideally, the wood would never shrink or swell. But this ideal is not realistic. It is just too difficult to accurately predict the appropriate equilibrium moisture content, and environments seldom remain stable.

The target moisture content depends upon a number of climatic and environmental factors, such as the local average and extreme levels of humidity, whether the finished item will be used indoors or out, and the extent of winter heating. In the Northeast, where the average annual relative humidity is typically in the 70% range, a moisture content of 12% is appropriate for outdoor items. For interior work, however, where central heating drives the relative humidity to 25% or lower, a moisture content of 7% or 8% is more appropriate.

The allowable moisture content would be understandably higher in humid areas such as the Gulf states and lower in arid regions such as the Southwest. I recall a day in

early June where the outdoor temperatures in central Massachusetts were in the mid-60s and the relative humidity was in the 60% to 80% range. Flying to Phoenix, Arizona, I discovered the day's weather featured a high of 113°F and a low of 84°F with a 6% to 24% range in relative humidity. Since this represented a transition from an EMC of 13% to 14% to one of 3% to 4% in only a few hours, I was glad I had not brought along a half-finished piece of sculpture to work on. Imagine the problems encountered by anyone moving furniture (or any wooden items) from one such extreme to another.

Figure 7.2 shows the average January and July levels of moisture content for interior woodwork in all areas of the United States. Drastic variation can also exist within a rather limited geographic region—the summer moisture content is 13% along the coast of California, while eastern California falls within the 4% isotherm. These data stress the need for becoming familiar with local weather history and for keeping track of current weather conditions.

CONTROL OF MOISTURE SORPTION

Preshrinking wood is one thing; keeping it at the shrunken dimension is another. Careful attention must be given to the second basic consideration—atmospheric control to minimize gain and loss of wood moisture. Air conditioning is effective but not always possible or even sensible, except for priceless museum objects and the like. Another approach is to control humidity through isolation, by keeping the wood in a reasonably airtight container. This may be a small display box, a glass jar, a plastic bag, a foil wrap, or, more commonly, a coat of finish (*Figure 7.3*).

If there were such a thing as a coating system for wood that was totally impervious to moisture, the problem would be solved. All subsequent loss or gain of moisture would be arrested and the original moisture content would not be very critical. In reality, however, no finish can block the passage of all moisture. Finishes are merely obstacles to moisture passage or buffers to curb the extremes. This point cannot be emphasized enough. As a companion to proper preshrinking, an effective finish is the most reliable approach to minimizing





Figure 7.2 • Average January and July levels of moisture content for interior woodwork in the United States.



dimensional response in our variable atmosphere, but even as we must appreciate the important potential role of finishes as moisture barriers, we must not expect too much of them. In chapter 12, I will return to this important subject and consider the relative effectiveness of various finishing materials in retarding moisture exchange with the atmosphere.

MECHANICAL RESTRAINT

In some cases the above measures may not be adequate to ensure the desired dimensional control. It may then be advantageous to prevent wood from changing its dimension through other means. One such approach is mechanical restraint.




Figure 7.3 • The moisture content of unfinished wood kept indoors in most parts of the United States fluctuates seasonally from 4% to about 14% (A). The moisture content of wood that has been kiln-dried and well finished with lacquer or varnish oscillates in a much narrower range, around 8% (B). Wood that has been air-dried and coated with a finish that continues to dry gradually then oscillates in the same range (C).

A stable material such as metal, whose strength is clearly greater than that of wood, can be used to limit swelling or shrinkage of the wood. Metal straps or long bolts can be used to some extent, as can plastics and other synthetics. More commonly, wood itself is used by taking advantage of its superior strength and stability in the grain direction. This is demonstrated in the cross-ply construction of plywood. Douglas-fir, for example, has an average tangential shrinkage of 7.6% to 7.8% and a longitudinal shrinkage of about 0.1%. When Douglas-fir plywood is made having equal amounts of wood in both directions, providing mutual restraint, the panel has identical shrinkage levels in both directions of only about 0.5%. With only a slight sacrifice of stability along the grain, the normal tangential shrinkage is reduced to one-fifteenth of its original value. Various types of composite boards (referred to generically as particleboard or flakeboard) have stability similar to that of plywood because of the mutual stabilization of the particles, chips, or flakes and the adhesive used.

Crossbanding solid lumber panels with thin veneers yields dramatic results. An interesting experiment is to make up panels of pine or basswood with and without hardwood plywood crossbanding on the face and back, trim the panels to the same size, leave them unfinished, and compare their dimensions over a period of time.

For even more revealing results, add a third matched panel that has a crossband on only one face. This will show the importance of **balanced construction** (symmetry on either side of the central plane with regard to thickness, species properties, etc.). Otherwise the uneven restraint will result in a surprising amount of warp. That is why plywood is made in odd numbers of plies, so the face and back plies **will** always have parallel grain direction, thus preserving

symmetry and balance of construction. Warping in plywood panels sometimes results from uneven sanding of the opposite face plies, thereby "unbalancing" the panel (*Figure 7.4*).

Cleats or other cross members are used in countless ways to restrain dimensional movement in wood, but such constructions are successful only if the restraint is uniformly transmitted and distributed. Adhesives offer the most uniformity, in contrast to the point attachment of mechanical fas-



Figure 7.4 • The consequences of unbalanced construction are evident here, where crossband and face veneer have been bandsawn off one side of a strip of lumber-core panel. (Photo by Randy O'Rourke)

teners. As in the face plies of plywood, restraint can be well distributed in thin layers by attachment along only one face. When lumber thicknesses are restrained on only one surface, the free surface may develop stress concentrations, resulting in checking. Also, when panels are restrained only at their ends, as in "breadboard" construction, strain concentration may cause failure in the unrestrained central area.

CHEMICAL STABILIZATION

Another approach to minimize dimensional change is stabilization with chemicals. A complete discussion of this subject is beyond the scope of this book. However, comments on two such treatments are offered below, one of which has interest to the small-shop woodworker, the other of which is commercially used in many familiar specialty wood products.

POLYETHYLENE GLYCOL (PEG) The stabilization treatment most widely used by woodworkers is polyethylene glycol (PEG), a polymer of ethylene glycol, the basic ingredient of most automobile antifreeze (although antifreeze cannot be used to permanently stabilize wood). The most appropriate polymer for stabilization has an average molecular weight of 1000, hence the designation PEG-1000. At room temperature, this chemical is a whitish solid with much the same appearance as paraffin wax. It melts to a syrupy liquid at 104°F and is very soluble in water.

PEG-1000 stabilizes wood by preventing shrinkage. When green or fully swollen wood is soaked in a solution of PEG-1000, the molecules of PEG-1000 replace the water molecules in the cell walls. When the wood dries, the PEG-1000 molecules remain in the cell wall, keeping it in its fully swollen dimension.

PEG will not prevent already dried and shrunken wood from swelling. To be effective, therefore, PEG must penetrate thoroughly—it depends on diffusion through free water in the cell cavities to reach the cell walls. The first key to success with PEG is to keep the wood at its original green moisture content. For woods whose green moisture content is low, such as white ash or the heartwood of many conifers, expect less than maximum stabilization. So not only must the wood be green and fully swollen, but its moisture content must be well above the fiber saturation point (about 30% moisture content) when treated with PEG. When wood at 100% moisture content is treated, shrinkage is reduced by nearly 90%.

The second key to success is grain direction. Just as liquid movement and diffusion are many times greater along the grain than across, PEG penetrates end grain much more readily than side grain. In practice, you cannot expect effective penetration into boards of average density much more

than 1 in. in thickness, or into cross-sectional pieces more than 3 in. to 4 in. along the grain. These limitations suggest the most appropriate applications of PEG: stabilizing cross-sectional disks of wood, small turnings, and carvings.

Penetrability varies among species. In general, the greater the density, the more difficult the wood is to treat. Woods with high extractive or resin content may also resist PEG penetration. Sapwood and heartwood within a species may behave differently—sugar maple sapwood treats well for its density, but the heartwood is considered unbeatable.

Strength of solution, temperature, and soaking time are critical factors. Solutions of 30% to 50% PEG work best, with the stronger solutions penetrating better. Equal parts (by weight) of PEG and water yield a 50% solution: 10 lb. of PEG in an equal weight (4.8 qt.) of water yield about 8.5 qt. of 50% solution. To mix a 30% solution, dissolve three parts of PEG in seven parts water, that is, 4.46 lb. of PEG in 5 qt. of water for 7 qt. of solution. Melting the PEG in a double boiler or fragmenting it speeds the process. Hot water also accelerates dissolving.

It is best to check the solution density with a hydrometer, as well as check the temperature. At 70°F (21°C) a 30% solution will have a specific gravity of about 1.05; a 50% solution about 1.083. As the wood absorbs the PEG, the solution may become diluted, or if water can evaporate from the soaking vat, the solution may become more concentrated. A hydrometer, along with the graph on the facing page (*Figure 7.5*), will indicate when it's time to add more PEG or more water. Leftover solution can be reused by restoring it to its original strength.

The soaking procedure and equipment can be quite simple. The objective is to find a container about the same size and shape as the wood being treated so as to minimize the solution volume needed for immersion. Any ceramic, enamel, or plastic container will work. Because metals (other than stainless steel) discolor many woods, line metal containers with a puncture-resistant rubber sheeting or 6-mil polyethylene. For large, long, or irregular objects, you could make a wooden or plywood tub and line it with polyethylene. Where a great deal of treating will be done, line the box with fiberglass resin and cloth.

In open tanks or vats, you must improvise some means of weighting or holding down pieces along with separating strips to ensure that the solution circulates around all surfaces. You may get layering of a high or low concentration of PEG during soaking, so stir at least daily with a stick or paddle.

The solution penetrates much faster at temperatures of up to 160°F, so where the project warrants it, it is worth heating the treating vat. A thermostatically controlled heat source would be ideal. My wife's Crock-Pot would make a perfect soaking vat for 6-in. disks, but even an improvised tank can be fitted with a thermostatically controlled immersion heater




Figure 7.5 • Specific gravity of aqueous solutions of PEG. Periodic monitoring with a hydrometer makes it possible to add more solution to keep it at the original strength.

and walls insulated with fiberglass wool. A simple way to get heat is to put the tank over or near a radiator. Placing the vat outdoors in the summertime to be warmed by the sun will work, except that it will be difficult to assess the treatment in terms of reproducing it closely another time.

How much PEG retention, stabilization, and soaking time for various types and dimensions of wood are critical questions to this discussion. But they are hard to answer and are best considered in terms of specific categories of treatment.

The first category involves pieces of wood with the pith included, where the greater tangential than radial shrinkage would result in radial cracks. Cross-sectional disks, intended for clock faces, coasters, lamp bases, or even table-tops, are typical examples. Although such pieces typically cannot be dried without defect when untreated, they are ideal subjects for PEG stabilization as long as their thickness (i.e., dimension along the grain) is not greater than 4 in. It is impossible to specify precise soaking schedules, but start with the guidelines suggested by the Forest Products Laboratory (*Table 7.1*).

The advantage of elevated temperature and increased solution concentration is obvious. For lower-density woods

such as white pine, cottonwood, or yellow-poplar, try one-half to two-thirds the times listed; for higher-density woods such as beech or hickory, double or triple the times. I have soaked cross sections of red oak, 6 in. in diameter and about 1 in. thick, in a 50% solution for a week at 120°F. No defects developed whether they were then dried rapidly or slowly. But red oak is quite permeable; I would not expect the same results with white oak. Experience will help identify the easy and difficult woods to stabilize: I have given up trying to treat sugar maple, but I have had excellent results with oak, black walnut, butternut, and elm. Others report good success with a wide variety of species including pines, spruce, redwood, cottonwood, willow, soft maples, beech, and apple. Cherry tends to develop internal checks (honeycomb) if treated at temperatures above 110°F

A second major category of PEG application is where any dimensional change due to moisture variation is undesirable in the final product, and maximum stabilization is the objective. A good example is gunstocks for target rifles, where small changes in the stock's dimension may affect accuracy. Another application involves the maple strips used in core laminations for archery bows, where humidity changes can cause twisting. Other PEG-stabilized products are musical instrument parts, bases and framing, large engraving blocks, and patterns. PEG-treated wood can be glued with resorcinol or epoxy, but polyvinyl (white) and aliphatic (yellow) glues do not work well. Treated lumber should be dressed with a jointer or surface planer as is done in routine gluing and laminating. Other than sanding, PEG-treated wood is easier to carve and machine than untreated wood. The PEG lubricates the tool, and there is less splintering. Removing surface traces of PEG by first scrubbing with toluol and washing with methanol produces the best

TABLE 7.1—Suggested soaking time in PEG-1000 for walnut disks. Below, disks properly treated with polyethylene glycol will dry without the usual radial cracking.

Solution concentration and temperature	Up to 9 in. in diameter and 1 in. to 1½ in. thick	More than 9 in. in diameter, 2 in. to 3 in. thick
30%, 70°F	20 days	60 days
50%, 70°F	15 days	45 days
30%, 140°F	7 days	30 days
50%, 140°F	3 days	14 days



No treatment; disk with checks. 50% solution, 1 day at 140°F; disk without checks.

glue joints. If joints will not be subjected to high stress, washing with alcohol alone will suffice.

Bowl turners also use PEG. It is difficult to dry blocks of considerable thickness (say, 5 in. to 6 in.) without degrade. Thus turners often rough-turn the bowls in the green condition. But when an untreated rough turning is dried, unequal dimensional changes may distort the bowl so much that final turning is impossible. With hard-to-season species or with irregularly grained pieces such as burl or crotch, where drying defects are common, PEG treatment of the rough turning will usually overcome these problems. If bowls are green-turned to wall thicknesses of 1/2 in. to 5/8 in., a wood with average density such as black walnut can be treated with a moderate schedule (e.g., three weeks at 70°F in a 30% PEG solution or one week at 140°F in a 50% solution) to achieve a high degree of stabilization.

PEG is described by the Forest Products Laboratory as "nontoxic, noncorrosive, odorless." It has been declared safe as an ingredient in cosmetics, ointments, and lotions, and as a binder for pharmaceutical tablets. Results of tests involving laboratory animals also support this classification. Where PEG-treated wood is used for utensils or containers such as bowls, PEG contamination of food does not appear to present any problems. Possible toxicity of finishes should, of course, always be considered with any food containers.

PEG treatment is also applicable to green woodcarvings (Figure 7.6). The green wood is carved to within 1/4 in. to 1/8 in. of the final surface. Between carving sessions, the piece is kept wrapped to prevent drying. Then the wood is treated enough to stabilize the surface to a depth beyond that which will finally be carved, thus avoiding surface checks. Minor changes in overall dimensions are usually acceptable. For a rough carving of approximately 8 in. by 6 in. by 24 in. in

yellow-poplar, I found that a four-week soak in 30% PEG solution at room temperature was sufficient.

For me as a hobby carver, the drawback is that I seldom finish a sizable carving quickly, so storing the green wood without stain or molding becomes a problem. Sometimes I put the carvings in my freezer. Remember, PEG treatment will offer only surface control of dimension; pieces containing the pith will still develop large radial cracks due to the tangential/radial shrinkage differential.

PEG has also proven useful in stabilizing waterlogged artifacts recovered by archaeologists. Long immersion in water causes cell walls to break down by hydrolysis, and exaggerated shrinkage results when the wood is dried. PEG can stabilize such material. Woodcarvings produced in tropical climates will suffer disastrous checking when imported to drier climates. Soaking and then treating with PEG can prevent those troublesome checks.

A final category of application is superficial treatment to eliminate drying degrade in thick planks or irregularly grained stock, used perhaps for furniture parts, carvings, or bowls. The objective is to get just enough penetration to control surfaces, where many drying defects begin; the treated surface material will later be totally removed from the completed item. Thick planks, soaked for a week to 10 days in 50% solution at 140°F, can be air- or kiln-dried without major defects even under drastic conditions. Surface checks, even end checks, are virtually eliminated. The retarded outer shrinkage apparently relieves internal compression that might result in collapse during the early stages of drying. Elimination of surface checks, which can become internal checks, helps avoid honeycombing. Since PEG is highly hygroscopic, it probably also reduces the severity of the moisture gradient by holding moisture near the surface.




Figure 7.6 • This head (A) was rough-carved in a piece of cork tree (*Phellodendron sachalinensis*) and soaked for three weeks in a 40% solution of PEG-1000 (B). The treated piece was then dried in an oven at 212°F without checking and was finish-carved. The carving, 6 in. high (C), was finished with penetrating oil. (Photos A and B by Richard Starr; photo C by Randy O'Rourke)

This treatment will leave a heavy concentration of PEG at the surface. In precarved sculpture, rough-turned bowls, or thick lumber, this is routinely removed as surface material is machined away. Abrasive belts will load with PEG-saturated dust, although they can be cleaned with a bristle brush and warm water.

Small disks cut smooth in the green condition and requiring only fine sanding should be leached by flooding with hot water, scrubbing, and sponging to remove excess PEG. Bark edges especially will retain excess PEG, which should be carefully rinsed away.

Before finishing, surfaces should be dried, which can be accomplished in a variety of ways. For thorough stability, drastic means, including ovens and direct sunlight, can be employed without harm. Wood dried in an oven, however, may darken noticeably. Pieces can be placed over radiators or in improvised drying boxes heated with light bulbs or simply left to come to equilibrium at room conditions.

It is not a good idea to leave PEG-treated objects unfinished. PEG is very hygroscopic, and treated wood will pick up enough atmospheric moisture in humid weather to feel damp on the surface. Surfaces that are left unfinished, especially when exposed to light, may also develop a dirty, sooty-looking discoloration.

After final sanding of dried pieces, apply a finish right away. Many finishes commonly used for untreated wood (such as shellac, alkyd varnish, and lacquer) cannot be used. The two best finishes are oil and moisture-cure polyurethane-resin varnishes.

I use Watco Danish oil because it is easy to apply and gives the finish I prefer, leaving the surface with a soft luster without covering the surface texture of the wood. Three or four well-rubbed coats are enough if the surfaces have been sanded smooth. I think it is the best finish for disks with the bark on because bark retains heavy concentrations of PEG and varnish will not adhere.

If you prefer a built-up finish, try four or five coats of moisture-cure polyurethane, sanded between coats with 200-grit paper. The heaviness of this type of varnish makes it difficult to apply without leaving brush marks. A couple of finish coats of conventional urethane varnish, rubbed with pumice and oil, will leave a flat luster.

In considering whether to use PEG, the cost of the chemical may be important. Ten pounds will make enough solution to treat a stack of disks in a small bucket. But a large cross-sectional disk, say 30 in. in diameter and 3 in. thick, will require several gallons of solution and some extra PEG to maintain the concentration. One final suggestion: Whenever you treat wood with PEG, always process a few similar pieces *without* treatment. This will give you a clearer indication of what effect the PEG really has. Without the control material for comparison, you will not be able to

assess the improvement. It will help you decide whether the treatment was worth it.

WOOD-PLASTIC COMPOSITE (WPC) Another noteworthy stabilization process is the impregnation of wood with chemicals that are then transformed into rigid plastic. The resulting product is termed wood-plastic composite (WPC). A common chemical used is the monomer (single molecule) form of methyl methacrylate. A special apparatus forces the chemical into the wood by vacuum and pressure, and the plastic is then cured with heat and a catalyst. This curing, or polymerization, links together monomers into multiple molecules, called polymers, in which form the plastic is hard and stable. (Commercially formed polymethyl methacrylate is familiar under the trade names Plexiglas and Lucite.) A composite structure of wood and plastic is thereby formed. In addition to being quite stable, WPC has superior hardness, toughness, and abrasion-resistance in comparison with untreated wood. Natural wood figure can be accented by adding dye to the monomer. WPC can be polished to a high luster, and further finishing is not necessary. Commercially available in small pieces from some suppliers of woodworking materials, WPC is popular for novelties such as chess pieces, jewelry, bowls, peppermills, and paperweights.

DESIGN

Let's not forget what is perhaps the most important consideration of all in coping with dimensional change—design. With all the scientific innovations and materials that allow us to seal or stabilize wood, it is tempting to forget the value of intelligent design, which allows dimensional change to take place if it must. Traditional woodworking methods reveal how essential logical design can be. Many wooden objects have remained intact for centuries only because they were designed to accommodate natural dimensional changes at a time when chemical treatments, synthetic finishes, and environmental control were unknown.

Frame-and-panel construction exemplifies the idea of capitalizing on a functional design requirement and making it an aesthetic feature. Centuries ago, woodworkers learned that a large rectangular surface would retain its intended dimensions only if it were built with a structural framework made of narrower pieces of wood arranged to minimize dimensional changes. The framed area was then filled with relatively narrow (nonstructural) panels with beveled edges set into grooves in the frame. This allowed the panel to change dimensions freely. Because the bevel is made quite wide, the eye does not detect the amount of change, which would show up if the panel were tightly fitted with a simple tongue-and-groove joint (*Figure 7.7*). The basic design has

infinite variations, from wall paneling and architectural woodwork to furniture and cabinet doors. We are all familiar with the six-panel door, another traditional application.

In the classic framed panel, it was customary to fasten the panel in the frame only at the center of the upper and lower stiles so that movement of the panel would be approximately equal within each side rail. Early woodworkers undoubtedly learned by experience the necessary amount of clearance to leave between the beveled panel edges and the bottom of the grooves in the side rails. Until such experience is gained, an intelligent estimate of the necessary clearance can be computed by the shrinkage formula given on p. 119.

To illustrate, consider an 18-in.-wide paneled cabinet door to be made from eastern white pine. In framed panels, it is disastrous to leave too little clearance but quite harmless to leave an excess. It is therefore a good idea to be a little liberal in making an estimate. In cases where the pieces are not strictly either flatsawn or edge-grained, the conservative assumption would be that all material is flatsawn. From *Table 6.2* on p. 117, tangential shrinkage (S_t) = 6.1%. Thus extreme moisture conditions might well be anticipated.

Let's prepare for a maximum moisture content of 14% but assume our lumber is at 8% moisture content. Since the

panel will be pinned in the center, we can assume symmetrical behavior and look at either half:

$$\Delta D = 9 \text{ in.} (0.061) \left(\frac{0.14 - 0.08}{0.28} \right) = 0.118 \text{ in.},$$

or approximately 1/8 in.

Therefore, at least 1/8 in. of clearance should be allowed for swelling of the panel and frame.

Let's also consider how much shrinkage would occur if the moisture content of the door dropped to 4%:

$$\Delta D = 9 \text{ in.} (0.061) \left(\frac{0.08 - 0.04}{0.28} \right) = 0.078 \text{ in.},$$

or about 5/64 in. Therefore, the final detailing of the joint should allow not only for swelling room but also for shrinkage.

The total estimated movement of some 0.196 in. at each side is of special concern with regard to the finishing of the door. If the door is to be stained, the bevel of the panel should be stained and given a preliminary finish before assembly. Otherwise, if assembled first and then stained at an intermediate moisture content, an unstained strip of the bevel will be revealed as the panel shrinks and withdraws from the frame.

When some naive woodworker tries to imitate only the appearance of a framed panel and pays no heed to the mechanics involved, the results can be disastrous. A panel tightly fitted into the frame can easily split itself lengthwise in a dry period or burst the frame apart during a humid spell.

It is interesting to note that a style that originally evolved to accommodate the dimensional change in wood is mimicked today in doors that are stamped out of sheet metal or molded in urethane plastic. For many, the style evidently is disassociated completely from the functional necessity that originally created it.

There are numerous other techniques for accommodating dimensional change by intelligent design. For example, in fastening wide tabletops to the apron by screws from below, slotted holes for the screws will allow the top to change dimension across its width. Drawer bottoms can shrink and swell if they are held without fastenings but with grooves in the sides. Attaching support strips to the ends of large panels with sliding dovetails provides for dimensional change of the panel across its width.

The shrinkage formula discussed on p. 119,

$$\Delta D = D_t S \left(\frac{\Delta MC}{fsp} \right),$$

suggests ways of modifying design to reduce the consequences of shrinkage and swelling. For example, one might




Figure 7.7 • In detailing a framed panel, anticipated clearances for panel swelling can be estimated.

reduce the dimensions (D.) of the members. Narrow flooring strips develop smaller cracks between boards than wide flooring; large tenons have a greater tendency to loosen than small ones.

Likewise, choosing a species with a small shrinkage percent (S) obviously helps; for example, mahogany is more stable than beech. Also, using edge-grain rather than flat-grain lumber can take advantage of the smaller radial shrinkage percentage (S_r) compared with tangential shrinkage percentage (S_t). A tangible estimate of the degree of improvement is suggested by the numerical quantities involved, as listed in *Table 6.2* on p. 117.

On p. 120, we considered the clearance allowance of a 9-in. maple drawer front, calculated to fit a drawer opening when swollen to an EMC of 12%. Our estimates indicated that at an EMC of 5%, a gap of 0.223 in. might be expected. If we respecified quartersawn maple, thus substituting radial shrinkage (S_r) = 4.8% for tangential shrinkage (S_t) = 9.9%, the gap would be reduced to

$$\Delta D = 9 \text{ in.} (0.048) \left(\frac{0.12 - 0.05}{0.28} \right) = 0.108 \text{ in.},$$

or slightly over 1/10 in.

Furthermore, if we were to select quartersawn teak instead of maple, we would be dealing with a radial shrinkage of 2.2%, so our anticipated gap would now be reduced to

$$\Delta D = 9 \text{ in.} (0.022) \left(\frac{0.12 - 0.05}{0.28} \right) = 0.050 \text{ in.},$$

or about 1/20 in.

If it were possible to redesign the drawer fronts to be only 5 in. high (that is, 5 in. across the grain radially), thereby reducing the dimension factor from 9 in. to 5 in., the dry weather gap would be estimated as only

$$\Delta D = 5 \text{ in.} (0.022) \left(\frac{0.12 - 0.05}{0.28} \right) = 0.0275 \text{ in.},$$

a mere 1/32 in. Thus, by carefully considering dimension, species, and growth-ring orientation, it is possible to shrink the gap from 7/32 in. to 1/32 in.

As I will repeatedly emphasize, reducing moisture variation (AMC) by using moisture-retarding finishes further reduces the magnitude of dimensional change.

I find that part of my own philosophical attitude toward woodworking seems to have come full circle. I began trying to use wood "in the raw," but I discovered I didn't know how. Then I became eager to learn ways to "overcome" all the "problems" that wood has, and I experimented with wood stabilizers and chemicals, impatient to improve upon nature's product. In time, however, I realized a certain elis-

taste for trying to make wood into something it isn't and for trying to make it do things other materials do better.

I'm back to using wood "as is" now but with a different point of view. I concentrate on learning what wood is, rather than worry about what it isn't; I try to work *with* it, not against it. Whether this makes me a better woodworker I am not sure, but I am more satisfied, for certainly part of the reward of working with wood is accepting the challenge of understanding it. The dimensional behavior of wood should be looked upon as simply a property of wood to be taken in stride, not as a problem to be corrected.

In summary, learn to live with the dimensional properties of wood by following some guidelines. First, season lumber to the average moisture content it will have in use before working it. Second, provide the finished work with the most impervious finish consistent with its intended use. Third, design the piece to allow normal dimensional change to take place. (Even if you don't think it necessary, it's a nice "fail-safe.") Finally, think about mechanical restraints and chemical stabilizers only when instability still remains unresolved.

MONITORING MOISTURE

I think it was Charles Dudley Warner who observed that everyone talks about the weather, but nobody does anything about it. I often get the same feeling about moisture in wood. An amazing number of woodworkers can recite informed and intelligent-sounding numbers about the recommended moisture content for such and such a job. Or they may even know three ways to determine moisture content. But they don't actually have a moisture meter, a balance, or an oven.

Likewise, I've heard museum people discuss the prescribed humidity conditions for safe-keeping valuable wooden objects, but they don't actually use humidity-measuring equipment. I've lost count of the number of woodworking shops that have capital outlays in six figures yet don't have instruments for measuring or monitoring moisture content or humidity. This holds true for the hobbyist or small-scale professional—whose equipment outlay may be many thousands of dollars—where a \$200 moisture meter or even a \$50 hygrometer could help avoid the problems that eventually probably total in the thousands. Not equipping to measure moisture, in the air or in the wood, is penny-wise but pound-foolish.

RELATIVE HUMIDITY Various instruments are now available for measuring relative humidity. About the simplest is the dual-bulb thermometer **hygrometer** (*Figure 7.8*). This instrument uses two liquid-filled glass thermometers—one is a **dry bulb**, the other has a damp cloth sleeve or "wick" over its bulb (therefore called a **wet bulb**). The wick of the

wet bulb usually dangles into a little vessel of water, or it may be moistened before each use. Water evaporation from the wick cools the wet bulb below the ambient temperature indicated by the dry bulb. The drier the air, the greater the evaporation rate and the lower the wet-bulb temperature. To make a reading, the wet bulb is fanned vigorously to maximize evaporation. When the wet-bulb temperature stops decreasing, the dry-bulb and wet-bulb temperatures are noted. The relative humidity is determined through the combination of dry-bulb temperature and wet-bulb depression by using psychrometric tables or charts (Figure 7.9).

Wall-mounted models such as the one shown in Figure 7.8 are quite popular and the least expensive, but a dual-bulb hygrometer can easily be built from a pair of accurate glass thermometers. Despite the simplicity and economy of the dual bulb, it is highly accurate. In fact, it is used to calibrate most other types.

A sling psychrometer is a common type of portable dual-bulb hygrometer. It is operated by whirling the pair of thermometers around on the end of a swiveled handle (Figure 7.10).

The dial hygrometer (Figure 7.11), while perhaps not as accurate as the dual-bulb thermometer, offers the convenience of information at a glance. You will be amazed to discover how rapidly the humidity can change.

Most recently, many companies offer digital hygrometers, usually in combination with thermometers. Battery operated, they can be wall mounted but also can be carried




Figure 7.8 • A dual-bulb hygrometer. The dry bulb (left) measures normal air temperature. The wet bulb (right) is covered with a moist cotton sleeve. The drier the air, the greater the evaporation rate and the greater the cooling effect on the wet bulb, which is fanned vigorously before taking a reading. (Photo by Randy O'Rourke)

around to provide readings wherever desired, although in some models an adjustment time period of several minutes is typically required to get ambient readings (Figure 7.12).

MOISTURE CONTENT The traditional standard for measuring the moisture content of wood is the **oven-drying method**. As the term implies, water is driven from the wood by placing a sample in an oven at 212°F to 221°F (100°C to 105°C) until constant weight is reached. This final weight is the **oven-dry weight**. If samples from boards or other pieces are taken as cross-sectional wafers no longer than 1 in. along the grain, oven-dry weight is usually attained within 24 hours. The procedure involves weighing the initial sample (W_i), oven-drying, and then determining the oven-dry weight (W_{od}). Moisture content (MC), expressed as a percentage, is calculated by the formula:

$$MC = \left(\frac{W_i - W_{od}}{W_{od}} \right) \times 100.$$

In determining weights, a balance must be available that can weigh samples within at least 0.5% of the sample weight; 0.1% is preferable.

MOISTURE METERS An easy way to determine moisture content is by using modern moisture meters, which give immediate and highly accurate readings. These ingenious little meters use the electrical properties of wood, and their development has followed the usual trend in electronics toward portable and miniature units with simplified operation. A wide range of models is now available to suit virtually every situation, from the hobbyist's use to production operations in the shop or in the field.

For typical woodworking applications, two principal types of meters are available. One is based on the direct-current electrical resistance of the wood and involves driving small, pin-type electrodes into the wood surface; the other uses the dielectric properties of the wood and requires only surface contact with the board (Figure 7.13, Figure 7.14).

The resistance meter takes advantage of the fact that moisture is an excellent conductor of electricity but dry wood is an effective electrical insulator. The meter itself is simply a specialized ohmmeter, which measures electrical resistance.

The piece of wood is arranged as an element in an electrical circuit by driving the two-pin electrodes into it. The current (typically supplied by a battery) flows from one electrode through the wood to the other, then back through the ohmmeter. Actually, by simply driving pairs of nails into a piece of wood for electrodes and taking resistance measurements with a standard ohmmeter, readings could be obtained that would indicate relative moisture content. But





Figure 7.9 • With readings from a hygrometer, the chart on the left will give approximate equilibrium moisture content (EMC) of wood. The chart on the right can be used either with hygrometer readings (subtract wet bulb from dry bulb to get wet-bulb depression) or with relative humidity figures from the local weather service. Locate the point at which the dry-bulb temperature intersects the appropriate relative humidity line, and read across to find the EMC. Charts like these are based on typical, low-extractive species, usually spruce. Woods with high extractive content, like mahogany, will have a slightly lower EMC at a given relative humidity.

commercial meters have the resistance translated directly into percent moisture content instead of ohms of resistance and are therefore more convenient.

Because electricity follows the path of least resistance, the wettest layer of wood penetrated by the electrodes will be measured. For boards that dry normally, a drying gradient usually develops from the wetter core to the drier surface with an average moisture content about one-fifth or one-fourth the board thickness from the surface. Thus for 1-in. lumber, the electrodes should penetrate only 1/4 in. to 1/5 in. in




Figure 7.10 • To take a reading with a sling psychrometer, the cotton sleeve on the wet bulb is first moistened. Then the instrument is whirled to maximize the evaporation from the wick until the wet-bulb temperature no longer drops. (Photo by Randy O'Rourke)




Figure 7.11 • This wall-mounted dial hygrometer indicates both relative humidity and temperature at a glance. It should be placed in a representative position with good air circulation. (Photo by Randy O'Rourke)



Figure 7.12 • A digital hygrometer usually comes with a thermometer. Easy to read and handy, its only drawback is that there is a lag time of several minutes when the humidity level changes. (Photo by Randy O'Rourke)




Figure 7.13 • This resistance meter has external electrodes that are driven into the board. (Photo by Randy O'Rourke)



Figure 7.14* The electrode on the back of a dielectric meter generates a radio-frequency field as it is pressed against the face of a board. (Photo by Randy O'Rourke)

some models, the electrodes are a pair of pins extending from one end of the unit that can be pushed into the wood by hand. In the model shown in *Figure 7.13*, the electrode pins are mounted in a separate handle attached by a plug-in cord to the meter box.

Electrodes of various lengths, up to 2 in. or more, are available for measuring thick material so the same meter can be used for everything from thin veneer to heavy planks. Electrodes should be inserted so current flow is parallel to the grain. Electrical resistance is greater across the grain than parallel to it, although the difference is minor at lower moisture-content levels.

The values obtained with a resistance meter can be expected to agree within one-half a percentage point with those obtained by oven-testing for samples in the 6% to 12% range: within one point in the 12% to 20% moisture-content range: and within one to two points in the range from 20% to fiber saturation.

Meters using the dielectric properties of wood have a surface electrode that generates a radio-frequency field that extends for a prescribed distance when placed against the wood. Some meters measure the power-loss effect, which varies according to moisture content, whereas others respond to changes in electrical capacitance. Different models have electrodes designed for field penetration to various depths. Field penetration to about half the stock thickness is usual. Where moisture content is uneven, a more or less average reading will be given.

Each type of meter has its strengths and weaknesses. Resistance meters have the disadvantage of leaving small pinholes wherever the electrodes were inserted, which might be unacceptable in exposed furniture parts, gunstocks, and the like. On the other hand, a given meter can be used with a variety of electrodes in a wide range of situations. Resistance meters with a 6% to 30% range are available down to pocket size, with both built-in short-pin electrodes and separate cord-attached electrodes.

Radio-frequency power-loss meters are available in compact hand-held models, with electrodes for 1-in. field penetration and scaled from 0% to 25% moisture content. Their distinct advantage is the ability to take readings without marring surfaces, thereby allowing measurements of completed items, even after the finish has been applied. These meters are extremely quick to use but are less versatile because a given electrode style works only for a particular area and depth of field.

Green wood may have an extremely high moisture content, but woodworkers are most concerned with moisture measurement of seasoned stock. Fortunately, the electrical properties of wood are most consistent at moisture levels below fiber saturation (25% to 30%), the range of most interest to woodworkers. Dielectric meters can indicate

moisture contents down to zero. The electrical resistance of wood becomes extreme at low moisture contents, limiting the lower end of the range of resistance meters to about 5% or 6%. More elaborate meters sometimes have scales extending to 60% or 80% moisture content, however, electrical properties are less consistent above fiber saturation, so readings in this range must be considered approximate.

Moisture meters usually give scale readings of percent moisture content that are correct for certain typical species at room temperature. Instruction manuals give correction factors for other species and different temperatures. Since density has little effect on electrical resistance, the species corrections are typically less than two percentage points for resistance meters; correction factors may be greater with power-loss meters. Resistance readings must also be corrected about one percentage point for every 20°F departure from the calibration standard. With dielectric meters, the correction is more complicated but is well explained in the instruction manuals. For anyone using meters under regular conditions—with one or a few common species and always at room temperature—correction factors either are not applicable or become routine. Recent innovations in the design of some meters include built-in corrections for species and temperature.

It is important to appreciate that a meter in good condition will faithfully and accurately measure the electrical properties of the wood being sampled. It must be realized that the moisture content in a tree may show considerable variation, which may be reflected in the lumber moisture content until an equilibrium has been reached. The operator must understand the vagaries of wood moisture and interpret accordingly. For example, a new owner of a meter might discover a variation of two or three percentage points up and down a given board. The common reaction is "the meter is accurate only to within three percent" or "it gives variable readings." But in fact the meter is properly measuring moisture variations that exist in the board. Thus, one must measure average or typical areas of boards and avoid the ends and cross-grain around knots, which dry most rapidly.

THE MOISTURE "WIDGET"

I am convinced that the greatest single impediment to moisture control is simply neglecting (or even refusing) to think about it. More lumber is dried and conditioned by assumptions and wishes than by controlling the atmosphere. An interesting gimmick for reminding oneself about moisture content is to build a simple gadget consisting of a horizontal wand with a wood sample suspended from one end and hung at its balance point (*Figure 7.15*). As the wood sample picks up and loses moisture in response to changes in humidity,

the free end of the wand will float up and down. The device can be made quite sensitive by making the wand out of the lightest material possible that is also nonhygroscopic (stiff, thin-walled plastic tubing works well); by making the wood sample a cross-sectional piece so it will have as much end grain exposed as possible; and by making the suspension points as frictionless as possible. (Note: Don't try to rest the wand across a fulcrum. The farther out of balance it gets the less stable it becomes, and it will fall off the fulcrum. It is best to suspend the wand by a short thread or eye screw.)

While merely noting the angle of the wand's inclination will be informative, the gadget can be made into a more sophisticated instrument. Hanging the wand parallel and close to a wall enables reference marks to be recorded where the tip of the wand is observed at intervals. If an oven and balance are available for moisture determination, the moisture content of the wood element can be determined by matched "control" material. Once the moisture content is known, the wand can be "calibrated" by hanging known weights (equivalent to the sample at various moisture content values) on the wand and marking the wall.

Once the gadget is installed and operating on a wall of a shop or classroom, it's easy to check it often. After a while, you think more and more about the effects of weather, and pretty soon you find yourself each morning wondering what it will read when you get to the shop that day. It's a great low-cost way to have a continuously reading hygrometer.




Figure 7.15 "This simple homemade gadget indicates equilibrium moisture content. The pointer rises and falls as the wood absorbs and desorbs atmospheric moisture. The wand can be calibrated with moisture content values derived from matched samples that were oven-dried. (Photo by Richard Starr)



Figure 8.1 • Pine boards air-drying.

(Photo by R. Bruce Hoadley)

DRYING WOOD

We have discussed many aspects of wood-moisture relationships, from the nature of water in the wood to final equilibrium between bound water and the atmosphere. Now we're ready to tackle the most important and perhaps the trickiest subject of them all—the process of drying wood. This critical process involves not only the removal of moisture but also the control of shrinkage-related stresses.




It's important for woodworkers to understand the drying procedure for two reasons. First, woodworkers should appreciate and recognize the difference between poorly dried and properly dried lumber. Assuming lumber is well dried because "they said it is," or because "it ought to be" won't help when the lumber turns out to have drying defects. Woodworkers should watch for telltale warnings of improper drying. Second, most woodworkers eventually

attempt some drying on one scale or another, either for economy or to acquire otherwise unavailable material—or just for the fun of it.

Abundant tree material is available to those who seek it out from such sources as storm-damage cleanup, construction-site clearance, firewood cuttings, and even direct purchase from local loggers and sawmills. With chain saws, wedges, bandsaws, and a measure of ingenuity, you can work out a way to get chunks and flitches for carving or even lumber. But many an eager woodworker has produced a supply of wood to the green-board stage and then found himself unable to dry it to usable moisture levels without serious degrade or even total loss. Therefore, it's quite appropriate that we look carefully at both the fundamentals and the procedures involved in drying (*Figure 8.1*).

TABLE 8.1 — Wood dries from the surfaces inward, shrinks differentially, and develops stress. The object is to regulate the rate of drying by slow air-drying or by controlled kiln-drying. This will keep stresses within tolerable levels and avoid defects.

Drying stage

	i	ii	iii
Moisture condition	Above fiber saturation point (FSP) throughout: Drying begins with loss of free water from surfaces.	Shell now below FSP, core still above FSP. Core moisture migrates outward to the shell.	Below FSP throughout, eventually reaches uniformly low EMC.
	 <p>Growth ring boundary Ray Above FSP</p>	 <p>Surface checks usually follow plane of rays Shell below FSP (in tension) Core above FSP (under compression)</p>	 <p>Slight cup (due to the board being flat-grained) Shell under compression Core in tension Honeycomb check (may be an extension of reclosed surface checks)</p>
Stress condition	Stress-free	Shell tries to shrink, thus it is in tension across surfaces. Drying sets shell in oversized condition. Shell (in tension) squeezes core into compression.	Core now trying to shrink away from oversized shell. Core develops tension, pulls shell into compression.
Defects	Defect-free	Surface may check; core may collapse as shown.	Interior is case-hardened; if severe, core may honeycomb as shown.

HOW WOOD DRIES

It should be emphasized here that the so-called "seasoning" of wood is a water-removal process, rather than the chemical-modification process that is associated with seasoning certain foods or with curing hides. As previously discussed, it involves removing all of the free water and part of the bound water down to the target equilibrium that is suitable for the finished item.

One is tempted to wonder why lumber can't simply be placed in an oven to drive off sufficient moisture, as is done when determining moisture content. We would certainly get the moisture out, but the uneven shrinkage would totally ruin the lumber. The drying sequence is a continuously changing process, but there are three stages through which every piece of wood passes in drying. Understanding these stages will reveal how stresses and defects develop.

Assume we take a plank of green wood and dry it under rather drastic conditions by placing it directly into an oven. Let's visualize the cross section of the plank well away from the ends, as shown in *Table 8.1* on p. 147. Initially, it is uniformly well above the fiber saturation point in moisture content. During stage I, the piece is free of stress and defects because although moisture (free water) is escaping from the surface, no shrinkage has yet taken place.

Eventually, the moisture content of wood near the surface drops below the fiber saturation point. The layer of wood near the surface, referred to as the **shell** (in contrast to the interior zone, known as the **core**) begins to shrink—or at least attempts to. (The critical shrinkage being considered here is perpendicular to the grain; longitudinal shrinkage is insignificant in this regard.) But the shell cannot shrink as much as it wants because the fully swollen core holds it in an oversized position. The shell therefore develops tension perpendicular to the grain around the outside of the board, characteristic of stage II. If these stresses exceed the strength of the wood, surface checks develop to relieve a portion of the stress (*Figure 8.3*). At the same time, the encircling tensile stress from the shell contracting around the core places the core in compression. This compression stress, aided by the capillary tension of free water being dried from the cells, may cause internal buckling of the wood cells in the core, called **collapse**, which may severely distort the board (*Figure 8.3*).

But suppose the stresses are not severe enough to cause surface checks or collapse. The shell nevertheless continues to dry and becomes set in its oversized condition. As drying continues further, the shell surface begins to level out at a low moisture content. Subsequently, the core continues drying, eventually drops below fiber saturation point, and attempts to shrink, making a transition to stage III. As the core tries to attain a smaller dimension, it not only draws the

shell inward but also gradually develops a reversal of stresses such that the core itself, being held outward by the shell, is now in tension and pulls the shell into compression. Stage III has been reached, and the wood is said to be **case-hardened**. With the shell in compression, any surface checks that developed in stage II now close up. If the case-hardening tensile stresses in the core are great enough, internal separation of the wood—called **honeycomb**—can occur. Honeycomb (*Figure 8.4*) is one of the worst defects that lumber can develop. These internal checks are often extensions of the surface checks developed in stage II as stress reversal follows in the transition to stage III. Even when the piece is eventually at uniform moisture content throughout, it will remain case-hardened. If such a plank is resawn, the two halves will cup (*Figure 8.5*).

Anyone can duplicate these stages and develop a case-hardened and even honeycombed board. Simply take a




Figure 8.2 • Surface checks developed as this red oak board dried (A). Crosscutting reveals surface checks penetrating deeply into this red oak board (B). (Photo A by Richard Starr; photo B by Randy O'Rourke)



Figure 8.3 • Extreme compression stress in drying may cause wood cells in the core to buckle or collapse, as in this imbuya board, which was sawn rectangular. (Photo by Randy O'Rourke)





Figure 8.5 • A wafer cut from a kiln-dried plank of white ash shows no symptoms of stress (left). Another section from the same plank after resawing (center) reveals the case-hardened condition (tension in the core, compression in the shell). Kiln operators cut fork-shaped sections that reveal case-hardening when prongs curve inward (right). (Photo by Richard Starr)



Figure 8.4 • Honeycomb checks in a black walnut plank follow the planes of the rays (A). Honeycombing in a maple square (B). Surface planing reveals the honeycombing in an oak board (C). (Photos A and C by R. Bruce Hoadley; photo B by Randy O'Rourke)



freshly cut flatsawn oak board, end-coat it well with a thermosetting sealer (resorcinol adhesive does nicely), and place it in an oven at 212°F or a bit warmer. In a day or two you'll probably have a case-hardened board. If case-hardening develops in lumber, it must (and can) be removed in a dry kiln, as discussed below.

So here is the catch-22 that must be resolved. No moisture will move except from areas of higher moisture content to areas of lower moisture content. Therefore, to get moisture to move out of a board you have to set up a moisture gradient, that is, a condition of moisture difference within the wood, drier at the surfaces than in the interior. If the gradient isn't steep enough, moisture will scarcely move. But since variation in dryness produces variation in shrinkage, stresses develop. To minimize these stresses, the gradient must be moderate, but then the moisture won't move fast enough. In the end, we must compromise between drying speed and drying defects.

Let's look first at how the drying compromise is handled in a commercial dry kiln, then at the problem of drying small quantities of lumber at home.

THE DRY KILN

A typical commercial dry kiln is a large, well-insulated room or chamber (*Figure 8.6*). It has controlled air circulation, temperature, and humidity. A neatly piled and stickered

load of lumber is centered in the kiln. Air is driven by large fans from one side through the pile to the other side and then directed back to the fans. Because water moves through wood more readily at higher temperatures and warmer air can carry more moisture, the kiln is heated, typically by banks of steam pipes in the path of the airflow. Humidity can be increased by water or steam sprays or reduced by vents at the top of the kiln.

In drying lumber, the kiln is started at a fairly high humidity level and at only slightly elevated temperatures. Sample boards are monitored for moisture content. The kiln remains at the first level of temperature and humidity until the sample boards indicate that the moisture content has dropped to a certain level. Then the temperature is raised slightly and the humidity lowered to the next step. A sequence of specified steps of temperature/humidity values called a **kiln schedule** is followed, which, from experience, is known to bring lumber of a designated species and thickness safely to the desired moisture content. By carefully controlling humidity, the kiln can utilize higher temperatures to increase the rate of moisture migration from the core




Figure 8.7 • Stress sections evaluate stress distribution in lumber. In the center piece, parallel prongs indicate a stress-free board. On the top, prongs curve inward, indicating case-hardening. On the bottom, prongs spread outward as the result of reverse case-hardening. (Photo by Randy O'Rourke)




Figure 8.6 • A typical commercial package-loaded kiln.

to the surfaces of the board without a dangerously steep moisture gradient.

The kiln schedule is designed so surface checking or collapse will not develop. However, the cost of kiln operation demands that some case-hardening be allowed, so long as it is not severe enough to develop honeycombing, since at the very end of the run, the case-hardening can be removed. This is done after the lumber is brought to final dryness with the lumber surfaces a little lower in moisture content than desired. Then, in the last step of the kiln schedule, the humidity is raised. This reintroduces moisture into the surfaces of the lumber to remove the residual moisture gradient and eliminate the case-hardening. This final "equalizing and conditioning" leaves the lumber free of stress, with a uniform moisture content. As stated above, the process of drying may sound somewhat routine. However, the successful drying of a charge of several thousand board feet of lumber is the craft of the kiln operator—as much art as science—and is usually gained only through years of experience.

The kiln operator maintains a direct weight/moisture check on samples throughout the run and also makes a more thorough inspection with a meter on the finished load of lumber. To check for stress, the operator cuts stress sections. These are cross sections from the boards, bandsawn into a tuning-fork shape (*Figure 8.7*). If the "tines" pinch in, the lumber is still case-hardened and must be conditioned further. If the tines remain straight, the job is done. If the equalizing and conditioning treatment is overdone, reverse case-hardening may develop, in which case the tines spread. This condition must be avoided because it cannot be remedied. Remember, checking for stress in lumber is equally important as checking moisture content.

DRYING YOUR OWN WOOD

For the person interested in drying small quantities of wood, the same general guidelines apply, namely, proper cutting, preparation, and stacking; controlling the drying rate; and monitoring the drying process. Let's review the application of these concepts to typical drying situations. We will consider the drying of short log segments or short thick stock, commonly used for woodcarvings or stout turnings, as well as regular lumber or boards. We will also assume that fairly small quantities such as several log chunks or up to a few hundred board feet are involved—as occurs when one suddenly falls heir to a storm-damaged tree or purchases enough lumber for several pieces of furniture.

In drying your own lumber or carving wood, one common problem is hesitation. You can't wait! If you do, fungi or checks will get ahead of you. Try to think out all the details *before* you get your wood supply; don't wait until

you get it home to decide how you are going to end-coat or where you are going to stack it.

First consider proper preparation of the material. Selection of pieces should favor those with normal structure and straight grain. If possible, avoid pieces with large, obvious defects. Lumber from trees with spiral grain will invariably twist upon drying. Irregularities such as crotch grain or burls are aesthetically interesting but chancy to dry, since their cell structure usually has variable and unpredictable shrinkage. Knots are troublesome if they are large enough to involve serious grain distortion. Logs with sweep or from leaning trees having an eccentric cross-sectional shape probably contain reaction wood and will almost surely develop warp and stress due to abnormal shrinkage.

Whether preparing lumber or carving blocks, remember that normal shrinkage is about double tangentially as radially. My initial rule in splitting carving chunks from logs is to avoid pieces containing the pith. A half log or less that does not contain the pith can dry with a normal distortion of its cross-sectional shape, like slightly closing an oriental fan (*Figure 8.8*).

Another advantage of not boxing in the pith is being able to see if any overgrown knots are present that may not have been apparent from the bark side (see *Figure 2.33* on p. 35). Every knot is a portion of a branch that developed from the pith, so it is important to examine pieces from the pith side to discover hidden branch stubs, especially if they have decay. Additionally, the pith area is often abnormal juvenile wood that might best be eliminated.

In sawing lumber, minimize cup by favoring quartersawn boards, which have no tendency to cup, or flatsawn boards taken farthest from the pith. Boards sawn through the center of the log, containing the pith or passing close to it, will typ-




Figure 8.8 • This half-log section, not containing the pith, was jointed flat before drying. It has dried check-free but not without distortion. (Photo by Richard Starr)



Figure 8.9 • End-coated half-log sections of eastern white pine are stickered and open-piled for slow drying. (Photo by R. Bruce Hoadley)

ically cup severely along the center (or split open if restrained). Consider ripping such pieces into two narrower boards (and discarding the pith) before drying.

To prevent rapid end-drying, which will ruin carving chunks and the ends of lumber, the end-grain surfaces should be coated (*Figure 8.9*). The idea in end-coating is to allow all moisture loss to take place only from lateral surfaces. Any relatively impervious material (such as paraffin, aluminum paint, or urethane varnish) in ample thickness will do nicely. End-coating can be applied to relatively wet surfaces by giving a primer coat of acrylic latex material first. It is important to end-coat as soon as possible after sawing, before even the tiniest checks can begin to develop. Once a check develops, the cell-structure failure will always be there, even if it later appears to have closed. Also, when normal drying stress develops, a small check can provide the stress concentration point for further failures, which otherwise might not have even begun in check-free wood.

Another good reason for immediate end-coating is to prevent ever-present airborne fungal spores from inoculating the surface. If the bark is loose, it should be removed: otherwise the layer of separation will become a fungal culture chamber.

In some species, radial drying may be significantly faster than tangential drying. Therefore, if the bark on larger carving blocks is tight (as with winter-cut wood), it may best be left on to slow the radial drying. If the bark has been removed from a heavy slab or flitch, it should be watched carefully during the early drying stages for signs of surface checking into exposed tangential surfaces.

Don't forget to mark a number and date on each piece. It is amazing how easily your memory can fail once you have several batches of wood in process.

Lumber must be correctly stacked so proper drying will result. Stacking must ensure maximum air circulation around virtually every surface of the material. With irregular carving blocks, merely piling them loosely may suffice, as long as flat surfaces do not lie against or very close to one another. No attempt should be made to restrain distortion of large chunks. With lumber, however, carefully designed, systematic stacking is best.

The usual stacking method for lumber is to arrange boards in regular layers, or courses, separated by narrow strips, or stickers (*Figure 8.10*). This permits free movement of air around the lumber, uniformity of exposure of the surfaces, and restraint to minimize warp. The stickers must be dry and free of fungi and at least as long as the intended width of the stack. To ensure uniform restraint in a course, lumber and stickers should be as uniform in thickness as possible. In planning the stack, stickers should be placed at the very ends of each course and at least every 16 in. along the length of the boards. Stickers should be lined up in straight vertical rows.

It is best to have lumber uniform in length, but if random lengths are unavoidable, they should be arranged in a stack as long as the longest boards; within each course, stagger the position of alternate boards so their alternate ends are lined up with the end of the stack. This "box-pile" system prevents excessive drying of overhanging ends. The ends of long boards hanging out of the stack lack restraint, resulting in excessive warp or sag. To prevent excessive drying degrade to the top and bottom courses, extra outer courses of low-grade lumber or even plywood can be added to the stack.

In large stacks, the majority of boards are restrained by the weight of others above (*Figure 8.11*). In small stacks, extra weight (old lumber, bricks, cinder blocks, etc.) should be placed atop. An alternate method of applying restraint is to assemble rectangular frames to surround the stack. The stack can be wedged against the frames (*Figure 8.12*) and the wedges tapped farther in to maintain restraint as the stack shrinks. Obviously the weighting or wedging should not be so extreme as to prevent shrinkage of the boards across their width or to actually crush the lumber or stickers.

Temperature and humidity in a dry kiln can be controlled, but to dry small quantities of wood in the home or shop you must make do with existing conditions. Choose locations or regulate conditions to allow only moderate drying at first, followed by more drastic conditions once the lumber has reached a lower moisture level. Remember, the drying compromise is especially delicate here. The gradient cannot become too extreme because we do not want surface checks, and case-hardening cannot be allowed since we cannot condition at the end. Nor can we slow down drying too much,





Figure 8.10 •
How to build
a lumber pile.

for surface drying must take place early enough to deter fungal activity.

One logical starting place is out-of-doors. Except for especially arid regions, the relative humidity is usually moderately high. Piles of blocks or stacks of lumber should be kept well up off the ground to avoid dampness and should be protected from direct rainfall and sun rays as well. Any unheated building that has good ventilation is ideal. Most garages serve well, and even unheated basements are suitable if plenty of air space around the stack is provided.

In air-drying outdoors, some rather obvious seasonal variations will be encountered. In many eastern areas, slightly lower humidity and more prevalent winds favor drying in spring months. In winter, if temperatures drop to near

or below freezing, drying may be brought to a standstill. You must therefore interpret conditions for each particular area. If wood is intended for finished items that will be used indoors, outdoor air-drying will not attain a low enough equilibrium moisture content. The material must be moved indoors to a heated location and again allowed to reach equilibrium before it is worked.

Surface checking should be closely watched. Minor shallow surface checking that will later dress out are routine and can be ignored. However, deeper checks should be considered unacceptable. The worst ones are those that open up but later reclose. Often they go unnoticed during subsequent machining, only to reveal themselves when staining and finishing. If any serious end checks develop, don't pretend they




Figure 8.11 • Most of the boards in the drying shed (A) are restrained by the weight of the others. A similar but simpler setup (B) uses a sheet of corrugated plastic to protect the wood. In both cases, the boards are stacked in the sequence they came off the saw. (Photos by Richard Starr)




Figure 8.12 • Small quantities of lumber can be boxed inside wooden frames. Double wedges are tapped in to maintain tension as the wood shrinks. If you are chainsaw-milling the logs yourself, keep the boards in the order they came off the tree.

don't exist or that they will ever get better or go away. For example, if a large carving block develops a serious check, this indicates fairly intensive stress; it is best to split the piece in half along the check, thus relieving the stresses, and to be satisfied with smaller pieces.

If wood must be located indoors from the start, drying may be too rapid. Any signs of surface checks in the material suggest that some retardation may be necessary. This can be accomplished by covering the entire stack with a polyethylene film. Moisture from the lumber will soon elevate the humidity and retard the drying, and some provision

must be made to allow moisture-laden air to slowly escape. This arrangement must be watched closely, since air circulation cannot be totally stopped. Moisture condensation on the inside of the plastic covering or any mold on the wood surfaces may mean the stack has been turned into a fungal culture chamber and signals the need for speeding up the drying again. Common sense will suggest how often to check the wood and how to modify the storage location to speed up or slow down the drying. The seasonal humidity fluctuation encountered in heated buildings must also be allowed for in determining the equilibrium moisture level.




Figure 8.13 • A drying block of wood can be weighed periodically and its weight recorded on a graph against time. The graph levels out as equilibrium moisture content is reached. The basswood carving at right, shown as it neared completion, was made from timber seasoned and monitored as described here. (Photo by R. Bruce Hoadley)



Drying progress can be monitored by weight. Weights should be taken often enough to be able to plot a fairly coherent graphical record of weight against time (*Figure 8.13*). Weighing should be accurate to within 1% to 2% of the total weight of the piece. A large chunk in the 100-lb. to 150-lb. range can be weighed on a bathroom scale. Pieces in the 10-lb. to 25-lb. category can be weighed with a food or infant scale. Small stacks of boards can be monitored by simply weighing the entire stack if this is convenient. In larger stacks, sample boards or small groups of boards can be pulled and weighed periodically.

The last stage of drying should be done in an environment that is similar to the one in which the finished item will be used. The moisture content of the pieces will eventually level out and reach a near constant equilibrium with only faint gains and losses of moisture in response to seasonal fluctuations in humidity.

When material comes into equilibrium weight with the desired environment, it's ready. Don't pay attention to generalizations such as "one year of drying for every inch of thickness." Such rules have no way of accounting for the tremendous variation in species characteristics or in atmospheric conditions. Basswood or pine decoy blanks 4 in. thick dry easily in less than a year, whereas a slab of rosewood 4 in. thick may take much longer to dry without defects. In

general, low-density woods are easier to dry than high-density woods. Since the average cell-wall thickness is less, moisture movement is greater and this results in faster drying. In addition, the weaker cell structure is better able to deform in response to drying stresses, rather than resisting and checking.

Whether drying log sections or boards, remember that the drying must be somewhat regulated; usually at the beginning, indoor drying proceeds too quickly and needs slowing down.

Although exact drying times are impossible to predict, the drying times listed in *Table 8.2* on p. 156 give an idea of the comparative ranges of drying time for representative species of domestic woods. After some experience is gained for a particular species and thickness dried in a certain location, a fairly reliable estimate can be made as to the necessary drying time. Here, the initial date you mark on the piece will serve you well.

Perhaps the greatest pitfall is greed. Most woodworkers never feel they have enough material and tend to overstock. With green wood, this can be disastrous. Don't try to handle too much. Don't even start to dry your own wood if you can't follow through. More material is ruined by neglect than by lack of know-how.

STORING LUMBER

The previous discussion of relative humidity and the emphasis on wood as a hygroscopic material should serve nicely to guide the woodworker in sensible storage for wood once it is dried. Wrapping *dry* lumber in polyethylene film or even heavy kraft paper can be a tremendous help in getting through peak periods of dryness or humidity without excessive moisture exchange.

Controlling humidity in the woodworking shop is too broad a subject to cover adequately in this book. In most cases, ordinary techniques of humidification or dehumidification can be used. Two improvisations mentioned below are an economical way to control humidity in a small chamber for small quantities of wood.

Woodworking and carving projects in progress are too often neglected in this regard. Rapid changes in relative humidity during the several days or weeks involved in the completion of a project must be taken seriously. Even as I have been writing this section, during the last of May and beginning of June, I have been startled by the change in humidity. It has been a late spring, but I still expected an earlier rise in the indoor RH. Watching the dial hygrometer on my office wall, it seemed stuck in the 20% to 30% range all through May. I actually wondered if it were broken. Even through a few rainy but raw days around the first of June it only edged to around 40%, then "stuck" again. Then, in the second week of June, things began to happen. A spell of warm weather moved in with lots of rain and fog. Within hours the hygrometer read 55% RH.

I was working on some experimental wind turbine blades involving laminated spruce spars and molded maple plywood skins. I quickly unrolled some polyethylene, stapled up some 8-ft. bags, and slid in the half-finished blade components. I'm glad I did. The hygrometer in the lab climbed to 76% RH and was headed higher. I can't imagine why more woodworkers and carvers don't give greater thought to wrapping their work between sessions.

The first method of controlling humidity is to determine the absolute humidity of the average ambient conditions, then to elevate the dry-bulb temperature sufficiently to reduce the relative humidity to the desired level. For example, suppose your shop is about 68°F and the humidity is 65%. The absolute humidity is about 5 grains per cu. ft. Suppose you wish to condition some pieces of wood to 6% moisture content. Raising the temperature to 92°F will drop the relative humidity to 30%. just about right to give an equilibrium moisture content of 6%. A small closet or plywood chamber with enough light bulbs to maintain a temperature of 92°F will effect the desired moisture conditioning. A small thermoregulator to turn off the light when the desired temperature is reached would be a useful addi-

tion. But keep in mind the fact that the dry-bulb temperature will have to be adjusted accordingly as the atmospheric humidity changes.

Another technique involves a tray of liquid that has a large enough surface area to influence the humidity in an enclosed chamber. If plain water is used and the chamber area is small compared with the area of the water surface, the air soon will be virtually saturated (100% relative humidity) and an equilibrium reached in the atmosphere with equal numbers of water molecules leaving and reenter-

TABLE 8.2—Approximate time to air-dry 4/4 lumber to 20% MC*

Softwoods	Days
Douglas-fir	20–200
Hemlock, eastern	90–200
Hemlock, western	60–200
Larch, western	60–120
Pine, eastern white	60–200
Pine, southern yellow	30–150
Pine, sugar	15–200
Pine, western white	15–150
Redwood	30–365
Spruce, red	30–120
Hardwoods	
Ash, white	60–200
Aspen, bigtooth	50–150
Basswood, American	40–150
Beech, American	70–200
Birch, yellow	70–200
Butternut	60–200
Cherry, black	70–200
Elm, American	50–150
Hickory	60–200
Maple, red	30–120
Maple, sugar	50–200
Oak, northern red	70–200
Oak, northern white	80–250
Oak, southern red	100–300
Sweetgum	60–300
Sycamore	30–150
Walnut, black	70–200
Willow, black	30–150
Yellow-poplar	40–150

*Minimum days given refer to lumber dried during good drying weather, generally spring and summer. Lumber stacked too late in the period of good drying weather or during the fall and winter usually will not reach 20% MC until the following spring. This accounts for the maximum days given.




Figure 8.14 • An ordinary aquarium can be converted to a conditioning chamber for small wood samples. Passing air through a saturated solution of a selected chemical salt controls relative humidity.

TABLE 8.3—Suggested salts for controlling relative humidity in closed containers.*

Approx. EMC (%)**	RH (%)***	Chemical	Salt
4.5	20.0	$KC_2H_3O_2$	Potassium acetate
6.0	32.0	$CaCl_2 \cdot 2H_2O$	Calcium chloride
6.5	33.5	$MgCl_2 \cdot 6H_2O$	Magnesium chloride
8.0	42.0	$Zn(NO_3)_2 \cdot 6H_2O$	Zinc nitrate
10.0	58.0	NaBr	Sodium bromide
12.0	66.0	$NaNO_2$	Sodium nitrate
14.5	76.0	$NaC_2H_3O_2 \cdot 3H_2O$	Sodium acetate
16.0	80.5	$(NH_4)_2SO_4$	Ammonium sulfate
17.5	84.0	KBr	Potassium bromide
20.0	90.0	$ZnSO_4 \cdot 7H_2O$	Zinc sulfate
24.0	95.0	$NaSO_4$	Sodium sulfate

* Since every potential reactive property or health hazard of chemical salts cannot be anticipated, the following precautions should be routinely observed when using any chemical salts.

1. Store and use only at or near room temperature, avoiding excessive heat.
2. Handle carefully, avoiding skin contact, inhalation of fumes, or ingestion.
3. Use only as aqueous (water) solutions and never intermix salts. Prevent contact with organic materials and metals. Mix only in glass or ceramic (nonmetal) containers using glass stirrers.

**For white spruce (*Picea* spp.)

***At 20°C (68°F)

ing the liquid surface. However, if chemical salt is dissolved into the water, fewer water molecules will leave the liquid surface. The equilibrium state will therefore have fewer water molecules in the air, and the humidity will be lower. Since different salts have different solubilities, different humidities can be created by choosing particular salts. A list of salts is given in *Table 8.3*. The choice would depend on cost as well as desired humidity level.

This technique has been used successfully in the display of museum objects that must be kept at a prescribed humidity level. Trays of solution in the display case are hidden from view by visual baffles. This technique would doubtless have application for such items as musical instrument parts, in which precise conditioning before machining is desired. An aquarium with a glass lid makes an excellent chamber (*Figure 8.14*) because the entire bottom can be filled with saturated salt solution. The rack for wood pieces should allow air circulation. An excess of undissolved salt in the solution is advisable so that if the temperature fluctuates slightly there will be enough salt to keep the solution saturated. It is also important to keep the solution slightly agitated and the air moving. A standard fish-tank aerator can provide this agitation and air circulation.

Everything that has been discussed in this section is directly or indirectly related to the fact that wood seeks to establish an equilibrium moisture content according to the relative humidity of the surrounding atmosphere. If this point is kept in mind, the rest will follow logically.



Figure 9.1 • A standard plane produces a jointed curl-type chip in 90° - 0° orthogonal cutting. (Photo by Richard Starr)

MACHINING AND BENDING WOOD

Of all things fashioned of wood, the list of those that use the tree or its branches in their natural form is brief: fence posts, wythes for baskets, and perhaps a few others. In nearly every other instance, the stem of the tree must be reformed, usually by removing parts of it, until the desired shape and size remains. An old-timer, a blacksmith by trade, told me bluntly that *my* hobby—woodcarving—was *easy*. He added, with a sly glance, "All you have to do is cut off what you don't want." If only it were that simple!

MACHINING WOOD

There is hardly a subject of more importance to the woodworker than machining. At the same time, I cannot imagine an aspect of woodworking that is more complex (*Figure 9.1*).

Machining of wood is a stress-failure process. By hand or machine power, force is transmitted to the wood by means of a cutting tool. The tool has pertinent geometry, and the wood has pertinent physical and mechanical properties. The orientation and direction of the force are controlled by the design of the tool and/or by the woodworker's hands, and these things determine the way stresses develop at the cutting edge and how the failure of the wood (or cutting) occurs.

Two factors are important in this regard. One is the sharpness of the tool, in which the cutting area (A) of the tool edge is small enough so that the force (P) applied to the tool will cause a stress (P/A) greater than the strength of the wood. The second factor is the condition of the wood—its moisture content, temperature, and defects.

It is appropriate to analyze machining as the action of a **cutting tool** on a piece of wood or **workpiece**, with the cutting action that takes place referred to as **chip formation**, wherein a portion of wood called the chip is separated from the workpiece. Chip formation involves the geometry of the tool, the condition of the wood, and the motion of the tool relative to the orientation of the structure of the wood.

The objective of machining always should be the paramount consideration. The approaches used may differ dras-

tically, depending on the objectives sought. These objectives may be classified as:

- **Severing:** When you make two or more pieces from one, for example, splitting firewood or bandsawing rough parts from a plank.
- **Shaping:** When you impart a specific shape to the workpiece, in some cases a flat-planed surface, in others some specific contour. Jointing a flat surface on a cupped board is one example; milling an ogee molding is another.
- **Surfacing:** When you create a surface of prescribed quality, such as sanding a surface prior to finishing or jointing edges to be suitable for gluing.

In most cases, two or even all three of the above are involved concurrently. In ripping boards into strips, for example, one might want the resulting surface to be true enough and of appropriate condition to be glued. In most machining, the objective is the workpiece, and the nature of the chip removed is irrelevant.

An interesting exception is knife-cut veneer, where the veneer is the chip and the surface left on the workpiece becomes one face of the veneer that will be removed by the next cut. Although the average woodworker is not involved in making veneer, anyone who uses it should understand the machining process involved in its manufacture.

Let's survey the interrelationship of the workpiece, the tool, and the chip formation during machining.

THE WORKPIECE

The aspects of wood that affect machining have already been covered in previous chapters. The structural nature of wood in terms of its three-dimensional properties is particularly important. Density variation among and within species is also of obvious importance, as is unevenness of grain, especially in ring-porous hardwoods and uneven-grained softwoods. Heartwood extractives in some species are particularly abrasive and contribute to tool dulling. Defects such as knots create both irregularities of grain direction and variations in density. Structural irregularities such as wavy or interlocked grain cause special machining problems. Moisture content influ-

ences machining as it affects the strength of wood and so do stresses or checks developed in drying.

Strength of wood is, of course, the bottom line. The relationship between the strength of wood parallel to the grain and perpendicular to the grain is perhaps most important, although every other factor affecting strength in turn affects machining.

THE TOOL

At the business end of a cutting tool, where chips are formed, the tool geometry can be described in terms of a **cutting edge** formed by its intersecting **face** and **back** surfaces, or planes (Figure 9.2). The critical geometry of the cutting edge is typically defined in terms of its direction of motion:


α = the **rake angle** (also called the **cutting angle**, the **hook angle**, the **chip angle**, and the **angle of attack**), the angle between the tool face and a line perpendicular to the direction of travel of the edge.

β = the **sharpness angle**, the angle between the face and back of the knife.

γ = the **clearance angle**, the angle between the back of the knife and the path of travel of the edge.

As required by circumstance, cutting-tool geometry can be varied considerably. The sharpness angle will always be a positive value. The cutting angle and clearance angle can be negative values; a negative clearance angle indicates interference between tool and workpiece.

Figure 9.2 • The business end of a cutting tool consists of an edge formed by its intersecting face and back surfaces. Its geometry is described by the rake angle, α , measured from a line perpendicular to the direction of travel to the tool surface; the sharpness angle, β , measured between the face and the back of the tool; and the clearance angle, γ , measured between the back of the blade and the direction of the cut.



CHIP FORMATION

Figure 9.3 shows an ideal cutting action, which will vary according to the resisting grain orientation of the wood and the tool geometry. Energy is consumed in severing or separating the wood structure to form the chip, in deforming or rotating the chip, and in the frictional resistance of the tool face against the chip and the tool back against the newly formed surface of the workpiece. Each element varies in importance, depending on the type of cutting. In riving shakes, for example, after initial entry of the cutting edge and initiation of the split, the chip forms by fiber separation




Figure 9.3 • Idealized cutting action. Energy is consumed in severing the wood to form the chip, in deforming or rotating the chip, and in friction of the tool face against both the chip and the workpiece.

well ahead of the knife edge, with energy being expended to overcome friction on both sides of the knife and to deform (usually by bending) the chip being separated. In planing wood across the grain, the edge of the blade severs cell structure with minimal frictional resistance from the weak chip being separated.

When the resulting shape and surface quality of the workpiece are important, it is critical to keep chip formation close to the tool edge itself. When the chip is being formed well ahead of the tool, as in splitting wood, neither its shape nor its surface quality can be well controlled.

It would seem advantageous to increase the cutting angle and reduce the sharpness angle, thereby reducing both the amount of distortion of the chip and the resulting forces against the tool. In practice, however, one soon runs up against the limitations of steel. Such an idealized cutting edge would have little strength and would soon break or become dull. Increasing the sharpness angle of the tool makes the edge more durable but eventually leads to excessive frictional resistance or to uncontrollable chip formation.

When cutting into wood tissue with a tool edge, two principles must be kept in mind: First, failure occurs only when ultimate stress is reached; second, stress is *always* accompanied by strain. This means that contrary to the idealized cutting action shown in *Figure 9.3*, we must imagine something




Figure 9.4 • Real-world cutting action. The wood does not fail until ultimate stress is reached, and stress is always accompanied by strain. As the cut proceeds, the workpiece deforms ahead of the tool, severs, then both the workpiece and the chip spring back to some extent.

else, where in order to develop enough stress to produce failure, the wood must first deform (*Figure 9.4*). Considered another way, since stress is load divided by area, then the smaller the area of application, the higher the stress that will be produced by a given load. We should therefore try to concentrate cutting force on the smallest possible area.

This, of course, is what we commonly call sharpness. Most people think of sharpness as the minuteness of the cutting edge, which influences the relative force required in cutting. But one must also think of sharpness or dullness in terms of the deformation of the wood tissue in both the chip and the workpiece.

A helpful model for visualizing this relationship is to try to take a $1/8$ in. slice from the edge of a wet cellulose sponge with an ordinary table knife. The sponge simply moves out of the way, and no cutting is done. With a very sharp knife or razor blade the sponge can be cut, but only after it deflects noticeably ahead of the knife. "Chip formation" is irregular. Some sponge may tear away in places other than at the exact blade edge. When the "chip" of sponge is finally severed, the "workpiece" springs back, and an irregular surface is the result because of the irregular deflection. The springback of material after the cutting edge passes also illustrates the need for an appropriate clearance angle.

TYPES OF CUTTING ACTION

There are two basic types of cutting action. The first is called **orthogonal cutting**, in which the tool edge is more or less perpendicular to its direction of motion. The cut is in a plane parallel to the original surface of the workpiece, and the chip is continuous. An ordinary plane peeling a shaving from the edge of a board is one example. The second type of cutting action is called **peripheral milling**, in which a rotary cutterhead with one or more cutting edges intermittently contacts the work surface. As the head turns, each cutter proceeds on a curved path and removes a single chip.

Virtually every cutting situation can be compared with either orthogonal cutting or peripheral milling. Note that as the cutterhead radius increases in peripheral milling, it approaches orthogonal cutting.

Visualize a cube of wood with its sides oriented in the radial, tangential, and longitudinal planes. According to notation developed in the 1950s by W. M. McKenzie as a basis for classifying cutting action, orthogonal cutting is described by two numbers. The first is the angle between the cutting edge and the cellular grain direction, and the second is the angle between direction of cutting and the grain direction. Thus there are three basic cutting directions: 90° - 0°




Figure 9.5 • The three types of orthogonal cutting. The first number in the designation is the angle between the cutting edge and the grain direction. The second number is the angle between the direction of cutting and the grain direction.

cutting, 90°-90° cutting, and 0°-90° cutting (Figure 9.5). Note that 0°-0° cutting does not produce a chip but rather runs down the surface of the wood.

By considering each type of orthogonal cutting, some common types of machining can be understood more clearly.




Figure 9.6 • Cutting action of a handplane. The cut begins at A. The chip bends as it slides up the knife, and the wood fails ahead of the edge due to tension perpendicular to the grain (B). Finally the chip breaks (C), whereupon the next segment of the cut starts (D). In 90°-0° cutting, this is known as a Type 1 chip, produced by a relatively large cutting angle.

90°-0° CUTTING (PLANING ALONG THE GRAIN)
 Parallel-to-grain cutting is typified by the standard handplane. The chip forms as the plane is pushed along the board. The typical cutting action involves a cyclic sequence of events (Figure 9.6). The blade, also called the iron, separates fibers lengthwise to begin a chip (A). As the knife advances, the separated chip slides up the iron. The chip is now a cantilever beam that resists bending. It lengthens itself by failure of the wood in tension perpendicular to the grain well ahead of the knife edge (B). Finally, the chip is so long that bending stresses equal the strength of the wood and the chip breaks (C). The cutting edge advances to the fracture point and begins to lift the next segment of chip (D) and so on. The chip, produced in a long, jointed curl (see Figure 9.1 on p. 158), is referred to as a Type I chip in 90°-0° cutting.

The typical plane iron is set at an angle of 45°. Sharpening to an angle of 30° leaves a 15° clearance angle. If the rake angle becomes too great, the friction of the chip upon the iron face would increase and the efficient bending and breaking action would be lost.




Figure 9.7 • At small cutting angles, the face of the knife produces more forward compression than upward lifting. Failure occurs as a diagonal plane of shear right at the cutting edge. With enough force and a thin chip, the workpiece surface can be left in excellent condition. This is a Type II chip in 90° - 0° cutting.

At smaller cutting angles, a greater component of forward compression and a smaller component of upward lifting are transmitted to the chip. Failure may occur as a diagonal plane of shear, bending the fiber structure, so chip formation develops as a continuously generated curl of deformed cell structure. This is classified as a Type II chip (Figure 9.7). The cutting edge produces the surface as it dislodges cell structure. Greater force is required because of the compression resistance. Where the tool is well controlled and a reasonably thin chip is taken, chip formation takes place quite uniformly, and an excellent surface is produced. Some handplanes with a cutting angle of only about 30° are designed to take advantage of this type of cutting action.

As small (or even negative) cutting angles are used, force is transmitted mainly as compression parallel to the grain. The cutting edge produces the surface as it shears free the cell structure. As the wood fails in compression, the damaged cell structure packs up against the cutting face and may form a wedge that transmits force and causes failure out ahead of the edge, often below the projected cutting plane. The failure is erratic and leaves an irregular surface and is accompanied by an irregular chip of mangled cell structure. This is Type III chip formation (Figure 9.8). With very low cutting angles, a smooth surface and uniform cutting action occur only when the chip taken is extremely thin and forms Type II chips. This is the cutting action of scrapers.

The quality of cutting depends mainly on two factors: the grain direction and the mechanics of chip breakage. Figure




Figure 9.8 • At very small or even negative cutting angles, force is transmitted mainly as compression parallel to the grain. The damaged cells pack up against the cutting surface, often causing erratic failure ahead of and below the edge. This is the Type III chip in 90° - 0° cutting. The snowplow effect can only be avoided by taking a very thin chip, whereupon it becomes Type II cutting. This is how cabinet scrapers work.

9.3 on p. 160 assumes perfectly straight grain, which in reality is often the exception. Usually some degree of cross grain exists wherein the fiber direction either rises ahead of the projected line of cut or leads down below it. The former case is termed cutting with the grain, the latter cutting against the grain (Figure 9.9).

Cutting with the grain is preferable, since the splitting of the wood associated with chip formation projects harmlessly into the next chip segment, which subsequently will be removed. The cut produces a new surface generated by the continuous severing of wood at the tool edge. Cutting with the grain is very efficient because most of the chip segments fail readily due to cross grain.

The woodcarver will find that cutting with the grain at an acute angle to the grain is a fairly efficient way to remove large amounts of stock. At the same time, 90° - 0° Type I chip formation using a hand chisel can be painfully undesirable in carving. The case in point involves carving with the grain, where a splinter-type chip slides all the way up the face of the tool and jabs the carver in the hand (Figure 9.10). I have numerous scars on the outside heel of my left hand thanks to this situation, and I collect another every time I fail to wear a glove when carving.

By contrast, cutting against the grain can result in chip formation where the splitting projects below the intended plane of cutting. The resulting surface is called chipped or torn grain. In some cases, as in planing the edge of a flat-

sawn board with spiral grain or in passing a flatsawn board with diagonal grain through a surface planer, the board can be alternately turned end-for-end so that cutting will occur with the grain. In other cases, however, as with the bulge of grain direction associated with a knot, some cutting must take place against the grain.

To minimize the depth of torn grain, the breaking length of the chip segments must be controlled. One remedy is to take an extremely thin cut, in so the chip segments break easily and frequently. Another approach is to introduce a "chip-breaker," such as the cap iron on a handplane




Figure 9.9 • In the real world, the wood grain is rarely parallel to the cutting direction. Typically the fibers are rising ahead of the line of the cut, and cutting with the grain leaves a very smooth surface (A). When the fibers lead down below the line of cut, cutting against the grain leaves a chipped surface (B). Woodworkers usually reverse either the work or the tool to cut with the grain.

(Figure 9.11). The cap must be located suitably close to the cutting edge and must fit tightly enough to the face of the iron so the chip will not slip beneath it and jam but will slide up easily and quickly bend beyond its breaking point. The face and mating edge of the cap iron should be shaped as precisely as the cutting edge of the iron itself, for the cap iron is an integral part of the cutting mechanism.

The importance of the clearance angle in the cutting process should be appreciated. As with the "springback" of a wet sponge, it is also true that some deflected cell structure will recover after the chip forms. In order for the back of the cutting edge to clear this material, frictional drag and pressure against the back of the blade must be eliminated. If the cutter were infinitely sharp, of course, little clearance would be needed, and recommended clearance angles of up to 15° may seem excessive. However, such large clearance angles are probably safeguards against less-than-perfect sharpening. If the beveled side of the cutter is not perfectly flat, the



Figure 9.10 • In woodcarving, a splinter-type chip resulting from $90^\circ\text{-}0^\circ$ cutting can slide up the tool face and jab an unwary carver in the hand. (Photo by Randy O'Rourke)




Figure 9.11 • In $90^\circ\text{-}0^\circ$ cutting with a handplane, the cap iron minimizes torn grain by breaking the chip near the cutting edge.

clearance angle is reduced. As will be pointed out when discussing sharpening, it is elementary that no portion of the cutter be deeper than the cutting edge itself.

In 90° - 0° cutting with a hand chisel, the bevel guides the cutting direction. The clearance angle is effectively zero, and springback is automatically compensated by the angle at which the tool is held. Frictional resistance is overcome by whatever force is applied to advance the chisel.

Most handplaning occurs along the grain and involves 90° - 0° cutting, whether the handplanes operate on the whole surface of the workpiece (as in planing a flat surface) or whether they plow a groove or form a rabbet. Spokeshaving down a canoe paddle is another example of 90° - 0° cutting where tool geometry and depth of cut are fixed by tool design and adjustment. Rough-shaving an ax handle with a drawknife and taking long shavings along the grain with a pocketknife are also 90° - 0° cutting; in these cases the cutting angle, clearance angle, and depth of cut are controlled by the way the tool is held.

PERIPHERAL MILLING (MACHINE PLANING) Orthogonal cutting in the 90° - 0° mode has its counterpart in peripheral milling when a revolving cutterhead operates along an edge or face of a board as in the jointer, single surfacer, spindle shaper, and router.

The cutting action is modified by the path of each cutting edge, which follows a trochoidal path due to the combined revolution of the cutterhead along the surface of the workpiece (*Figure 9.12*). Each cutting edge takes a curved chip




Figure 9.12 • In peripheral milling, each cutter follows a trochoidal path relative to the workpiece, the result of cutterhead rotation plus feed. Each cutter takes a curved chip from the workpiece, usually by up-milling (inset).

from the workpiece. Customarily, rotation of the cutterhead is opposed to the feed, representing the upmilling condition.

In most rotary cutterhead designs, the cutting angle is decreased to between 10° and 30° . This requires more power to make the cut, but the chip type produced approaches a scraping Type II or Type III chip rather than a splitting action, as in Type I chips, since there is less uncontrolled splitting ahead of the blade. Also, the rotational speed of such cutters translates into relatively thin chips.

The surface generated by the overlapping cutting arcs of successive edges is wavelike. These waves are often visible and are known as knife marks. *Figure 9.13* shows an extreme case of knife marks in crudely planed structural lumber—only 4 to the inch. The marring of the surface is plainly visible. The best surface for finish lumber is produced with 12 to 25 knife marks per inch. The height of the waves is typically quite small and may not be seen easily with the naked eye. Their visibility is the result of crushed or buckled cells, as well as the actual surface irregularity of the waves (*Figure 9.14*).

When the number of knife marks per inch exceeds 30, unless the cutting edges are *extremely* sharp, the surface will be worse than the one made with fewer marks per inch. With so many knife marks per inch, the chip gets so small that each cutting edge does not bite but rather rides over the surface, as with the table knife and the wet sponge. Frictional heat also may be produced, and the resulting surface, although apparently smooth, is simply glazed by the crushed cell structure and chemically altered by heating. Extremely slow feed rates can also scorch the surface, which is clear from the obvious discolored band that results when a board gets stuck or pauses in a thickness planer. Such glazed surfaces on boards are not acceptable for gluing.




Figure 9.13 • The crude knife marks in this sugar maple board are delineated by crushed and buckled cells. (Photo by Randy O'Rourke)



Figure 9.14 • Light reflection reveals closely spaced knife marks on this butternut board. (Photo by Richard Starr)

Another problem with chip formation in peripheral milling is related to the practice of jointing the knives. After the knives are set, a sharpening stone is passed along the revolving cutterhead. Any high spots are ground back, ensuring that all the edges lie on the same cutting circle and that each knife takes a chip of equal depth. The jointing produces a flat area or land behind the knife edge, which has a 0° clearance (*Figure 9.15*). When knives are set nearly perfectly in the cutterhead, jointing is not necessary.

Jointed knives have both advantages and disadvantages. A very narrow land less than 0.01 in. will not create problems because the area of zero clearance is very small; at the same time, the sharpness angle will be increased, thus making the cutting edge more durable. A little extra jointing can effectively sharpen the knives, but the width of the land is thereby increased. As the cutting circle moves forward along the workpiece, a jointed back surface actually becomes a





Figure 9.15 • Jointed knives have the back side of the bevel ground so that each knife is exactly the same height. The problem with jointing knives is that if it is done to excess, it creates a negative clearance angle, and the back side of the blade will pound the surface of the wood. If the jointed land is kept as narrow as possible, the practice is a useful one.

Figure 9.16 • A sharp edge becomes dull with breakage and wear. The profile becomes blunt, and the leading edge is no longer the lowest point, which results in a negative clearance angle (γ).



negative clearance angle, and as the land becomes excessively wide, say 0.03 in. to 0.04 in., the wood surface is pounded and heated. Dull or rounded cutting edges also produce a negative clearance angle that compresses the wood surface (*Figure 9.16*).

Pounding caused by dull knives and excessive jointing of blades can produce serious defects in the wood. **Raised grain** results when wood is unevenly compressed during cutting, with resulting uneven springback. The extreme situation occurs on the pith side of flatsawn boards of uneven-grained conifers (*Figure 9.17*). The acutely angled layers of latewood are driven down into the weak supporting layers of early wood as they pass under the knife. Then they spring back and rise up above the machined surface. In extreme cases, the cell structure of the supporting earlywood is so badly damaged by compression that upon springback, the layers of latewood actually separate. This is referred to as **loosened grain** or **shelled grain**. When wood has MC 12%

to 15%, raised grain may also occur as a result of soft earlywood, even if the knives are sharp.

Raised or loosened grain is usually apparent immediately. In some cases, however, additional strain recovery or separation takes place at a slower rate. Even boards that are sanded smooth may continue to recover for years afterward. This effect is doubtless amplified by variations in moisture content. The "grain" will often show through or "telegraph" onto the surface of a painted board years later. Remember that the worst effects of raised grain in softwoods appear on the pith side, so it can be minimized by using a board so that the bark side is visible and the pith side is concealed. (This memory crutch may help: B stands for better and bark side, P stands for poor and pith side.)

Woolly or **fuzzy grain** (*Figure 9.18*) may result from planing material with a high moisture content, especially at low rake angles. Milling tension wood in hardwoods will also produce such a surface.





Figure 9.17 • Raised grain occurs during peripheral milling when layers of harder latewood are driven down into the soft earlywood and then spring back unevenly (A). It's typically worse on the pith side of a flatsawn board (B), and in extreme cases the earlywood layers may actually fracture, resulting in loosened grain (C). (Photos A and B by Richard Starr; photo C by R. Bruce Hoadley)



Figure 9.18 • Woolly grain occurs when planing material with a high moisture content or when machining tension wood in hardwoods. (Photo by Randy O'Rourke)



Figure 9.19 • Chip marks are the result when a machine's exhaust system isn't capable of clearing debris from the cutterhead. (Photo by Randy O'Rourke)

Another common defect that results from faulty surface planing is **chip marks** (Figure 9.19). This problem is machine related, not due to inherent flaws in the wood. It occurs when chips are not being cleared from the cutterhead because of insufficient air flow or static electricity. Instead, the chips are caught by the knives and then dragged through the region of chip formation, where they cause compression on the surface that has already been produced.

90°-90° CUTTING (PLANING END GRAIN) Planing across the end-grain surface of a board is a common example of 90°-90° cutting (Figure 9.20). Here the cutting edge must sever the chip by cutting longitudinal cell structure across the grain. The chip is displaced as much by shear deformation and failure as it is by bending, and it often moves up the face of the cutting edge as a partially connected string of rectangular chip segments.

Since the cutting tool must sever fibers across the grain, a dull edge (or a low rake angle) will drastically deform the wood in compression perpendicular to the grain during cutting. This may result in severely bent-over fiber ends and even splits down into the surface of the resulting cut. For this reason, high rake angles, low sharpness angles, and sharp cutting edges are essential to minimize damage on end-grain surfaces.

Ripsawing with a bandsaw or frame saw is a special case of 90°-90° cutting. Unlike planing across the end of the board, where the blade is typically wider than the cut, rip-




Figure 9.20 • 90°-90° cutting action: If the tool is dull or a thick chip is taken, damage may extend deep into the end-grain surface.

sawing incorporates a cutting-edge width, or **saw kerf**, that is narrower than the workpiece.

Since the objective of sawing is often simply to cut one piece into two separate parts, we may tend to think of it as similar to slicing a loaf of bread. However, we should keep in mind that in sawing we are working primarily at the surface of the bottom of the kerf. Therefore, in addition to forming the chip, we must sever it along its lateral faces in order to free it from the bottom of the kerf. But since the shear strength parallel to the grain is so low compared with the stress developed by the rake angle of the cutter face, the chip is easily sheared free along its sides.

To avoid frictional contact of the saw against the sides of the cut, its teeth must have **set**—that is, the saw must be made wider across its cutting edges than the overall saw-blade thickness (Figure 9.21). This is usually accomplished either by **swage-setting** or **spring-setting**. If rip-saw teeth have the set developed by swaging or spring-setting at the very tip, the sawn surface they produce is characterized by distinct tooth lines that stand out against the somewhat roughened plane produced when the chips were sheared free from the side walls of the kerf. Slightly jointing the sawteeth back as far along the sides of the teeth as the depth of the chip will clean up the sheared wood and will leave a smoother surface. However, excessive side jointing is counterproductive to set and will result in frictional heating.

Chopping out the ends of a rectangular mortise is another example of 90°-90° cutting accompanied by lateral




Figure 9.21 • Setting a saw involves making the tips of the teeth slightly wider than the gauge of the saw. It prevents the saw from binding in the kerf. Swage-set teeth are spread at the tip; spring-set teeth (more common on rip saws) are bent alternately to the sides.




Figure 9.22 • A table saw approaches ideal ripping action (90° - 90° cutting) when the blade is raised to its maximum height. It is also a more dangerous working situation. When the saw is lowered for safety or to make a grooving cut, 90° - 0° cutting is involved.

shearing out of the severed chip. Here also the sharpness angle should be as low as it can be and still survive.

On a table saw, the cutting action approaches 90° - 0° when the blade is raised to its fullest height (Figure 9.22). But when the blade is adjusted for making a shallow grooving cut, the rip teeth develop 90° - 0° cutting and shear the chips laterally from the cut. The chips removed from the bottom of the kerf tend to be more stringy.




Figure 9.23 • Veneer slicing is an example of 0° - 90° cutting. Unbalanced pressure from the knife causes checks in the loose side of the veneer. A counterbalancing nosebar and the greatest possible rake angle minimize knife checks.

0° - 90° CUTTING (PLANING ACROSS THE GRAIN) While 0° - 90° cutting is exemplified by using a handplane across the side-grain surface of a board, the classic case is veneer cutting. In making veneer, the chip itself is as important as the surface generated in the workpiece. In fact, one can produce a small strip of veneer by planing wet wood across the grain. With low-density species such as basswood in the green condition and especially if heated, a fairly respectable ribbon of veneer can be produced by taking a thin cut. However, if a thicker cut is attempted on unheated wood, you'll feel and hear a clicking as the chips are broken as they bend away from the workpiece. Examining the cutting action (Figure 9.23), we see that failures called **knife checks** are produced at regular intervals in the veneer. The face of the veneer having the knife checks is called the **open** or **loose side**. The opposite side is called the **closed** or **tight side** of the veneer. Knife checks are more pronounced in veneer greater than 1/8 in. thick. As veneer is cut thinner and thinner, knife checks tend to become insignificant.

In cutting veneer, the maximum possible rake angle minimizes knife checking. It is limited by the minimum sharpness angle that will hold up (about 21° in commercial veneer cutting) plus a clearance angle (0° - 2°). A rake angle of about 68° typically results. Even with properly designed and sharpened knives, checking is still a serious problem, so an




Figure 9.24 • With the nosebar retracted (A), the veneer checks seriously as it curls over the knife. A little nosebar pressure (B) reduces the checking. When nosebar pressure is in the range of 15% to 20% of the veneer thickness (C), checks are nearly eliminated. In this series of photos, the veneer being cut is relatively thick, exaggerating the knife-check effect. (Photos by U.S. Forest Products Laboratory)

auxiliary tool component, the **nosebar**, is introduced (*Figure 9.24*) to restrain the veneer as it is cut. By setting the nosebar to give proper pressure, knife checks can be minimized or virtually eliminated without unduly damaging the veneer by overcompression.

In gluing veneer, it is important to determine which side has the knife checks. It is common practice to place this side into the glue line. This ensures a check-free surface that will accept finish more uniformly. This presents a special problem when book-matching veneers, since half of the veneer slips will have the loose side exposed.

In woodcarving, 0° - 90° shaving is often an easy way to remove material with very little force. However, the wood tissue yields and easily tears ahead of the cutting edge, both above and below the plane of cut, so some tearing out of the surface may result. Any dull spots on the tool cutting edge will be signaled by scuffs along the severed surface.

Planing across the grain is often a desirable compromise on irregular grain, which will be torn by 90° - 0° planing no matter which way it is oriented. Other common applications of 0° - 90° machining include cleaning up the bottom of a dado with a router plane, chiseling into the sides of a rectangular mortise, and slotting a lathe turning with a parting tool.

CROSSCUT SAWING Sawing wood across the grain using a rip saw seldom produces a fine, smooth cut because the rip tooth can easily initiate chip formation from the main piece (by 0° - 90° cutting) as the result of parallel-to-grain fiber separation. However, the chip remains anchored by longitu-




Figure 9.25 • Red oak end grain is cut with a rip saw (A), which mangles the cell structure, and with a crosscut saw (B), which severs the fibers cleanly. (Photos by R. Bruce Hoadley)

dinal cell structure, across which shear resistance is extremely high. The forming chip has to be displaced by shearing across the grain or by simply ripping the cell structure loose. It is possible to crosscut with a saw designed for ripping, but the end-grain surfaces produced will show badly mangled cell structure (*Figure 9.25*). Where cleanly cut end grain is desirable, an additional cutting action is necessary to




Figure 9.26 • The teeth on a classic two-man crosscut saw are ideally designed for their purpose. Spring-set scratchers filed to a spear point cut the fibers free at the edge of the kerf, then slightly shorter raker teeth come along to roll out the chips. Such a saw cuts when pulled in either direction.

sever the chip loose at its end-grain faces. The design of the old-fashioned one- or two-man crosscut log saws is a classic solution to this problem. The crosscut design embodies two kinds of teeth (*Figure 9.26*). **Scratcher teeth** in even-numbered sets (typically two or four) are filed to a spear-point profile in side view and to a slim, almost knife edge as viewed from the end of the saw. In each set, alternate scratchers are spring-set and filed to opposite sides. Their job is to sever fibers at each edge of the kerf *before* the chip is formed. This is a sort of 90° - 90° cutting. Once the ends of the potential chip layer have been separated in this manner, the **raker teeth** roll the wood out of the kerf by 0° - 90° cutting. To ensure that the chips are severed before they are formed, the saw must be sharpened so the scratcher teeth project $1/64$ in. to $1/32$ in. beyond the cutting plane of the rakers.

The raker teeth are somewhat forked, with cutting edges facing in both directions so the saw cuts both ways. The chip formed by this saw can be compared to a very narrow strip of veneer, although it is quite shattered by severe knife checking because of the rather low rake angle of the rakers.




Figure 9.27 • The teeth of a crosscut handsaw are typically fine enough to eliminate the need for rakers. The spear-point teeth are spring-set alternately left and right.




Figure 9.28 • Circular combination saws can be used to rip or crosscut. The style shown, similar to the crosscut saw, has four cutting teeth per raker.

The deep gullets to each side of the tall raker teeth are necessary to roll up and hold the long, stringy chips being "raked" from the kerf. The piles of "caterpillars" that emerge from the cut are the hallmark of a well-tuned crosscut saw. To me, there is magic in the way a well-filed crosscut saw almost effortlessly whisks wood out of a green hardwood log. It is fun to watch an old-fashioned crosscut saw melt through a log and even beat a modern chainsaw at a woodsman's field competition.

Modern circular crosscut saws, which cut in only one direction, are a modification of the two-man crosscut saw. The periphery of the blade has sets of teeth interrupted by




Figure 9.29 • The standard wood-boring bit has double spurs and double twist. The spurs, which have a fairly large rake angle and a slim sharpness angle, form the sides of the hole. The lips, with a rake angle of around 40° and a clearance angle of 10° to 15° , follow behind the spurs to clear chips from the bottom of the hole.

large gullets. Behind each large gullet, the first tooth of a section is a raker tooth filed straight across, followed by an even number (typically four) of "cutting" teeth, with alternately filed points set to one side or the other. Rakers are filed $1/64$ in. below the outer cutting circle.

In carpenters' crosscut handsaws, the rakers are commonly eliminated (Figure 9.27). The spring-set pointed teeth shear the sides of the kerf, and fragments break loose into particles of sawdust. Crosscutting circular saws also are made in similar styles.

Combination saws are designed to cut as both rip and crosscut saws. One style resembles the alternately pointed crosscut except that the teeth are wider and their cutting edges are closer to straight across, but they are not perfectly straight across as in rip teeth. Another type of circular combination saw is similar to the crosscut, with sets of raker and cutting teeth (Figure 9.28). The cutting teeth are not as pointed and there are often only two cutter-type teeth per raker.




Figure 9.30 • In boring a hole perpendicular to the grain, the spurs alternate through a sequence of 90° - 90° and 90° - 0° cutting. The quality of this cutting determines the quality of the hole. At the bottom of the hole, the lips of the drill bit cycle between 0° - 90° and 90° - 0° cutting action as they clear the chips.

Boring bits are another example of rather complicated combinations of cutting action. The typical wood-boring bit (Figure 9.29) is of the double-spur, double-twist type. For hand-augering, it typically has a screw-threaded point to control the feed into the wood. Bits for machine-boring usually have only a brad point or no point at all. The spur does the initial cutting, forming the side surfaces of the hole.

During one revolution in a typical hole bored across the grain, the spur cycles through two complete transitions from 90° - 0° to 90° - 90° and back to 90° - 0° (Figure 9.30). The spur has a fairly large rake angle and slim sharpness angle with little if any clearance angle. Once the hole is generated by the spurs, the lips remove stock from the bottom of the hole: in so doing they vary between 90° - 0° cutting and 0° - 90° cutting. The lips are typically filed to a rake angle of 40° with a clearance angle of 10° to 15° . Because of the variable resistance to cutting—across, with, along, and




Figure 9.31 • The metal-worker's twist drill is commonly used for drilling small holes in wood. It has neither spurs nor point; the surface of the hole is made by the outer corners of the lips.

against the grain—the hole may be diagonally oval, not round. In boring parallel to the grain, the spurs are cutting in the 0° - 90° mode, the lips 90° - 90° .

The standard twist drill (*Figure 9.31*), commonly used for boring metals, is sharpened by grinding the clearance angle on the back face of the cutting edge on the lips. The bit has no spurs or point; the surface of the hole is generated by the cutting action of the outer corner of the lip. Although the quality of hole produced is inferior to that which can be drilled with a standard auger bit, the simplicity of this bit makes it well suited to small-diameter holes, as for screws and dowels.




Figure 9.32 • Summary of machining classification by orthogonal cutting type.

COMBINATION AND COMPROMISE

Some forms of machining such as veneer cutting, handplaning, and ripsawing are virtually pure cases of orthogonal cutting (*Figure 9.32*). Some tools, such as the two-man crosscut log saw, involve a combination of cutting modes. But many involve cutting action that is a compromise between two types (for example, planing the bevel across the end of a raised panel) or that varies between two types (as in ripsawing with a circular blade raised to different heights or the spurs of an auger through each half-revolution).

Some aspects of woodworking involve all conceivable interactions and combinations. Woodturning and woodcarving are good examples where every imaginable combination of wood structure and cutting direction seems eventually to present itself. Through experience, a woodworker develops a sense for the best cutting action or compromise to use in a given situation. Through intuition, a woodworker turns a workpiece this way and that from cut to cut, to favor 90° - 0° cutting with the grain and to avoid the costly splits of carving against the grain. There would be no value in attempting to analyze every cut in terms of orthogonal cutting or tool geometry. But the better the various types of cut-




Figure 9.33 • Under sufficient magnification, even a razor-sharp plane iron has a jagged edge. (Photo by Richard Starr)





Figure 9.34 • The photo shows a new jackknife factory-ground to a large sharpness angle. It won't cut wood when held normally. The large sharpness angle results in a negative clearance angle (A). When rotated to eliminate the negative clearance angle (B), the cutting angle is so small that it's difficult to form a chip. Both faces of the blade must be lengthened to reduce the sharpness angle (C), or all the sharpening must be done on one face, keeping the other flat (D). (Photo by Randy O'Rourke)

ting action are understood, the more successfully a woodworker will develop his intuition. And oftentimes, when a chronic machining problem such as torn side grain or scuffed end grain seems insoluble, careful analysis of the cutting action will suggest whether the problem is one of depth of cut, cutting angle, or tool sharpness.

SHARPENING

To me, the term sharpness includes two things. The first is the condition of the cutting edge, that is, how well the face and back surfaces combine to form a line of intersection. The closer the face and back approach true planes, the more

closely the cutting edge approaches a straight, not irregular, line. Of course, no matter how well the edge is formed, if magnified enough it will look like a mountain range (Figure 9.33). The second aspect of sharpness is correct tool geometry. A sharp edge is of little use if it is not associated with suitable cutting, sharpness, and clearance angles.

A common example is the ordinary pocketknife (Figure 9.34). It is usually sold with polished blades, with narrow factory-ground faces forming a cutting edge that includes a large sharpness angle. The cutting edge may be well formed and it may be sharp enough to cut your finger, but the geometry is all wrong for cutting wood.




Figure 9.35 • Microsharpening creates a larger sharpness angle near the edge without significantly affecting chip formation. Shown here are a microsharpened gouge and a microsharpened plane iron.

Try a typical paring cut and the knife won't work at all. It just slides along the wood surface. If you hold the knife in the usual position, the negative clearance angle prevents cutting. If you rotate the blade enough to eliminate the negative clearance, the rake angle becomes so small that the knife cuts poorly, with too much force required. The sharpness angle is simply too great. Its geometry must be corrected so that the cutting edge contacts the wood, meaning that the clearance angle is zero or greater when the knife is held in a comfortable position. For utility cutting toward and away from you, reducing the sharpening angle by lengthening both faces is one compromise. For whittling with a jackknife in the traditional draw-grip position, I like to keep the side of the knife that contacts the wood flat and do all my sharpening on a bevel on the other side. This way I have only one side to work on and one side to correct if I get it fouled up.




Figure 9.36 • Stropping the cutting edge against a nonrigid surface such as leather probably causes a slight rounding near the cutting edge. Stropping on the face bevel instead of on the back ensures that the cutting edge remains the lowest point on the tool and that the clearance angle is never less than 0° .

(Some tools, such as a standard ax, for example, must be sharpened on both faces to function properly.)

Another concept the woodworker can use to advantage is **microsharpening**, that is, increasing the sharpness angle near the very edge of the cutting tool. Most cutting geometry (a carving chisel and a jackknife are good examples) is a compromise between maximizing the rake angle for ease of cutting and maximizing the sharpness angle for a durable edge.

Microsharpening offers an interesting tradeoff by increasing the sharpness angle at the very edge (where it is needed for durability) without appreciably changing the rake angle in the area associated with rotation of the chip. On a woodcarving gouge, for example, a sharpness angle of 15° can be strengthened to 30° by a microbevel of 0.005 in.




Figure 9.37 • To sharpen a carving chisel, the author first hollow-grinds the bevel against an abrasive wheel, then hones the bevel with a fine India stone followed by a hard Arkansas stone. This produces flats at the tip and heel of the bevel. Next, the face is microbeveled, followed by a light stropping, mainly on the face of the microbevel.

with almost imperceptible change in the cutting resistance (*Figure 9.35*). With a standard bench plane whose iron is set at a rake angle of 45° and sharpened to about 30° , the sharpness angle can be microbeveled to about 40° , still leaving a clearance angle of 5° or so for good measure. Plane-sharpening instructions often refer to this as the "honing angle." The moderate jointing of planer knives is also microsharpening. Once again, microsharpening must not produce a negative clearance angle; the cutting edge must always be the deepest part of the tool.

When a blade is stropped on a nonrigid surface such as leather, I can't believe the faces are not altered at the very edge. I visualize something such as shown in *Figure 9.36*. This slightly rounded spear-pointing may then in effect be equivalent to microsharpening. With this in mind, I try to bias my stropping to favor heavier removal on the face than on the back of the edge.

While it is tempting to let this discussion wander over into techniques of sharpening, that subject is beyond the scope of this book. But I can't resist adding a few comments. First, the quality of the tool face and back and therefore of the edge formed at their intersection is closely related to the scratch pattern left by whatever abrasive was used to do the sharpening. Needless to say, deep scratches leave larger, fragile projections at the edge, and breakage of larger projections causes faster dulling. The finest abrasives leave the shallowest scratch patterns and a more durable as well as a "sharper" edge.

A certain mystique has been created around the notion of hollow grinding. I suggest it be looked at in terms of tool geometry. Hollow grinding gives a greater clearance where the back bevel is restricted, as with a planer knife. But it also reduces the sharpness angle, sometimes too much. In the case of a planer knife, a slight jointing takes care of this. I see hollow grinding as a convenient partner to microsharp-




Figure 9.38 • A gleaming bevel is the hallmark of a sharp edge. (Photo by Randy O'Rourke)

ening. In sharpening carving tools, for example, I like to hollow-grind the bevel (*Figure 9.37*). This establishes a basis for the sharpening and honing angles that I like to do by hand on flat stones, adding a final microbevel with a hard Arkansas pencil and stropping lightly with a piece of notebook paper. The hollow grinding narrows the area to be stone-sharpened to the edge and heel of the back. It also reduces friction in cutting (*Figure 9.38*).

Experienced woodworkers agree that sharpening is important. The beginner too often is slow to acknowledge this reality. The beginning woodcarver always asks, "Which tools should I buy first?" My stock answer, "a set of good stones," is seldom received with joy. Experience with dull and really sharp tools, however, quickly confirms that tools are almost worthless if they cannot produce the desired cuttings action.

BENDING SOLID WOOD

Bending wood is among the ancient arts of woodworking, as evidenced by early canoe frames, snowshoes, and utensils. That is not surprising, since bending wood into a curved form has two distinct advantages over machining. First, it requires narrower pieces so it wastes much less wood. Second, it reorients the grain to the curving axis of the part and results in much greater strength by avoiding cross-grain weaknesses. So, the question is not should I bend, but rather how should I bend.

GREEN-WOOD BENDING

In some cases, the weaker strength properties of green wood can be used to advantage. Green wood can be bent beyond its proportional limit, and allowing for a bit of elastic spring-back, it can be dried in the bent position. Back spindles for chairs are traditionally formed this way, and the weaving of ash splints in basketmaking is another traditional application. But since green wood must then be dried, the resulting shrinkage and drying defects may present a severe problem. What's more, bending to even greater extremes than can be accomplished with green wood is sometimes desired. Some means of additional plasticizing of the wood must therefore be found.

STEAM BENDING

The age-old method for plasticizing wood is with heat and moisture, a combination that markedly extends the plasticity. Let's review our earlier discussion of strength properties and in particular beam mechanics. A bent beam is in compression on the concave side and in tension on the convex side. When a beam is bent beyond its elastic limit, greater deformation occurs in compression than in tension. In fact, about 1% elongation in tension causes failure. Steaming the wood increases the compressibility to as much as 30% or more but only slightly increases the elongation ability in tension, perhaps no more than 2%. Yet by bending thin pieces to moderate curvature, many woods can be successfully shaped without failure.

In the trout-net bow shown in *Figure 9.39* for example, the 1/2-in.-thick strip of air-dried walnut bent to form like wet leather after 15 minutes of steaming. However, for sharper bends and for thicker stock, the 1.5% to maybe 2.0% tensile strain limit would be exceeded in a "free" bend. To restrict elongation of the convex face, a tension strap is used to restrain that surface of the wood (*Figure 9.40*). The strap is made of steel or other metal to which end blocks are



Figure 9.39 • The bow of this trout net was made from black walnut, free-bent after steaming without a tension strap. (Photo by Randy O'Rourke)




Figure 9.40 • When wood is bent without restraint, tension and compression stresses are balanced on opposite sides of the centrally located neutral axis. A steel strap with end-block restraints added to the convex side of the bend will carry most of the tension stress. This shifts the neutral axis toward the strap so the wood undergoes mainly compression strain.

attached. Because the tension strap acts as part of the beam, it carries the stress on the tension side of the bend. As bending takes place, the neutral axis is effectively shifted to or very near to the tension strap, so most of the bending strain in the wood must occur in compression. But since steaming will greatly increase the wood's plasticity in compression, the extreme compressive strain, if uniformly distributed, can be absorbed without undesirable results.

The critical interrelated factors that enter into bending are species, moisture content, steaming time, and geometry. The ratio of the radius of the bend to the thickness of the stock usually determines whether the wood can be bent free or whether a tension strap is required.

Softwood species are not well suited to steam bending. Among hardwoods, there is extreme variation in bending success. The species that bend well include ash, hickory, beech, walnut, white oak, birch, elm, and hackberry. Judging by catalpa's ability to take a bend in the green condition, I would guess it is another species worth trying.

For centuries woodworkers have been discussing what might be the best moisture content for bending stock and how long the piece should be steamed. Such considerations are interrelated, since the drier the wood, the stronger it is to begin with and the longer it must steam to become sufficiently plasticized. Wood bends best at a moisture content near its fiber saturation point, but then the wood must be dried down after bending and drying defects may occur. Low moisture content would eliminate drying defects, but the bending would be riskier. A fair compromise is air-dry levels of 12% to 20% MC, which are wet enough to bend fairly well but dry enough to minimize drying defects.

Because surface discoloration is usual and resurfacing generally is needed, some feel that drying distortion is not a serious problem and prefer to begin with wetter stock. In some species having extremely high green moisture content, the cell cavities are virtually filled with free water. If bending stress is applied, they cannot deform normally, and the internal hydrostatic pressure developed may cause the cells to burst.

The rule of thumb for time in the steambox is one hour of steaming for each inch of thickness of air-dried wood and one-half hour per inch of green wood. Everyone must adjust that rule to the circumstances at hand. As an old man once told me (about something other than steam bending, but it works), "Whatever works best for you, you use *that*." It is also important to remember that permanent reduction in the strength of wood can result from prolonged heating. When the steaming time is held to the minimum necessary for successful bending, strength losses should be no more than 10% to 20%.




Figure 9.41 • The basic elements of a steambox are the steaming element and the box; the rest depends on ingenuity. The main considerations are insulation, allowing condensate to drain from the chamber, introducing steam to the chamber at the point along the workpiece where the bend will be greatest, and supporting the workpiece so steam circulates all around it.




Figure 9.42 • Bending failures. Failure in free-bending wood with cross grain (A). Typical compression failure (B).

The curvature that can be achieved using steamed 1-in. air-dried stock varies. The better-bending species can be free-bent to a radius of 12 in. to 15 in.; using a restraining strap, bends to a 2-in. radius or less can be achieved. It always amazes me that bent stock stays in place as well as it does, especially if it can stay restrained on the form while its moisture content equalizes. Upon drying, the curve will often bend even more sharply due to the greater longitudinal shrinkage of the overcompressed concave side.

Intuition, rather than instruction books, has probably designed most steaming arrangements. Any vessel capable of boiling water and directing it into a steam chamber will do the job (*Figure 9.41*). A wallpaper steamer makes a nice steam source. For a steam chamber I have used everything from aluminum irrigation pipes to aluminum downspouts. I avoid ferrous metals because of discoloration problems. Although I've never tried it, I like the idea of building a steam chest out of plywood because its insulating value should minimize condensation compared with a thin-walled metal enclosure.

If you are choosy about the quality of bending stock, steam bending will probably be easier and more fun than you imagined. Any irregularity is apt to concentrate the strains and develop a compression buckle, which is the usual catastrophe once you have tension restraint worked out (*Figure 9.42*). Any knots, other irregularities, or reaction wood should be expected to cause trouble. Straight grain is a must. Decay, shakes, surface checks, pith, and similar defects should be eliminated. Take care to condition the stock to a uniform moisture content before bending.

PLASTICIZING WITH AMMONIA

In recent years, much interest has focused on treating wood with ammonia to plasticize it for bending. Ammonia treatment is more effective than steaming, apparently because ammonia interacts with the lignin as well as with the cellulose portion of the cell-wall structure. Species that bend well with steam are most readily bent with ammonia plasticizing, and even most species considered unsuited to steam

bending can be successfully plasticized with ammonia. Experiments in bending thin, ammonia-treated hardwood strips (1/16 in. to 1/2 in. thick) have shown that the technique can be applied to creating art forms and sculpture as well as functional bentwood objects such as room dividers, lamp bases, novelties, picture frames, furniture parts, and sporting equipment.

Two basic systems have been developed: immersion in liquid anhydrous ammonia at atmospheric pressure, and treatment with gaseous anhydrous ammonia in closed chambers at 145-psi pressure. (Household ammonia, commonly used for cleaning, is a water solution of ammonia and is useless in plasticizing wood.) Depending on the permeability of the species, treatment takes from one-half hour for 1/16-in. veneers to many hours for 3/4-in. lumber. Upon removal from the liquid or gas treatment, the pieces can be bent to shape with little springback. Within minutes to an hour, the ammonia dissipates from the wood sufficiently to set the bend in place, and eventually stiffness and rigidity are restored virtually to original levels.

In spite of the striking results possible with ammonia treatment, it is hardly a panacea for the difficulties of bending wood. Although the scientific principle is straightforward enough, the process involves expensive equipment in addition to working conditions that are disagreeable and potentially hazardous. With the liquid immersion process, heavy-duty refrigeration equipment is required to keep the ammonia below its boiling point of -28°F (-33°C). With gaseous treatment, a pressure chamber with connected holding tanks and pumping equipment is necessary. Therefore, only people experienced in the handling of hazardous chemicals should experiment with anhydrous ammonia. Because the ammonia fumes emitted while treated wood is being bent are extremely offensive, work must be done in the open air, with powerful exhaust facilities, or while wearing a gas mask and protective equipment.

Although plasticizing with ammonia may have important future potential for commercial woodworking, it is probably not likely to replace simple steam bending in the small workshop.



Figure 10.1 • The classic dovetail joint.

(Photo by Charley Robinson)

JOINING WOOD

How many things are made from single pieces of wood? I immediately think of salad bowls and spoons, walking sticks, baseball bats, rulers, some sculpture and carvings, ice-cream sticks—it's not a very long list. As you try to compose such a list, you soon realize how many products are made of more than one piece of wood, somehow joined, held, or stuck together, or of pieces of wood attached to one another by materials other than wood. The list of products made of joined pieces is endless, and the more functionally elaborate and important the things—furniture, boats, pianos, houses—the more complex and varied are the means used to join their components.

Wooden items are rather more prone to fall apart than to break. It is the rule rather than the exception that the weakest point in any wooden construction is at a joint. The successful woodworker focuses not just on each piece of wood but on the interrelationship of pieces of wood and especially on how they are joined together.

In our modern world, new and more complex forms of wood are constantly being invented. These new materials and products owe their success mostly to some kind of marriage between wood and other materials. The evolution of products is paralleled by the evolution of systems for fastening them together. New methods of fastening evolve, and each advance in turn paves the way for a new array of products (see *Figure 10.1*).

THE ELEMENTS OF JOINTS

I will not attempt to catalog or discuss the many joints in woodworking. Rather, I'll discuss the four critical considerations that determine the success of any given joint. One of the four may be of overriding importance in some particular situation, or any one may be interrelated with one or more of the others. These four basic considerations are:

- the stress system involved,
- the grain direction of the joined parts,
- dimensional change in response to moisture,
- the surface condition of the mating parts.

The **stress system** is what the joint is being asked to do mechanically, as a consequence of its being part of a structure for use. Joints may be in compression, tension, shear, or racking (bending), and usually the great difference in the strength of various joints depends on the stress situation. Most compression joints give little trouble, and shear stress is not too difficult to accommodate. Joints subject to tension and racking are typically the most troublesome. *Figure 10.2* shows joints under representative stress systems. Although it is not usually necessary to figure the loads precisely, one must have a general grasp of the direction and relative magnitude of stress in order to design and construct good joints. This analysis can come only from realistic examination of the structure in which the joint will be used and of the loads it is likely to encounter in service.

The second element is the **grain direction** in each mating surface of the joint, as related to the stresses involved. For example, the most difficult surface combination to fasten is end grain to end grain (see *Figure 10.2*). It would be easy to secure if the load were exclusively compression, but this is most uncommon without some racking stress. As a result, timber framers who must often lengthen stock to span a space have evolved an elaborate system of scarf joints, many with mechanical interlocks, whose principal purpose is to convert mating end-grain surfaces to long-grain surfaces.

End grain to side grain (see *Figure 10.2B*) is a very common situation, which can be accomplished quite satisfactorily if all factors are considered. When stressed in compression, the strength of such a joint is usually limited by the perpendicular-to-grain compression strength of the side-grain piece. When stressed in tension, the fastening to the end grain is the limiting factor, and when under racking stresses, either part may be the limiting factor. The solution typically involves a mechanical interlock formed on the end-grain piece or made by adding a third piece of wood to cross the joint.

Side-grain to side-grain joints (see *Figure 10.2C, D*) can be as strong as the wood itself when they are adhesive-bonded, even when the grain directions of adjacent members are not parallel. But here the third element comes strongly into play, the dimensional properties of the wood in response to changing moisture conditions.


























TYPE OF JOINT	COMPRESSION	TENSION	SHEAR	BENDING
A End grain to end grain 				
B End grain to side grain 				
C 				
D Side grain to side grain (parallel) 				
E Side grain to side grain (perpendicular) 				

Figure 10.2 • Some typical joints under loading stress.

Dimensional change in response to moisture is usually no problem in the case of end-grain to end-grain or parallel side-grain to side-grain joints (see *Figure 10.2*) because the orientation of the growth rings can be the same in both pieces. In these same joints, if the growth rings are not similarly oriented, the difference between radial and tangential movement might cause visual difficulties, if not structural problems.

In perpendicular side-grain to side-grain joints and in end-grain to side-grain joints (see *Figure 10.2*), the conflict between dimensional change along the grain and across the grain (especially where tangential direction opposes longitudinal direction) may become more important than the stress/strength of the original joint. The potential self-destructiveness of such joints should always be anticipated. A lap joint (see *Figure 10.2*), for example, might be very strong when glued, but it could self-destruct as a result of dimensional change.

The last element is the **surface condition** of the mating parts, including the precision of fit and evenness of bearing, the trueness of the surfaces, and the severity and extent of damage to cell structure resulting from the surfacing process. Uneven surfaces may concentrate enough stress to overcome the strength of wood or glue, while the same joint would survive very well if it had fit properly. Poorly fitted parts may also allow unintended motion, ending in destruction. Joints may fail not along a glueline but in adjacent wood tissue that had been mangled by poorly sharpened tools or bad woodworking technique while the joint was being cut. In joinery, the combinations of stress, strength, dimensional change, and surface quality are endless.

BASIC TYPES OF JOINTS

The term joint has various and sometimes overlapping meanings. In its broadest sense, it refers to any junction between two components or materials. Without reference to any accompanying means of fastening, joints can be characterized on the basis of the grain orientation of the mating surfaces as end to end, end to side, or side to side (*Figure 10.2*). Flat mating surfaces are loosely termed butt joints, although this term usually suggests either end-to-end butt joints or end-to-side butt joints (see *Figure 10.2A, B*). Side-grain to side-grain joints are more clearly designated as edge joints when the mating grain directions are parallel or as lap joints when the grain directions are perpendicular (see *Figure 10.2C, D*). The special case for miters and scarf joints could be termed cross-grain to cross-grain joints.

Obviously, such joints have no structural integrity without some means of holding or fastening the pieces together. I prefer to consider three basic types of joints or a combination thereof:

- **worked joints**, where the wood is physically interlocked or fitted together
- **fastened joints**, where a "third party," the fastener, is attached mechanically to both components
- **glued joints**, where an adhesive forms a continuous bond between two pieces by surface attachment.

I will discuss worked joints and fastened joints in this chapter. Gluing is a special technology involving chemical bonding and will be treated separately in chapter 11.

Each type of joint has its ancestor far back in history. The first worked joints might have been tree stems with forks or splits, interlocked with others, or perhaps circular branches inserted into knotholes. The first fasteners were probably thongs of hide or vines used to lash wooden parts together. Who can say when the first crude metallic nail replaced a wooden pin to hold two pieces of wood together? Adhesives were probably discovered when residues from cooking meat accidentally stuck two pieces of wood together. Modern fastening systems are merely refinements of each of these more primitive methods, evolving into complex and ingenious combinations.

WORKED JOINTS

Creating interfitting or interlocking shapes to provide strength and integrity in a joint has been a hallmark of the woodworking tradition. Although modern machines can simplify the making of fitting parts, the pride of accomplishment in hand-execution of difficult and beautiful joints will always be among the challenges, pleasures, and rewards of woodworking.

THE MORTISE AND TENON

Fastening of end-grain to side-grain joints can be accomplished with a high level of success using the mortise and tenon. The basic joint is fashioned by forming the end-grain component, the tenon, into a round or rectangular cross section and inserting it into a hole, or mortise, of the same size and shape in the side-grain component. By closeness of fit alone, this joint can have positive resistance in compression, shear, and racking, in which cases the strength of the wood in compression perpendicular to the grain limits movement in the joint (*Figure 10.3*).

The mortise and tenon is commonly associated with frame construction. In window frames, paneled doors, and other squared frames, the rectangular form is common. In chairs, round shapes are typically used.

The mortise-and-tenon joint has mechanical restraint in every direction except direct withdrawal of the tenon from the hole. Although this is the way a joint normally comes

apart, it most often does so only after damage due to racking. A racking load on a rectangular frame acts to deform it diagonally. Under racking loads, the tenon pivots in the mortise.

The basic "dry" joint can be improved in several ways. The most obvious is to glue it, thus adding side-grain to side-grain shear resistance along the mating mortise-and-tenon cheek surfaces to oppose the rotational effect. A second approach (*Figure 10.4*) adds a shoulder to the tenon, giving additional bearing surface to share the compressive resistance on the outside of the mortise.

In the discussion of beam strength in chapter 4, I pointed out that the greater the depth of a beam, the lower the axial stress developed when the beam is loaded. The mortise and tenon (end-grain to side-grain joint) can be thought of as a cantilever-beam attachment, so increasing the height of the "beam" will reduce stress (*Figure 10.5*). This also increases the surface area of the cheeks and thus the gluing area. Lengthening the insertion depth will further increase the resisting glue-shear areas.

At the same time, the improvement in mechanical advantage obtained by increasing height is offset by increased dimensional conflict between longitudinal and transverse grain orientation. Some careful compromises must therefore be worked out. For example, since tangential shrinkage (and swelling) is about twice the radial movement, it is best to have the radial (rather than tangential) grain direction of the tenon matched to the longitudinal grain direction of the mortise. It is also better to have the radial direction of the mortise matched to the longitudinal direction of the tenon. In *Figure 10.6*, joint A would be best, since radial/longitudinal grain direction is matched along the mortise cheeks both vertically and horizontally, and tangential grain direction is matched perpendicular to the plane of the mortise. Joint D has the worst dimensional conflict. As the height of the mortise (along the grain) is increased, joint survival increasingly depends upon moisture control.

The usual solution to dimensional conflict is to divide the joint into multiple sections (*Figure 10.7*). By keeping the




Figure 10.3 • Even without glue, a mortise-and-tenon joint has positive resistance to compression, shear, and racking but has no resistance to tension.




Figure 10.4 • Shear strength in the glue-line bonding the cheeks of a tenon restricts rotation in a shouldered tenon subjected to racking. The bearing surface of the shoulder carries compressive stress at A, while a gap (G) may open so that shear in the upper area of the tenon (S) will be greater than below (S-).




Figure 10.5 • A mortise-and-tenon joint functions like a cantilever beam, so increasing the height of the tenon will reduce the stress on the joint if the force (M) remains the same.

dimensions of each tenon within limits, dimensional conflict can be reconciled by mechanical restraint. Thus there is considerable advantage, especially in wide or thick stock, in multiple tenons or multiple splines. These considerations also emphasize the importance of well-made, well-glued joints designed for mechanical restraint of the dimensional conflict as the wood moves, as well as for initial strength.

In summary, the rectangular mortise and tenon seeks to join end-grain to side-grain by making them into a side-grain to side-grain gluing situation. The additional gluing surfaces offer optimum mechanical resistance by maximizing the depth of the joint while still surviving dimensional conflict. For example, in *Figure 10.8*, joint B offers three distinct advantages over joint A. First, the depth of the individual tenons more than offsets the loss of width. Second, the height of the glued side-grain surfaces is increased. Third, the number of side-grain to side-grain interfaces is multiplied.

The round mortise-and-tenon joint has advantages and disadvantages. By turning the tenon on a lathe and by drilling the mortise, it can be produced with a high level of precision. However, poor tool geometry or poor sharpening commonly leaves drilled hole surfaces and tenon surfaces in

poor condition. The joint may therefore have weak mating surfaces. Also, the proportion of side-grain to side-grain gluing surface is somewhat limited and cannot be improved by increasing the dowel diameter. The best side-grain to side-grain gluing area is located at the mid-depth of the dowel, where it can do the least for racking resistance. Moreover, it seems apparent that gluing can do little to improve lateral shear strength. Much of the integrity of a round mortise-and-tenon joint depends on racking strength (that is, resistance to pivoting) from surface bearing. Joints having a shallow insertion of the tenon into the mortise will be prone to racking failure. It is therefore best to maintain the depth-to-diameter ratio above a certain level (about 3:2) to distribute the stress as much as possible.

A further complication of the round joint is the development of compression-set loosening at the top and bottom edges, the result of both poor gluing characteristics and dimensional conflict. This emphasizes the importance of well-machined surfaces and of matching tangential-grain to tangential-grain directions. Experiments with the moisture-cycling performance of joints indicate the high degree of success achieved by using a good glue to mechanically restrain at least some of the dimensional conflict. Some




Figure 10.6 • The best possible orientation of growth rings in a mortise and tenon is with radial/longitudinal grain direction matched along the mortise cheeks both vertically and horizontally, as in A. Joint D, the worst orientation of grain, is apt to split.




Figure 10.8 • The multiple mortise and tenon (B) is preferable to a single wide tenon (A). Tenon depth more than offsets the loss of width, and the increase in tenon height and the number of side-grain to side-grain interfaces greatly improves the strength of the joint.

Figure 10.7 • Although joints A and B have the same amount of wood in each component, joint B has triple the **bonding** surface and more balanced dimensional restraint.






Figure 10.9 • This round tenon was split radially and tangentially before assembly. After moisture cycling, compression shrinkage developed entirely in one direction, opening the radial split. The tangential split remains tightly closed and the glueline is intact. (Photo by Randy O'Rourke)

additional reduction of compression-shrinkage loosening of tenons may be afforded by presplitting the tenon (*Figure 10.9*). As compression shrinkage develops in moisture cycling, the split can open to further relieve stress on the glueline. Perhaps this mechanism contributes to the success of wedged tenons. Although the wedge is primarily intended to produce lateral pressure to the glue surfaces and perhaps also to splay the tenon for a dovetail-style mechanical lock, it may play the more important role of providing a stress-relief slot that helps the glueline survive.

DOVETAIL JOINTS

Nothing is more symbolic of the woodworking tradition than the dovetail joint (*Figures 10.10 and 10.1*). It is a strong and beautiful way to execute the corner side-grain to end-grain joint and is commonly used in carcase construction. The joint consists of interlocking tails and pins, giving it strength in tension along the tail member but not along the pin. It should therefore be oriented to resist tension against




Figure 10.10 •The dovetail, a standard carcase joint, has strength in tension along the side with the tails.

the tails. In a drawer, for example, the tails should be in the drawer sides, the pins in the drawer front. In case construction, the pins should be in the sides and the tails in the top to prevent the sides from spreading. Although the joint strength results from the wedging action of the tails against the pin faces, the joint is held in place principally by gluing the side-grain to side-grain mating faces of the tails and pins.

The joint strength depends largely on the success of the glue bond between the side-grain faces (the end-grain areas behind the pins and tails cannot be depended upon for any substantial contribution to the strength) and the shear strength (parallel to the grain) of the wood of the tails. Joint strength therefore increases as the number of tails increases, as long as enough wood remains across the narrow part of the tails. However, if the joints are cut by hand, the added labor should also be considered in determining the number of pins and tails per joint.

In designing the joint, the slope of the tails must be a compromise. If the angle is not great enough, the wedging-locking action will be lost. If the angle is too great, the splayed tips of the tail will be too fragile, and a component of end grain will be introduced. This impairs the side-grain integrity of the gluing surfaces. An angle of 11° to 12° has proven satisfactory over generations.

When a large number of pins and tails can be cut with precision, as is possible with machines, the glued surfaces alone can develop adequate strength. In fact, the joint can relinquish the wedging taper and have straight tails. Thus evolved the finger joint or box joint, which gains its strength from the many closely fitting side-grain to side-grain glue-lines (not unlike the spline joint, *Figure 10.7B*).

MITER JOINTS

Parallel side-grain to side-grain miters make a very efficient corner joint (*Figure 10.11C*). However, miter joints where the grain directions meet at a 90° angle present serious technical problems. Because of the difference between dimensional change along and across the grain, the joint may open if the moisture-content change is great or if the members are wide. If nailed perpendicular to the outside face of either member, the nail must penetrate deeply into the end grain to ensure adequate holding. Gluing miter joints is of marginal effectiveness because of the large component of exposed end grain. Doweled miters, splined miters, or combination lap-and-miter joints can improve strength by providing side-grain to side-grain gluing surface (*Figure 10.11A, B*). Modified splines of the "biscuit" type are also an effective method of joining mitered surfaces.




Figure 10.11 • End-grain mitered joints can be strengthened by dowels (A) or by splines (B). A properly glued side-grain miter (C) will have adequate strength by itself.

DOWELED JOINTS

Dowels are cylindrical wooden rods used in a number of ways to fasten and strengthen joints. I think of dowels as falling into three categories: as tenons, as pins, and as gluing accessories.

In cases where dowels are used to modify end-grain to side-grain joints (*Figure 10.12*), a dowel is inserted into a hole in the end of the perpendicular member. Since the piece has side-grain to side-grain contact, a high degree of integrity can be expected. The dowel becomes a tenon extension of the piece (multiple dowels, of course, can also be used). The mating hole in the side-grain surface of the joint becomes a mortise into which the tenon is fitted. In double-dowel joints that are subjected to racking, one of the dowels carries a critical share of the load in tension. The remaining load is transferred as surface compression. In designing such a joint, increasing the height of the member is advantageous because it enables the dowels to be spaced as far apart as

possible (*Figure 10.13*). The design should incorporate dowels that are large enough in diameter to carry tensile load and deep enough to resist pullout. The dowels should also be able to carry and transfer the shear load parallel to the side-grain member of the joint.

Dowels as pins provide physical constraint to a joint without glue (although glue may still be applied). Examples might include a pinned slip joint, a wooden hinge pin, the guide pins in a table leaf, and flooring pins. Historically, large wooden dowels called trunnels (tree nails) pinned framing members together in buildings and ships. The pin typically has its grain direction perpendicular to the grain direction of both parts being joined. These parts may have parallel grain directions, but they are more often perpendicular to one another. Pins are sometimes added as a fail-safe measure or as a way of providing clamping pressure to draw a joint home. An example of the former is the pin normally concealed in the neck of a duck decoy, which will hold the head on in case the neck breaks because of weak grain direction. An example of the latter is the draw-bored mortise and tenon, where the hole drilled through the tenon is slightly offset from the one through the mortise, so pounding a pin home pulls the joint tightly together.

Despite the obvious success of the draw-bored mortise and tenon, dowels are most often misused as gluing accessories to hold parts in alignment. For example, in making a tabletop, boards might be edge-glued and held with a series of bar clamps. To ensure alignment of board surfaces at the joints, dowels are sometimes used. However, if gluing is correctly done, full wood strength can be developed by a plain side-grain to side-grain joint—no reinforcement is necessary. Because they do not provide strength, the pins therefore need only be long enough and numerous enough to ensure alignment. For edge-gluing 1-in. lumber, $\frac{3}{8}$ -in. or $\frac{1}{4}$ -in. dowels that are 1 in. long are plenty. Needless to say, the holes should be bored a little deeper than the length of the dowels. Dowels should fit snugly into accurately positioned holes.




Figure 10.12 • Dowels used in end-grain to side-grain joints in effect become tenons; the mating holes act as mortises.

When the joints are clamped, no attempt need be made to glue the dowels into the holes in the mating edges. The loss of glueline due to the dowels is negligible. For example, in edge-gluing $\frac{3}{4}$ -in. lumber, a $\frac{1}{8}$ -in. dowel placed every 8 in. along the joint reduces the glueline area less than 29c.

Although it might seem advantageous to make the dowels "good and long" and glue them in "good and tight," a negative effect can actually result. The restraint to normal shrinkage and swelling may cause the wood to fail at or near the glue joint (Figure 10.14). If gluelines fail at edge joints, the problem should be rectified by troubleshooting the gluing procedure rather than by pinning a bad joint with dowels in an attempt to bring it up to standard. If the gluelines are properly made (in terms of surface preparation, glue spread, clamping, etc.), there is little to gain in trying to reinforce the joints, since the strength of the wood on either side of the joint is still the limiting factor.

Edge joints can be modified by various tongue-and-groove configurations to assist in alignment. The logic that such joints are stronger because of greater surface area is questionable. If the quality of gluing is up to standard, the glueline is as strong as the adjoining wood with no need for additional area. In joints of end-grain to side-grain combination, the spline may become a tenon or a simple locking device.




Figure 10.13 • Increasing the spacing between dowels reduces the tensile load that each must carry. This makes the joint more resistant to racking.




Figure 10.14 • If long dowels are used across an edge joint and glued into the holes, shrinkage will be restrained across A-B. Tensile stress will develop across A'-B' as the boards attempt to shrink.

In edge-gluing, the idea of "strengthening" the joint with a longitudinal spline may be tempting but is a serious misconception. When the spline is continuous, the reduction in surface area of the board is substantial (Figure 10.15). For example, if a $\frac{1}{4}$ -in. spline runs the length of a $\frac{3}{4}$ -in.-thick joint, the strength of the joint is reduced by one-third. If the spline is very thin only slight weakening will occur, providing the spline is centrally located along the neutral axis.

FASTENED JOINTS

The term fastener refers to any item that holds together two members. When used in the sense of a pin, wooden dowels are examples. Other wooden components, such as cross-battens, corner blocks, and plywood gusset plates, might also be thought of as fasteners. Usually the term suggests nails and screws. It is likely that when civilization learned to extract and shape metals, nails and spikes for wood were among the first items produced. Until the last century, handmade nails had hardly changed and screws were relatively expensive. Today, however, with automated production, improved fastener design, and power installation equipment, mechanical fasteners have become inexpensive and efficient alternatives for assembling wood components.




Figure 10.15 • Reinforcing an edge-glued joint with a cross-grain spline actually weakens the joint at the margins of the spline.

It has been estimated that some 75,000 fasteners—primarily nails—are used in the average house. Most woodworkers readily appreciate the importance of nails in general carpentry and softwood construction but also assume the traditional notion that fasteners should be avoided in cabinetmaking, as if any construction using fasteners is somehow inferior. But it has been perceptively observed that wood joints "can be poorly made with considerable ease," and this would certainly apply to many fastened joints. On the other hand, fastened joints can also be well made. Woodworkers should carefully study mechanical fasteners as an alternative means of joining wood.

Since most fasteners are metal and thus have superior strength, failure of the fastener itself need not be a concern. The primary requirement is holding power, which is the ability of fasteners to transfer stress from one member to another without detaching, dislodging, or causing failure in either member. Holding power is closely related to the structural strength properties and the condition of the wood.

NAILS

The common wire nail, with its bright finish, diamond-cut point, and flat head, is the most familiar of nails. In typical use, it is driven forcefully and rapidly through one or more materials, embedding its point into the side grain of seasoned wood. A general empirical formula for direct withdrawal (*Figure 10.16*) of a bright-finish, common wire nail immediately after driving is:

$$p = 7,850G^{5/2} DL,$$

where

p = maximum withdrawal load, in pounds

G = the specific gravity of the wood

D = the nail diameter in inches

L = the depth of penetration, in inches, of the nail into the member holding the point.

Under these standard conditions, direct withdrawal varies directly with the diameter and length of the nail; the greater the length or the diameter, the greater the holding power. The formula also reveals that denser woods develop greater holding power.

When a nail is driven into a side-grain surface, the longitudinal cell structure is separated or split apart and also compressed ahead of the point, depending on the point's taper or bluntness. As the nail progresses, many cells in the path of the nail are broken, and their severed ends are bent and compressed in the direction of driving. The tendency of the cell ends to recover causes them to press against the nail surface, resulting in resistance to withdrawal. Withdrawing the nail restraightens the cells, increasing the bearing against

the fastener. Only when slippage occurs does the nail finally pull out.

Experiments have shown that in many woods, a spear point with a slim taper results in the greatest holding power. However, the wood fibers also separate, and in some species this type of point causes splitting. A blunt point has less tendency to cause splitting because a plug of compressed wood structure is torn loose and pushed ahead of the point, rather than being pushed aside to start a split. The greater cell damage reduces holding power. The common diamond point, then, is a compromise that seems to afford the greatest holding power with the least splitting in common softwood structural lumber.

The fact that nails can be driven without preboring pilot holes has apparently led to the assumption that they should be driven without preboring. An unfortunate corollary seems to be that nails are therefore limited to use where they can be driven without splitting the wood or bending over. In reality, the best holding power results when nail holes are prebored. While most woodworkers accept the idea of installing woodscrews in prebored holes to prevent splitting and to maximize holding power, they seldom consider preboring nail holes.

In nailing two pieces together, driving the nail through the first piece builds up a compression zone that may cause splitting or other disruptions as the nail emerges and enters the second piece. The resulting rupture can keep the pieces from maintaining close contact. Appropriate preboring eliminates this problem.

Pilot holes ranging from 60% of nail-shank diameter for low-density woods to 85% of shank diameter for high-density woods give maximum withdrawal resistance. In routine construction and carpentry, it is obvious that preboring is not feasible. For cabinetmaking and other woodworking, however, nails installed in prebored holes are extremely effective fasteners and deserve greater consideration.

The holding power of nails diminishes over time following installation. The long-term holding power, especially where extreme moisture variation causes dimensional change in the wood, can be reduced to as little as one-sixth the loads indicated by the formula given.

Holding power can be improved considerably by surface modification of the nail shanks (*Figure 10.17*). Resin-coated nails (called cement-coated nails) have about double normal holding power but this advantage disappears over time. Withdrawal resistance can be substantially improved by placing annular grooves on the nail shank (*Figure 10.18*). Annularly threaded nails are understandably harder to drive, but when installed into side-grain-prebored holes they provide positive resisting surfaces for bent-over fibers. Spiral-threaded nails have improved holding power that appears




Figure 10.16 • The holding power of a nail is a function of its diameter (D), its driven length (L), and the grain direction and density of the wood into which it is driven.

least reduced over time, perhaps because of the minimum damage to the holes as the nails "screw" into place.

All nails have less holding power when driven into end grain than into side grain. Test results indicate that the difference is smallest with high-density woods, but with low-density woods end-grain holding power may be as little as half of side-grain holding power. Unfortunately, one hears the flat statement that nailing into end grain should be avoided on the grounds that holding power is reduced. Actually, pre-boring and increasing the diameter, length, or number of nails can compensate for the lower holding power.

Nailing into end grain may be beneficial in certain situations. For example, when a nail is driven into side grain, later shrinkage shifts the wood along the nail shank, causing the nail head to protrude rather than pushing the point deeper into the wood. The longer the nail, the greater the protrusion. This is why, in drywall work, the shortest nail that will hold the gypsum board in place is recommended. When the wood swells, it moves equally away from each side of the shank center, thereby backing the point still farther from the bottom of the hole. Repeated cycles cause further emergence of the nail. In end grain, however, since wood does not change dimension along its grain direction, using longer nails for greater holding power does not increase nail popping.

In lateral loading (*Figure 10.19*), joint slip rather than maximum load is critical. Stouter nails offer increased bearing against the wood so lateral load resistance increases exponentially with nail diameter. If the diameter is doubled, the lateral resistance is increased by a factor of $2^{\frac{3}{2}} = \sqrt{2^3} = 2.8$.

It is also important that the fastener be stout enough to transmit load without bending. A long, slender nail crushes



Figure 10.17 • At the right is a common nail with a smooth, bright finish; at left is a spiral grooved nail; and in the center is an annularly grooved nail. (Photo by Randy O'Rourke)




Figure 10.18 • When a nail is driven perpendicular to the grain, annular grooves provide added bearing surface for bent wood fibers, which resist the withdrawal of the nail. (Photo by Randy O'Rourke)

the wood near the surface and bends, then becomes loaded in withdrawal and "snakes" out of the hole.

The head design of a nail is also critical. The broad heads of common nails are normally large enough to carry full withdrawal load without pulling through the top member. However, the small heads of finishing nails limit the effectiveness of deep penetration because they readily pull through the top board. Thus, while a joint can be made stronger by using longer common nails, beyond a critical point a joint with finishing nails might best be improved by increasing the diameter or the number of nails, if space permits.

Appearance is a strong influence in the bias against using nails in woodworking joints. However, there are many places where nails could be the most efficient and effective fastener. Take for instance, drawer sides. The half-blind dovetail is the traditional joint, but it would be interesting to compare a well-nailed half-blind tongue-and-rabbit joint for overall strength.




Figure 10.19 • When a nail subject to lateral loading fails, it typically crushes the wood near the surface, then bends and pulls out of the hole.




Figure 10.20 • Common woodscrews (from left) are flat head, round head, and oval head.

WOODSCREWS

Most woodworkers recognize the superiority of correctly installed woodscrews (*Figure 10.20*) over other fasteners. Their great holding power is understandable in terms of the positive engagement of the threads into relatively undamaged wood structure. The key to maximum holding power is preboring pilot holes for both the threaded portions of the screw and for the shank. Slightly undersized shank holes should be prebored to provide a snug fit and firm bearing without developing enough stress to cause splitting. Pilot holes for the threaded portion should be from 70% of root diameter in low-density woods to 90% in high-density woods. (In the densest woods, it is best to bore the pilot hole the same diameter as the root, especially for brass screws.) Lubricating the threads with wax facilitates driving and minimizes screw breakage without loss of holding power.

When woodscrews are correctly installed into the side grain of seasoned wood, maximum withdrawal loads can be estimated by the empirical formula:

$$p = 15,700G^2DL$$

where

p = maximum withdrawal load, in pounds

G = the specific gravity of the wood

D = the screw shank diameter, in inches

L = the depth of penetration, in inches, of the threaded portion of the screw into the member receiving the point.

As with nails, the holding power of screws increases directly with diameter and length and exponentially with the density of the wood. Similarly, holding power diminishes over time, and withdrawal resistance for loading conditions of long duration might be as little as 20% of the values estimated by the formula given above. Screws driven into end-grain surfaces average only about 75% as much holding power as those driven into side grain, and holding power will be more erratic. As with nails, it is preferable to design joints to load screws laterally rather than in direct withdrawal.

Besides nails and screws, a host of various other fasteners are available for use with wood, such as clamp nails, corrugated fasteners, and staples. In addition, various hardware items serve as fasteners in the role of a "third party," which is fastened to the two or more wood components by nails and screws. These include mending plates, flat corner irons, angle braces, T-plates, and hinges. In evaluating the use and effectiveness of each, the integrity usually depends on the holding power of the attachment fasteners in terms of stress application relative to grain direction. In construction joints, for example, special framing anchors have been developed that transfer loads from one member to the other by loading fasteners laterally rather than in withdrawal. These anchor plates also provide for the proper number and placement of fasteners (typically nails) for maximum strength.



Figure 11.1 •The moderate squeeze-out of glue in the center glueline indicates proper spread of glue.

(Photo by Vincent Laurence)

ADHESIVES AND GLUING

Everyone has a familiarity with the idea of "sticking" pieces of wood together. You simply use glue—it's as simple as that.

Or is it? Not quite. When two pieces of wood are fastened together with nails or screws or assembled with a dovetail joint or pegged with dowels, it's fairly obvious how and why the union works, and the probability of success can be reasonably estimated by inspection. With glue, however, the integrity of a joint we can hardly see depends on chemistry most of us do not understand, and we cannot know by sight whether the joint will hold beyond the destruction of the wood itself, or if it will pop apart at the touch of a finger. This chapter will review some common woodworking adhesives and some of the basic elements of successful gluing (*Figure 11.1*).

ADHESIVE JOINTS

Laminated items assembled with glue have been discovered in the tombs of early Egyptian pharaohs, and it is probable that the use of adhesive substances for holding wood parts together predates recorded history. Through the ages, most glues were made from fish, animals, and vegetable starch and showed little change or improvement. In this century, however, the development of the plywood industry initiated drastic changes in the types and properties of adhesives. Further stimulated by the demands of World War II and the scientific plunge into the space age, a dynamic adhesive technology has given us numerous multipurpose and specialized adhesives, with the promise of a parade of new ones well into the future.

Today's woodworkers use adhesives in a number of ways—to make large pieces out of smaller ones (such as carving blocks and laminated beams), to create combinations for strength or aesthetic improvement (such as plywood, veneers, and marquetry), and to join parts to create a final product, as in furniture, sporting goods, and structures. A complete discussion of gluing technology is impossible here, but certain basic considerations that may be overlooked or misunderstood often cause serious gluing problems. It's worth a systematic review.

The general term **adhesive** includes any substance having the ability to hold two materials together by surface attachment. Those most commonly used for wood are called **glues**, although materials described as **resins**, **cements**, and **mastics** are equally important in the assembly of wood products.

No truly all-purpose adhesive has yet been manufactured and probably never will be. A general-purpose adhesive cannot hope to attain all the individual capabilities and attributes of closely designed ones, although any of the standard commercial glues will do a satisfactory job if the wood is reasonably dry and the temperature remains within the human-comfort range. There is an increasing trend toward development of special adhesives to increase performance and ease of use. Choosing an adhesive is not as easy as it once was and must take into account factors such as species, type of joint, working properties as required by anticipated gluing conditions, performance and strength, and, of course, cost.

A wide and confusing array of adhesive products confronts the woodworker. A common pitfall is the belief that some glues are better than others; the notion that simply acquiring "the best" will ensure success is careless and may give disastrous results. With certain qualifications, all commercially available adhesives will perform satisfactorily if chosen and used within their specified limitations. An important corollary is that no adhesive will perform satisfactorily if not used properly. Within the specified limitations, most woodworking adhesives will develop joints equal in strength to the weaker of the woods being joined. Thus, the wood, rather than the glue or its bond, is the weak link in a well-made joint.

One interesting adhesive is water. It is easily spread, wets wood well, and solidifies to form a remarkably strong joint. It is delightfully inexpensive. However, it is thermoplastic, and its critical maximum working temperature is 32°F. At temperatures at which it will set it has a very short assembly time. But due to its temperature limits, water will never capture a very important position among woodworking adhesives. (The rest of this chapter will be serious.)

Glues made from natural materials have been used from earliest times, and even today hide glue (made from the

hides, tendons, and hooves of horses, cattle, and sheep) and casein (primarily a milk derivative) are still in use. For certain work, such as museum object conservation and restoration work, animal glues are still utilized because their use is easily reversible with heat and moisture.

Through the decades following World War II, a number of synthetic compounds were developed for gluing wood, and a short list of these, with only slight variation and modification, became the chosen few for virtually all gluing needs of both industrial and small-shop gluing.

Perhaps the most versatile of the "standard" woodworking adhesives are the **polyvinyl acetate emulsions (PVA)**, commonly called white glues. More recently, **yellow glues (modified PVA)** have emerged, which have greater rigidity, improved heat resistance, and better "grabbing" ability. These yellow glues are satisfactory for the bonding jobs of most craftsmen. They are easy to use and are more tolerant to unfavorable conditions than are white glues. Yellow glues also cause less trouble in clogging abrasive paper. **Urea-formaldehyde, or plastic-resin glues**, are water-resistant but not heat-resistant, as are resorcinol-formaldehyde adhesives. Also available are **epoxy resins**, which offer the advantage of being good "gap fillers" because they have insignificant shrinkage upon curing.

The most recent additions to the menu of woodworking adhesives are **polyurethane glues** and **cianoacrylate glues**, plus an array of special-purpose adhesives ranging from contact cements and hot-melt glues to mastics and construction adhesives. Each has its special application, property, and performance features. An adequate review of the virtues of each of the many woodworking glues is beyond the scope of this book, but a number of references in the Bibliography (n. b., Marra, Young, and *Wood Handbook*) give excellent summaries of modern adhesives.

GLUING FUNDAMENTALS

A logical starting point for understanding adhesives is to know why glue sticks at all. It is sometimes assumed that adhesion results from the interlocking of minute tentacles of hardened adhesive into the fine, porous cell structure of the wood surface. Scientific research has shown that such **mechanical adhesion** is secondary to the chemical attachment due to molecular forces between the adhesive and the wood surface, or **specific adhesion**. The assembled joint, or bond, is often discussed in terms of five intergrading phases (*Figure 11.2*), each of which can be thought of as a link in a chain. The weakest phase determines the success of the joint. Phases 1 and 5 are the pieces of wood, or **adherends**, being joined. Phases 2 and 4 are the interpenetrating areas of wood and adhesive where the glue must "wet" the wood to




Figure 11.2 • The five phases of a glue joint.

establish molecular closeness for specific adhesion. Phase 3 is the adhesive itself, which holds together by **cohesion**.

Fundamentally, gluing involves machining the two mating surfaces, applying an adhesive in a form that can flow onto and into the wood surface and wet the cell structure, and then applying pressure to spread the adhesive uniformly thin and hold the assembly undisturbed while the adhesive solidifies. The typical adhesive is obtained or mixed as a liquid but sets to form a solid glue layer. This happens either by loss of solvent, which brings the adhesive molecules together and allows them to attach to one another, or by a chemical reaction that develops a rigid structure of more complex molecules.

Different woods have different gluing properties. In general, less dense, more permeable woods, such as chestnut, poplar, alder, basswood, butternut, sweetgum, and elm, are easier to glue. Moderately dense woods such as ash, cherry, soft maple, oak, pecan, and walnut glue well under good conditions. Hard and dense woods, including beech, birch, hickory, maple, osage-orange, and persimmon, require close control of glue and gluing conditions to obtain a satisfactory bond. Most softwoods glue well, although in uneven-grained species, earlywood bonds more readily than denser latewood. Extractives, resins, and oils may introduce gluing problems by inhibiting bonding, as with teak and rosewood, or by causing stain with certain glues, as with oaks and mahogany.

Since most adhesives will not form satisfactory bonds with wood that is green or high in moisture content, wood should at least be well air-dried. Ideally, wood should be conditioned to a moisture content slightly below that desired for the finished product to allow for the adsorption of whatever moisture might come from the adhesive. For furniture, a moisture content of 59c to 19c is about right. However, when using urea-formaldehyde glues, the moisture content should not be below 19c. For thin veneers, which take up a proportionately greater amount of moisture, an initial moisture content below 59c might be appropriate.

Machining is especially critical. In some cases, especially for multiple laminations, uniform thickness is necessary for uniform pressure. Flatness is required to allow surfaces to be brought into close proximity. The surfaces to be glued should have cleanly severed cells, free of loose fibers. Accurate handplaning is excellent if the entire surface, such as board edges, can be surfaced in one pass. On wide surfaces, peripheral milling (planing, jointing) produces adequate surfaces. Twelve to twenty-five knife marks per inch produce an optimum surface. Fewer may give an irregular or chipped surface; too many may glaze the surface excessively.

Dull knives that pound, heat, and glaze the surfaces can render the wood physically and chemically unsuited for proper adhesion even though it is smooth and flat. Planer saws are capable of producing surfaces acceptable for gluing, but in general, sawn surfaces are not as good as planed or jointed ones.

Surface cleanliness must not be overlooked. Oil, grease, dirt, dust, and even polluted air can contaminate a wood surface and prevent proper adhesion. Industry production standards typically call for "same-day" machining and gluing. Freshly machining surfaces just before gluing is especially important for species high in resinous or oily extractives. Where this is not possible, washing surfaces with acetone is sometimes recommended.

Don't expect a board machined months or years ago to have surfaces of suitable chemical purity. If lumber is flat and smooth but obviously dirty, a careful light sanding with 240-grit or finer abrasive backed with a flat block and followed by thorough dusting can restore a chemically reactive surface without seriously changing flatness. Coarse sanding, sometimes thought to be helpful by "roughening" the surface, is actually harmful because it leaves loose bits. Tests have shown that intentionally roughening a surface, as in "toothed planing," does not improve adhesive-bond quality. In summary, wood should be surfaced immediately prior to gluing for cleanliness and to minimize warp and should be kept free of contamination to ensure an acceptable gluing surface.

Shelf life is the period of time an adhesive remains usable after distribution by the manufacturer. Unlike photographic films, adhesives are not always expiration-dated, even though they lose effectiveness with age. A good rule of thumb is to use any adhesive within a year or two of purchase. Beware of containers that have been on a dealer's shelf too long; outdated package styles are an obvious tip-off. It is wise to mark a bottle or can with your date of purchase because it is amazing how fast time can pass while glue sits idle in your workshop. If possible, refrigerate glues in tight containers to prolong shelf life. In general, if the

glue is spreadable when mixed according to instructions, it is suitable for use, but adding water to restore spreadability is not a good practice.

The adage "when all else fails, read the instructions," all too often applies to glue. It is unfortunate that instructions are so incomplete on retail glue containers. Manufacturers usually have fairly elaborate technical specification sheets but supply them only to quantity consumers. Too often, many critical factors are left to the user's guesswork or judgment. Mixing proportions and sequence typically are given clearly; they should be followed carefully.

Glues with a pH above 7 (alkaline), notably caseins, will absorb iron from a container and react with certain woods such as oak, walnut, cherry, and mahogany to form a dark stain. Coffee cans or other ferrous containers can contribute to this contamination. Nonmetallic mixing containers such as plastic cups or the bottom portions of clean plastic milk or bleach jugs work nicely.

Once glue is mixed, the **pot life**, or **working life**, must be considered. Most adhesives have ample working life to handle routine jobs. The period between the beginning of spreading the glue and placing the surfaces together is called **open assembly time**; **closed assembly time** indicates the interval between joint closure and the development of full clamping pressure. Allowable closed assembly time is usually double or triple the open assembly time.

With many ready-to-use adhesives, there is no set open time; it's best to spread the glue and close the joint as soon as possible. If the joint is open too long, the glue may pre-cure before adequate pressure is applied, resulting in a **dried joint**. In general, assembly time must be shorter if the wood is porous, the mixture viscous, the wood at a low moisture content, or the temperature above normal. (As a rule, it is a good policy to avoid gluing when the temperature of the room or of the wood is below 65°F.) With some adhesives, such as resorcinol, a minimum assembly time and double spreading (that is, applying adhesive to each of the mating surfaces) may be specified for dense woods and surfaces of low porosity to allow wetting of the wood and to permit thickening of the adhesive to prevent excessive squeeze-out.

Proper spread is difficult to control. Too little glue results in a starved joint and a poor bond. A little overage can be tolerated, but too much results in wasteful and messy squeeze-out. Though some squeeze-out is assurance that sufficient adhesive has been applied, squeeze-out may cause problems in machining or finishing. With experience the spread can be eyeballed. It is useful to obtain some commercial specifications and conduct an experiment to see just what they mean. Spreads are normally given in terms of pounds of glue per thousand square feet of single glue-line, or MSLG. A cabinetmaker will find it more convenient to




Figure 11.3 • Average clamping pressure of typical woodworking clamps. To find out just how much load each clamp could apply, Hoadley attached open steel frames to the crossheads of a universal timber-testing machine. With a clamp positioned to draw the frames together, the load applied was indicated on the machine. The clamps are described in the table, with the last column giving the average of three trials by an average-sized man. The quick-set clamp listed first in the table was used to calibrate the set-up: A secretary squeezed 330 lb., a hockey player squeezed 640 lb., and the author squeezed 550 lb. Repeated trials by each person yielded readings that agreed to within 10%. An asterisk indicates that the clamp began to bend, and the test was stopped at the value listed.


convert to grams per square foot by dividing lb./MSGL by 2.2. Thus a recommended spread of 50 lb./MSGL, typical of a resorcinol glue, is about 23 grams per square foot. Spread it evenly onto a square foot of veneer for a fair visual estimate of the minimum that should be used. Usually, the recommended spread appears rather meager.

Double spreading is recommended whenever it's feasible. This provides full wetting of both surfaces without relying on pressure and flatness to transfer the glue and wet the

opposite surface. With double spreading, a greater amount of glue per glue line is necessary, perhaps one-third more.

Glue should be spread as evenly as possible, even though some degree of self-distribution will result when pressure is applied. Toothed spreaders, rollers, or stiff brushes are best for this purpose. Some speed is necessary; when many pieces are to be assembled, it pays to have them ready in the order of assembly. With most common glues, it's also wise to make a dry run to check the joints and rehearse the clamping strategy.

Figure 11.4 •
Cover boards
(cauls) distribute
clamping pressure
evenly.



The object of clamping a joint is to press the glueline into a continuous, uniformly thin film and to bring the wood surfaces into intimate contact with the glue and hold them undisturbed until setting or cure is complete. Since loss of solvent causes some glue shrinkage, an internal stress often develops in the glueline during setting. This stress becomes intolerably high if gluelines are too thick. Gluelines should be no more than a few thousandths of an inch thick.

If mating surfaces were perfect in terms of machining and spread, pressure wouldn't be necessary. The "rubbed joint," skillfully done, attests to this. If two mating surfaces are perfectly flat and spread with glue, simply sliding them together and sliding the pieces back and forth will evenly thin the glueline down to a minimum. If left undisturbed until the adhesive sets, a quality bond will result. Few of us can do this well. Unevenness of spread and irregularity of surface usually require considerable external forces to properly bring surfaces together. The novice commonly blunders on pressure, both in magnitude and uniformity.

Clamping pressure should be adjusted according to the density of the wood. For domestic species with a specific gravity of 0.3 to 0.7, pressures should range from 100 psi to 250 psi. Dense tropical species may require up to 300 psi. In bonding composites, the required pressure should be determined by the lowest-density layer. In gluing woods with a specific gravity of about 0.6, such as maple or birch, 200 psi is appropriate. Thus gluing up 1 sq. ft. of maple requires pressure of 28,800 pounds (12 in. by 12 in. by 200 psi). More than 14 tons! This would require, for an optimal glueline, 15 to 20 C-clamps, or about 50 quick-set clamps. Conversely, the most powerful C-clamps can press only




Figure 11.5 •
When an edge-
glued panel (A) is
surfaced while the
glueline is still
swollen with mois-
ture (B, C), a
sunken joint (D)
results.

10 sq. in. to 11 sq. in. of glueline in maple. Jackscrews and hydraulic presses can apply loads measured in tons. But since clamping pressure in the small shop is commonly on the low side, one can see the importance of good machining and uniform spread. *Figure 11.3* gives an indication of how much gluing pressure can be delivered from various clamps.

Another troublesome aspect of clamping is uniformity, usually a version of what I call "the sponge effect." Lay a sponge on a table and press it down in the center; note how the edges lift up. Similarly, the force of one clamp located in the middle of a flat board will not be evenly transmitted to its edges. It is therefore essential to use heavy wooden cover boards or rigid metal cauls to ensure proper distribution of pressure (*Figure 11.4*).

Clamp time must be long enough to allow the glue to set well enough so that the joint will not be disturbed when the clamps are removed. Full cure time, or the time required for development of full bond strength, is considerably longer. If the joint will be under immediate stress, the clamp time should be extended.

Finally, cured joints need conditioning periods to allow moisture added at the glueline to be distributed evenly through the wood. Ignoring this can result in sunken joints (*Figure 11.5*). When edge-gluing pieces to make panels, moisture is added to the gluelines, especially at the panel surfaces where squeeze-out contributes extra moisture (see *Figure 11.5A*). If the panel is surfaced while the glueline is still swollen (see *Figure 11.5C*), the glueline will shrink when the moisture is finally distributed (see *Figure 11.5D*), leaving a joint that is sunken.



Figure 12.1 • Clear finishes protect the surface of wood and enhance the appearance. (Photo by Alec Waters)

FINISHING AND PROTECTING WOOD

The word finish in woodworking usually describes some final surface treatment that protects the wood and enhances its appearance. Most woodworkers agree that some form of protection is typically necessary. The matter of appearance, however, is more controversial, depending on individual taste and preference. In addition to the protection of finishes at the surface, protection may be needed throughout the wood, namely against fungi and insects. This aspect of protection will be discussed as a final topic of this chapter.

Let's first consider protection. It is usually desirable to protect wood surfaces from accumulating dirt and to create a surface that can be cleaned easily. Finishes may also protect against abrasion or indentation and prevent changes in color due to light or atmospheric pollutants. But their most important function is to impede the exchange of moisture with the atmosphere, thus helping to avoid the consequences of dimensional change.

On the subject of surface appearance, it is impossible to generalize because of the variation in circumstance and personal preference as to what looks best. Some woodworkers want to preserve wood in its natural state as much as possible, while others wish to change the wood in both color and appearance. Some prefer to retain any visible surface irregularity due to cell structure, while others desire a surface that is perfectly smooth. Some want a matte finish, others a high gloss. Some try to retain or even accentuate variation in figure and color, others attempt to achieve uniformity. In this chapter, I will concentrate on basic points about protection and appearance without regard to functional requirements or aesthetic preferences.

Achieving a good-looking finish on wood involves a combination of two elements, the **surface condition** of the wood and the **finishing treatment** applied to it (*Figure 12.1*). Although done separately, they are interrelated and must be planned with respect to one another. Certain surface conditions will call for particular treatments and vice versa, but there is no such thing as the single best combination for all projects. I have fun experimenting, and it seems I rarely finish two items in exactly the same way.

SURFACE CONDITION

Most finishing instructions begin with surface preparation, emphasizing such things as proper sanding and dusting just prior to treatment. But the concern must begin long before that because surface condition is influenced by every step of woodworking, from sawing the log and drying the lumber to machining the surfaces and gluing the joints. It is appropriate to evaluate surface condition using four criteria: trueness, evenness, smoothness, and quality.

Trueness compares the actual to the intended geometry of the surface. Planed surfaces are expected to be flat, turnings are expected to be round, edges are expected to be straight, and so forth. Residual stresses due to improper drying of lumber and warp resulting from change in moisture content are the most common causes of cup, bow, and twist in flat surfaces. Similarly, crowning of surfaces near edges is often the result of careless sanding or planing.

An otherwise attractive and successful finishing job can be overshadowed by lack of trueness or **evenness** of the surface. Raised grain is a common cause, traceable to machining and moisture problems. The unevenness of elevated latewood can result from careless hand-sanding that scours more deeply into earlywood than latewood in uneven-grained woods, especially on flat-grained surfaces. A planer or jointer that is out of adjustment can leave chatter marks, chip imprints, or snipes on board surfaces. Raised, sunken, or mismatched joints can produce an uneven surface as a complication of poor gluing procedures. When these problems develop in a core material, they can telegraph through face veneer.

Surfaces may, of course, be intentionally made uneven with satisfying results. Sandblasting and scorching out earlywood to provide a textured surface are examples of novel techniques used successfully in both sculptured and paneled surfaces.

Smoothness is the absence of surface irregularity, such as the undulating knife marks left after machine-planing or the chatter marks left by careless scraping. Corrugations in veneer, especially those associated with knife checks, are further examples. Minute tearouts, which may occur when planing against the grain, destroy surface smoothness. (I do




Figure 12.2 • Machine-planed maple shows open vessel elements, but smaller features are obscured by torn and pounded fibers. The knife has moved across the surface from lower left to upper right, burrning the fibers into one another. (Photo by Stephen Smulski)




Figure 12.3 • When the surface is scraped with a steel scraper blade, torn and rolled wood tissue fills most of the wood vessels, and the surface becomes scratched by the minute ruggedness of the scraper's edge. 50X magnification. (Photo by Stephen Smulski)



Figure 12.4 • The sample sanded with 220-grit paper looks much like the scraped surface, although there are more visible scratches. Dust, rather than torn fibers, seems to have filled the open vessels. A surface like this would feel quite smooth to the touch. 50X magnification. (Photo by Stephen Smulski)

not include the surface voids traceable to cell cavities as departures from smoothness because they are an inherent feature of wood, not of its condition.) Generally smoothness is measured by the depth and uniformity of the scratch pattern left from sanding. The smoothest surfaces result from hand-planing with the grain, scraping, and fine sanding (Figure 12.2, Figure 12.3, Figure 12.4).

Of equal importance is the quality of the surface cell structure in terms of the cell damage that results from forming the surface. The ideal surface for finishing could be produced by light skim cuts with a razor blade, which would cleanly sever exposed cell walls with no damage to the remaining structure. Such an ideal surface, however, can hardly be expected in common woodworking practice.

Try to think of any surface in terms of cellular damage. One illustration of this point would be knife marks on a longitudinal surface. The surface may be true and even, and the knife marks may leave the surface amazingly smooth. With a well-sharpened planer, with lumber fed at a rate that produces 20 knife marks per inch, the knife marks would be imperceptible to the touch. One would certainly consider the surface smooth, yet the variation in cell damage along the surface can cause each knife mark to stand out as visually distinct. Microscopic examination reveals that variable light reflection from damaged cells, more than physical surface irregularity, is responsible for the visibility of the knife

marks. This damage can be obscured by the more uniform pattern of damage that is created by fine sanding or scraping along the grain.

Another example relates to sanding. If you sand with the grain using 180-grit paper, the surface will feel quite smooth. Sand the same wood across the grain with 240-grit paper and it will also feel just as smooth, yet when this piece is stained, the scratches will show up because of the very different manner in which the surface cell structure was broken up, which in turn causes variations in the absorption of stain.

No point needs greater emphasis than sanding *parallel* to rather than *across* the grain. On abrasive paper, each granule of abrasive is a tiny cutter (Figure 12.5, Figure 12.6). Since most of these granule faces have negative cutting angles, a scraping type of chip forms (Figure 12.7). This cutting action carves out cell-wall material from the surface parallel to the grain, but when directed across the longitudinal cells, frayed and broken-out cell walls result. As in planing, wherever crossgrain occurs, sanding *with* the grain is preferable. Sanding end grain leaves some broomed-over cell material, so sanding in one direction will produce the most uniform surface damage.

Developing surface smoothness by sanding is best done using a progression of grit sizes, each of which produces a scratch pattern at least to the depth of the previous one (Figure 12.8). Resist the considerable temptation to skip




Figure 12.5 • This photomicrograph at 100X magnification shows the surface of a sheet of new 200-grit open-coat garnet sandpaper. Each granule on the paper acts like a tiny cutter that produces a scraping type of chip. (Photo by Stephen Smulski)




Figure 12.6 • Sandpaper is made up of mineral particles attached to a backing. The minerals adhere to the glue coat (properly called the make coat) and are locked in place with a size coat.




Figure 12.7 • The cutting action of a sandpaper particle yields a scraping type of chip.




Figure 12.8 • Proper sanding requires progressing through ever-finer grits so that the finer scratch pattern of each replaces the coarser pattern of the previous grit (top). Skipping a grit will leave deep scratches in the finished surface (above).

grits in the progression; when you do so, the surface may look and even feel smooth, but the first coat of finish will reveal a few deep scratches left by the coarsest grit.

Other kinds of damaged cell structure, though apparently smooth, may later show variable light reflection or uneven stain or finish retention. Common problems are minute seasoning checks or compression failures that have gone unnoticed and hammer indentations or cell structure "bruises" below the surface from the action of rasp teeth. The glazed, pounded, and scorched surfaces produced by dull cutter-heads can hardly be considered as having quality even if they are smooth. Such surfaces may show later problems of grain raising, uneven stain retention, or poor adhesion of coatings. In hardwoods having tension wood, surfaces may be sanded to apparent smoothness. However, the microscopic woolliness of the severed cell walls will result in blotchy staining.

In any machining process, some fragile projections of damaged cell-wall material remain on the wood surface. Eventual adsorption and desorption of moisture will cause these cell fragments to distort and to project out from the surface. Where a surface coating buries and locks them in place, the fragments may be of no consequence. Otherwise, the raising of surface debris may detract from smoothness.

It is therefore desirable to remove loose cell-wall material as a final step in surface preparation. To do so, simply wipe the wood surface with a slightly damp (not moist or wet) cloth. The ambient temperature must be warm and the relative humidity not high. The moisture from the cloth will be adsorbed quickly by the damaged cell-wall fragments, causing them to raise from the surface. The surface will soon reestablish moisture equilibrium with the environment without any significant increase in overall moisture content. The projecting "whiskers" can then be removed by very light sanding with very fine (600-grit) abrasive paper. The trick is to remove the whiskers without further abrading the surface, which will only produce more whiskers. An extremely smooth and high-quality surface can be produced in this manner.

Surfaces should regularly be wiped or blown free of dust during and after sanding. Accumulated dust may cause "corns" on the abrasive paper, which can mar the surface. In addition, excess dust packed into the cell structure can mar the finish, so the final cleaning should be thorough. An air hose or vacuum cleaner may help if you have one, and it's a good idea to get in the routine of completing the cleaning job with a tack rag.

Commercially available tack rags seem well worth the money, but a fairly good one can be made easily from a lint-free cloth, such as an old handkerchief. Dampen the cloth slightly with turpentine, and sprinkle on a teaspoonful of

varnish or lightly paint meager streaks of varnish across the cloth with a brush. Then thoroughly wring the cloth to distribute the varnish. It should feel tacky, not wet. Store it in a glass jar. To use it, whisk the surface lightly to pick up dust, repeatedly folding the cloth. When it has lost its effectiveness, discard it and make a new one. Commercial spray products (such as Endust) for treating household dust rags work quite well for me.

Surface quality must also be considered from the chemical standpoint. Chemical discoloration resulting from such things as sticker stain in drying or fungal activity may cause visual defects in the finish. Traces of previous finish, glue spills, or accidental contamination with such things as oil, wax, silicone spray, and other contaminants can interfere with the evenness of stain retention or the adhesion of finish coats. As with glues, bonding of finishes depends in large measure upon molecular adhesion. If there is any doubt as to possible contamination of the surface, a final sanding and dusting prior to finishing will promote good adherence.


The four criteria of surface condition must be considered separately. For example, a tabletop that is machined to true and even flatness may have poor quality if it has been sanded across the grain. On a carved surface, the trueness must be judged in relation to the desired shape. If the surface is produced by a sharp gouge properly used (with the grain), the surface may be of high quality but intentionally uneven. If the unevenness of a high-quality carved surface were undesirable, sanding might make the surface more even but at the same time might reduce its smoothness and quality. In a sense, the moisture content of the wood also should be considered a factor in surface condition, for if it changes after finishing, the trueness, evenness, or surface quality may be belatedly altered.

In considering finishing treatments for wood, there are no "right" answers, only countless alternatives. Function, aesthetics, time, and cost ultimately are the deciding factors. As with the drying of wood, a great deal of lore and tradition influences our modern practices, yet few areas of woodworking are so touched by modern advances. Although no subject as complex as finishing can be generalized or simplified, I have come to recognize three basic categories of surface treatment: coatings, that is, treatment **on** the surface; penetrating finish, that is, treatment **in** the surface; and **no** treatment at all.

► NO TREATMENT

Usually, some sort of surface application is required for protection and appearance, and the instances where no finishing treatment at all makes sense are apt to be few and far between. Yet too often tradition seems to force the assump-

Figure 12.9 • This catalpa statue (standing 13 in. tall) was sanded with coarse sandpaper and left unfinished. (Photo by Randy O'Rourke)



tion that something must be brushed, swabbed, wiped, or sprayed onto the surface of a completed work. Leaving the wood untreated is rarely considered.

The more you work with wood and the more deeply you come to understand it, you become more sensitive to the value of natural tactile surfaces and have greater appreciation for the appearance of wood in the raw. Here more than ever, however, the surface condition, especially smoothness and quality, is vitally important. The longer I work with wood, the more I am able to recognize those special cases where the absence of finish can be the most gratifying treatment for wood (*Figure 12.9*).

Certain items, if kept indoors, really need no finish. These are often decorative, such as carvings and sculpture, but may also be functional, such as trays, bowls, and utensils. They often will be made of a single piece of wood, which can change dimension without affecting function or




Figure 12.10 • This white pine carving was made 32 years ago and finished with nothing at all. Periodic sanding with 400-grit sandpaper keeps its color bright and fresh. (Photo by R. Bruce Hoadley)

appearance. For example, I have a small abstract carving of eastern white pine (*Figure 12.10*). Its smooth, dry surface is light in color with only a subtle growth-ring figure displayed at the surface. Any treatment of the surface would bring out this figure too strongly. About as often as you might oil or polish a coated item, I simply resand the surface lightly with 400-grit paper to remove any accumulated dirt, dust, and discoloration from handling. After 32 years, it still looks fresh and clean.

For such items as utensils and tool handles, the normal dirt accumulation and surface abrading from handling create a finish that is both unique and appropriate. Many years back I needed a netmaker's needle, so I whittled one out of black cherry and put it to work immediately without coating it with anything. The years of use have given it a finish I would never trade for anything that comes in a can. I also marvel at the natural finish that develops on well-worn hammer and wheelbarrow handles, railings, and chair arms once

Figure 12.11 • The unfinished finish of this carved catalpa grouse, obtained from weathering for many years, was more appropriate to the nature of the carving than any finish made. (Photo by R. Bruce Hoadley)



the original coating of paint or varnish has worn off. Unfinished wood typically darkens or "ages" more rapidly than wood protected with coatings, especially coatings that contain ultraviolet filters. However, the anticipation of color change can be an integral part of the design of any wooden object, and the patina developed over time on a wood surface can be a valuable asset.

The no-treatment finish also has fantastic potential for outdoor wood objects as well. But the effects of the elements will be far more drastic and complicated, and the changes that will take place must be understood and anticipated. We somehow seem obsessed with the idea that everything must be made to last forever. Consequently, we often fail to take advantage of nature's own progression. Why not consider a finite life for an object and allow gradual deterioration to take place, especially where the effect is beautiful?

In nature we see examples of fallen trees and weathered driftwood where silvery-gray sculptured surfaces surpass all human creativity. In building design and architecture, the natural aging of materials has long been used to both decorative and functional advantage. Likewise, sculpture can become more and more attractive as the ravages of time erode the surface and establish a venerable graying, as in the totems of the Pacific Northwest. By sensible selection of wood species and intelligent sculptural design, this deterior-

ation can be programmed into the life of the piece. If a decay-resistant species is chosen and the design permits water to run off, deterioration can be restricted to surface weathering. Many years ago, I carved a ruffed grouse and set it out on a post next to my driveway (*Figure 12.11*). It was caned out of catalpa and left unfinished. Over time, the weathered surface of grays and browns became more appropriate to the subject of the carving than any finish I could have applied. Because it was mounted "high and dry" and because catalpa is quite resistant to decay, it remained intact for about 25 years. Toward the end, the beak eroded back and the tail split, so it was "retired." If I had it to do over, I'd use the same nonfinish.

The weathering of wood is a combination of physical, mechanical, and chemical effects. The wetting and drying of the surfaces cause expansion and compression set followed by shrinkage, resulting in surface checking. Water that freezes and expands in the surface leads to further breakdown. Ultraviolet radiation also causes the surface structure to deteriorate. Windborne particles abrade the surface. Despite all this, weathering alone will remove only about $\frac{1}{4}$ in. of wood per century from exposed surfaces.

Normally the breakdown of lignin leaves a cellulosic residue on the surface, which along with water staining produces a predominantly gray color. Dark woods tend to

lighten as they weather, and light woods tend to darken. Some species develop a silvery-gray color, others a dark gray or a brownish tinge. However, the moisture condition of the wood can complicate the process, especially when it remains high enough to allow fungi to grow. In such cases, uneven surface discoloration and darkening may result before normal weathering develops. Commercial "bleaching oils" that contain water repellents and fungicides are used as an initial treatment for exposed shingles and boards to give temporary, superficial protection until natural weathering takes over. Understanding and using natural weathering to advantage seems to be among the lost arts. But it frequently is far more gratifying to understand and work with nature than to strive for results in defiance of natural forces.

COATING TREATMENTS

The most universally used finishes are the transparent coating treatments applied to the surface. The word varnish is sometimes used loosely to include any or all such treatments. Usually, however, it refers more specifically to those clear finishes consisting of tough resins dissolved in oil-based solvents. When the solvent, or vehicle, evaporates, the resin hardens, or polymerizes, and remains firmly adhered to the wood surface.

Modern varnishes are specified according to their resins. The newer synthetic varnishes, especially urethanes, are applied by hand easily and are extremely tough. Various chemical additives can produce a full range of surfaces from high gloss to dull satin. A varnished surface is highly resistant to water and alcohol.

Another traditional favorite is shellac varnish, usually called simply shellac. It is quick drying, easily applied, adheres well, and although not as water-resistant as other varnishes is generally appropriate for interior surfaces. Shellac is a natural gum secreted by the lac bug, an insect found in southern Asia. The finish is prepared by dissolving this gum in denatured alcohol. When applied, the alcohol quickly evaporates, leaving a film of shellac. The shellac can be resoftened by alcohol, however, so the finish is not effective on surfaces where alcoholic beverages might be spilled.

The third major coating finish is lacquer. The principal variety has a nitrocellulose resin in a vehicle such as amyl acetate. Lacquers are crystal clear and available in formulations suited to either spraying or brushing. They harden by loss of solvent but do not build layers as thick as most varnishes.

In recent years, concerns about environmental air quality have prompted legislation in many states to limit the volatile organic compounds (VOCs) released by finishing materials.

As a result, chemists have new formulations of old recipes and some new finishes altogether.

Clear water-based finishes are one of this class, and while relatively new to the market, they are growing in popularity. When they first came on the scene, water-based finishes were embraced by woodworkers for their ease of cleanup and quick drying times, even though they were not as durable as the old oil-based finishes. New formulations of water-based finishes are tougher and more UV-resistant, and they are beginning to rival the old standbys for suitability in a wide variety of conditions.

Even with a flat, true surface, achieving a fine smooth finish with a varnish-type coating takes some effort. The surface should be freshly sanded to avoid raised whiskers, and then cleaned with a tack rag. Woods with open grain—that is, which drink up finishing material, as redwood does—are often sealed before the final finish goes on. Suitable sealers include a dilute coat of shellac, a special lacquer sealer, or a dilute coat of the final finish itself. When you want a perfectly smooth surface, woods with large open pores such as oak or walnut should be given a coat of paste wood filler. Like much advice in finishing, fillers are a matter of taste, not an obligatory step. If you like the surface open pores impart, there is no rule requiring you to fill them.

Once the surface is prepared, it's vital to take the time to study the label on the can. It will specify suitable staining and sealing materials and will typically warn against incompatible solvents or stains. It may also say something about timing, since many modern resin varnishes must be recoated within a specified time or else the second and subsequent coats will not bond with the first.

A frequent difficulty encountered in applying varnish-type finishes in the home shop or small commercial shop is dust. The surface tension around a dust particle landing in a film of wet finish causes a noticeable blemish, which must later be sanded out. For those who must do finishing in the same location as woodworking, it is impossible to produce even a reasonably dust-free surface. The faster-drying lacquer and shellac finishes have an advantage in these situations.

A photographer offered me a great trick for reducing airborne dust particles in a workroom. About a day or two before the finishing job, "dust" around the room to remove much of the dust and stir up the rest. Then set up a 20-in. window fan in the middle of the room with a 20-in. by 20-in. furnace filter sprayed with Endust or equivalent against the intake side. Over the next 24 to 48 hours, redust the flat surfaces in the area. Meanwhile, the fan will recycle the air in the room many times, and the filter will catch most of the airborne dust. The difference will be evident by the change in color of the filter, as well as by the drastic reduction of dust specking on the subsequent finishing work.

Bubbles are another problem. They sometimes result from striking the brush off on the side of the can, then the bubbly varnish drips back onto the liquid surface in the can and makes the remaining varnish bubbly. Keep the bubbles out of your varnish by striking off the brush into an empty coffee can. A few bubbles are to be expected, but if the varnish is thinned properly they will break within a few minutes and the film will settle without a blemish.

Temperature change can also cause serious bubble problems. I stumbled onto this fact one time when I decided to avoid my dusty cellar shop and varnish a yellow birch candlestand in the most dust-free room in the house—the dining room. I spread my drop cloth, set everything up, dusted the room, and returned to the cellar to let any remaining dust settle. Meanwhile, I strained the varnish and got the brush worked in. I brought the candlestand upstairs to the dining room, gave it a last whisk with a tack rag, and started by varnishing the underside of the top. Everything appeared to be going well, but as I finished the second leg I noticed the first leg was speckled with bubbles. As I brushed out the bubbles on the first leg, I could see more developing on the second leg. I was baffled. The brush was in perfect condition, and the varnish can was virtually free of bubbles.

After long puzzling moments of watching bubbles appear before my eyes, I realized that each bubble developed at the end of a vessel opening. Then came the dawn. The cellar was considerably cooler than the dining room. When I brought the work into the warmer room, the air inside the wood gradually began to expand. Each vessel had become a minute bubble pipe! I've since verified my observation through controlled experiments in the laboratory. Since then I always make certain that a piece to be varnished is kept at an even temperature or moved from a slightly warmer to a slightly cooler location just before finishing. No more bubble problems of that type.

Since everything I varnish seems to wind up with dust specks, I sand lightly between coats with 280-grit paper on a flat block just enough to knock the tops off the dust spots, then go over the whole surface lightly with 5/0 steel wool followed by a tack rag. After the final coat, I use 600-grit paper on a good flat block and work carefully to level every high spot flush with the surroundings. Here is where corns on the paper cause trouble. Next, I rub with pumice and oil, then with rottenstone and oil. Last is a rub with lemon oil or sometimes paste wax. No question about it, this method makes an attractive finish, but during all these stages of work you really become aware that you are working on the finish coating, not upon the wood.

PENETRATING FINISHES

The third general type of finish is *in* the wood, not on the surface. Oil finishes, or penetrating resin-oil finishes such as Watco and Minwax, are in this category. To apply, the finish is simply flooded onto the surface and as much as possible is allowed to soak in. Additional finish is applied to any dry spots that develop. After 15 to 30 minutes, any remaining liquid is removed from the wood surface, and the surface is buffed dry in the process. Most of the finish remains in the cell cavities or is absorbed by the cell walls. Only an imperceptible amount covers the exposed wood surfaces. Repeated coats give more complete and deeper treatment and result in a very slight build on the surface. Enough finish remains to accent the figure of the wood, but there is the illusion that none really covers the surface (*Figure 12.12*). This finish is a delightful compromise when the natural wood surface is preferred but some protection is needed. A penetrating oil finish also can fill the open pores of the wood if it is sanded with fine-grit wet-dry paper while it is soaking in. This makes a fine paste of wood mixed with finishing material, and subsequent buffing pushes this mixture into the pores and levels the surface.

Linseed oil is a traditional favorite, but since it does not harden completely, it may later bleed out on the surface. It




Figure 12.12 • This catalpa carving of mushrooms stands 5 in. tall and is finished with several coats of Watco oil and a coat of paste wax. (Photo by Randy O'Rourke)

also attracts dirt, yellows in color, and darkens the wood. Commercial penetrating finishes have resins that polymerize in time and become permanently set in the wood, consolidating and hardening the surface.

A real advantage of oil finishes in the small shop is that there is no trouble from dust because any remaining liquid is wiped free. They are truly quick and easy to apply. However, experience soon reveals that the time saved in finishing with oils might well be invested in preparing the surface. Penetrating finishes are the acid test of surface condition, especially smoothness and quality, because every imperfection is not only exposed by lack of surface build but is in fact accented even more than if the wood were left unfinished. It really pays to "de-whisker" the surface because the real quality of an oil finish is determined by the surface quality of the wood itself. This is in contrast to a varnish finish, which masks many slight imperfections, scratches, and tearouts in the wood and where the final surface belongs to the varnish, not to the wood.

COMBINATIONS AND COMPROMISE

I love to experiment with finishes, and it seems I always wind up trying something I've never tried before (*Figure 12.13*). I especially like to try to amalgamate varnish and oil finishes (*Figure 12.14*). A good starting point is a mixture of one part boiled linseed oil, one part alkyd varnish, and two parts turpentine. Go heavy on the turpentine for better penetration; go heavy on the varnish for more build. Don't go heavy on the linseed oil, but you might substitute something else, such as tung oil. The result is somewhere in between a varnish finish and a commercial penetrating finish. It wipes on dust-free but gives more build, depending on proportions.

Over the years I have become intrigued with tung, or chinawood, oil. It is about as close to the one-shot all-purpose finish as I can imagine. Tung oil is an aromatic natural drying oil that is obtained from the nut of the tung tree (*Aleurites* spp.), originally from China but now grown extensively in the southern United States. Commercial preparations contain a drying agent and can be used as purchased. Tung oil can be applied directly to the wood surface much as other oil finishes, but it's a good idea not to allow it to remain more than about 15 minutes before wiping clean. This is because it sets up more quickly than most oil finishes. After a couple of hours drying, the surface can be recoated. It gives a better build than the usual penetrating oil finishes, and it holds up well outdoors. I have found it to be the most satisfactory treatment for outdoor thresholds. I have also used it for everything from kitchen furniture to woodcarvings and wooden jewelry.



Figure 12.13 • Black shoe polish with a top coat of paste wax makes an attractive finish for this n-in.-tall eastern white pine carving. (Photo by R. Bruce Hoadley)

Figure 12.14 • This black walnut carving measures 8 in. tall and is finished with an oil/varnish mixture. The hair has been rough-sanded, the face fine-sanded, and the chisel marks were left on the neck. (Photo by Randy O'Rourke)



SLOWING MOISTURE EXCHANGE

Although a primary objective of finishing treatments is to prevent moisture exchange, no finish is totally effective at doing so. Given enough time, moisture will be adsorbed into wood from a humid atmosphere or will escape to a dry atmosphere through any finish. But as discussed earlier, the important role of the finish is to retard the rate of exchange enough to buffer the temporary extremes of high and low humidity. Obviously, some finishes are better than others in this respect. The effectiveness of a particular finish may also be affected by the number of coats applied and the time of exposure to a different humidity level.

Research conducted at the U.S. Forest Products Laboratory at Madison, Wisconsin, under the leadership of

TABLE 12.1—Moisture-excluding effectiveness of various finishes on ponderosa pine*.

Finish	Moisture-excluding effectiveness (%)				Finish	Moisture-excluding effectiveness (%)			
	No. of coats	1 day	7 days	14 days		No. of coats	1 day	7 days	14 days
Linseed oil sealer (50%)	1	7	0	0	Alkyd house primer paint (tall maleic alkyd resin)	1	85	46	24
	2	15	1	0		2	93	70	49
	3	18	2	0		3	95	78	60
Linseed oil	1	12	0	0	Enamel paint, satin (soya/tung/alkyd; interior/exterior)	1	93	69	50
	2	22	0	0		2	96	83	70
	3	33	2	0		3	97	86	80
Tung oil	1	34	0	0	4	98	92	85	
	2	46	2	0	5	98	93	88	
	3	52	6	2	6	98	94	89	
Paste furniture wax	1	6	0	0	Floor and deck enamel (phenolic alkyd)	1	80	31	18
	2	11	0	0		2	89	53	35
	3	17	0	0		3	92	63	46
Water repellent	1	12	0	0	Shellac	1	65	10	3
	2	46	2	0		2	84	43	20
	3	78	27	11		3	91	64	42
Latex flat wall paint (vinyl acrylic resin)	1	5	0	0	4	93	75	58	
	2	11	0	0	5	94	81	67	
	3	22	0	0	6	95	85	73	
Latex primer wall paint (butadiene-styrene resin)	1	78	37	20	Nitrocellulose lacquer	1	40	4	1
	2	86	47	27		2	70	22	8
	3	88	55	33		3	79	37	19
Alkyd flat wall paint (soya alkyd)	1	9	1	0	Floor seal (phenolic resin/tung oil)	1	31	1	0
	2	21	2	0		2	80	37	18
	3	37	5	0		3	88	56	35
Acrylic latex house primer paint	1	43	6	1	Spar varnish (soya alkyd)	1	46	6	0
	2	66	14	2		2	80	36	15
	3	72	20	4		3	87	53	30
Acrylic latex flat house paint	1	52	12	5	Urethane varnish (oil-modified)	1	55	10	2
	2	77	28	11		2	83	43	23
	3	84	39	16		3	90	64	44
Solid-color latex stain (acrylic resin)	1	5	0	0	4	91	68	51	
	2	38	4	0	5	93	72	57	
	3	50	6	0	6	93	76	62	
Solid-color oil-based stain (linseed oil)	1	45	7	1	Aluminum flake pigmented urethane varnish (oil-modified)	1	90	61	41
	2	84	48	26		2	97	87	77
	3	9	64	42		3	98	91	84
FPL natural finish (linseed-oil-based semitransparent stain)	1	62	14	3	4	98	93	87	
	2	70	21	6	5	98	94	89	
	3	76	30	11	6	99	95	90	
Semitransparent oil-based stain (commercial)	1	7	0	0	Polyurethane finish, clear (two components)	1	48	6	0
	2	1	0	0		2	90	66	46
	3	21	1	0		3	94	81	66
Marine enamel, gloss (soya alkyd)	1	79	38	18	Polyurethane paint, gloss (two components)	1	91	66	44
	2	91	66	46		2	94	79	62
	3	93	74	57		3	96	86	74
					Paraffin wax, brushed	1	97	82	69
					Paraffin wax, dipped	1	100	97	95

*Specimen was initially finished and conditioned to 28°C (80°F) and 20% RH, then exposed to the same temperature and 90% RH.

Source: The Wood Handbook: Wood as an Engineering Material, Gen. Tech. Rep. FPL-GTR-113, Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory, 1999.

Dr. William Feist, investigated the moisture-excluding effectiveness of different finishes on a standard wood sample. The effects of multiple coats and different periods of exposure were included in the study. A summary of the results is given in *Table 12.1*. Although the values listed in and of themselves have little direct meaning, the numerical data give an excellent basis for comparative rating among the finishing materials listed.

It is easy to imagine that the first coat of finish, while penetrating, may disperse itself into the cell structure. After curing, however, it provides a barrier that concentrates subsequent layers at the surface to form a more complete barrier. It would seem then that in the case of penetrating finishes, multiple coats are especially crucial to developing moisture retardance. It is also important to recognize the difference between moisture-repellant finishes and moisture-excluding finishes. A moisture repellent is highly effective in preventing the intrusion of liquid water but may have no effectiveness in retarding the passage of molecular water vapor.

If there is anything worse than no moisture barrier at all, it's an uneven moisture barrier, which allows moisture to be adsorbed or desorbed unequally in different areas of the wood. In carcase pieces, for example, it is tempting to work conscientiously on the exposed surfaces and forget the insides. It is crucial that all sides of every board receive equal finish. The concept of balanced construction also applies to finishes. Forgetting this is a major cause of surface cupping. For this reason, many experienced cabinet-makers finish all the wood in a carcase before final assembly, taking care not to drip finishing material onto gluing surfaces, which can be protected with masking tape. In frame-and-panel construction, this is the only way to be sure that an unfinished line will not appear along the edge of a raised panel. It is also an effective way to avoid having to rub down finish in tight corners.

EVALUATION OF FINISHED SURFACES

One of the most effective ways to evaluate the quality of finished surfaces is by observing line patterns reflected at low angles across a surface. You need only a target card with boldly ruled horizontal, vertical, and diagonal lines (*Figure 12.15*). Hold this card perpendicular to the surface, and examine the lines reflected on the surface. The clarity of the reflection will reveal the relative uniformity of gloss developed in the finish. Waviness or discontinuities in the lines will indicate the lack of surface trueness, evenness, and smoothness. Generally, such defects as sunken joints, raised grain, and lathe checks can be pinpointed.




Figure 12.15 • The smoothness and gloss of a finish are indicated by how it reflects a black-lined target card. Surface roughness is indicated by distortion or breakup of the lines. Glue-line creep will show as an abrupt breakup in diagonal vertical-line reflections. (A) Reflection on Formica over plywood. (B) Reflection on a marquetry tabletop. (Photos by Richard Starr)

PRESERVATIVE TREATMENT OF WOOD

When wood is used in a location where its moisture content can range above 20%, finished or not, wood-inhabiting fungi will probably take up residence. Termites and carpenter-ant infestations are also encouraged by high moisture content, and some insects are troublesome even in dry wood. Certain wood species have heartwood extractives that resist the attack of fungi and are termed decay-resistant or durable woods (see *Table 2.1* on p. 44), while certain woods have selective resistance to insect attack. In many cases, however, where conditions favorable to biological deteriora-

TABLE 12.2—Penetration of the heartwood of various softwood and hardwood species*.

Ease of treatment	Softwoods	Hardwoods
Least difficult	Bristlecone pine (<i>Pinus aristata</i>) Pinyon (<i>P. edulis</i>) Ponderosa pine (<i>P. ponderosa</i>) Redwood (<i>Sequoia sempervirens</i>)	American basswood (<i>Tilia americana</i>) Beech (white heartwood) (<i>Fagus grandifolia</i>) Black tupelo (blackgum) (<i>Nyssa sylvatica</i>) Green ash (<i>Fraxinus pennsylvanica</i>) Pin cherry (<i>Prunus pensylvanica</i>) River birch (<i>Betula nigra</i>) Red oaks (<i>Quercus</i> spp.) Slippery elm (<i>Ulmus rubra</i>) Sweet birch (<i>Betula lenta</i>) Water tupelo (<i>Nyssa aquatica</i>) White ash (<i>Fraxinus americana</i>)
Moderately difficult	Baldcypress (<i>Taxodium distichum</i>) California red fir (<i>Abies magnifica</i>) Douglas-fir (coast) (<i>Pseudotsuga menziesii</i>) Eastern white pine (<i>Pinus strobus</i>) Jack pine (<i>P. banksiana</i>) Loblolly pine (<i>P. taeda</i>) Longleaf pine (<i>P. palustris</i>) Red pine (<i>P. resinosa</i>) Shortleaf pine (<i>P. echinata</i>) Sugar pine (<i>P. lambertiana</i>) Western hemlock (<i>Tsuga heterophylla</i>)	Black willow (<i>Salix nigra</i>) Chestnut oak (<i>Quercus prinus</i>) Cottonwood (<i>Populus</i> spp.) Bigtooth aspen (<i>P. grandidentata</i>) Mockernut hickory (<i>Carya tomentosa</i>) Silver maple (<i>Acer saccharinum</i>) Sugar maple (<i>A. saccharum</i>) Yellow birch (<i>Betula alleghaniensis</i>)
Difficult	Eastern hemlock (<i>Tsuga canadensis</i>) Engelmann spruce (<i>Picea engelmannii</i>) Grand fir (<i>Abies grandis</i>) Lodgepole pine (<i>Pinus contorta</i> var. <i>latifolia</i>) Noble fir (<i>Abies procera</i>) Sitka spruce (<i>Picea sitchensis</i>) Western larch (<i>Larix occidentalis</i>) White fir (<i>Abies concolor</i>) White spruce (<i>Picea glauca</i>)	American sycamore (<i>Piantanus occidentalis</i>) Hackberry (<i>Celtis occidentalis</i>) Rock elm (<i>Ulmus thomasii</i>) Yellow-poplar (<i>Liriodendron tulipifera</i>)
Very difficult	Alpine fir (<i>Abies lasiocarpa</i>) Corkbark fir (<i>A. lasiocarpa</i> var. <i>arizonica</i>) Douglas-fir (Rocky Mountain) (<i>Pseudotsuga menziesii</i>) Northern white-cedar (<i>Thuja occidentalis</i>) Tamarack (<i>Larix laricina</i>) Western redcedar (<i>Thuja plicata</i>)	American beech (red heartwood) (<i>Fagus grandifolia</i>) American chestnut (<i>Castanea dentata</i>) Black locust (<i>Robinia pseudoacacia</i>) Blackjack oak (<i>Quercus marilandica</i>) Sweetgum (redgum) (<i>Liquidambar styraciflua</i>) White oaks (<i>Quercus</i> spp.)

*As covered in MacLean (1952).
Source: The Wood Handbook: Wood as an Engineering Material. Gen. Tech. Rep. FPL-GTR-113, Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory, 1999.

tion cannot be avoided and where resistant species are not available, the best alternative may be to treat the wood with a substance that will give it the desired durability. Such chemicals are called **wood preservatives**. (This term sometimes includes treatments to make the wood nonflammable, although the term **fire-retardant** is preferred for such materials.)

The ideal preservative would readily penetrate the wood and be permanently toxic to fungi and insects, safe to handle, colorless, compatible with coatings and finishes, and of course, inexpensive. No one chemical has yet been devel-

oped that has all of these attributes, but a wide array of chemicals with various advantages has emerged for specific purposes.

Coal-tar creosote has been used commercially to preserve such things as railroad ties and utility poles. Oil-borne preservatives, such as pentachlorophenol and copper naphthenate, and some water-borne preservatives, mostly salts of copper, zinc, chromium, and arsenic, also have been employed—each of these has specific advantages and disadvantages. As regulations regarding preservatives are constantly changing, many of the preservatives widely used in

the past are now banned for use in buildings where human contact may occur. EPA-approved proprietary brands are available at retail building-materials dealers.

The key to the performance of preservatives is penetration. Only areas of the wood that are penetrated by preservative chemicals will be protected. A first consideration, then, is choosing the most penetrable wood. Generally, sapwood or species with low extractive content (e.g., ponderosa pine)—often those that have the least natural decay resistance—are the best choices for preservative treatment. *Table 12.2* groups selected species according to ease or difficulty of penetration by preservatives. Except for very thin pieces, the only way to attain any worthwhile degree of penetration is under pressure. Commercially, this is done by using cylinders that produce pressures up to about 150 psi and sometimes also by using vacuum treatment or elevated temperatures. Since such operations are beyond the capability of the average woodworker, it is usually most logical to buy commercially treated lumber for use where constant moisture problems prevail.

Building materials treated with wood preservatives are now commonly available at retail lumberyards. The treated products include dimensioned lumber, posts, landscape timbers, fencing, and plywood. Perhaps the most common preservative used in treating retail products is chromated copper arsenate (CCA), which is recognizable by the olive-green color it imparts to the wood.

Nonpressure treatments include soaking, dipping, and brush application. For any use involving contact with the soil or constantly wet or moist conditions, such as fence posts or sills lying on bare ground, nothing less than immersion in preservative for several days will be worth the expense and effort. The wood should be at least air-dried to facilitate penetration and to ensure that no further drying occurs after penetration, which might open checks and thus expose untreated wood.

Where possible to do so safely, heating the treating solution will improve penetration. Heating the wood expands and drives out air from the cell structure; when allowed to cool, the remaining air contracts, drawing the preservative solution into the cell structure. Cutting open a test piece can indicate the degree of penetration, while commercial preparations are available for determining the penetration of colorless materials.

Brush-and-dip methods give only superficial treatment and should be relied upon only where the wood needs surface protection, as with aboveground parts of a structure exposed to intermittent rainfall. Total immersion for a few minutes will do a far better job than brush treatment for reaching vulnerable voids such as bolt holes, deep end

checks, splits, and loose knots. Dipping or flooding the surface may give fairly good end penetration, but side-grain penetration by either method may be as little as $\frac{1}{32}$ in., varying somewhat according to species.

The most common mistake in using surface treatments is applying them after rather than before construction. Consider an outdoor structure such as a deck, porch, bench, boardwalk, railing, or flower trellis. During a rain, water seeps and settles into joints and crevices and is absorbed by the wood, especially at concealed end-grain surfaces such as the bottom ends of vertical posts resting on horizontal surfaces. After the rain, most exposed surfaces, particularly side-grain surfaces, dry quickly enough that fungal activity does not make significant progress. However, in hidden joints, water is held longer, absorption is prolonged, and drying is delayed.

The hidden surfaces of joints are therefore the most vulnerable places, and preservatives brushed on after construction seldom reach them. For this reason, every effort should be made to apply preservative to bolt holes, joint surfaces, and inside mortises before assembly. In nailing exposed horizontal surfaces such as deck boards or stair treads, nail heads should be driven in flush. Setting nails below the surface exposes end grain and creates a water pocket.

Preservative treatment, especially superficial brush treatment, can never compensate for poor design of an item. For exterior structures, promoting runoff and preventing entrapment of water should be primary considerations. Many modern fungicidal preservatives are both water-repellent and fungicidal; these are marketed as water-repellent preservatives. In combination with good design, brush application of these preservatives can be quite effective. Remember, however, that no brushed-on preservative will last forever. The chemical itself eventually leaches out of the wood, becomes diluted, or simply degrades after prolonged exposure to the weather. This deterioration takes place from the exposed surfaces inward, another reason why depth of penetration is so important.



Figure 13.1 • Dimension lumber—a common commodity found in lumberyards. (Photo by R. Bruce Hoadley)

LUMBER

When wood is mentioned, most people probably think of **lumber**. Lumber has been defined as the product of the saw and planing mill, with no further manufacturing other than sawing, resawing, passing lengthwise through a standard planing machine, crosscutting to length, and matching. The word lumber further carries the connotation of thickness (say, $\frac{1}{2}$ in. or more) in contrast to thin sheets of **veneer**. Lumber is also thought of as single-piece items of wood in contrast to pieces glued together as in **plywood** or **laminated** beams or fastened together as in **trusses**. Another feature of lumber is that the cell structure is undisturbed from its original state in the tree in contrast to the reoriented cell arrangement in **hardboard**, **fiberboard**, and **particleboard** or the distorted cell structure in **compreg** (compressed, impregnated wood). Abbreviations of common lumber terms are listed in *Table 13.1*.

In summary, then, lumber is simply an elongated, rectangular, solid piece of wood that has been separated from the log by sawing. Lumber is produced in a lumber mill or sawmill, where logs go through a characteristic sequence of operations in being reduced to lumber (*Figure 13.1*).

At the lumber mill, logs are stored in log ponds or in piles. Ponding allows one man to handle large logs, and storing the wood in water inhibits fungal growth and end-checking. In large mills the logs are first debarked. This is done for two important reasons. Debarking removes the embedded dirt and stones that would dull the milling equipment, and it allows the log slabs and edgings to be converted into high-grade (bark-free) pulp chips or particles for composite products. The bark is removed by grinding with mechanical cutterheads or by blasting with high-pressure water jets. The debarked logs are then rolled onto a sloping ramp called the **log deck** to await sawing.

A log to be sawn is loaded onto a **log carriage**, a low, heavy trolley mounted on tracks. A mechanism at the log deck rolls the log onto the carriage and turns it to the desired position. Dogs on the carriage firmly grip the log, holding it in place. By moving the position of the dogging system, the side of the log can overhang the edge of the carriage so that as the edge of the carriage passes the **headsaw**, a slab is cut




Figure 13.2 • Four ways to saw lumber. (A) In sawing around the log, the best face is sawn first. When defects are encountered, the log is turned to its next face, and so on. Defects are concentrated in the boxed heart. (B) Sawing through and through, or gang sawing, is used for low-grade logs. (C) Quartersawing yields edge-grain stock. First the log is quartered, then each log in turn is gang-sawn or returned to the carriage and sawn. (D) A chipping headrig first removes the outer residue, then boards of predetermined size are cut by a gang resaw.

TABLE 13.1—Abbreviations of common lumber terms.

AD: Air-dried	HDO: High-density overlay	MH: Mountain hemlock	SP: Specialty grade
AW&L: All widths and lengths	HEM: Hemlock	MSR: Machine stress-rated	SQ: Square
B&BTR, also B&B: Grade B and better	IC: Incense cedar	NSR: Not stress-rated	SR: Stress-rated
BD: Board	IN.: Inch or inches	P: Load, concentrated	SS: Select structural
BD, FT.: Board feet	IWP: Idaho white pine	PAD: Partially air-dried	STD: Standard
BDL: Bundle	J&P: Joists and planks	PP: Ponderosa pine	STK: Stock
BM: Board measure	JTD: Jointed	P&T: Posts and timbers	STR, also STRUCT: Structural
B&S: Beams and stringers	KD: Kiln-dried	R: Radial	S4S: Surfaced four sides
BTR: Better	L: Length	RC: Redcedar	S2S: Surfaced two sides
CLR: Clear	L: Larch	RDM: Random	SYP: Southern yellow pine
COM: Common	LBR: Lumber	RES: Resawn	T: Tangential
DET: Double end trimmed	LFT.: Lineal feet	RGH: Rough	TBR: Timber
DF: Douglas-fir	LGR: Longer	RL: Random lengths	T&G: Tongue and grooved
DIM: Dimension	LGTH: Length	RW: Random widths	VG: Vertical (edge) grain
D&M: Dressed and matched	LL: Longleaf	S: Shrinkage percentage	WCH: West Coast hemlock
DOUG FIR L: Douglas-fir or larch	LP: Lodgepole pine	S-DRY: Surfaced at a moisture content not exceeding 19%	WDR: Wider
E: Edge	M: Thousand	SEL: Select	WF: White fir
EE: Eased edges	MBF: Thousand board feet	SG: Slash or flat grain	WRC: Western redcedar
EG: Edge grain	MBM: Thousand (feet) board measure	S-GRN: Surfaced at a moisture content above 19%	WTH: Width
EM: End-matched	MC: Moisture content	SIT SPR: Sitka spruce	WW: White woods, any combination of Engelmann spruce, true fir, western hemlock, and white pine
EMC: Equilibrium moisture content	MC 15: Moisture content not exceeding 15%	SL: Shiplap	YP: Yellow pine
ES-AF: Engelmann spruce, alpine fir	MDO: Medium-density overlay	SM: Surface measure	
FAS: Firsts and seconds	MG: Mixed grain	SP: Sugar pine	
FG: Flat or slash grain			
FT BM: Foot board measure			

off. By advancing the log on successive passes of the carriage, board thicknesses are removed from the log.

Headsaws or headrigs are principally of two types: **band-saws** and **circular saws**. Sawmills commonly are referred to in terms of their headsaws as well as the type of lumber cut, so one might hear of a **hardwood circular mill** or a **softwood band mill**.

Band mills can be built for larger-sized logs and are therefore more prevalent among the large softwood timber mills in the western United States. Bandsaws have the added advantage of taking a narrower kerf. Circular saws typically have smaller capacity, and they are less expensive, making them suited to the smaller hardwood operations typical of the eastern and southern United States.

It is important to realize that logs usually contain their clearest material just under the bark. Because branches arise from the pith and commonly persist for a number of years, the core of the log near the pith has abundant knots. Therefore, when opening a log, the best-looking face is sawn first. After taking a **slab cut**, successive boards are removed as long as they are clear. When knots or other defects are encountered, the log is turned to the next clear-

est face and sawn until more defects appear (*Figure 13.2*). This removes the maximum amount of material in clearer grades and leaves the knot defects mostly boxed into the central portion. The center can then be sawn into low-grade lumber for pallet stock or crating, or it can be used intact as a timber or railroad tie. This process of sawing "around the log" produces mostly flatsawn or tangential lumber.

When a log has numerous defects, as is common with small logs, little is gained by turning. Such logs may therefore be sawn "through and through" (*Figure 13.2B*). Sawing low-grade logs this way is done most efficiently with a **gang saw**, a set of equally spaced sash saws or circular saws that makes an entire series of cuts during one pass of the log. A gang saw may serve as a headrig for low-grade logs, or a gang resaw is sometimes used to reduce large, clear cants or timbers into uniform boards for millwork, molding, or sash stock.

Quartersawing, on the other hand, produces edge-grain stock. As the term suggests, a large log is halved and then each half is redogged onto the carriage and quartered, the quarters in turn being resawn either a board at a time on the




Figure 13.3 • Quartersawn lumber at a utility price. Boards sawn through and through often contain pith and many knots. They are usually in wide widths for shelving. Take one of these boards and rip it twice to remove the pith. The result is two quartersawn boards, each with nearly perfect edge grain.




Figure 13.4 • From log to finished board: The typical sequence of manufacturing rough, green lumber at a sawmill.

headsaw or by being passed through a gang resaw. By using this method, the widest boards will be most truly edge-grained (*Figure 13.2C*).

In many applications, edge-grained stock is preferred because the radial surfaces have more uniform wearing and finishing properties and radially cut boards have greater dimensional stability across the width. There are drawbacks to quartersawing, however. It is certainly more time-consuming and often more wasteful. Also, major branches are likely to occur as spike knots across the wider boards, especially in smaller logs, and much of the outer clear material winds up in the narrowest boards. Quartersawing is therefore most appropriate for fairly large or reasonably clear logs or where the products need not be very wide (as in strip flooring).

The above considerations explain why quartersawn lumber is less common and more expensive than flatsawn lumber. Rather than insisting on quartersawn lumber, the woodworker often can take good advantage of softwood lumber that has been sawn through and through. Because many such boards contain the pith and lots of knots, they are usually sold in relatively wide pieces for utility shelving. Ripsawing down the center to remove the pith and crosscutting to remove the worst knots yield short lengths of clear, quartersawn stock at a utility price (*Figure 13.3*).

A modern innovation for optimum recovery from the log is the chipping headrig. Best suited for small logs of uniform size, this machine first trims them to a rectangular shape by using profile cutterheads, thereby reducing to chips or flakes (for pulp or composite board manufacture) the portions of the log that would normally be removed as slabs, edgings, and sawdust. The shaped log then proceeds through a gang saw, where specific lumber sizes are produced (*Figure 13.2D*).

After boards are separated, they are typically passed through an **edger**, a machine that has twin saws of adjustable spacing to remove bark edges or edge defects, leaving parallel edges on the board. The board then may be crosscut to length, with the defects cut out, in the **trimmer**. The board moves out of the mill along a conveyor called the **green chain** (*Figure 13.4*) to be sorted by size and species. At this stage, the lumber has sawtooth marks on its surfaces and is termed **rough lumber**. Hardwood lumber is then graded for shipping from the mill.

Softwood lumber is normally dried and dressed at the mill where it is produced. The lumber may be stacked outdoors in piles to air-dry or dried to prescribed levels in kilns. The dry, rough lumber then goes to the **planing mill**, where it is dressed to uniform thickness.

Usually both sides and both edges are dressed (surfaced four sides, abbreviated S4S), or at least both surfaces are dressed (S2S), leaving the edges roughsawn. In the planing

mill, the lumber may be **matched** (dressed on both surfaces and tongue-and-groove edged), **shiplapped** (edges rabbeted), or **patterned** (molded to a special shape, such as casings, coves, and panel moldings).

LUMBER MEASURE

Lumber is typically sold by volume according to its nominal size. Nominal size refers to the dimensions when rough-sawn. The unit of volume is the **board foot** (bd. ft.), equivalent to a piece of lumber 1 ft. long, 1 ft. wide, and 1 in. thick, or 144 cu. in. (*Figure 13.5*). Softwood lumber is usually produced in rough-size multiples, in which thickness and width are given in inches and length in feet. A piece of framing lumber, for example, might be sawn 2 in. by 10 in. rough (called a two-by-ten, simply written 2x10), although it will be dressed to standard dimensions of 1½ in. by 9¼ in. as shown in *Table 13.2*. Similarly, a 1x12 board (roughsawn 1 in. by 12 in.) will be dressed dry to ¾ in. by 1¼ in. (Lengths are expressed in actual measurement.) A 1x12 contains 1 bd. ft. per lineal (running) foot. A 2x10 contains ⅔ bd. ft. per lineal foot.

The price is calculated by the bd. ft. volume the piece had *before* surfacing. This system is based on the logic that the discrepancy in volume between nominal and actual dimensions reflects the material lost in shrinkage perpendicular to the grain during drying and the necessary removal of material to improve the surface—losses that the buyer would suffer later if these services were not provided as part of the manufacturing process. Millwork, such as moldings and sash stock, is usually measured and sold by the lineal foot.

In hardwood lumber, rough nominal thickness is commonly expressed to the nearest quarter inch as a nonreduced fraction, so that 1-in. lumber is referred to as 4/4 (four-quarter) lumber. 1½-in. lumber is 6/4, 3-in. lumber is 12/4, and so on. Since hardwood lumber is normally sold on a random width and length basis, board footage is based on actual surface area and nominal thickness.

The usual way to calculate the board footage in a given piece of lumber is to multiply its thickness in inches by its width in inches by its length in feet and divide by 12.

$$\text{Board feet} = \frac{T(\text{in.}) \times W(\text{in.}) \times L(\text{ft.})}{12}$$

Lumber prices are typically based on the cost per thousand board feet (MBF), which is sometimes abbreviated MBM [Thousand (feet) board measure]. Thus red oak at \$2,500/MBF costs \$2.50 a board foot. However, MBF prices almost always increase as the quantity decreases because of the extra handling small quantities require.

TABLE 13.2—Standard American sizes for construction lumber.

Item	Thickness (in.)			Face width (in.)		
	Nominal	Minimum dressed Dry	Green	Nominal	Minimum dressed Dry	Green
Boards	1	3/4	25/32	2	1 1/2	1 9/16
	1 1/4	1	1 1/32	3	2 1/2	2 9/16
	1 1/2	1 1/4	1 9/32	4	3 1/2	3 9/16
				5	4 1/2	4 3/8
				6	5 1/2	5 3/8
				7	6 1/2	6 3/8
				8	7 1/4	7 1/2
				9	8 1/4	8 1/2
				10	9 1/4	9 1/2
				11	10 1/4	10 1/2
				12	11 1/4	11 1/2
				14	13 1/4	13 1/2
			16	15 1/4	15 1/2	
Dimension	2	1 1/2	1 9/16	2	1 1/2	1 9/16
	2 1/2	2	2 1/16	3	2 1/2	2 9/16
	3	2 1/2	2 9/16	4	3 1/2	3 9/16
	3 1/2	3	3 1/16	5	4 1/2	4 3/8
	4	3 1/2	3 9/16	6	5 1/2	5 3/8
	4 1/2	4	4 1/16	8	7 1/2	7 1/2
			10	9 1/2	9 1/2	
			12	11 1/2	11 1/2	
			14	13 1/2	13 1/2	
			16	15 1/2	15 1/2	
Timbers	5 and greater		1/2 less than nominal	5 and greater		1/2 less than nominal




Figure 13.5 • One board foot is 144 cubic inches of wood.

TABLE 13.3—Lumber classification based on use, degree of manufacture, and size.**Use classification**

1. *Yard lumber*: Lumber of those grades, sizes, and patterns generally intended for ordinary construction and building.
2. *Structural lumber*: Lumber 2 in. or more in nominal thickness and width for use where working stresses are required.
3. *Factory and shop lumber*: Lumber produced or selected primarily for remanufacturing.

Manufacturing classification

1. *Rough lumber*: Lumber that has not been dressed (surfaced) but has been sawn, edged, and trimmed at least to the extent of showing saw marks in the wood on the four longitudinal surfaces of each piece for its overall length.
2. *Dressed (surfaced) lumber*: Lumber dressed by a planing machine (for the purpose of attaining smoothness of surface and uniformity of size) on one side (S1S), two sides (S2S), one edge (S1E), two edges (S2E) or a combination of sides and edges (S1S1E, S1S2E, S2S1E, S4S).
3. *Worked lumber*: Lumber that, in addition to being dressed, has been matched, shiplapped, or patterned.
 - a. *Matched lumber*: Lumber worked with a tongue on one edge of each piece and a groove on the opposite edge to provide a close tongue-and-groove joint; when end-matched, the tongue and groove are worked in the ends also.
 - b. *Shiplapped lumber*: Lumber rabbeted on both edges of each piece to provide a close-lapped joint.
 - c. *Patterned lumber*: Lumber shaped to a pattern or to a molded form, in addition to being dressed, matched, or shiplapped, or any combination of these.

Size classification

1. *Nominal size*
 - a. *Boards*: Lumber less than 2 in. in nominal thickness and 2 in. or more in nominal width. Boards less than 6 in. in nominal width may be classified as strips.
 - b. *Dimension*: Lumber from 2 in. to, but not including, 5 in. in nominal thickness and 2 in. or more in nominal width. Dimension lumber may be classified as framing, joists, planks, rafters, studs, small timber, etc.
 - c. *Timbers*: Lumber nominally 5 in. or more in least dimension. Timber may be classified as beams, stringers, posts, caps, sills, girders, purlins, etc.
2. *Rough-dry size*: The minimum rough-dry thickness of finish, common boards, and dimensions of size 1 in. or more in nominal thickness shall not be less than $\frac{1}{8}$ in. thicker than the corresponding minimum finished dry thickness, except that 20% of a shipment may not be less than $\frac{1}{16}$ in. thicker than the corresponding minimum-finished dry thickness. The minimum rough-dry widths of finish, common strip, boards, and dimension shall not be less than $\frac{1}{8}$ in. wider than the corresponding minimum-finished dry width.
3. *Dressed sizes*: Dressed sizes of lumber shall equal or exceed the minimum American standard sizes (Table 13.2).

LUMBER CLASSIFICATION AND GRADING

Because of the many and varied uses and requirements for lumber, no single system of classification would be useful in every type of situation. It is therefore appropriate to classify lumber initially according to its use and further according to its degree of manufacture or on the basis of the size of the pieces (Table 13.3). Under various classification levels, **grades** are established that attempt to group pieces according to quality. There are broad general differences between softwoods and hardwoods, both with respect to the end uses and the manner of working. Softwoods generally are used in large sizes for building and construction. Much of the final working of softwood lumber is completed during its manufacture, so that pieces can be used full size with little or no additional surfacing. The bulk of hardwood lumber, on the other hand, is typically only roughly manufactured initially because it is cut to smaller pieces and further worked in the final processing of the finished product.

HARDWOOD LUMBER

Hardwood lumber falls into three basic marketing categories: **factory lumber**, **dimension parts**, and **finished market products**. The last category includes such items as flooring, millwork parts, and moldings, in which little or no further manufacture is needed. Grade designations for finished parts indicate appearance and general freedom from defect.

Factory lumber and dimension parts are both expected to receive further working in assembling the finished product. Dimension parts are processed so each piece can be completely used virtually in the size provided. Pieces are produced to specific sizes (rough or dressed) as either flat stock or squares. Within these categories, grades reflect freedom from defect and end-use suitability.

FACTORY LUMBER GRADES Most hardwood is manufactured as factory lumber, which is primarily intended to serve the industrial customer. Because it is assumed that the lumber will be cut up into smaller useful pieces, factory lumber is handled in random lengths and widths within thickness sortings. The grade is based on the proportion of a board that can be cut into a certain number of clear-faced cuttings not smaller than a specified size.

The hardwood factory grade rules generally used throughout the United States are those established by the National Hardwood Lumber Association (NHLA). These rules list the following grades in descending order of

TABLE 13.4—Minimum requirements for grading factory hardwood lumber.

Grade	Board size		Conversion factor (% clear face)	Minimum size of cuttings	Maximum number of cuttings for board SM
	Minimum width	Length			
Firsts	6 in.	8 ft.–16 ft.	11 x SM (91 ² / ₃ %)	4 in. by 5 ft. or 3 in. by 7 ft.	1 for SM 4 ft. by 9 ft. 2 for SM 10 ft.–14 ft. 3 for SM 15 ft. or more
Seconds	6 in.	8 ft.–16 ft.	10 x SM (81 ² / ₃ %)	4 in. by 5 ft. or 3 in. by 7 ft.	1 for SM 4 ft.–7 ft. 2 for SM 8 ft.–11 ft. 3 for SM 12 ft.–15 ft. 4 for SM 16 ft. or more
Selects	4 in.	6 ft.–16 ft.	11 x SM (91 ² / ₃ %) 10 x SM (83 ¹ / ₃ %)	4 in. by 5 ft. or 3 in. by 7 ft.	1 for SM 2 ft.–3 ft. 1 for SM 4 ft.–7 ft. 2 for SM 8 ft.–11 ft. 3 for SM 12 ft.–15 ft. 4 for SM 16 ft. or more
No. 1 Common	3 in.	4 ft.–16 ft.	9 x SM (75%) 8 x SM (66 ² / ₃ %)	4 in. by 2 ft. or 3 in. by 3 ft.	1 for SM 2 ft. 1 for SM 3 ft.–4 ft. 2 for SM 5 ft.–7 ft. 3 for SM 8 ft.–10 ft. 4 for SM 11 ft.–13 ft. 5 for SM 14 ft. or more
No. 2 Common	3 in.	4 ft.–16 ft.	6 x SM (50%)	3 in. by 2 ft.	1 for SM 2 ft.–3 ft. 2 for SM 4 ft.–5 ft. 3 for SM 6 ft.–7 ft. 4 for SM 8 ft.–9 ft. 5 for SM 10 ft.–11 ft. 6 for SM 12 ft.–13 ft. 7 for SM 14 ft. or more
No. 3A Common	3 in.	4 ft.–16 ft.	4 x SM (33 ¹ / ₃ %)	3 in. by 2 ft.	Unlimited
No. 3B Common	3 in.	4 ft.–16 ft.	3 x SM (25%)	1½ in. by 2 ft.	Unlimited

quality: Firsts, Seconds, Selects, No. 1 Common, No. 2 Common, No. 3A Common, No. 3B Common, Sound Wormy. The grade rules are summarized in *Table 13.4*.

Hardwood lumber is graded rough and usually in the green condition because there are no moisture-content specifications. Grading is determined from the poorer face of each board (except in Selects grade). More often than not, Firsts and Seconds are combined into one grade called Firsts and Seconds (FAS). Sound Wormy is similar to No. 1 Common, but worm holes are allowed.

Hardwood grades are specified according to the percentage of the total board surface [surface measure (SM) in square feet] that could be cut into the form of rectangular, clear-faced pieces (called cuttings). To determine this percentage, a unit of measure called the cutting unit is used. A cutting unit is equivalent to an area 1 in. wide and 1 ft. long (or 12 sq. in.). The number of cutting units in a cutting can be calculated quickly by multiplying the width in inches by the length in feet. There are therefore 12 cutting units in a square foot. The total number of cutting units in any board is simply its surface measure times 12 (SM x 12).




Figure 13.6 • Steps taken by a lumber grader to evaluate a typical board.

TABLE 13.5—Some major lumber-grading associations and the species under their jurisdiction.

Hardwood grading associations	Species
<p>Hardwood Manufacturers Association (HMA) 400 Penn Center Boulevard, #530 Pittsburgh, PA 15235 (800) 373-WOOD, (412) 829-0844 (fax)</p>	Hardwoods (hardwood furniture dimension, squares, laminated stock, interior trim, stair treads and risers)
<p>Maple Flooring Manufacturers Association 60 Revere Drive, Suite 500 Northbrook, IL 60062 (847) 480-9138, (847) 480-9282 (fax)</p>	Maple, beech, birch (flooring)
<p>National Hardwood Lumber Association P.O. Box 34518 Memphis, TN 38184-0518 (901) 377-1818, (800) 933-0318</p>	Hardwoods (furniture cuttings, construction lumber, siding, panels)
<p>National Oak Flooring Manufacturers Association P.O. Box 3009 Memphis, TN 38173-0009 (901) 526-5016, (901) 526-7022 (fax)</p>	Oak, pecan, beech, birch, hard maple (flooring)
Softwood grading associations	
<p>Cedar Shake & Shingle Bureau P.O. Box 1178 Sumas, WA 98295 (604) 462-8961, (604) 462-9386 (fax)</p>	Western redcedar (shingles and shakes)
<p>National Hardwood Lumber Association P.O. Box 34518 Memphis, TN 38184-0518 (901) 377-1818, (800) 933-0318</p>	Baldcypress, eastern redcedar
<p>Northeastern Lumber Manufacturers Association, Inc. 272 Tuttle Road P.O. Box 87A Cumberland Center, ME 04021 (207) 829-6901, (207) 829-4293 (fax)</p>	Balsam fir, eastern white pine, red pine, eastern hemlock, black spruce, white spruce, red spruce, pitch pine, tamarack, jack pine, northern white-cedar
<p>Southern Pine Inspection Bureau 4909 Scenic Highway Pensacola, FL 32504-9094 (850) 434-2611</p>	Longleaf pine, slash pine, shortleaf pine, loblolly pine, Virginia pine, pone pine, pitch pine
<p>West Coast Lumber Inspection Bureau P.O. Box 23145 Portland, OR 97281 (503) 639-0651, (503) 684-8928 (fax)</p>	Douglas-fir, western hemlock, western redcedar, incense cedar, Port-Orford-cedar, Alaska cedar, western true firs, mountain hemlock, Sitka spruce
<p>Western Wood Products Association 522 SW Fifth Avenue, Suite 500 Portland, OR 97204-2122 (503) 224-3930, (503) 224-3934 (fax)</p>	Ponderosa pine, western white pine, Douglas-fir, sugar pine, western true firs, western larch, Engelmann spruce, incense cedar, western hemlock, lodgepole pine, western redcedar, mountain hemlock, red alder

Each hardwood grade specifies the percentage of the surface area that must be in clear cutting units. This percentage is stated as some fraction with the denominator 12. Therefore, to determine the number of clear units a particular grade board must have, the total units in the board ($SM \times 12$) is multiplied by this fraction. For example, Firsts requires % of the board to be available in clear-face

cuttings. The total clear units in a board to make the grade of Firsts must therefore be:

$$\frac{11}{12} \times (SM \times 12) = 11 (SM).$$

The required units to make a particular grade can be calculated by multiplying the numerator of the fraction by the

TABLE 13.6—Grades and sizes of dimension yard lumber as designated by the American Lumber Standards Committee.

Category	Grades	Sizes
Light framing	Construction, Standard, Utility	2 in.–4 in. thick 2 in.–4 in. wide
Studs	Stud	2 in.–4 in. thick 2 in.–4 in. wide
Structural light framing	Select Structural No. 1, No. 2, No. 3	2 in.–4 in. thick 2 in.–4 in. wide
Appearance framing	Appearance	2 in.–4 in. thick 2 in. and wider
Structural joists and planks	Select Structural No. 1, No. 2, No. 3	2 in.–4 in. thick 6 in. and wider

surface measure. Thus, if a board has a surface measure of 9 sq. ft., it must have $11 \times 9 = 99$ cutting units in clear-face cuttings to be graded Firsts. This logic explains the fractional percentages (e.g., $91\frac{1}{2}\% = \frac{1}{16}$) specified in the grade rules.

A hardwood grader goes through several steps to evaluate a typical board (*Figure 13.6*). In practice, an experienced grader can assign grades to most boards with rather brief inspection, often in only a few seconds. However, boards at the borderline of a grade category must be measured individually by going through every step of the procedure. Because the hardwood rules are specific, the grade of each board can be assigned by precise numerical measurement rather than by depending on subjective judgment alone.

For the average woodworker, No. 1 Common may be the best all-around grade when price is considered against its yield of about 65% clear material. Where larger cuttings are needed, the FAS grade with its 80% to 90% yield may justify the much higher price. The best way to assess the overall quality of each grade, however, is to visit a dealer so you can look over material in the various grades.

Being able to grade hardwood lumber rapidly takes years of experience. However, with a basic knowledge of fundamentals and a grade book in hand to check the many details (which the grader has committed to memory), a woodworker can check-grade a shipment to determine whether it meets the specifications of the grade that was ordered.

SOFTWOOD LUMBER

The basis for most classification and grades of softwood lumber is the American Softwood Lumber Standard PS 20-94, established by the U.S. Department of Commerce through the American Lumber Standards Committee. Although specific grade rules for various species have been developed by many associations throughout the country, such as the Western Wood Products Association and the Southern Pine Inspection Bureau, there is general conformance to Standard PS 20-94. *Table 13.5* lists some of the major associations and the species for which they establish rules.

Although some softwood lumber is sold for remanufacture through industrial suppliers and wholesalers, most softwood lumber is for general construction and falls into three major categories: appearance lumber, nonstress-graded lumber, and stress-graded lumber. The term "yard lumber" is loosely applied to the appearance lumber and nonstress-graded softwood lumber commonly carried by retail lumberyards. This lumber is manufactured to final dressed size and is assumed to be usable in its full size. Unlike hardwood lumber, softwood lumber is assumed to be dried to some extent, so dimension specifications are tied to moisture content. For example, a 2x10 is dressed dry to $1\frac{1}{2}$ in. by $9\frac{1}{4}$ in.; if green, it is dressed to $1\frac{1}{16}$ in. by $9\frac{1}{2}$ in. (see *Table 13.2*). Pieces are graded after final surfacing. The grading is done on the better face of the piece, and grades are designated by describing the allowable size and number of defects, rather than by defining the necessary clear cuttings as in hardwoods.

Appearance grades are the highest grades, commonly termed Select or Finish. Originally grades ran A Select through D Select. However, because so few pieces would now meet A Select standards and because there is very little difference between A and B, the highest grade offered now is typically B and better (B&BTR). For western white or Idaho white pine (IWP), the B&BTR, C, and D Select grades are called Supreme, Choice, and Quality, respectively. C Select is slightly better for painted or clear-finished surfaces, while D Select has excellent potential for cutting into high-quality furniture or cabinet parts.

It is important to note that although appearance grades are the highest grades, they are not the strongest grades, being limited as to knots but not as to grain deviations, density, and rings per inch. Other yard lumber is graded on the basis of its general integrity for building. Boards other than Selects are usually separated into various common grades. Within dimension yard lumber, light framing 2x4s, for example, are graded as Construction, Standard, or Utility (*Table 13.6*). Structural joists and planks are graded as Select Structural No. 1, No. 2, or No. 3.





Figure 13.7 • Examples of softwood lumber grade stamps. A stamp typically designates the association whose grading rules are used and the manufacturing mill number, plus the grade, species, moisture condition, and sometimes the stress rating. For example, in the grade stamp shown above, the board was produced by Stimson-Arden, mill No. 212, of lodgepole pine or ponderosa pine, surfaced dry, and graded as No. 2 common or better under grade rules of the Western Wood Products Association. (Photo above by R. Bruce Hoadley; photo at right courtesy Western Wood Products Association)



Structural lumber, that is, lumber 2 in. or more in nominal thickness for use where working stresses are encountered, is stress-graded either visually or by machine to assign working stress values for bending stress (F_b), modulus of elasticity (E), and other properties.

Before lumber leaves the mill, it is grade-stamped with the emblem of the trade association that sponsors the grading standards and the number of the mill that manufactured the piece. The stamp gives the buyer critical information about grade, species, and moisture content, and if there is any question or complaint regarding the lumber, the responsible mill and association can be traced (Figure 13.7).



Figure 14.1 • Assorted veneers display the wide range of color and figure available in wood. (Photo by Randy O'Rourke)

VENEER AND PLYWOOD

As the supply of larger trees diminishes and the cost of wood continues to increase, veneer will become a more important part of the wood market. **Veneer** is wood in the form of a thin layer or sheet with the grain direction of the wood parallel to the surface. Common thicknesses are $\frac{1}{40}$ in. and $\frac{1}{20}$ in. for hardwood veneers used in furniture and cabinetmaking; thicknesses of $\frac{1}{10}$ in. to $\frac{3}{16}$ in. are common for softwood veneers used to manufacture plywood. Veneer can be cut as thin as $\frac{1}{100}$ in., but veneer this thin is too fragile for most uses. Thicknesses of up to about $\frac{1}{4}$ in. are classed as veneer, while knife-cut sheets of wood of greater thickness are called **slice-wood** (Figure 14.1).

Wood in the form of veneer has three important categories of application. The first is to decorate surfaces. Typically, veneer of high value or striking appearance is applied over a lower-quality substrate. Valuable or unusual wood can thereby be extended to cover far greater surface area than it could if used as boards. Veneer is also used to make decorative inlay, in the form of pictures or designs for covering large surfaces (marquetry), as well as in the form of geometric border strips for ornamenting furniture and small wooden objects.

The second application of veneer is its use in crossply construction for making plywood panels. The advantages of plywood over solid wood include more uniform strength across the panel in all directions and the virtual elimination of both splitting and dimensional instability.

The third category is veneer used where very thin wood is appropriate, as in tongue depressors, ice cream sticks, coffee stirrers, and the like. Veneers are also used in commercial containers such as fruit trays and baskets. Veneers can be bent to shapes, as in commercial basket making where knife-cut veneer has replaced traditional splint. Also, veneers can be formed to shape in a mold by gluing multiple layers. Contours and angles can be formed that otherwise cannot be attained with a single piece of wood of similar thickness without chemical modification. Bent laminations and molded plywoods are examples. A given application may embrace any or all three of the above categories.

Veneer dates back thousands of years as evidenced by Egyptian artifacts displaying surface decoration for art

objects and furniture. Veneer was probably first made by splitting thin slats of wood and painstakingly scraping them down to desired smoothness and thinness. The development of saws allowed larger sheets of wood to be cut, even from logs with irregular grain direction. In post-Renaissance Europe, handsawn veneer was the material of choice for the most lavish furniture. It permitted intricate pictorial effects and abundant use of rare and precious woods, on both flat and curved surfaces. But it wasn't until the last half of the 19th century that knife-cutting was developed as an important production technique.

Early in 20th century, veneering flourished in commercial furniture production, even in applications where solid wood had always been serviceable. But because the adhesives then in use could not resist moisture, delamination was commonplace. This earned veneered products a bad name that prevailed through mid-century. The assertion that furniture was "solid mahogany" or "solid cherry" or "solid" whatever implied superiority, despite the fact that some of the very finest furniture of the past several hundred years had been veneered. Even today, advertisers proudly proclaim that their rustic benches are made of "solid pine."

Since the development of moisture-resistant and fully waterproof adhesives, veneered products now can routinely be made with all the moisture-resisting integrity of solid wood. Veneer has regained its rightful place as a respectable medium for woodworking of all types.

Today, commercial sawing produces only a limited amount of veneer, either for specialty uses or from very dense or brittle species. Some craftsmen do saw their own veneer on a bandsaw to get the most from an unusual plank or to achieve a curved shape. Most commercial veneer, however, is knife-cut by using one of two basic techniques: rotary cutting and slicing.

In **rotary cutting**, a log is center-chucked at its ends in a large lathe (Figure 14.2). As the log revolves, a large knife peels off a continuous layer of veneer in a manner analogous to unrolling a roll of paper towels. During each revolution of the log, the knife uniformly advances toward the center of the log by one increment of veneer thickness. Rotary cutting has the advantage of high production rate, and the continuous veneer can be clipped into sheets of desired width. It is




Figure 14.2 • Cutting plywood veneers. Softwoods for plywood are rotary-cut with a veneer lathe, while hardwood veneers are typically sliced, either vertically (center) or horizontally. The illustration at right shows the relationships between nosebar and knife, which determine the quality of the veneer.

thus well suited to high-volume production of softwood veneer for structural plywood. However, peeling produces a continuous tangential cut, whose figure is recognizable as rotary veneer. It cannot masquerade as sawn lumber of greater thickness.

In **slicing** veneer, a log portion, called a **flitch**, is first prepared by sawing. The flitch is firmly dogged in a horizontal position against a rugged frame that can move up and down. A veneer knife, also mounted horizontally, is positioned alongside the flitch. A slice of veneer is produced as each downward stroke of the frame forces the flitch against the knife, the knife being advanced toward the flitch by one thickness of veneer after each upstroke. As they are cut, the veneer slices are kept in sequence so that after drying they can be restacked in the original order of cutting. This reassembled package of all the veneers from the same piece is also called a flitch. For commercial use in production or architectural applications, the entire flitch is the customary sales unit. For smaller-quantity sales, a flitch of veneer may be divided into **books**, each consisting of successive **sheets** or leaves of veneer.

In slicing, the production rate is much lower than in peeling, and the dimensions of the flitch govern the width of veneer sheets. However, the manner of sawing the flitch and the position in which it is mounted in the slicer control the growth-ring orientation to produce a desired figure. Because the veneers are sliced straight through the log, their figure is indistinguishable from that of board surfaces. Various meth-

ods of flitching logs are shown in *Figure 14.3*. Rotary cutting can be modified by off-center chucking or by **stay-log** cutting to produce **half-round**, **back-cut**, or **rift-cut** veneers. (*Figure 14.4*).

Despite the obvious differences between lathes and slicers, the cutting action that separates the veneer layer is essentially similar in both. As the knife separates the veneer from the flitch, the separated layer of wood is severely bent and stresses build up in the region near the knife edge. If the strength of the wood is exceeded, the stress is relieved by failure, and the plane of failure thus formed is called a **knife check** (see *Figure 9.24* on p. 170). This bending and breaking cycle continues, and each sheet of veneer is liable to have regular checks across the side that was against the knife during the cut. This side is called the **loose side** or **open face**. The side that was away from the knife is called the **tight side** or **closed face**.

The tendency to develop knife-checking varies according to the species of wood, the temperature of the wood, the thickness of cut, and the accuracy maintained in the slicing machinery, particularly the setting of the nosebar. Diffuse-porous hardwoods with fine, well-distributed rays, such as birch, cut cleanly and are more likely to yield tight, uniform veneer. Coarse ring-porous hardwoods, such as red oak, can be severely knife-checked, particularly in thicker sheets.

The tightness of a piece of veneer can be assessed by manually flexing it. The veneer will feel stiffer when flexed to close the checks but more limp when the checks are flexed




Figure 14.3 • Many ways to cut veneer. The basic cutting directions can be modified to vary the figure. Such modifications include half-round cutting, off-center chucking, and stay-log cutting. The species in parentheses are commonly cut by each method; wide dark lines represent the backboards left after cutting.

open (*Figure 14.5*). Veneer with a rough or corrugated surface is probably loosely cut (*Figure 14.6*). Veneer that flexes about as easily both ways is considered tight.

Knife checks are of more than academic interest. The most common consequence is parallel-to-grain cracks through the finish on the veneered surface (*Figures 14.7, 14.8*). This problem is especially aggravating because the cracks may not appear for months or years after the work is done. Glue may also bleed through the previously invisible checks, showing up as dark lines in light-colored woods or causing finishing problems. In plywood, knife checks may cause a type of failure known as rolling shear (see *Figure 4.22* on p. 87). Therefore, inspect veneers for tightness




Figure 14.4 • Veneer being cut by half-rotary method. (Photo courtesy University of Massachusetts)




Figure 14.5 • Veneer flexes more easily when checks are opened (A) than when they are closed (B). This simple test distinguishes the tight and loose faces. (Photos by Randy O'Rourke)



Figure 14.6 • The loose side of Douglas fir veneer shows roughness associated with lathe checks. (Photo by Randy O'Rourke)



Figure 14.7 • After several years of exposure to variable humidity, the lathe checks in the oak veneer on this cabinet fractured the surface coating of varnish (A). The corrugation on this maple veneer identifies the loose surface (B). (Photo A by R. Bruce Hoadley; photo B by Richard Starr)

before using them. Whenever possible, the loose side should be the one spread with glue. With luck, the glue will penetrate the checks and keep them closed. Take care when the time comes to sand, since it's easy to sand through the tight surface into the knife checks. Book-matched patterns present a problem, since the veneer must be placed with alternate open and closed faces up. Thus, it is especially important to avoid loose veneers when book-matching.

Any mill with adequate quality control can manufacture veneers with reasonable tightness. Beware of loose veneer being sold at bargain prices. The best guideline is to buy veneer from reputable dealers and to know how to detect knife checks.



Figure 14.8 • To indicate the depth of lathe checks, strips of veneer are brushed under dye, glued to blocks, and then leveled on a disk sander. (Photo by Randy O'Rourke)




Figure 14.9 • Typical plywood construction consists of five plies, with the grain direction of adjacent plies running perpendicular to one another.

PLYWOOD

Common plywood is composed of an uneven number of thin layers of wood glued together. The adjacent layers are arranged so that the grain directions are perpendicular to one another (Figure 14.9). The thin layers, called plies, are typically wood veneers but may be other materials, such as edge-glued lumber panels. Because of the crossply construction, most properties are approximately equalized across the surface of the panel and are dominated by the greater strength and dimensional stability of wood parallel to the grain. However, bending properties are usually somewhat greater in the grain direction of the face ply. Thus, when used as sheathing, subflooring, or shelving, plywood should be oriented with the grain direction of the face ply in the span direction. Crossply construction also virtually eliminates the parallel-to-grain splitting problems characteristic of solid wood. On the other hand, plywood splits easily in the plane of the panel, which must be remembered when attaching hinges or fasteners to panel edges. Another major advantage of plywood is its availability in panels considerably wider than any natural boards.

Although examples of crossply construction have been known since ancient times, plywood as we know it can be rightfully thought of as a modern material, for only within the 20th century did plywood become established among the

principal primary wood products. Veneering techniques developed in the late 1800s paved the way, but the success of today's plywood industry must be attributed to the development of economical moisture-resistant adhesives. Although plywood can be produced in a small shop, there are two important considerations when making your own. The first is balanced construction, that is, providing mirror-image equality of plies on either side of the panel centerline with respect to thickness of plies, grain direction, and moisture content. The second is gluing pressure. For example, a piece 12 in. by 12 in. would require a minimum of 7 tons and an optimum of 14 tons to develop adequate pressure on maple veneer, especially if it is at all rough-cut.

Commercially produced plywood is readily available but the array is broad. Woodworkers should become familiar with the many combinations of species, veneer grades, adhesive types, and specialty variations, thus ensuring that you get the correct panel for your needs.

In manufacturing plywood, veneers can be produced to a fairly high degree of accuracy in thickness and also can be routinely dried to low moisture content. After gluing under pressure, plywood panels are machine-sanded to final panel thickness and surface smoothness, then trimmed to final dimensions and squareness. The ability to control the moisture of veneers, the stability afforded by crossply construction, and the greater dimensional accuracy in manufacturing usually result in very consistent panel dimensions.

Plywood is manufactured in a variety of thicknesses up to 1 in. In surface dimension, the 4-ft. by 8-ft. sheet (or its metric equivalent) is the common standard, although specialty types are produced in other sizes. Plywood is typically priced by the square foot of surface measure (or by the standard sheet).

The outermost plies of plywood are called **faces** or **face plies**. If they are different in grade, value, or appearance, the better of the two is designated as the **face**, the poorer as the **back**. When of equal quality or of unspecified quality, both are considered faces. The center ply (whether veneer, edge-glued lumber, particleboard, or other material) is termed the **core**. In plywood having more than three plies, the veneers immediately beneath the faces are usually termed **crossbands** or **crossbanding**. These terms are used especially to designate the layers of veneer running perpendicular to the faces and core in lumber-core plywood panels.

The terminology is somewhat inconsistent, however. For example, sometimes all the plies between the central core and the faces are termed crossbands; in other cases, all the plies within the faces are termed core plies, or collectively, simply the core. Materials other than wood used to form the surfaces of the panel, such as metal sheets, foil, or resin-impregnated paper, are called **overlays**.

TABLE 14.1—The APA-The Engineered Wood Association classification of plywoods. The lower the group number, the greater the strength and stiffness of the plywood panel.

Group 1	Group 2	Group 3	Group 4	Group 5	
Apitong	Cedar, Port-Orford	Maple, black	Alder, red	Aspen	Basswood
Beech	Cypress	Mengkulang	Birch, paper	bigtooth	Fir, balsam
Birch	Douglas fir ²	Meranti, red	Cedar, Alaska	quaking	Poplar, balsam
sweet	Fir	Mersawa	Fir, subalpine	Catibo	
yellow	California red	Pine	Hemlock, eastern	Cedar	
Douglas-fir ¹	grand	pond	Maple, bigleaf	incense	
Kapur	noble	red	Pine	western red	
Keruing	Pacific silver	Virginia	jack	Cottonwood	
Larch, western	white	western white	lodgepole	eastern	
Maple, sugar	Hemlock, western	Spruce	ponderosa	black (western	
Pine	Lauan	red	spruce	poplar)	
Caribbean	almon	Sitka	Redwood	Pine	
ocote	bagtikan	Sweetgum	Spruce,	eastern white	
Pine, southern	mayapis	Tamarack	black	sugar	
loblolly	red lauan	Yellow-poplar	Engelmann		
longleaf	tangile		white		
shortleaf	white lauan				
slash					
Tanoak					

¹Douglas fir—grown in Northwest

²Douglas fir—grown in Southwest

CLASSES OF PLYWOOD

Commercial plywood falls basically into two major classes: (1) construction and industrial and (2) hardwood and decorative, manufactured under somewhat different product standards. Within each group, there is classification according to exposure durability, based on the type of adhesive and grade of veneers used. Construction and industrial types are commonly referred to as "structural plywood," intended primarily for building uses and manufactured principally of rotary-cut veneer from softwoods, mostly native species. Plywood classed as hardwood and decorative is typically used for decorative wall panel, furniture, and cabinetry and includes a high proportion of imported woods as well as domestic species. It also includes both rotary-cut and sliced veneers.

Anything approaching a complete review of plywood of all categories, types, and specialties is quite beyond the scope of this chapter, and the reader is referred the *Wood Handbook* (see the bibliography on p. 272) for a more detailed discussion of product standards and technical descriptions of commercial plywood). However, following

are summary highlights as an introduction to the major features of commercial plywood presented under the simple headings of **softwood plywood** and **hardwood plywood**.

SOFTWOOD PLYWOOD The softwood-plywood industry developed principally around the manufacture of Douglas-fir plywood. Once established, however, other species gained prominence, including true firs, southern yellow pines, western larch, western hemlock, cedars, and redwood. Member mills of the APA-Engineered Wood Association now manufacture most softwood plywood. The association's grading rules and manufacturing standards have been developed in cooperation with performance standards set by the U.S. government. Species are segregated into five groups based on strength properties (*Table 14.1*), with Group 1 representing the strongest and stiffest.

Softwood plywood is manufactured under four exposure durability classifications. **Exterior** plywood is bonded with waterproof glue and has C-grade or better veneers throughout. **Exposure 1** plywood is bonded with waterproof glue but may include D-grade veneers. **Exposure 2** plywood is bonded with




Figure 14.10 • A typical plywood grade stamp and what it means.

glue having intermediate moisture resistance. **Interior** plywood may be bonded with interior, intermediate, or waterproof glue and admits D-grade veneers for interior and back plies.

Softwood plywoods may also be designated under two main categories: engineered grades and appearance grades. As the terms indicate, engineered grades are designed for applications where strength and serviceability are of primary concern. Appearance grades assume the plywood will be used where appearance is important. Face veneers are therefore graded as N (best), A, B, C plugged, C, and D (poorest). Grade N veneers are special-order and are intended to take a transparent finish, as in furniture and cabinetwork. Other veneer grades are established on the basis of the size and number of repairs or defects such as knots, splits, and insect damage. The grade designation generally incorporates the veneer grade of the face and back plies. For example, in A-A grade plywood, both faces have grade-A veneer; in C-D grade plywood, the better face has C-grade veneer and the poorer face has D-grade veneer.

In certain engineered grades of unsanded plywood, such as C-D sheathing, an identification index of two numbers indicates the maximum roof-frame spacing if the panel is used as roof sheathing and the maximum spacing of floor framing if the panel is used as subfloor. For example, an identification index of 32/16 would indicate a maximum 32-in. rafter spacing and a maximum 16-in. floor-joint spacing.

A number of specialty plywoods may be of particular interest to the woodworker. For example, **marine plywood** is exterior plywood that has A- or B-grade faces and no voids in interior plies, so that the plies are supported and so that the edges will not have voids even if the panel is cut—important features where structural strength and watertight integrity are vital.

Medium-density overlay (MDO) and **high-density overlay (HDO)** plywood is faced with resin-impregnated paper. This plywood is particularly good for exterior painted surfaces such as signs, where surface defects that commonly result from knife checks in face veneers are a problem. Special surface effects, particularly for use as building, siding, or interior wall covering, are also available. Striated and brushed surfaces are especially effective in disguising the knife-check defects on panel surfaces. Kerfed and grooved surfaces will hide panel joints.

Summary information of panel specifications normally appears as a grade stamp on each panel. An example is shown in *Figure 14.10*. Grade stamps indicate the panel grade, the veneer grades and species or species group, panel

TABLE 14.2—Categories of commonly used species for hardwood plywood based on specific gravity ranges based on oven-dry weight and volume at 12% moisture content.

Category A (0.56 or higher specific gravity)	Category B (0.43–0.55 specific gravity)	Category C (0.42 or lower specific gravity)
Ash, commercial	Ash, black	Alder, red
white	Avodire	Aspen
Beech,	Bay	Basswood, American
American	Cedar, eastern red-*	Boxelder
Birch, yellow	Cherry, black	Cativo
sweet	Chestnut, American	Cedar, western red-*
Bubinga	Cypress*	Ceiba
Elm, rock	Elm, American	Cottonwood
Madrone,	(white, red, or gray)	black
Pacific	Fir, Douglas-*	eastern
Maple,	Gum, black, sweet	Pine,
black (hard)	Hackberry	white*
sugar (hard)	Lauan (Philippine	ponderosa*
Oak,	mahogany)	Redwood*
commercial red	Limba	Willow, black
commercial white	Magnolia	Yellow-poplar
Oregon	Mahogany, African	
Paldao	Honduras	
Pecan, commercial	Maple, red (soft)	
Rosewood	silver (soft)	
Sapele	Primavera	
Teak	Sycamore	
	Tupelo, water	
	Walnut, American	

*Softwood

thickness, exposure durability, and span ratings, as well as the trade association, mill number, and product specification under which the panel was manufactured.

HARDWOOD PLYWOOD Hardwood plywood is made especially to display the aesthetic qualities of its face veneers. Panels are, in fact, identified according to the species of the face ply; the backs and inner plies may be of another hardwood species, a softwood species, or even another material such as particleboard. On the basis of specific gravity, species are separated into three categories (*Table 14.2*). In addition to species, the grade of the face ply is identified in hardwood plywood. Hardwood face-veneer grade standards are listed in *Table 14.3*. (Certain softwood veneers commonly used in faces because of their decorative features are included with the hardwood standards.)

A requirement of **Premium Grade** (A or #1) is that multiple veneer pieces used to make a panel face must be **matched**, that is, arranged in special sequence according to their figure display. Some common arrangements are book-matching, slip-matching, and random-matching (*Figure 14.11*). Matching of veneers and of successive sheets of plywood can produce beautiful results. Special combinations of figure and matching combinations can be stipulated by specifications within the **Specialty Grade** (SP), and often can be




Figure 14.11 • Some veneer matches used in hardwood plywood.




Figure 14.12 • Common hardwood plywood construction.

TABLE 14.3—Face grades of hardwood plywood. Hardwood plywood is manufactured in several specific grades. As in softwood plywood, each face must be specified.

Specialty Grade (SP)	This is a special plywood made to order to meet the specific requirements of a buyer. Plywood of this grade usually entails a special matching of the face veneers.
Premium Grade (#1)	The veneer on the face is fabricated for matched joints, and contrast in color and grain is avoided.
Good Grade (#1)	The good face is fabricated to avoid sharp contrasts in color and grain.
Sound Grade (#2)	The veneer on the face is not matched for color or grain. Some defects are permissible, but the face is free of open defects and is sanded smooth. It is usually used for surfaces to be painted.
Utility Grade (#3)	Tight knots, discoloration, stain, worm holes, mineral streaks, and some slight splits are permitted in this grade. Decay is not permitted.
Backing Grade (#4)	This grade permits larger defects. Grain and color are not matched, and the veneer is used as the concealed face. Defects must not affect strength or serviceability of the panel made from it. At the manufacturer's option, this face can be of some species other than the exposed face.

produced to order. Depending on the use, the veneers are incorporated into a wide range of panel constructions, ranging from special three-ply, $\frac{3}{16}$ -in.-thick aircraft plywood to $2\frac{1}{4}$ -in.-thick flush doors. Common constructions are shown in *Figure 14.12*. Hardwood plywood is used in countless products, from architectural cabinetry and furniture to sporting goods, musical instruments, and jewelry boxes.

Four types of hardwood plywood are recognized on the basis of adhesive specifications. **Technical Type** and **Type I** both use waterproof adhesives and will therefore withstand all degrees of moisture exposure without delamination. **Type II** is made with moisture-resistant adhesives but is not intended for use where repeated or prolonged wetting might occur. **Type III** is made with adhesives of even lower moisture resistance, adequate for uses such as packing cases or crates.

When hardwood plywood is manufactured to U.S. government standards, certification may accompany the shipment or may be stamped directly on each panel. A typical

grade stamp of the Hardwood Plywood & Veneer Association (HPVA) would indicate the association trademark, the product standard, the adhesive bond type, lay-up description, grade and species of the face, the panel's formaldehyde emissions and flame-spread ratings, and the mill identification number.

A variety of other plywood products may appear in the retail market. A noteworthy example is Finnish birch plywood, in panels with up to 13 plies. The veneers throughout are of uniformly high quality, providing exceptional stability and excellent surface and edge properties of parts cut from the panels. This material is therefore preferred for components with higher-quality requirements such as jigs and fixtures, instruments, and frames or bases for electronic equipment. Its uniform appearance and minimal edge slivering make it suitable for furniture, toys, and accessories.




Figure 15.1 • Wood particles classified as strands form an interesting surface mosaic on this composite panel. (Photo by Randy O'Rourke)

COMPOSITE PANELS

Early composites such as plywood and laminated beams were inspired by the need to extend or modify natural wood sizes or properties. The development of modern composites, however, has the additional incentive of using manufacturing waste and residues, as well as smaller and lower-grade trees. The result has been a wider range of versatile products with different but more consistent properties, with the likelihood that even greater advancements in technology lay just ahead. To summarize a discussion of this growing array of composites, this chapter will address **composite panels**, and the following chapter will consider **engineered lumber**.

Panel products fabricated with cross-ply layers of veneer have been around for centuries and are well known as plywood, but the term composite panels is the catchall for virtually everything else. Just as there are many species of wood and many types of plywood, so is there an expanding list of composite panels in the modern market. Attempts to classify them might well begin with a consideration of the source, size, and form of the ingredient wood elements used in their manufacture.

Some elements are milled directly from logs; others are derived from lumber or veneer residues. These residues include thin, flat, uniform-thickness elements that vary from the largest wafers the size of playing cards, narrow strands up to 3 in. long, and toothpick-like slivers to medium and small flakes, shavings, and sawdust (*Figure 15.1*). At the smallest elemental size, tissue aggregates or even individual wood fibers are the raw material for some composites. Beyond constituent element size, bonding agents, physical characteristics, mechanical properties, and uses are considered as criteria for classification.

Although there is certainly no simple or perfect system for separating the array of composite-panel products into exact categories, the complex subject of composite panels can be covered under three broad headings: particleboard, wafer- and strand-based panels, and fiber-based panels.

PARTICLEBOARD

The wood particleboard industry grew out of the need to utilize the large quantities of residues generated in the manufacture of other wood products. By today's standards, the first particleboards manufactured in the early 1950s left much to be desired. Misuse of these early prototypes, often with unsatisfactory results, gave particleboard a bad reputation. The greatest dissatisfaction has resulted from attempts to use particleboard as a substitute for any and every application of solid wood or plywood. When used intelligently according to their respective properties, today's particleboards constitute a versatile array of superior products for many facets of building and woodworking.

The term particleboard indicates simply a panel product manufactured by spraying wood particles with adhesive, forming them into a mat, and compressing the mat to desired thickness between heated platens to cure the adhesive. Such panels may have varied characteristics and range from low-density particleboard suitable for utility cabinets or panel core material to high-density panels used for flooring underlayment. For example, the particles can be manufacturing residues such as planer shavings, veneer scraps, or sawmill chips, or they can be prepared flakes or splinters. The board may have controlled layering, with the placement of coarse particles in the center and with flakes or finer particles at the surfaces for superior strength and to enhance uniformity and smoothness of the finished board. An array of typical particleboard products is shown in (*Figure 15.2*).

Particleboards are classified by particle type and further by adhesive type, density, and strength class (*Table 15.1*). **Type 1** particleboard utilizes a urea-formaldehyde resin suitable for most routine interior uses. However, for applications where greater heat and moisture resistance is required, **Type 2** boards bonded with waterproof adhesive are appropriate. Varying the percentage of resin and the compaction of the particle mat produces low-, medium-, and high-density boards, ranging in density from 25 pcf to 70 pcf. Within each density group, boards are produced in two strength classes: **Class 2** is stronger than **Class 1**. Strength properties of some particleboards equal solid-wood strengths of low-density species. For example, a particle-

TABLE 15.1—Standards for particleboard developed by the National Bureau of Standards (Commercial Standard CS 236-66).

Type	Density (grade) min. avg.	Class	Modulus of rupture, min. avg. (psi)	Modulus of elasticity, min. avg. (psi)	Internal bond, min. avg. (psi)	Linear expansion, max. avg. (%)	Screw holding min. avg.	
							Face (lb.)	Edge (lb.)
1	A (High density, 50 pcf and higher)	1	2,400	350,000	140	0.55	450	—
		2	3,400	350,000	200	0.55	—	—
	B (Medium density, 37 pcf to 50 pcf)	1	1,600	250,000	60	0.35	225	160
		2	2,400	400,000	70	0.30	225	200
	C (Low density, 37 pcf and lower)	1	800	150,000	20	0.30	125	—
		2	1,400	250,000	30	0.30	175	—
2	A (High density, 50 pcf and higher)	1	2,400	350,000	125	0.55	450	—
		2	3,400	500,000	400	0.55	500	350
	B (Medium density, lower than 50 pcf)	1	1,800	250,000	60	0.35	225	160
		2	2,500	450,000	65	0.25	250	200

board of medium-density Class 2 is required to have an MOR (breaking strength in bending) of 2,400 psi and an MOE (modulus of elasticity) of 400,000 psi.

Because of the random distribution of particles, properties of particleboard are uniform in all directions across the board faces. In particleboard types having flat or elongated particles, the constituent particles lie with their grain direction generally parallel to the board surface, and the random arrangement gives cross-ply effects. Particles are mutually stabilized to a great extent, somewhat like veneers in plywood, thus giving particleboards uniformly reduced dimensional properties across the panel faces.

The effective shrinkage percentage of particleboard is generally in the same range as that of plywood. For example, industry standards for medium-density particleboard allow linear swelling of up to 0.35% in response to atmospheric change of 50% to 90% RH; for particleboard made from flakes, 0.20% linear swelling is allowed. At the same time, because of side-grain compaction and springback of crushed particles, the boards have the least stability perpendicular to the surface and under cyclic moisture conditions can swell as much as 10% to 25%. Thus, particleboard bonded with urea-type resins is not recommended for use where it will be subjected to wetting. Particleboard products bonded with phenolic resins are designed for exterior applications such as siding and have improved dimensional properties, but they should also avoid direct uptake of water.

Mechanical fasteners driven perpendicular to the surface hold well in particleboard, especially when appropriate pilot holes are driven. The random particle orientation virtually

eliminates splitting. However, because of surface compaction in manufacturing or by intentional layering, particleboards are typically less dense at the center than near the surface. Fasteners driven into the center of panel edges hold poorly. Where it is necessary to fasten into panel edges, edge banding with solid wood or the use of special fasteners may be required to assure adequate holding power.

Most particleboard is used in the manufacture of home and office furniture, kitchen cabinets, and housings for television and stereo sets. A significant percentage is used in floor underlayment for carpeting or resilient floor covering and as core material for hardwood plywood, wall paneling, doors, furniture, and casegoods. Particleboard is well suited for facing with veneer to produce panels of various thicknesses. Special grades of particleboard are manufactured whose surfaces are especially suited for painting. In manufacturing these boards, fine particles are used to form the surfaces, which are then filled and sealed so that subsequent telegraphing through the paint is minimal. In summary, smoothness of surface is associated with higher density and finer particles. On the other hand, lower-density boards having larger particles, such as flakes, have less-smooth surfaces but greater overall dimensional stability.

Under sustained bending loads, particleboard will creep, so when used as shelving, supports should be more closely spaced than for solid-wood shelves of equal thickness. Particleboard (even when bonded with waterproof resins) will not maintain surface integrity under exterior weathering conditions and should therefore be used only where protected from the elements.

WAFER- AND STRAND-BASED PANELS

Waferboard and **oriented strandboard (OSB)** deserve separate mention from the general array of particleboard products (*Figure 15.2*). Developed as structural-panel products for sheathing and subflooring in light-frame construction, these types of panels have several distinguishing features. Their constituent elements of wafers or strands are larger than can be derived from residues. They are produced directly from green roundwood, enabling control of dimensions, especially thickness and length. The longer, thinner elements develop superior bending properties at the expense of surface smoothness that is characteristic of common particleboards. Waferboard, which evolved first, is produced with wafers laid down in random orientation, producing MOR values averaging 2,500 psi. In the manufacture of OSB, the equally long wafers are reduced in width to elongated strands, allowing them to be oriented in forming the board mats.



Figure 15.2 • An array of composite panel materials includes (top to bottom) oriented strandboard, structural waferboard, counter-top-grade particleboard, and chipboard cedar-closet liner. (Photo by Randy O'Rourke)

OSB panels are layered with the strands of the face layers parallel to the length of the panel and with the core layer perpendicular. This provides overall panel dimensional stability as in plywood construction and superior MOR (8,000 psi to 10,000 psi) in the longitudinal direction, with little sacrifice of strength perpendicular to the panel. OSB is therefore replacing the earlier waferboard and competes on a performance basis with plywood. It is predicted that OSB will soon have an equal share with plywood in the structural-panel market.

The preferred species for making OSB panels is aspen, although other low-density hardwoods such as yellow-poplar and softwoods such as spruce have been found to be suitable. Whereas urea-type adhesives are most common in particleboard, OSB is typically bonded with phenol-formaldehyde resins, although isocyanate resins are being used increasingly as well.

FIBER-BASED PANELS


A number of composite panel types have evolved using wood fibers as the constituent elements. Of the materials of interest to the woodworker, they can be grouped into three categories on the basis of density as hardboard, medium-density fiberboard, and insulation board.

Hardboard is a general term referring to fiber-type board interfelted and consolidated under heat and pressure to a specific gravity averaging 1.0 (50 pcf to 80 pcf). W. H. Mason, founder of the Masonite Corp., first produced this type of board in 1924. Although many firms now produce hardboard, the term Masonite is used somewhat generically for all types and brands of hardboard.

The most commonly available hardboards have a density of 60 pcf to 65 pcf and are termed standard. For purposes where lower strength and hardness are acceptable, service hardboards having a density of 50 pcf to 55 pcf can be used. Tempered hardboards are produced by impregnating standard high-density hardboard with resin and heat-curing. Tempering appreciably improves water resistance, hardness, and strength and results in boards having a density of 60 pcf to 80 pcf. As with particleboard, hardboard is unstable in thickness but has dimensional properties similar to particleboard in the plane of its surface. However, since hardboard is commonly produced in thicknesses of only $1/8$ in. or $1/4$ in., uneven moisture exchange between the two surfaces may result in bulging or warping.

Depending on the manufacturing process, hardboard is either smooth on both sides or has a screen pattern imprinted on one face (*Figure 15.3*). A wide variety of spe-

Figure 15.3 • Pieces of $\frac{1}{8}$ -in. hardboard show the smooth face (above) and the screen pattern back (back). (Photo by Randy O'Rourke)



cialty hardboards is produced with simulated wood figure or decorative surfaces or with surfaces embossed with simulated raised grain. Some hardboard is perforated in peg-board pattern or with geometric designs to form decorative screens. Hardboard has a host of uses in woodworking, ranging from furniture backs and drawer bottoms to curved surfaces and panel inserts.

Medium-density fiberboard (MDF) includes composite-panel products produced from wood fibers and wood-fiber bundles bonded with synthetic resins (*Figure 15.4*). It commonly has a specific gravity of 0.5 to 0.8 (31 pcf to 50 pcf). Its principal use is in the manufacture of kitchen cabinets and furniture used in much the same way as particleboard or lumber-core plywood.

One important advantage of MDF over particleboard is that it has nearly uniform density throughout so it can be machined along its edges as solid wood and has reasonable edge holding for fasteners. MDF provides a smooth.




Figure 15.4 • A sample of medium-density fiberboard (MDF) shows the smooth surface and uniformity through the panel thickness. (Photo by Randy O'Rourke)

paintable surface where strength equal to solid wood is not needed. Its properties are summarized in *Table 15.2*.

Insulation board refers to a group of panel products having a specific gravity range of 0.16 to 0.50. In its manufacture, fiber mats are wet-formed without resin, cold-pressed to thickness, and then dried (*Figure 15.5*). Fiber-to-fiber bonding is attained primarily by hydrogen bonding, as in paper products. This product has been used most often as acoustical ceiling tiles, although the current trend is toward more fire-resistant products. Modest quantities of insulation board are manufactured for structural insulation sheathing and for backing on aluminum siding and roofing components. A popular product marketed under the name Homosote is made from recycled fiber. Insulation board is commonly used with a facing of sheet cork or burlap as tack-boards or bulletin boards and in-store and museum displays.




Figure 15.5 • On this sample of insulation board the rough edge to the left is the production trim cut. The smooth edge to the right was cut on a shop table saw. (Photo by Randy O'Rourke)

TABLE 15.2—Strength and mechanical properties of fiberboards.

Property	Unit	Value for structural insulating board	Value for medium-density fiberboard	Value for high-density hardboard	Value for tempered hardboard
Density	pcf	10–30	33–50	50–80	60–80
Specific gravity	—	0.16–0.42	0.53–0.80	0.80–1.28	0.93–1.28
Modulus of elasticity (bending)	1,000 psi	25–125	325–700	400–800	650–1,100
Modulus of rupture	psi	200–800	1,900–6,000	3,000–7,000	5,600–10,000
Tensile strength parallel to surface	psi	200–500	1,000–4,000	3,000–6,000	3,600–7,800
Tensile strength perpendicular to surface	psi	10–25	40–200	75–400	160–450
Compressive strength parallel to surface	psi	—	1,000–3,500	1,800–6,000	3,700–6,000
Shear strength (in plane of board)	psi	—	100–475	300–600	430–850
Shear strength (across plane of board)	psi	—	600–2,500	2,000–3,000	2,800–3,400
24-hour water absorption	% by volume	1–10	—	—	—
24-hour water absorption	% by weight	—	5–20	3–30	3–20
Thickness swelling, 24-hour soaking	%	—	2–10	10–25	8–15
Linear expansion from 50% to 90% relative humidity	%	0.2–0.5	0.2–0.4	0.15–0.45	0.15–0.45
Thermal conductivity at mean temperature of 75°F	Btu per inch of thickness per hour per square foot of surface per degree Fahrenheit	0.27–0.45	0.54–0.75	0.75–1.40	0.75–1.50




Figure 16.1 • Contrasting heartwood and sapwood show the finger-joint detail in this yellow-poplar window sash component. (Photo by Randy O'Rourke)

ENGINEERED WOOD

To some, the term *engineered wood* suggests a sad loss of time-honored customs and values and perhaps signals a vanishing heritage. I see the term as an indication of the growing attention paid to improving manufacturing and especially performance efficiency of wood products. It reflects changes in the industry and in our bountiful timber resource, as well as a break from outdated traditions and bad habits. These are forced changes, perhaps, but in the end I see an opportunity to develop products with superior characteristics and to put smaller trees and underutilized species to work. In the words *engineered lumber*, we should hear the promise of using lower-value trees with technologies such as kerfless cutting and residue recovery to make building materials with larger sizes, improved uniformity, and greater efficiency than ever before.

The term *engineered wood* is loosely used to refer a variety of structural composite wood products. In the previous chapter, I discussed composite panels. Those described in this chapter are linear products used as alternatives to traditional lumber, especially in building applications.

Engineered lumber can be considered in four major categories: finger-jointed lumber, glued-laminated timber (also called glulam), structural composite lumber, and I-joists.

FINGER-JOINTED LUMBER

Sawn lumber is always limited in length to the logs that produced it. If clear material is desired, the limit is the longitudinal distance between defects in the tree or log. We now have fewer high-quality trees, yet our preference in most woodworking endeavors is nevertheless for clear wood in whatever lengths the job requires. One means of producing long lengths of clear material is by joining smaller pieces end-to-end.

A long tapering scarf bonded with adhesive is perhaps the strongest method to join wood end-to-end, but it results in a considerable waste of material. A reasonable compromise is the finger joint, which is a series of alternating short scarf joints in a narrow band across the ends of the pieces being joined (*Figure 16.1*).

Production finger jointing was perfected as a means of creating long lengths and upgrading laminations as required in glulam. An increasing number of products are finger jointed to attain long lengths of knot-free material. Finger joints are being used to produce clear stock for millwork parts such as windows, doors, and casings (*Figure 16.2*). Finger jointing is excellent for products customarily sold in long lengths such as handrails, closet poles, strip moldings, and trim. The production finger joint is routinely superior to end-to-end joints handmade at the job site.

Finger-jointed lumber in standard board sizes is also on the market. Another retail product is **blockboard**, which are solid-wood panels, typically pine, made of finger-jointed strips 2 in. to 3 in. wide that have then been edge-glued to panel widths of 24 in. to 36 in. (*Figure 16.3*). For painted surfaces, finger-jointed lumber is better than the knotty lumber it replaces. However, under cyclic moisture conditions the finger joints may telegraph through paint, especially if the woods joined have different grain orientation or unequal moisture content, resulting in uneven dimensional change on either side of the joint. Finger-jointed lumber is routinely used as laminations in the manufacture of glulam and as flanges for some versions of I-joists, as discussed below.

When properly made, finger joints can attain 75% to 85% of the tensile strength of the clear wood, which is probably higher in strength than the wood might have had if the defects remained.

With modern equipment, successful finger jointing of lumber is routinely accomplished at a high production rate. The ends of lumber pieces are first milled with matching finger-joint configuration, then spread with adhesive and moved into a clamping device that holds mating pieces together while the bond is microwave-cured in just a few seconds. The line of joined pieces moves on to position the next piece to be joined, and the gluing operation is repeated. The continuous strip of stock is cut to length at desired intervals.

In the future, finger-jointed material is certain to become more commonplace in both lumber and finished products as a means of upgrading defective material to clear and in creating otherwise unavailable long lengths.




Figure 16.2 • In this strip of preprimed brick molding, the paint was sanded off to show the otherwise concealed finger joint. (Photo by Randy O'Rourke)



Figure 16.3 • Short pieces of pine are finger-jointed into strips, which are then edge-glued to form wider lumber or panels. These products are sold as "Blockboard" or "Laminate." (Photo by Randy O'Rourke)




Figure 16.4 • Glulam is a stress-rated product made up of two or more layers of lumber glued together with their grain directions parallel to one another. This is a finger joint in a lamination of glulam decking (shown in Figure 16.5, top center). (Photo by Randy O'Rourke)

GLULAM

Structural glued-laminated timber, commonly called glulam, refers to engineered stress-rated products consisting of two or more layers of lumber, called laminations, glued together with their grain running parallel (*Figure 16.4*, *Figure 16.5*).

Laminated beams were among the first engineered wood products, fashioned from boards or planks spiked or doweled together as found in early ships, bridges, and building construction. Earliest attempts at glued laminations utilized casein adhesive, which was somewhat water-resistant but by no means waterproof by today's standards. With the waterproof synthetic resin glues and fabrication technology developed during World War II, the glulam industry was launched and has subsequently flourished.

Glulam technology can produce structural members longer and larger than the source trees, virtually as long as can be handled and transported. Members up to 140 ft. in length, 7 ft. in depth, and 20 in. in width have been produced.

Glulam has distinct advantages over sawn heavy timber of comparable dimension. Because each lamination can be kiln-dried to an appropriate moisture content, subsequent dimensional-change problems such as checking or radial cracking are eliminated and higher design values can be used for the drier, stronger wood. Beams can be designed for stress consideration. Grades of lumber can be sorted and arranged in the beam to place the best grades at the highly stressed surfaces. Where knots are present, they are ran-



Figure 16.5 • Glulam products: plank for ceiling decking (top left), laminated floor decking (top center), stock sizes of beams (bottom and right). (Photo by Randy O'Rourke)

dornly distributed throughout the assembly and therefore are less significant. The cross sections of beams can be tapered or varied to provide adequate net section where bending moments are greatest. Glulam also maintains the aesthetic effect of natural and solid wood, which is largely lost in other composite beam products.

Although large glulam members are usually manufactured to order for architectural applications, many stock sizes commonly used in residential construction for garage-door headers, carrying beams, and exposed ceilings are available through retail dealers.

STRUCTURAL COMPOSITE LUMBER

Structural composite lumber (SCL) is the accepted term for the family of recently developed products characterized by smaller elements of wood, such as veneer or particles, glued together into more or less homogeneous form in sizes common for solid-sawn lumber and timbers. SCL products are primarily intended as structural members that function as beams or columns where axial stresses are critical. They are appropriately grouped by generic types as laminated veneer lumber (LVL), parallel strand lumber (PSL), laminated strand lumber (LSL), and oriented strand lumber (OSL).

Laminated veneer lumber (LVL) is typically manufactured using veneers of Douglas-fir or southern yellow pine in $\frac{1}{8}$ -in. or $\frac{1}{16}$ -in. thicknesses. Dried veneers are spread with phenol-formaldehyde adhesive and fed into a continuous press, then bonded in process by heat and pressure (*Figure 16.6*). Instead of butt jointing, the ends of the consecutive veneers in a given layer are overlapped for a few inches. The double-thickness lap joint causes a localized area of excessive compression perpendicular to the grain among adjacent plies but with little loss of axial strength (*Figure 16.7*).

LVL is produced in thicknesses up to $3\frac{1}{2}$ in., in widths up to 4 ft., and in lengths up to about 80 ft., the maximum that is practical for shipping. Production stock can then be further cut to shorter lengths and ripped to desired widths. However, since the veneers are graded and sorted for layup with the best veneers near the faces and the lower-quality veneers in the core, LVL should be used in the full thickness as manufactured. The original brand was Microllam, but LVL is now produced by a number of manufacturers.

Although more expensive than standard lumber, LVL is more consistent and of higher stress rating than solid-sawn lumber of equal dimension, and with its longer available lengths is ideal for applications such as carrying beams and garage-door headers. LVL is especially valuable as scaffold planking because of its predictable strength and uniformity.



Figure 16.6 • Laminated veneer lumber (LVL) is more consistent in quality than standard lumber, is available in longer lengths, and has a higher stress rating. Here are three examples of LVL. The center piece is a scaffold plank with rough surfaces. (Photo by Randy O'Rourke)



Figure 16.7 • In the manufacture of LVL, weak end-grain butt joints are avoided by overlapping consecutive veneers in a given layer to provide side-grain bonding. (Photo by Randy O'Rourke)



Figure 16.8 • Parallel strand lumber (PSL) utilizes materials unusable for making LVL. Though of uniform strength and reliability, PSL is relatively heavy and has a rough, porous surface. This example shows the random arrangement of aligned veneer strands. (Photo by Randy O'Rourke)




Figure 16.9 • A large slab of laminated strand lumber, prior to cutting into parts for framing upholstered furniture. The strands are bonded with isocyanate adhesive and cured with steam, which also makes the wood denser. (Photo by Randy O'Rourke)

Parallel strand lumber (PSL) was first manufactured under the trade name Parallam. Rather than sheets of veneer, the raw material is $\frac{3}{8}$ -in.-wide strips of $\frac{1}{8}$ -in. veneer, which utilizes materials that are unusable in the LVL process (Figure 16.8). Most veneer is obtained as scrap from rounding-up logs in rotary cutting, and the veneer is therefore mostly high-quality sapwood. Douglas-fir, southern yellow pine, western hemlock, and yellow-poplar are currently used. The veneers are sprayed with waterproof adhesive and fed into a continuous press, where the adhesive is microwave-cured under pressure. The continuous billet of up to 11 in. by 19 in. in cross section is cut to lengths up to 66 ft. and can later be crosscut and ripped to smaller sizes as needed.

As with LVL, parallel strand lumber offers softwood structural members of larger sizes to satisfy requirements of uniform high strength and reliability.

With both LVL and PSL, the woodworker accustomed to solid-sawn lumber will recognize a couple of differences right away. First, the weight of the material is greater than that of the common species for which it substitutes. Second, the surface is rough and porous, especially PSL. This surface roughness is a source of nasty splinters, so handling with work gloves is recommended.

Laminated strand lumber (LSL) is a more recent addition to the growing array of composite lumber types. LSL products represent a linear version of OSB panel technology, with the strands aligned parallel to the length (Figure 16.9). Unlike PSL, the strands average just 0.040 in.

thick and are knife-cut directly from roundwood. This utilizes small-diameter, low-grade logs. Aspen has been the principal raw material, but yellow-poplar and other underutilized species are compatible with the process. Unique features of the process include bonding with MDI (isocyanate) in a stationary press, where the resin is cured by steam injection, which also densifies the wood. Billets that are 8 ft. wide and up to $5\frac{1}{2}$ in. thick and 48 ft. long are produced, which can then be ripped or crosscut to desired dimensions.

Current uses for LSL are cut parts for such applications as door and window assembly (especially if they are to be vinyl-coated) and for structural components of upholstered furniture. The uniform consistency of the material allows large billets to be reduced to components with minimum waste. This class of materials will likely find increasing use as structural material in the coming years.

Oriented strand lumber (OSL) is similar to LSL but utilizes longer strands. The technology is still in the developing stages, but it is likely to present another important category to the growing family of SCL products.

I-JOISTS

Although the wide array of preassembled products such as roof trusses and wall panels is beyond the scope of this book, I couldn't resist commenting on wooden I-joists. This impressive contribution to the construction industry is the

culmination of emerging technologies of adhesives and composite materials in response to the realities and challenges of changing timber resources and modern human needs. The / of the term I-joist comes from the cross-sectional shape as is familiar in traditional steel I-beams; the *joist* from the most common use as a replacement for the usual dimension lumber used as floor joists in light-frame construction. As with classic steel I-beams, the distribution of the material reflects the fact that the greatest axial stresses in a beam are at the upper and lower surfaces. Additional material—the *flanges*—is needed to resist axial stresses, but these flanges must be held in position by a connection—the *web*—which must also resist shear stresses (see *Figure 4.24* on p. 88). The wooden I-joist accomplishes this with fascinating mechanical success and efficiency of material.

Concepts of both box beams and I-beams of wood evolved from wartime technology for aircraft design in the 1940s. These designs allocated species and strength properties to portions of beams to satisfy stress requirements. But it was not until the late 1960s when the Trus Joist Corporation introduced I-joists to the commercial market. Since then, I-joists of a variety of combinations have been developed, with flanges made from stress-rated sawn lumber or LVL and flanges of plywood or OSB bonded with waterproof resin adhesive. *Figure 16.10* shows examples of I-joist materials and configurations.

The greater depths of I-joists available permit clear spans longer than those possible using conventional lumber. In routine sizes, I-joists of equal strength are competitive in price with traditional sawn lumber joists. An added advantage is the lower weight of the I-joists, making their handling and placement easier on the job site. Care must be taken when cutting through I-joists for plumbing and wiring, so that through cuts won't disturb high-stress portions. Special fastening procedures are necessary with I-joists to assure that the flanges are secured to adjoining framing members. When construction guidelines are followed, I-joists offer a successful and superior alternate to the solid-lumber joist system of a building.




Figure 16.10 • Sections of typical I-joists. The two on the left have finger-jointed solid wood flanges (note the finger joint exposed in the top flange of the second I-joist). The two on the right have LVL flanges. The first and third have plywood webs; the second and fourth have OSB webs. (Photo by Randy O'Rourke)



Figure 17.1 • Buy your wood where
you can pick your own. (Photo
by Vincent Laurence)

FINDING WOOD

Each time I launch into a new woodworking endeavor, step one is to figure out how and where to get the wood I need. Several factors are involved—availability, quality, convenience, and price. As often as not, moisture content of the wood is important. Eventually the compromise among all these considerations is what determines where I go to buy or find what I need. The options are varied, from sawmills and lumberyards to woodworkers' retail outlets and web sites (Figure 17.1). Yet another source, the one that is overlooked because it is perhaps too obvious, is the tree itself. This might well be the first consideration, so I'll begin my comments here.

TREES

It is ironic that while trees surround us, quality wood for woodworking is so hard to come by. Extracting workable wood from a tree is no casual pastime; trees are a source of wood only for those willing to expend much time and physical effort. However, if you love wood and woodworking, the psychological reward is well worth the effort. Another reward might be a forced introduction to green woodworking, that is, working with wood before it is dried. If you have never dabbled with this, you simply *must* try it. Start with a simple project, a carved bowl or spoon. Soon you'll be anxious to try a chair or basket or maybe even a dugout canoe! Working directly from the tree will also provide some slabs or chunks in sizes never available in stores, such as rare figured pieces from discarded stumps or crotches.

Before you take on the considerable job of cutting your own wood, be sure to think through the whole job. Make sure you have the ways and means to end-coat, stack, and store your entire harvest properly (see chapter 8). If you wait to end-coat until checking begins, your stock may be good only for firewood.

The basic equipment required for cutting your own lumber is a chainsaw (or a good two-man crosscut saw if you can find one and know how to file it) and safety gear, including gloves, hard hat, safety shoes, and eye protection. A peavey or log jack will be a valuable addition. If you are a woodcarver, a splitting maul or sledgehammer, wedges, ax,

and drawknife will harvest all the various blocks, chucks, slabs, and flitches you will ever require. A froe is also handy for splitting out slats. If you want boards or a number of fairly uniform slabs, you might consider a chainsaw mill or portable bandmill.

A chainsaw mill is a chainsaw modified with a roller frame that allows the saw to make lengthwise passes along a log lying on the ground (Figure 17.2). A key feature of this machine is the special saw chain designed to rip-cut rather than the usual cross-cut. A board tacked to the top of the log guides the first pass, producing a flat face on the top of the log. The next cut uses the flat top as a jig, with the chainsaw



Figure 17.2 • The chain saw mill produces boards from a log. (Photo by Vincent Laurence)

Figure 17.3 • The Wood-Mizer portable mill utilizes a horizontal bandsaw that travels parallel to the log and produces smooth, accurate cuts. (Photo by R. Bruce Hoadley)



cutting a set depth below the face. By slabbing three or four sides of a log first, you can saw square-edge lumber of uniform width. Chainsaw mills are often referred to as Alaska mills because they offer a viable approach to producing lumber on-site in a remote area or wilderness.

Another small-scale solution is a compact, portable bandmill that can be towed behind a pickup truck (*Figure 17.3*). Unlike traditional sawmills in which the saw is stationary and the log moves past it on a carriage, a Wood-Mizer holds the log stationary while a horizontally mounted bandsaw moves along the log guided on sturdy rails. On some models, the operator rolls the log into place, while on others, hydraulics do the work. Accessory equipment assists in turning the log and in holding it firmly in position while sawing. By slabbing first around the log, square-edge lumber can be sawn. Alternately, the log can be flitch-cut, and the wane-edge boards can be stood on edge in the mill (individually or in packs) and cut square.

A portable bandmill has an impressive range of capacity. The smallest models cut logs up to 11 ft. in length and 28 in. in diameter, with cutting rates up to 15 ft. per minute. Larger models cut logs up to 21 ft. long and 26 in. in diameter. The saws can also handle pieces as short as 1 ft. long, making it useful for sawing burls or crotches to produce feather-grain figured boards or blocks. The resulting surfaces are as smooth as those produced on boards sawn by a shop bandsaw, and the accuracy of the dimensions is much closer than mill-sawn boards. In addition, these machines are both faster and quieter than chainsaw mills.

An advantage of a portable bandmill is that you can bring it to the location of the logs and easily set it up to be ready to saw in about 15 minutes. If there is a downside for the average woodworker, it is the price. The tricked-out versions cost about as much as a fancy car. The purchase of a portable mill as a group undertaking by a woodworkers' club or cooperative is worth considering if you are in an area with access to desirable trees. Happily, these mills are often owned by individuals who afford them by doing part-time custom sawing on an hourly basis. The price is typically quite reasonable, so when a storm blows over the huge walnut or cherry tree in your backyard, you can have it milled into lumber right where it fell.

If you don't want to wait for such natural disasters, you'll have to seek out appropriate trees in your area. If you live in or near the country, farmers and landowners are often willing to give or sell you a tree or two, or they will arrange to give you the choice portions of the tree trunk if you buck up the remainder into firewood for their use. Check with landscapes and others who cut a fair amount of firewood. Most will be willing to swap some choice trunk wood for your labor. Orchard managers often replace unproductive, overly mature trees with young ones, providing a source for lumber.

Keep track of construction work in your area. Construction crews are seldom concerned about trees destroyed when clearing land and are likely to burn or bury the wood. You may get that wood for the asking.

Residential and roadside tree work can also yield some valuable material. Whenever I hear a chainsaw, I stop and

investigate. I have never been refused when I asked a tree crew for a chunk of wood to use for carving. The carving shown in *Figure 8.13* on p. 155 came from a basswood tree blown down in a summer storm. I snagged a chunk on my way home from work. In addition to the more common oak, butternut, basswood, maple, and pine. I have picked up beautiful carving blocks of black walnut, honeylocust, yellowwood, corktree, and catalpa. These are species not native to my area but grown as ornamentals.

Two words of caution: First, residential and roadside trees often contain foreign material—fence wire, staples, clothesline pulleys, gate hinges—particularly in the lower 6 ft. This is why tree crews can't sell the logs to sawmills and why mills aren't usually willing to custom-saw a log for you. Second, residential trees often are available precisely because they are defective. Unless a construction clearing or road widening is involved, perfectly healthy trees aren't normally cut down. Likewise, defective trees are the most likely to be blown down in windstorms. Be wary of limewood, which typically has pronounced reaction wood.

It is helpful to establish acquaintance with crews of local highway departments, firewood cutters, utility companies, and tree-service companies. They may be able to let you know when a particularly exotic tree is being cut down. In short, spread the word. Let people know what you want. Before too long, you'll have more wood than you can use.

Some years ago I developed a fondness for carving catalpa, so I began to make my wishes known. The electric company crew trimming around power lines on my road left the pile of catalpa chunks shown in *Figure 17.4* for me.

One morning a short time later, I found a dozen short logs dumped at the foot of my driveway. A friend had happened upon them and remembered my remarks. Soon after that, another friend brought a catalpa log 12 ft. long and 20 in. in diameter. I've since received three more offers of catalpa trees in people's yards on a come-and-get-it basis.

Over the years, I've learned to keep my eyes and ears open for those choice logs and chunks that are free for the asking. At the same time, I have learned to decline material that is not in excellent form and condition, material I can't deal with promptly and properly, and material in excess of what I really want or need. A woodstove or fireplace will be a willing recipient of any culled material you generate in your quest for woodworking raw material.

RECYCLING USED WOOD

Used lumber and timbers are an excellent potential source of wood, although the supply is somewhat unpredictable and sporadic. Old houses, barns, warehouses, and factories can yield fantastic material. By our modern standards, the lumber used for such mundane purposes is unbelievable. Old timbers were often straight-grained and amazingly free of defects. Although nails can be a problem, they were used sparingly as a rule; worked joints were commonly employed. The most hardware-free material is often found in roof and barn framing. Attics and lofts often have wide floor planks laid in place with little or no fastening. Occasionally, beautiful lumber is found squirreled away in a barn or attic.



Figure 17.4 • A pile of catalpa chunks left from a power-line clearing operation. Two of the best chunks were saved for carving blocks. (Photo by R. Bruce Hoadley)

Old furniture, such as church pews or government surplus desks and tables, were often made of very good wood, even if the furniture is poorly constructed. If the veneers are peeling (often the case when made before modern moisture-resistant adhesives), check the cores. Clear chestnut or yellow-poplar are common. Tables may have massive pedestal bases of oak or mahogany that yield sizable carving blocks or turning blanks. The furniture may be a total loss, but the wood could be in perfect condition.

LOCAL SAWMILLS

Large mills are geared to high-volume wholesale trade and normally handle no retail sales whatsoever. Among smaller mills, however, the policy is variable. Some small mills will be happy to sell to an individual; some will refuse. But if you can find one willing to work with you, buying direct from a local mill is one of the best ways to obtain lumber at a low price (*Figure 17.5*). If the stock is rough and green, and you'll have to do your own drying and surfacing.

Small sawmills dot the country, although they rarely advertise. You can locate them through the telephone book yellow pages or through inquiries to the local chamber of commerce. Sometimes you come upon them only by dili-

gent exploration of side roads in your own county or by following a truck carrying logs. Small mills may supply hardwood to the furniture industry or make quantities of wooden parts to order. Many of them saw only rough stock for fencing, pallets, and shipping crates. When approaching a sawyer, keep one thing in mind: The mill is in operation to make money, not to do favors for woodworkers. You should therefore expect to pay at least the going rate for the logs or lumber you buy, plus perhaps a little something extra for the miller's time and effort. In time, your fairness will be more than rewarded and once you become a "special" customer, a small-mill operator usually will outdo himself in putting up your order.

Here are a few tips that may help. First, pool your needs and resources with other woodworkers and place as large an order as possible. The larger the quantity you can buy, the larger the mill that will deal with you. Don't expect a mill operator to stop his work to pick apart a pile of lumber so you can select a board or two. Second, indicate in advance what you are looking for in terms of species, quality, lengths, widths, grades, and approximate quantity, leaving reasonable flexibility in your specifications. Make it clear you are willing to pay a fair price and be reasonable about accepting a portion of the material that does not make the grade if the main portion is up to your specs. Remember also that a local



Figure 17.5 • This pine lumber is air-drying at a small, family-owned mill yard, where small orders can be filled at a reasonable price. (Photo by R. Bruce Hoadley)

mill cannot produce lumber of higher grades and of larger dimensions than the available local timber resource.

LUMBERYARDS

Because lumber is perhaps the most common of the woodworker's primary materials, the lumberyard would seem a most likely place to shop. But the typical modern lumberyard is primarily a builders' supply center, vending everything from hardware, paint, electrical equipment, plumbing, and masonry supplies to roofing, flooring, fencing, and garden tools. The line of wood products available at such places is mainly softwood structural and yard lumber, millwork and specialty items, plus an array of sheet materials—plywood, prefinished hardwood paneling, hardboard, and particleboard.

An important difference between a typical lumberyard and a local sawmill is that the majority (if not all) of the materials come from elsewhere. The inventory will depend in large part on the demand. If you and others repeatedly inquire about special grades, sizes, or species, the yard may agree to carry them. The stock in each yard is largely influenced by the species available in that geographic region, the local building traditions, and the prevalent construction in the area. Certain items may be in demand locally and therefore are commonly stocked. In coastal towns, where boat-building and repair are popular, yards often carry mahogany, teak, and Sitka spruce. If local homeowners prefer weathered exteriors, cedar, redwood, and cypress are likely to be in stock.

Every yard will have plenty of structural lumber, mostly the stronger, uneven-grained conifers such as Douglas-fir (*Figure 17.6*), southern yellow pine, hemlock, and larch, and the moderately even-grained species such as spruces and firs. Structural grades commonly used for residential framing are seldom appropriate for shop woodworking. Occasionally, large timbers and posts of cedar or Douglas-fir contain clear portions suited to carving or sculpture. A major drawback of structural lumber is that the moisture content may be drastically higher than is suitable for most interior cabinetwork. Before the wood is suitable for general shop use, it must be properly dried.

The average yard stocks an assortment of lengths and widths of 1-in. (actually about 3/4in.-thick) pine yard lumber but possibly only one or two grades, usually No. 1 or No. 2 common and perhaps with an offering of some selects. In addition, matched boards of Douglas-fir and hard pine (used for subflooring and sheathing) might be in stock. Western redcedar and redwood may be available in the higher grades (for exterior trim) or the common grades (for exposed siding or decking).

Specialty and millwork items may also be useful. Doorjamb, panel strips, lattice stock, handrails and rounds, stair treads, and thresholds may offer useful material that is dried to levels suitable for interior use. You may find that many of the linear products such as lumber strips and moldings are in reality finger-jointed material, which is well suited for work that will be painted but less desirable for natural-finish projects.

Many lumberyards carry a modest stock of hardwoods in finished board form. These hardwoods are typically kiln-



Figure 17.6 .The average lumberyard may be mainly a builders' supply outlet, so dimension lumber, such as the spruce and fir shown here, is a common commodity. (Photo by R. Bruce Hoadley)



Figure 17.7 • Woodworking supply stores offer small quantities of a variety of woods in different forms, from boards to turning squares. (Photo by Vincent Laurence)

dried and displayed in bins in the store rather than out in the yard sheds with the construction lumber (*Figure 17.7*). This lumber is usually sold by the board, dressed on all four sides, and is available in 3/4-in. thickness, 6-in. to 10-in. widths, and 3-ft. to 6-ft. lengths. Red oak and yellow-poplar are commonly available. Wider panels of edge-glued stock are suitable for furniture and cabinetwork. This material may be quite ready to use for many products but may also come with "sticker shock."

Although the inventory of solid-wood items is shrinking, a typical lumberyard now stocks a growing variety of modified sheet products including plywood, particleboard, fiberboard, and hardboard, most of which are construction types and grades. Many yards also offer birch-veneered lumber-core or particleboard-core panels in 3/4-in. thickness, high-quality imported solid-birch plywood, hardwood plywood paneling (useful for drawer bottoms, dust panels, and carcass backs), and plywood with an overlay of resin-

impregnated paper for exterior painted surfaces as in door panels and signs. Except for special panel-edge banding, veneer is not commonly sold at lumberyards.

Larger yards are now stocking an array of common sizes of engineered products such as glulam and laminated veneer lumber as well as I-joists. These may be just the items you need for a two-bay garage header or to support the roof on the open side of a new porch. In smaller yards, engineered lumber will usually be available for reasonably quick delivery on special order.

► THE WOODWORKERS' RETAIL OUTLETS

This group contains a diverse range of suppliers who deal in various species, forms, and quantities of cabinet woods. Because of the suppliers' diversity, they cannot be described easily or put into neat categories. At one extreme are large commercial wholesalers who deal mostly in hardwood shop lumber, which is sold by grade and is sometimes dried and dressed, sometimes rough and green. These wholesalers normally have minimum order requirements and sell to volume users such as furniture manufacturers, contractors, and architectural woodwork companies.

At the other extreme, you can buy wood by the board foot or by the measured piece at woodworking supply houses that stock a limited inventory of choice and exotic woods, high-grade cabinet lumber, turning squares, carving blocks, and veneers. As expected, the price is relatively high. Such firms commonly operate a combination retail store/mail-order/Internet business.

The average small-shop woodworker is probably interested in something between the extremes of wholesale quantities and the single board. A serious woodworker might typically be looking for moderately small quantities (say, between 30 bd. ft. and 300 bd. ft.) of the higher grades of hardwood lumber that has been kiln-dried to the appropriate interior EMC conditions for the area. Since surfacing equipment is not common in many small shops, the woodworker might prefer the material surfaced on two sides to uniform thickness.

In response to the demand for more moderately priced lumber in limited quantities, numerous small retail outlets and wood stores that typically specialize in local species are springing up all across the country. In many cases, these enterprises are affiliated with local sawmills and their lumber is often "mill run," or ungraded. Boards are sold by the square foot of surface measure and carving blocks by the board foot or by the pound. Such operations may offer additional services such as surface-planing and milling-to-pattern.

A small-shop woodworker can realize the most economical buys on small quantities from such dealers. A frequent

complaint, however, concerns the lack of moisture-content control and especially the loose claims made about stock being dry that actually is not. I cannot imagine operating such a business without humidity control for storage and without a meter for measuring the moisture in the lumber. I can think of no more important quality-control feature upon which to build customer confidence than to provide reliable moisture-content information. But until this is the rule rather than the exception, it behooves the buyer to have a moisture meter to check the moisture content of each purchase.

INDUSTRIAL ARTS TEACHERS

For locating sources of supply at all levels but especially at the intermediate level, local high school or college industrial arts teachers are excellent contacts. They routinely face the problem of locating sources and also must pay attention to economics on behalf of their students. You will usually find them quite helpful, and you may be able to purchase any overstock.

MAGAZINES

Certain organizations (such as the National Woodcarvers Association and the International Wood Collectors Society) issue a journal or bulletin that includes announcements or classified listings of sources. Consumer magazines such as *Fine Woodworking*, *Workbench*, *Wood*, and the *National Carvers Review* feature periodically updated sources of supply and carry classified ads from dealers. Trade magazines also carry advertisements and classified listings. For example, *Wood and Wood Products*, *Panel World*, and *Plywood and Panel* magazines list veneer and plywood firms all across the country. Most forest-industry trade magazines publish an annual directory issue, and most trade associations publish various shoppers' guides.

SPECIALTY WOODS

Specialty woods can be found in association with specific fields of woodworking. For example, high-grade spruce spar stock and thin hardwood plywood are available through boating and aircraft supply houses. They can be located through the advertisements and classified sections in yachting, boating, and sport-flying magazines. Similarly, musical instrument makers rely on premium-quality wood in dozens of species, both domestic and imported. Miniature makers and dollhouse builders have sources of thin stock in small pieces. Patternmakers use great quantities of mahogany.

clear pine, and cherry and might be willing to sell you some or lead you to their sources.

THE YELLOW PAGES AND OTHER LISTINGS

The Yellow Pages carries listings under at least the following headings: Cabinetmakers; Hobby and Model Construction Supplies-Retail; Hardwoods; Hardboard; Lumber-Drying; Lumber-Retail; Lumber-Treated; Lumber-Used; Lumber-Wholesale; Millwork; Patternmakers; Plywood and Veneer; Sawmills; Wood Products; Wood Turning; and Woodworkers. Local chambers of commerce have listings of all the firms in the general area that produce various products. Newspaper classified ads contain an often-overlooked building materials section. Found at public libraries, the *Thomas Register of American Manufacturers* lists the names of firms geographically, under appropriate material, or under product headings.

INTERNET

By spending a few hours on the Internet, you can find hundreds of sources of supply. Any list of suppliers set down in print will soon be outdated since new sites go up daily, but to get started, try any of your favorite search paths or even the auction sites, such as eBay or Yahoo. You'll find everything from individual pieces of lumber to measured lots, at a fixed price or up for auction bidding, and offers of stock in variable quantity priced by the board foot.

As you "shop," pay close attention to the location of the source and the shipping costs that apply. I have looked at various offers where the price or going bid would be doubled by the shipping cost. The same rules apply as elsewhere, so check out the reputation of the firm or ask around before you buy. Be prepared to inquire about the moisture content and drying history.

On some sites, photographs accompany the offers, especially on the pricier items, otherwise you are buying sight unseen.

LUMBERMEN

The agricultural extension service or forestry department at most state universities can help locate local sawmills and logging companies. Nobody knows the lumber business better than lumbermen—ask at the sawmill, lumberyard, and millwork shop. Once you get started, one good supplier usually will lead to several more.

AFTERWORD: FORESTS PAST AND FUTURE

Most woodworkers are understandably concerned about our timber supply, both in America and worldwide. We often hear alarming forecasts that continued increases in wood consumption will deplete our forests and eventually result in a timber famine. However, in the face of dire predictions I remain optimistic. I do not suggest that we can continue using our forest resources the way we have in the past and get away with it. Rather, I have faith that we will be able to adopt new ways of managing our forests and of using the timber we grow.

To understand the present situation and to realize where we must go from here, it is important to appreciate the extent to which our civilization, and American society in particular, has evolved with a dependence upon timber. Exactly where the story begins is not clear, for the use of trees and wood as a source of food, shelter, weapons, and tools predates recorded history. Since the first civilizations, wood has been a primary engineering material. It was also used in sophisticated craft and art, as evidenced by artifacts such as the remarkable wooden objects preserved in Egyptian tombs. Scholars have probably reconstructed pre-history with disproportionate emphasis on the surviving stone and metal artifacts. We grossly underestimate the role wood played in early cultures, simply because the biodegradable evidence no longer remains.

We all know how well our American forefathers built with wood, made furniture and cabinetry, tools, wagons, and ships. But perhaps we overlook the fact that in the early days of our country, wood was also the principal source of energy. As late as 1859, 90% of the national heating requirement was met by burning wood. Annual per-capita consumption was about 4½ cords, mostly as fuel in open fireplaces. Further, 80% of the people lived on farms that had been cleared from the continental forest. Many of life's necessities were taken, through home industry, directly from the local woodlot—the farmer who needed a new shed for his animals, or a handle for his hoe, started making it by felling a tree. Our forefathers relied upon a detailed "wood lore" developed through experience, hearsay and handed-down recipes, with emphasis on how or when to do a thing, not on why it would work.

The average American a century or more ago was—by necessity—knowledgeable about wood from local trees to a degree far surpassing what most of us know today. This education doubtless began in childhood, fetching and carrying from woodpile to hearth. The ability to identify both standing trees and converted wood was as routine to children then as learning ABCs or telling time is today. The child could not help learning which species was best for kindling a fire and which would make the best handles, as surely as our offspring learn to adjust vertical roll on a television set.

In the cities, on the other hand, work was likely to be both more specialized and more skilled. Still, many of the tradesmen were primarily woodworkers: the wheelwright, the cabinetmaker, the cooper, the shipwright, the carpenter, the carver. And as the nation grew, depending on wood for its very survival, the local supply of easily available fuelwood became threatened. The hunger for fuel caused woodlots to be recut as fast as sprout growth reached cordwood size. But always, out there just beyond, was the original forest, an inexhaustible supply of old-growth trees silently holding their wide, clear boards and cords of fuel.

As a flourishing America crossed into the 20th century, the most rewarding and respected trades still dealt with woodworking. Though more and more handwork was replaced by powered machines, their operation was largely manual, and a well-versed apprenticeship system continued to pass the traditions of the various trades from generation to generation. Manufacturing specialization and division of labor superseded "do-it-all-yourself" as the American way of life, so commodities were increasingly made by "someone else." Though technologies of metal, stone, and glass also expanded, the rising standard of living was paced by wooden homes and furniture, and ever more paper goods, especially for packaging.

The consequences were inevitable. By the late 1800s the prime forests of New England had been lumbered off, and then across the Northeast to the Great Lakes and on to the South and finally to the great Western reserves. The last of the virgin stands began to fall before the loggers' saws.

It took a while for Americans to realize that our great forest resource was not inexhaustible. Forest management came

too little, too late. In one area after another, the old growth was logged and relogged, and although most of our forests still exist, their nature has been changed, perhaps forever.

The 20th century brought two important changes in the way we use our forests. First, fossil fuels replaced wood as a source of heat and power. As we learned how to use the trees of prehistoric times, the woodbox was replaced first by the coalbin and then by the oil barrel. Although we now face the consequences of depending on petroleum, it may have prevented catastrophe in the forests. For although our population has risen from about 76 million in 1900 to more than 265 million in 2000, our annual consumption of wood has risen only from 11 to 14 billion cubic feet.

Second, in the past century we developed the technology of composite products. Made possible by progress in adhesive technology, first plywood and then particleboard, fiberboard, and engineered lumber have expanded the horizons of the previous tradition of using wood mostly in solid form.

Today, we find ourselves in an interesting but complex situation. For although we are considered to be in the space age, our national appetite for the oldest of materials—wood—has never been greater. We in the United States consume wood at an annual rate of about one ton per person. This total tonnage equals the combined tonnage of all other structural materials. About half of that tonnage of wood is made into paper and related fiber products.

At present our annual volume of timber growth exceeds the volume harvested by about a third, although in the category of softwood sawlogs, the cut exceeds the regrowth. In the future, however, there will be no more offset in consumption by reduced use of fuelwood, for fuelwood consumption is once again increasing. Over the next quarter century, as population increases, our consumption of wood is expected to double.

At this point we might wonder if there are not alternatives to our forest resources, such as substituting other materials or importing the wood we need. In recent decades, sophistication in the manufacture of metals, plastics, and other synthetics suggested that manmade substitutes for wood might eventually ease the drain on our forests. However, we now appreciate that these potential substitutes are themselves made from nonrenewable resources. In their manufacture they require many times the energy and they pollute the environment significantly more than their counterpart products in wood. It appears that we must face, rather than evade, the challenge of increasing timber production. The question is not, "*Shall* we use our forests?" but, "*How* shall we use our forests?"

Unfortunately, the practices of the forest industry sometimes seem to be at odds with the quality of our environment. Thoughtless and wasteful treatment of our country's forests has given a large segment of the population a preservationist, rather than a conservationist, attitude. We proudly accept the transformation of our great prairies to "amber waves of grain," but the cropping of our forests creates a frightful image of futureless destruction. I hope the polarized attitudes toward our forest resource can reach a compromise: As timber producers see the need and the wisdom of intelligent management and harvesting practices, the environment-minded public may come to accept the reality of multiple-use forest management that includes timber production. Besides, everyone, in spite of their apparent political views, seems to share shamelessly in the consumption of the products of the forests.

WILL THERE BE ENOUGH WOOD?

The major question today is whether we can in fact continue to meet our demands for wood, or whether we are heading for a timber famine.

My belief that we can meet future needs is based first of all on the fact that trees grow. Wood is a renewable resource. It is easy and pleasant to be reminded of this fact. My area of central Massachusetts has some magnificent stands of hardwoods—sugar maple, red and white oaks, cherry and more. Walking in such impressive forests, one notices a network of stone walls, reminders that this land was once cleared and used for crops or pasture. What wasn't cleared for agriculture was probably leveled at one time or another for lumber, firewood, or charcoal. One nearby town, 37% forested in the 1840s, is 97% forested today. On abandoned land, holding back the development of a forest is a greater problem than making one grow.

Nevertheless, in our forests we can see an unfortunate tradition that prevailed in the past and persists even today: the practice of logging and relogging an area, each time taking the best of what grows there with no provision for the future. This has the tragic effect of selecting poorer and poorer residual stock, the inverse of survival of the fittest, with predictable results. When finally allowed to regrow, the forest must spring from the stunted and malformed trees that the loggers did not want, and a forest of the highest quality cannot result. Although unintentionally, the forest has been genetically degraded. In some parts of New England, it has been systematically degraded for 250 years.

For the future, better forest management is imperative. Silvicultural and genetic improvements can vastly increase productivity. Actually speeding up the rate of cutting on some overmature stands may be justified. Reforestation may offset areas falling to the urban sprawl. Since fire, insects, and decay consume as much timber as does man, the value of forest protection is obvious.

In the past, timber prices could not support the cost of intensive management. Today, however, the premium value of sawlog and veneer stumpage changes the picture considerably. The increasing value of low-grade trees and weed species for fuelwood, pulpwood, or for composite products now can pay for stand improvement, which heretofore was not economically feasible. In one way or another we must stop thinking of our forests as wild lands where we simply scavenge what we need. Such a destructive and unproductive approach must be replaced by systematic and intensive forest management for multiple uses—wildlife habitat, watershed protection, recreation, and timber harvest.

As we realize that environmental policy, forest management, and silviculture must address our future needs, so must technology. It should be the goal of every wood technologist to develop improved products to satisfy human needs, at a competitive price and using our changing timber resource. The first serious challenge in this regard is to continue to increase the product yield of the trees we grow and harvest. Under traditional logging and milling practices of converting trees into lumber or veneer, far less than half of the tree found its way into the final product. Residues and waste occurred at every step of conversion. Logging slash and stumps were left in the woods to rot. At the mill, bark, slabs, edgings, trimmings, and sawdust were just a nuisance to be burned or dumped. Throughout secondary processing, additional waste was associated with virtually every manufacturing step.

Today, an integrated modern operation can convert more than 80% of the tree into useful products, with most of the residue converted to fuel. Obviously the goal is to use the entire tree. This approach involves both reduction of residues by more efficient technology as well as finding uses for those residues that will always be a part of solid wood conversion.

Ever greater forest production inevitably means relying on smaller and younger trees. Our annual production will include a smaller proportion of large, solid pieces and a larger proportion of slabs, edgings, and other residues. Therefore the forest products of the future will be—and must be—of a new, different, and changing technology. Structures will be framed using components and materials manufactured from poorer trees but will be characterized by closer functional design rather than wasteful use of choice

material. Furniture will be made of parts glued up from smaller pieces or stained to allow lower-value species to imitate those of higher traditional appeal. As in all wood products, intermarriage with other materials such as plastics, metals, and fabrics will be increasingly appropriate. Many structural and functional wood products will become less and less recognizable as ever having been part of a tree. Plywood and composite products such as particleboard will be the rule rather than the exception.

In the first edition of *Understanding Wood* I wrote, "...today we find ourselves on the threshold of a new era of changing technology, based on a timber resource characterized by smaller, younger trees of seemingly lower quality, processed for greater total yield, into routine consumer products that are less and less recognizably wood." We have now passed through that threshold and we see the changes as they occur. For example, we use composite panels such as oriented strandboard to match plywood as structural sheathing, waste veneer to produce parallel strand lumber, and low-grade aspen trees to produce laminated strand lumber. We will also see continued development of engineered components, from more sophisticated I-joists and roof trusses to energy-efficient floor and wall assemblies.

Such a glimpse of the future frightens some people into believing that solid-wood products will disappear completely. Hardly. Much of the above commentary refers to the commodity use of wood for construction. Traditional wood in its natural form will become more respected and more valuable than ever. The crafting of fine furniture and instruments, and the creation of carvings and sculpture will be elevated just that much higher on the scale of cultural respect.

But there will be some changes to reckon with. The high cost of lumber will encourage the woodworker to look beyond the lumber store and shop the mills directly, or start directly with the tree, the way one did a century or more ago. But this time around the craftsman has the tools and knowledge of modern science and technology: a chain saw to harvest the tree and a chain-saw mill to rip it into lumber or planks; a meter to measure its moisture content as it dries; portable high-speed tools with carbide bits to cut through knots; abrasive papers to work the surface smooth; and stains and finishes for every desired surface effect and functional requirement.

Wood has a future at all levels of use. For our forests will give us not only a backbone resource for large-scale commodities but also the semiprecious jewels for our woodcrafting endeavors. Historians tell us we have passed through the stone and bronze and iron ages. We now hear mention of the space age. But it may well be that yet ahead is a new age of wood... for those who understand it.

APPENDIX 1: COMMERCIAL NAMES FOR LUMBER

Sometimes lumber is sold under the same name as the tree from which it was cut. Sometimes a commercial lumber name corresponds to several species. This list correlates commercial lumber names with common tree names and with botanical names. It is adapted from the U. S. Forest Products Laboratory *Wood Handbook* FPL-GTR-113.

Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree	Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree
Alder, red	Red alder	<i>Alnus rubra</i>	Douglas Fir	Douglas-fir	<i>Pseudotsuga menziesii</i>
Ashi			Cottonwood	Balsam poplar	<i>Populus balsamifera</i>
Black	Black ash	<i>Fraxinus nigra</i>		Eastern Cottonwood	<i>Populus deltoides</i>
Oregon	Oregon ash	<i>Fraxinus latifolia</i>		Black Cottonwood	<i>Populus trichocarpa</i>
White	Blue ash	<i>Fraxinus quadrangulata</i>	Cucumber	Cucumbertree	<i>Magnolia acuminata</i>
	Green ash	<i>Fraxinus pennsylvanica</i>	Cypress:		
	White ash	<i>Fraxinus americana</i>	Baldcypress	Baldcypress	<i>Taxodium distichum</i>
Aspen (popple)	Bigtooth aspen	<i>Populus grandidentata</i>	Pond cypress	Pondcypress	<i>Taxodium distichum</i> var. <i>nutans</i>
	Quaking aspen	<i>Populus tremuloides</i>	Dogwood	Flowering dogwood	<i>Cornus florida</i>
Basswood	American basswood	<i>Tilia americana</i>		Pacific dogwood	<i>Cornus nuttallii</i>
	White basswood	<i>Tilia heterophylla</i>	Eastern softwoods	Black spruce	<i>Picea mariana</i>
Beech	American beech	<i>Fagus grandifolia</i>		Red spruce	<i>Picea rubens</i>
Birch	Gray birch	<i>Betula populifolia</i>		White spruce	<i>Picea glauca</i>
	Paper birch	<i>Betula papyrifera</i>		Balsam fir	<i>Abies balsamea</i>
	River birch	<i>Betula nigra</i>		Eastern white pine	<i>Pinus strobus</i>
	Sweet birch	<i>Betula lenta</i>		Jack pine	<i>Pinus banksiana</i>
	Yellow birch	<i>Betula alleghaniensis</i>		Pitch pine	<i>Pinus rigida</i>
Box elder	Boxelder	<i>Acer negundo</i>		Red pine	<i>Pinus resinosa</i>
Buckeye	Ohio buckeye	<i>Aesculus glabra</i>		Eastern hemlock	<i>Tsuga canadensis</i>
	Yellow buckeye	<i>Aesculus octandra</i>	Elm, rock	Tamarack	<i>Larix occidentalis</i>
Butternut	Butternut	<i>Juglans cinerea</i>		Cedar elm	<i>Ulmus crassifolia</i>
Cedar:				Rock elm	<i>Ulmus thomasi</i>
Alaska	Yellow-cedar	<i>Chamaecyparis nootkatensis</i>		September elm	<i>Ulmus serotina</i>
				Winged elm	<i>Ulmus alata</i>
Eastern red	Eastern red-cedar	<i>Juniperus virginiana</i>	Elm, soft	American elm	<i>Ulmus americana</i>
Incense	Incense-cedar	<i>Libocedrus decurrens</i>		Slippery elm	<i>Ulmus rubra</i>
Northern white	Notern white-cedar	<i>Thuja occidentalis</i>	Fir:		
Port Orford	Port-Orford-cedar	<i>Chamaecyparis lawsoniana</i>	Alpine	Subalpine fir (alpine fir)	<i>Abies lasiocarpa</i>
				Balsam fir	<i>Abies balsamea</i>
Southern white	Atlantic white-cedar	<i>Chamaecyparis thyoides</i>	Balsam	Balsam fir	<i>Abies balsamea</i>
Western red	Western red-cedar	<i>Thuja plicata</i>	California red	California red fir	<i>Abies magnifica</i>
Cherry	Black cherry	<i>Prunus serotina</i>	Douglas-fir	Douglas-fir	<i>Pseudotsuga menziesii</i>
Chestnut	American chestnut	<i>Castanea dentata</i>	Fraser	Fraser fir	<i>Abies fraseri</i>
			Grand	Grand fir	<i>Abies grandis</i>
			Noble fir	Noble fir	<i>Abies procera</i>
			Pacific grand	Pacific silver fir	<i>Abies amabilis</i>
			White	White fir	<i>Abies concolor</i>
			Gum	Sweetgum	<i>Liquidambar styraciflua</i>

Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree	Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree
Hackberry	Hackberry	<i>Celtis occidentalis</i>		Laurel oak	<i>Quercus laurifolia</i>
	Sugarberry	<i>Celtis laevigata</i>		Northern pin oak	<i>Quercus ellipsoidalis</i>
Hem-fir	Western hemlock	<i>Tsuga heterophylla</i>		Northern red oak	<i>Quercus rubra</i>
	California red fir	<i>Abies magnifica</i>		Nuttall oak	<i>Quercus nuttalli</i>
	Grand fir	<i>Abies grandis</i>		Pin oak	<i>Quercus palustris</i>
	Noble fir	<i>Abies procera</i>		Scarlet oak	<i>Quercus coccinea</i>
	Pacific silver fir	<i>Abies amabilis</i>		Shumard oak	<i>Quercus shumardii</i>
	White fir	<i>Abies concolor</i>		Southern red oak	<i>Quercus falcata</i>
				Turkey oak	<i>Quercus laevis</i>
Hem-fir (North)	Western hemlock	<i>Tsuga heterophylla</i>		Willow oak	<i>Quercus phellos</i>
	Pacific silver fir	<i>Abies amabilis</i>	White	Arizona white oak	<i>Quercus arizonica</i>
Hemlock:				Blue oak	<i>Quercus douglasii</i>
Carolina	Carolina hemlock	<i>Tsuga caroliniana</i>		Bur oak	<i>Quercus macrocarpa</i>
Eastern	Eastern hemlock	<i>Tsuga canadensis</i>		Valley oak	<i>Quercus lobata</i>
Mountain	Mountain hemlock	<i>Tsuga mertensiana</i>		Chestnut oak	<i>Quercus prinus</i>
Western	Western hemlock	<i>Tsuga heterophylla</i>		Chinkapin oak	<i>Quercus muehlenbergii</i>
Hickory	Mockernut hickory	<i>Carya tomentosa</i>		Emory oak	<i>Quercus emoryi</i>
	Pignut hickory	<i>Carya glabra</i>		Gambel oak	<i>Quercus gambelii</i>
	Shagbark hickory	<i>Carya ovata</i>		Mexican blue oak	<i>Quercus oblongifolia</i>
	Shellbark hickory	<i>Carya laciniosa</i>		Live oak	<i>Quercus virginiana</i>
Holly	American holly	<i>Ilex opaca</i>		Oregon white oak	<i>Quercus garryana</i>
Ironwood	Eastern hophornbeam	<i>Ostrya virginiana</i>		Overcup oak	<i>Quercus lyrata</i>
Juniper,				Post oak	<i>Quercus stellata</i>
Western	Alligator juniper	<i>Juniperus deppeana</i>		Swamp chestnut oak	<i>Quercus michauxii</i>
	Rocky Mountain juniper	<i>Juniperus scopulorum</i>		Swamp white oak	<i>Quercus bicolor</i>
	Utah juniper	<i>Juniperus osteosperma</i>		White oak	<i>Quercus alba</i>
	Western juniper	<i>Juniperus occidentalis</i>	Oregon myrtle	California-laurel	<i>Umbellularia californica</i>
Larch, Western	Western larch	<i>Larix occidentalis</i>	Osage-orange	Osage-orange	<i>Madura pomifera</i>
Locust	Black locust	<i>Robinia pseudoacacia</i>	Pecan	Bitternut hickory	<i>Carya cordiformis</i>
	Honeylocust	<i>Gleditsia triacanthos</i>		Nutmeg hickory	<i>Carya myristiciformis</i>
Madrone	Pacific madrone	<i>Arbutus menziesii</i>		Water hickory	<i>Carya aquatica</i>
Magnolia	Southern magnolia	<i>Magnolia grandiflora</i>		Pecan	<i>Carya illinoensis</i>
	Sweetbay	<i>Magnolia virginiana</i>	Persimmon	Common persimmon	<i>Diospyros virginiana</i>
Maple:			Pine:		
Hard	Black maple	<i>Acer nigrum</i>	Bishop	Bishop pine	<i>Pinus muricata</i>
	Sugar maple	<i>Acer saccharum</i>	Coulter	Coulter pine	<i>Pinus coulteri</i>
Oregon	Big leaf maple	<i>Acer macrophyllum</i>	Digger	Digger pine	<i>Pinus sabiniana</i>
Soft	Red maple	<i>Acer rubrum</i>	Knobcone	Knobcone pine	<i>Pinus attenuata</i>
	Silver maple	<i>Acer saccharinum</i>	Idaho white	Western white pine	<i>Pinus monticola</i>
Oak:			Jack	Jack pine	<i>Pinus banksiana</i>
Red	Black oak	<i>Quercus velutina</i>	Jeffrey	Jeffrey pine	<i>Pinus jeffreyi</i>
	Blackhack oak	<i>Quercus marilandica</i>	Limber	Limber pine	<i>Pinus flexilis</i>
	California black oak	<i>Quercus kelloggii</i>	Lodgepole	Lodgepole pine	<i>Pinus contorta</i>
	Cherrybark oak	<i>Quercus falcata</i> var. <i>pagodaefolia</i>	Lodgeleaf	Lodgeleaf pine	<i>Pinus palustris</i>
			Slash	Slash pine	<i>Pinus elliottii</i>

Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree	Commercial name for lumber	Common name of tree	Scientific (botanical) name of tree
Northern white	Eastern white pine	<i>Pinus strobus</i>	Sycamore	Sycamore	<i>Platanus occidentalis</i>
Norway	Red pine	<i>Pinus resinosa</i>	Tamarack	Tamarack	<i>Larix laricina</i>
Pitch	Pitch pine	<i>Pinus rigida</i>	Tanoak	Tanoak	<i>Lithocarpus densiflorus</i>
Ponderosa	Ponderosa pine	<i>Pinus ponderosa</i>	Tupelo	Black tupelo, blackgum	<i>Nyssa sylvatica</i>
Radiata/Monterey	Monterey pine	<i>Pinus radiata</i>		Ogeechee tupelo	<i>Nyssa ogeche</i>
Southern pine major	Loblolly pine	<i>Pinus taeda</i>		Water tupelo	<i>Nyssa aquatica</i>
	Longleaf pine	<i>Pinus palustris</i>	Walnut	Black walnut	<i>Juglans nigra</i>
	Shortleaf pine	<i>Pinus echinata</i>	Western woods	Douglas-fir	<i>Pseudotsuga menziesii</i>
	Slash pine	<i>Pinus elliotii</i>		California red fir	<i>Abies magnifica</i>
Southern pine minor	Pond pine	<i>Pinus serotina</i>		Grand fir	<i>Abies grandis</i>
	Sand pine	<i>Pinus clausa</i>		Noble fir	<i>Abies procera</i>
	Spruce pine	<i>Pinus glabra</i>		Pacific silver fir	<i>Abies amabilis</i>
	Virginia pine	<i>Pinus virginiana</i>		Subalpine fir	<i>Abies lasiocarpa</i>
Southern pine mixed	Loblolly pine	<i>Pinus taeda</i>	White woods	White fir	<i>Abies concolor</i>
	Longleaf pine	<i>Pinus palustris</i>		California red fir	<i>Abies magnifica</i>
	Pond pine	<i>Pinus serotina</i>		Grand fir	<i>Abies grandis</i>
	Shortleaf pine	<i>Pinus echinata</i>		Noble fir	<i>Abies procera</i>
	Slash pine	<i>Pinus elliotii</i>		Pacific silver fir	<i>Abies amabilis</i>
	Virginia pine	<i>Pinus virginiana</i>		Subalpine fir	<i>Abies lasiocarpa</i>
Sugar	Sugar pine	<i>Pinus lambertiana</i>		White fir	<i>Abies concolor</i>
Whitebark	Whitebark pine	<i>Pinus albicaulis</i>		Mountain hemlock	<i>Tsuga mertensiana</i>
Poplar	Yellow-poplar	<i>Liriodendron tulipifera</i>		Western hemlock	<i>Tsuga heterophylla</i>
Redwood	Redwood	<i>Sequoia sempervirens</i>		Engelmann spruce	<i>Picea engelmannii</i>
Sassafras	Sassafras	<i>Sassafras albidum</i>		Sitka spruce	<i>Picea sitchensis</i>
Spruce:				Lodgepole pine	<i>Pinus contorta</i>
Blue	Blue spruce	<i>Picea pungens</i>		Ponderosa pine	<i>Pinus ponderosa</i>
Eastern	Black spruce	<i>Picea mariana</i>		Sugar pine	<i>Pinus lambertiana</i>
	Red spruce	<i>Picea rubens</i>		Western white pine	<i>Pinus monticola</i>
	White spruce	<i>Picea glauca</i>	Willow	Black willow	<i>Salix nigra</i>
Engelmann	Engelmann spruce	<i>Picea engelmannii</i>		Peachleaf willow	<i>Salix amygdaloides</i>
Sitka	Sitka spruce	<i>Picea sitchensis</i>	Yew, Pacific	Pacific yew	<i>Taxus brevifolia</i>

APPENDIX 2: FINDING THE SPECIFIC GRAVITY OF WOOD

For some time I've been trying to work out a shortcut for determining the specific gravity of wood. (It's useful in wood identification, as well as in other aspects of wood-working, such as in building decoys.) I finally came up with the following method:

1. Machine the sample to rectangular or cylindrical dimensions that will give a volume equal to one of the numbers of cubic inches given in the table. (I have also included sets of dimensions that will yield the given volumes.)
2. Place the sample in an oven at 212°F for 24 hours.
3. Weigh the sample.
4. Use the chart to determine density, as shown in the examples.

NOTES:


1. *If possible, weights should be to the nearest 0.1 gram or to the nearest 0.01 ounce. (The chart will show how much a deviation of weight will affect accuracy. As an example, for a sample with a volume of 6.75 cubic inches and a weight of 60 grams, a variation of 1 gram will represent only about 0.01 variation in specific gravity. For a sample with a volume of 1 cubic inch and a weight of 10 grams, however, a 1-gram variation will affect accuracy by about 10%.)*
2. *Remember that the specific gravity of wood machined to dimension while green, room-dry, or air-dry will be based on that original volume. If specific gravity on an oven-dry basis is desired, cut the piece 10% or more oversize, oven-dry, cool, and quickly machine to the desired dimensions. Then return the wood to the oven for an hour and weigh it again to determine oven-dry weight.*

EXAMPLES:

A. Assume a piece of hickory is machined to $\frac{3}{4}$ in. by $\frac{3}{4}$ in. by 6 in., for a volume of 3.375 cubic inches, and that after oven-drying it weighs 1.35 ounces. Its specific gravity will be 0.69.

B. Assume a piece of eastern white pine is cut to $1\frac{1}{2}$ in. by $1\frac{1}{2}$ in. by 6 in. for a volume of 13.5 cubic inches, and that after oven-drying it weighs 78.6 grams. Its specific gravity will be 0.355.

C. Suppose you have a piece of sugar maple turned to a diameter of 1 in. To determine specific gravity, we might want about 5 cubic inches. Since $V = 5 \text{ in.}^3 = \pi r^2 h$, then $h = 5 / \pi (\frac{1}{2})^2 = 6.37 \text{ in.}$ Therefore, cut the dowel to a length of 6.37 in. Suppose we oven-dry the dowel and it now weighs 50.88 grams. The specific gravity would be 0.62.



GLOSSARY

ABSOLUTE HUMIDITY

The weight of water vapor per unit volume of air, usually expressed as grains/cu. ft. *See also* Relative Humidity.

ABSORPTION

The gain of free water by the cell cavities.

ACROSS THE GRAIN

Generally perpendicular to the grain direction.

ADHESIVE

Any substance such as glue, resin, cement, or paste capable of holding or joining materials (adherends).

ADSORBED WATER

Same as Bound Water.

ADSORPTION

The gain of bound water by the cell wall from adjacent air.

ADULT WOOD (MATURE WOOD. OUTER WOOD)

Wood produced after cambial cells have attained maximum dimensions. *See also* Juvenile Wood.

ADVANCED DECAY

An older stage of decay readily recognized as wood that has become punky, soft and spongy, stringy, ringshaked, pitted, or crumbly.

AGAINST THE GRAIN

Reference to cutting direction, as in planing a board surface, such that splitting ahead of the cutter follows the grain direction downward into the wood below the projected cutting surface. Also, generally perpendicular to the grain direction, across the grain. *See also* With the Grain.

AIR-DRIED (AIR-SEASONED)

Having reached equilibrium with outdoor atmospheric humidity. When unspecified, 12% moisture content is the assumed value. *See also* Kiln-Dried.

ALIFORM PARENCHYMA

As seen in cross section, an arrangement of parenchyma cells grouped closely around pores and forming winglike lateral extensions.

ALLOWABLE STRESS

A lumber stress level published for design use and identified with species and grade description and use specification.

ALONG THE GRAIN

Generally parallel to the grain direction.

ANGIOSPERM

Belonging to the class of plants having seeds enclosed in an ovary. Within this class, the subclass dicotyledons includes all hardwood trees.

ANGLE OF ATTACK

Same as Cutting Angle.

ANISOTROPIC

Not having the same properties in all directions.

ANNUAL RING (ANNUAL GROWTH RING, ANNUAL INCREMENT)

See Growth Ring.

ASSEMBLY TIME

The time elapsed between spreading adhesive on surfaces to be joined and application of pressure to the joint. Open assembly time is from the beginning of spreading to joint closure. Closed assembly time is from joint closure to application of full pressure.

BACK

The poorer of the two faces of a panel of plywood or other composite.

BALANCED CONSTRUCTION

Symmetrical construction of plywood or other composites having matching layers on both sides of the central plane so that changes in moisture content will not cause warp.

BANDED PARENCHYMA

As viewed in cross section, parenchyma cells that collectively appear as thin, lighter-colored tangential lines (as occur in hickory).

BARK

The tree tissue outside of the cambium, including inner (living) bark and outer (dead) bark.

BASTARD GRAIN (BASTARD SAWN)

Lumber having growth rings that form angles of 30° to 60° with the faces.

BEAM

An elongated member usually supported horizontally and loaded perpendicular to its length.

BIRD'S EYE

Small circular or elliptical areas resembling birds' eyes on the tangential surface of wood, formed by indented fibers. Common in sugar maple and used for decorative purposes; rare in other species.

BLACK KNOT

Same as Encased Knot.

BLEMISH

A defect or anything that mars the appearance of wood.

BLUE STAIN (SAPSTAIN)

A bluish or grayish discoloration of sapwood caused by the growth of certain dark-colored fungi on the surface and inside the wood,

BOARD FOOT

A unit of lumber measurement equivalent in volume to a piece having nominal dimensions of 1 ft. (length) by 12 in. (width) by 1 in. (thickness).

BOARDS

Lumber 2 in. or more wide THAT IS NOMINALLY LESS THAN 2 in. THICK. Boards LESS THAN 6 in. WIDE are also called STRIPS.

BOLE

A tree stem or trunk LARGE ENOUGH FOR CONVERSION INTO LUMBER or veneer.

BOLT

A short SECTION of a tree TRUNK.

BOUND WATER (ADSORBED WATER, HYGROSCOPIC WATER)

Water held hygroscopically in the CELL WALL; WATER IN WOOD BELOW the fiber SATURATION POINT.

BOW

A form of warp; DEVIATION FROM LENGTHWISE FLATNESS IN A BOARD.

BRASHNESS

Brittleness IN WOOD, CHARACTERIZED by abrupt FAILURE RATHER THAN splintering. Causes include REACTION wood, juvenile wood, compression FAILURE, HIGH TEMPERATURE, AND EXTREMES OF GROWTH RATE.

BROKEN STRIPE

Ribbon figure in which THE STRIPE EFFECT is intermittent.

BROWN ROT

Decay CAUSED by a type OF FUNGUS THAT ATTACKS CELLULOSE RATHER THAN lignin, LEAVING a brownish RESIDUE.

BULK PILING

See Solid Piling.

BURL (BURR)

A hard, WOODY OUTGROWTH on a tree, MORE OR LESS ROUNDED IN FORM, usually RESULTING FROM the entwined GROWTH of a cluster of adventitious BUDS. BURLS are a source OF highly figured veneers.

CAMBIUM

The thin layer of living, meristematic (reproductive) CELLS BETWEEN bark AND WOOD which, by cell division, FORMS NEW BARK AND WOOD cells.

CASE-HARDENING

A condition in dry lumber WHEREIN RESIDUAL drying stresses leave the OUTER LAYERS UNDER COMPRESSION BUT THE INNER CORE in tension.

CAVITY (CELL CAVITY, LUMEN)

The void SPACE of a cell ENCLOSED by the CELL WALL.

CELL (ELEMENT)

The basic STRUCTURAL UNIT of wood (and OTHER PLANT) TISSUE CONSISTING of an outer cell wall SURROUNDING a central CAVITY or lumen. WOOD cell TYPES INCLUDE TRACHEIDS, VESSEL ELEMENTS, FIBERS, LONGITUDINAL parenchyma, AND RAY CELLS.

CELLULOSE

A polymer CHAIN CARBOHYDRATE, $(C_6H_{10}O_5)_n$, the MAJOR CONSTITUENT of wood CELL WALLS.

CHECKS

Separations of wood CELLS ALONG THE GRAIN as a result of uneven shrinkage, most common on end-GRAIN SURFACES of lumber.

CHIP ANGLE

Same as Cutting Angle.

CHIPPED GRAIN (TORN GRAIN)

A machining DEFECT IN WHICH SMALL CHIPS ARE TORN FROM THE SURFACE below THE INTENDED PLANE OF CUT, USUALLY as the RESULT of cutting against THE GRAIN.

CLEAR

In reference to lumber, free of defects or blemishes.

CLEARANCE ANGLE

The angle between the back of the knife and the path of the cutting edge. It is usually designated by the Greek letter γ .

CLOSE GRAIN (FINE GRAIN, DENSE GRAIN, NARROW GRAIN)

Slowly grown wood having narrow, usually inconspicuous growth rings in contrast to coarse grain or open grain.

CLOSED ASSEMBLY TIME

See Assembly Time.

CLOSED FACE

Same as Closed Side.

CLOSED GRAIN

See Fine Texture.

CLOSED SIDE (CLOSED FACE, TIGHT SIDE)

The veneer surface not touching the veneer knife during peeling or slicing, which is free of knife checks.

COARSE GRAIN

Descriptive of wood having wide and conspicuous growth rings in contrast to close grain. Sometimes used synonymously with "coarse texture" to designate woods with relatively large cell size.

COARSE TEXTURE

Descriptive of wood having relatively large pores, especially in reference to finishing. Preferred to "open grain."

COLLAPSE

A shriveled or irregular appearance of wood due to flattened or caved-in cell structure, usually caused by capillary tension during early stages of drying wet wood.

COMB GRAIN

See Rift Grain.

COMPRESSION FAILURES

Irregular planes of buckled cells, caused by excessive compressive stress parallel to the grain, appearing as fine cross-wrinkles on longitudinal planed surfaces.

COMPRESSION WOOD

See Reaction Wood.

CONDITIONING

Exposure under controlled relative humidity to bring wood to a desired moisture content. Also, the final stage of a kiln schedule designed to relieve residual case-hardening stress.

CONFLUENT PARENCHYMA

As seen in a cross section, parenchyma cells so grouped as to form a more or less tangential band connecting two or more pores.

CONIFEROUS WOOD

Same as Softwood.

CORD

A unit of measure for round-wood, such as firewood and pulpwood. The standard cord is a pile of 4-ft. long logs, 4 ft. high, 8 ft. across.

CORE

The inner portion of a board, equivalent to half its thickness. See also Shell. In plywood, the center ply, or collectively, all layers between the face and back plies.

CORE WOOD

Same as Juvenile Wood.

CRACK

A large radial check resulting from greater tangential than radial shrinkage.

CREEP

Time-dependent deformation of a wood member or adhesive joint due to sustained stress.

CROOK

A form of warp; deviation from end-to-end straightness along the edge of a board.

CROSSBANDS

In plywood with more than three plies, those veneers immediately beneath the faces, having grain direction perpendicular to that of the faces. See also Straight Bands.

CROSS BREAKS

Transverse planes of failure in tension parallel to the grain, caused by localized abnormal longitudinal shrinkage (as in reaction wood) restrained by adjacent normal wood.

CROSS GRAIN

Deviation of grain direction from the longitudinal axis of a piece of wood or from the stem axis in a tree. Pronounced deviation from the surface, especially in veneer, is termed short grain. See also Spiral Grain, Diagonal Grain.

CROSS SECTION (TRANSVERSE SECTION)

A section cut perpendicular to the grain, or the surface exposed by such a cut.

CROTCH GRAIN

Figure produced by cutting centrally through a tree crotch in the common plane of both branches.

CUP

A form of warp; deviation from flatness across the width of a board.

CURING

The setting of an adhesive by chemical reaction. Also, the drying of wood, though this is not the preferred usage.

CURLY FIGURE (FIDDLEBACK GRAIN. TIGER GRAIN)

The figure produced on surfaces, particularly radial, of wood having wavy grain.

CURLY GRAIN

Same as Wavy Grain. Also, sometimes the distorted grain around bird's eyes is called curly-grained wood.

CUTTING ANGLE (ANGLE OF ATTACK: CHIP. HOOK. OR RAKE ANGLE)

The angle between the face of a cutting edge and a plane perpendicular to its cutting direction, usually designated by the Greek letter α .

DECAY (ROT)

The decomposition of wood by fungi.

DECIDUOUS TREES

Trees whose leaves normally drop after the yearly period of growth is over.

DEFECTS

Irregularities or abnormalities in wood that lower its strength, grade, value, or utility.

DELAMINATION

The separation of layers in laminated wood or plywood caused by failure of the adhesive itself or of the interface between adhesive and adherend.

DENSE GRAIN

Same as Close Grain.

DENSITY

The weight of a body or substance per unit volume.

DESORPTION

The loss of bound (adsorbed) water from the cell wall.

DEWPOINT

The temperature at which atmospheric water vapor condenses out as a liquid.

DIAGONAL GRAIN

Cross grain exhibiting deviation of the growth-ring plane from the longitudinal axis, commonly the result of sawing boards other than parallel to the bark of the log.

DIAMONDING

A form of warp resulting from greater tangential than radial shrinkage, which causes square sections to become diamond-shaped or round sections to become oval.

DICOTS (DICOTYLEDONS)

A class of plants (within the angiosperms) characterized by having two cotyledons or seed leaves. All hardwood tree species fall within the dicots. See also Monocots.

DIFFUSE-POROUS WOOD

A hardwood in which the pores are of approximately uniform size and are distributed evenly throughout each growth ring. See also Ring-Porous Wood.

DIMENSIONAL STABILIZATION

Treatment of wood to minimize shrinkage and swelling.

DIMPLES

Numerous small depressions in growth rings, especially obvious on split tangential surfaces. Occasionally occurs among certain conifers, notably ponderosa and lodgepole pines.

DIP GRAINED

Having a single wave or undulation of fiber direction, such as occurs in wood along either side of a knot.

DRESSED SIZE

The dimensions of lumber after being surfaced with a planing machine.

DRY-BULB TEMPERATURE

The temperature of the air as indicated by a standard thermometer. See also Wet-Bulb Temperature.

DRYING DEFECTS

Irregularities resulting from drying that may lower the strength, durability or utility of wood, such as checks or casehardening.

DRY KILN

Same as kiln.

DRY ROT

A term loosely applied to any dry, crumbly rot, but especially to that which, when in an advanced state, permits the wood to be crushed easily to a dry powder. The term is actually a misnomer for any decay, since all fungi require considerable moisture for growth.

DURABILITY

A general term referring to resistance to deterioration; frequently refers specifically to decay resistance of wood, but also to resistance of adhesive bonds and finishes to deterioration.

EARLYWOOD (SPRINGWOOD)

The first-formed portion of the growth ring, often characterized by larger cells and lower density.

EDGE GRAIN (QUARTERSAWN, VERTICAL GRAIN, RADIAL CUT)

Referring to pieces in which the growth rings form an angle of 45° or more (ideally 90°) with the wood surface or lumber face: approaching or coinciding with a radial surface. See also Rift Grain.

ELASTICITY

A property of a material that causes it to return to its original dimensions after being deformed by loading.

ELECTRODES

Components of moisture meters that contact or penetrate the wood when measuring moisture content.

ELEMENT

Same as Cell.

ENCASED KNOT (LOOSE KNOT, BLACK KNOT)

The dead portion of a branch embedded in the stem by subsequent growth of the tree.

END GRAIN

A cross-sectional surface or the appearance of such a surface.

EQUILIBRIUM MOISTURE CONTENT (EMC)

The moisture content eventually attained in wood exposed to a given level of relative humidity and temperature.

EVEN GRAIN

Wood having uniform or nearly uniform structure throughout the growth ring and little or no earlywood/latewood distinction, as in bass wood.

EXTRACTIVES

Substances deposited in wood in the transition from sapwood to heartwood, often imparting significant color and decay resistance.

FACE

Either side or surface of a plywood panel. Also, the surface of plywood having the higher quality, in which case the opposite side is called the back.

FACE GRAIN

The figure or pattern on the face side of a plywood panel or board.

FACTORY AND SHOP LUMBER

Lumber intended to be cut up for use in further manufacture.

FEATHER CROTCH (FEATHER GRAIN)

The figure produced by a longitudinal section through a tree crotch, characterized by a featherlike appearance.

FIBER

A specific hardwood cell type, typically elongated with pointed ends, having thick walls and contributing notably to the strength of wood. Also, in the plural, used as a general term for separated wood cells collectively, as in papermaking.

FIBERBOARD

A panel product manufactured of refined or partially refined wood fibers.

FIBER SATURATION POINT (FSP)

The condition of moisture content where cell walls are fully saturated but cell cavities are empty of free water.

FIDDLEBACK

Same as Curly Figure.

FIGURE

Any distinctive appearance on a longitudinal wood surface resulting from anatomical structure, irregular coloration or defects.

FINE GRAIN

See Close Grain. Also, sometimes used synonymously with "fine texture" to designate woods with relatively small cells.

FINE TEXTURE

Descriptive of hardwoods having small and closely spaced pores, or softwoods with small-diameter tracheids. Preferred to "closed grain" in reference to finishing.

FLAME GRAIN

Applied to figure produced on flatsawn boards or rotary-cut veneer.

FLATSAWN (FLAT GRAINED, PLAINSAWN, SLASH GRAINED, SIDE GRAINED, TANGENTIAL CUT)

Indicating wood machined along an approximately tangential plane, such that growth rings intersect the surface at an angle of less than 45°.

FLECKS

See Pith Flecks. Ray Flecks.

FLITCH

A portion of a log sawn on two or more faces, commonly on opposite faces, leaving two waney edges. When intended for resawing into lumber, it is resawn perpendicular to its original wide faces. Or, it may be sliced or sawn into veneer, in which case the resulting sheets of veneer laid together in the sequence of cutting are called a flitch.

FLUORESCENCE

The absorption of invisible ultraviolet (black) light by a material that transforms the energy and emits it as visible light of a particular color.

FREE WATER

Moisture held in the cell cavities of the wood, not bound in the cell wall.

FUNGI

Simple forms of microscopic plants, whose parasitic development in wood may cause mold, stain or decay.

FUZZY GRAIN

See Woolly Grain.

GELATINOUS FIBERS

Fibers in hardwoods with abnormal inner cell walls, associated with tension wood.

GRADE

A designation of the quality of a log, or of a wood product such as lumber, veneer, or panels.

GRAIN

A confusingly versatile term whose specific meaning must be made apparent by context or by associated adjectives. Among its uses are direction of cells (e.g., along the grain, spiral grain), surface appearance or figure (e.g., ribbon grain), growth-ring placement (e.g., vertical grain), plane of cut (e.g., end grain), growth rate (e.g., narrow grain), early/latewood contrast (e.g., uneven grain), relative cell size (e.g., open grain, meaning coarse-textured), machining defects (e.g., chipped grain), or artificial decorative effects (e.g., graining). See also specific compound terms.

GRAIN DIRECTION

The direction of the long axes of the dominant longitudinal cells or fibers in a piece of wood.

GRAINING

Painting or otherwise I M I T A T I N G T H E F I G U R E O F W O O D S U R

GRAIN SLOPE

See Slope of Grain.

GREEN

Freshly cut AND UNSEASONED. ALSO, HAVING MOISTURE content above fiber saturation POINT.

GROSS FEATURES

Physical features OF WOOD THAT CAN BE PERCEIVED with THE UNAIDED eye, sometimes INCLUDING MACROSCOPIC FEATURES.

GROWTH RING (GROWTH LAYER, GROWTH INCREMENT)

The layer OF WOOD (or bark) ADDED TO THE STEM IN A given GROWTH period; in THE TEMPERATE zones, one layer is ADDED per YEARLY GROWTH period and IS OFTEN TERMED annual ring.

GYMNOSPERM

The class OF PLANTS HAVING NAKED SEEDS (not enclosed in AN OVARY). Within this GROUP ARE all trees yielding softwood lumber.

HAND LENS

A magnifying lens, HAND-HELD, USED TO EXAMINE wood; 10x IS THE standard magnification USED.

HARDNESS

The property OF WOOD THAT measures its resistance to INDENTATION.

HARDWOOD (POROUS WOOD)

Woods produced BY BROAD-LEAVED trees in the botanical group referred to AS ANGIOSPERMS. SINCE THESE WOODS HAVE vessels, they are also TERMED POROUS WOODS, BECAUSE A VESSEL IN cross section is termed a pore. (The term HARDWOOD IS NOT a designation of ACTUAL hardness in WOOD.)

HEADSAW

The principal BREAKDOWN MACHINE IN A SAWMILL, usually EITHER A CIRCULAR saw or a BANDSAW.

HEART SHAKE (HEART CHECK, RIFT CRACK)

Radial crack IN THE VICINITY OF THE pith.

HEARTWOOD

The central core of wood IN MATURE STEMS. AT ONE time HEARTWOOD was sapwood but it no longer conducts SAP or has living CELLS. IN most species, extractives IMPART A DARKER COLOR TO heartwood.

HONEYCOMBING

Checks that OCCUR IN THE INTERIOR OF A PIECE OF WOOD, usually IN THE plane of THE RAYS, AS A RESULT OF case-hardening stresses developed in drying.

HOOK ANGLE

Same as Cutting Angle.

HOOKE'S LAW

A law that STATES FOR ELASTIC MATERIALS, STRAIN IS proportional TO stress within the ELASTIC RANGE. See Modulus of Elasticity.

HYDROMETER

An elongated, WEIGHTED GLASS INSTRUMENT THAT measures the specific gravity OF LIQUID by the depth TO WHICH it sinks when FLOATED in the LIQUID. USED by woodworkers to DETERMINE the STRENGTH OF PEG solutions.

HYGROMETER

An instrument THAT measures the relative HUMIDITY of THE atmosphere. See also Psychrometer.

HYGROSCOPICITY

The ability OF A SUBSTANCE TO ADSORB AND DESORB water.

HYGROSCOPIC WATER

Same as Bound Water.

HYPHAE

The microscopic filaments of a fungus, which digest and adsorb material from its host. See also Incipient Decay, Mycelium.

INCIPIENT DECAY

An early stage of decay in which hyphae have invaded the cell structure, sometimes discoloring the wood, but have not perceptibly reduced the hardness of the wood.

INCLUDED SAPWOOD

Areas of light-colored wood, apparently sapwood, found within the portion of stem that has become heartwood.

INCREMENT

The growth added in a given period. See also Growth Ring.

INNER BARK

See Bark.

INTERGROWN KNOT (TIGHT KNOT RED KNOT)

A portion of a branch that was alive when intergrown with the surrounding stem.

INTERLOCKED GRAIN

Repeated alternation of left- and right-hand spiral grain, each reversal usually distributed over several growth rings.

ISOTROPIC

Having equal properties in all structural directions.

JOIST

One of a series of parallel beams used to support floor and ceiling loads, usually installed with its wide dimension vertical. See also Plank.

JUVENILE WOOD (CORE WOOD. PITH WOOD)

Wood formed near the pith of the tree, often characterized by wide growth rings of lower density and abnormal properties. See also Adult Wood.

KILN (DRY KILN)

A heated chamber for drying lumber, veneer, and other wood products, in which temperature, humidity, and air circulation are controlled.

KILN-DRIED

Having been dried in a kiln to a specified moisture content; for cabinet woods, usually implies dryness below that attainable by air drying. See also Air-Dried.

KILN SCHEDULE

A sequence of dry-bulb and wet-bulb temperatures specified for successive stages of drying lumber in a kiln, designed to attain desired dryness without defects.

KINK

A form of warp characterized by abrupt deviation from straightness or flatness due to either localized grain distortion (as around knots) or to deformation by misplaced stickers.

KNIFE CHECKS (LATHE CHECKS)

Parallel-to-grain failures developed cyclically in one side of knife-cut veneer during its manufacture; depth of checks varies with species and cutting conditions. Also called lathe checks, especially in peeled veneer. See also Closed Side, Open Side.

KNOT

A portion of a branch overgrown by the expanding girth of the bole or a larger branch. See also Intergrown Knot, Encased Knot, Spike Knot, Pin Knot.

LAMINATED VENEER LUMBER (LVL)

A structural lumber manufactured from veneers with the V E N E E R S

LATEWOOD (SUMMERWOOD)

The portion of the growth ring formed after earlywood, often characterized by smaller cells or higher density.

LATHE CHECKS

See Knife Checks.

LEAF GRAIN

Another term for flat-grain figure.

LIGNIN

A complex chemical substance making up approximately 25% of wood substance, interspersed with cellulose in forming the cell wall. Lignin stiffens the cell and functions as a bonding agent between cells.

LONGITUDINAL

Parallel to the stem axis of the tree or branches, therefore describing the axial direction of the dominant cell structure: along the grain.

LONGITUDINAL GRAIN

Any plane cut parallel to the grain direction of wood. It may be radial, tangential, or an intermediate plane.

LOOSE KNOT

See Encased Knot.

LOOSENED GRAIN (SHELLED GRAIN)

Separation of latewood layers from a planed surface, usually accompanying pronounced raised grain and typically occurring on the pith side of flatsawn boards.

LOOSE SIDE

Same as Open Side.

LUMBER

Pieces of wood no further manufactured than by sawing, planing, crosscutting to length, and perhaps edge-matching.

LUMEN (CELL LUMEN)

See Cavity.

MACROSCOPIC

Referring to features visible with low-power magnification (e.g., a 10x hand lens), as distinguished from microscopic features.

MATURE WOOD

See Adult Wood.

MEDULLA

See Pith.

MEDULLARY RAYS

Rays connected with the pith. Often used (loosely) to refer to all rays.

MERISTEM

Reproductive tissue. Apical meristems are located in twig tips and produce elongation. The cambium is a lateral meristem producing girth.

MICROBEVEL

An extremely narrow bevel along a cutting edge, which increases the sharpness angle for greater edge durability.

MICROMETER (um)

$\frac{1}{1000}$ of a millimeter, or approximately $\frac{1}{25,000}$ of an inch.

MIL

$\frac{1}{1000}$ of an inch.

MIXED GRAIN

Referring to a quantity of lumber containing both edge-grain and flat-grain pieces.

MODULUS OF ELASTICITY

The ratio of stress to strain, within the elastic range of a material.

MODULUS OF RUPTURE

In reference to wood, the stress in bending sustained at failure.

MOISTURECONTENT

The weight of water in the cell walls and cavities of wood, expressed as a percentage of oven-dry weight.

MOISTURE GRADIENT

The variation of moisture content in wood, such as the gradation from wetter core to drier surface in a drying board.

MOISTUREMETER

An instrument used for the rapid determination of moisture content in wood by electrical means.

MOLD

A fungal growth on wood taking place at or near the surface, usually greenish to black in color.

MONOCOTS (MONOCOTYLEDONS)

A class of plants (within the angiosperms) characterized by a single cotyledon or seed leaf. *See also* Dicots.

MOTTLED FIGURE

A type of broken stripe figure having irregular interruptions of curly figure.

MYCELIUM

The mass of hyphae (microscopic elements) of a fungus, often visible as a cottony mat or layer on the surface of wood with advanced decay.

NARROW GRAIN

Same as Close Grain.

NEEDLE-POINT GRAIN

Same as Rift Grain.

NOMINAL DIMENSION

The dimension by which lumber is known and sold in the market (the actual dimension after drying and dressing may be somewhat less).

NONPOROUS WOOD

See Softwood.

OLD GROWTH (VIRGIN TIMBER)

Trees in a mature, naturally established forest, whose timber is characterized by large size, straight holes and freedom from knots.

OPEN ASSEMBLY TIME

See Assembly Time.

OPEN FACE

Same as Open Side.

OPEN GRAIN

See Coarse Texture. Also, descriptive of wood having widely spaced growth rings, in contrast to *close or dense grain*.

OPEN PILING

Stacking wood products in layers separated by stickers to permit air circulation.

OPEN SIDE (LOOSE SIDE, OPEN FACE)

The surface of veneer against the knife during peeling or slicing; may contain knife checks.

ORIENTEDSTRANDBOARD(OSB)

A type of panel product made from strandlike flakes that are aligned in directions that improve the properties of the panel in the alignment directions over panels with random flake orientation.

OUTER BARK

See Bark.

OUTER WOOD

Same as Adult Wood.

OVEN-DRY WOOD

Wood dried to constant weight in an oven maintained at temperatures of 101°C to 105°C (214°F to 221°F).

OVERLAY

Sheet materials other than veneer (plastics, paper, metal) glued to the surface of wood panels.

PARENCHYMA

Thin-walled wood cells (living when part of sapwood) involved mainly with food storage and distribution. With a hand lens, groupings of parenchyma may appear as light-colored areas on cross sections. See also Prosenchyma.

PECK (PECKINESS, PECKY DRY ROT)

Advanced decay in living trees that occurs in the form of elongated pockets of rot; most familiar in baldcypress and incense cedar.

PEELED VENEER

Same as Rotary-Cut Veneer.

PHLOEM

The tissue of the inner bark, which conducts food in the tree. Also used loosely in reference to bark in general.

PIGMENT FIGURE

Figure in wood resulting from irregular deposits of colored extractives.

PINHOLES

Small round holes in wood caused by insects.

PIN KNOT

A knot less than $\frac{1}{2}$ in. in diameter.

PITCH

Material formed in the resin canals of softwood; also, accumulation of resin, as in pockets, streaks, or seams, or as is exuded from wounds.

PITCH POCKET

A flattened round or oval tangential separation in the wood of conifers, which contains (or did contain) solid or liquid resin (pitch).

PITH (MEDULLA)

The small core of soft, spongy tissue located at the center of tree stems, branches, and twigs.

PITH FLECKS

Longitudinal streaks of wound tissue caused by the vertical tunneling of fly larvae belonging to the genus *Agromyza*.

PITH WOOD

Same as Juvenile Wood.

PITS

Recesses or unthickened portions of the secondary cell walls through which fluids pass from cell to cell.

PLAIN SAWN (PLAIN GRAIN)

Same as Flatsawn.

PLANK

A piece of structural lumber installed with its wide dimension horizontal, usually intended as a bearing surface. See also Joist.

PLYWOOD

A composite board of veneers glued together with the grain directions of adjacent layers mutually perpendicular.

POCKET ROT

A localized, sharply delineated volume or pocket of advanced decay surrounded by apparently sound wood.

PORE

The cross section of a hardwood vessel.

PORE MULTIPLE

Two or more pores arranged radially and in close contact.

POROUS WOOD

Same as Hardwood.

POT LIFE

Same as Working Life.

POWDER-POST BEETLES

Small beetles, especially of the genus *Lyctus*, that attack mainly sapwood of large-pored hardwoods, reducing the tunneled wood to fine powder.

PRESERVATIVE

Any substance used to treat wood for protection against fungi, insects, or marine borers.

PROSENCHYMA

Nonliving wood cells that function in conduction and support. Includes tracheids, vessels, and fibers and accounts for most of the volume of wood structure. See also Parenchyma.

PSYCHROMETER

A type of hygrometer for measuring atmospheric humidity by dry-bulb and wet-bulb thermometers.

QUARTERSAWN (QUARTERED, QUARTER GRAIN)

See Edge Grain.

QUILTED FIGURE

Figure sometimes found in bigleaf maple, characterized by crowded bulges in the grain direction.

R

Symbol for radial section or surface.

RADIAL

The horizontal direction in a tree between pith and bark. A radial section is along a plane that would pass lengthwise through the pith.

RADIAL CUT (RADIAL GRAIN)

See Edge Grain.

RAISED GRAIN

A condition developed in planing causing the elevation of latewood above earlywood, without separation, typically on the pith side of flatsawn boards. Also, the severed cells caused to rise above a surface by intentional wetting, as done in preparation for final sanding.

RAKE ANGLE

See Cutting Angle.

RATE OF GROWTH

The relative rate of increase in tree girth, usually expressed as rings per inch.

RAY FLECKS

The conspicuous appearance of rays on an edge-grain surface.

RAY

Flattened bands of tissue composed of ray cells, extending horizontally in a radial plane through the tree stem. See also Medullary Ray.

REACTION WOOD

Abnormal wood formed in leaning stems and branches in trees. In softwood trees, it forms on the lower side of the stem and is called compression wood: it is denser but more brittle and has greater than normal longitudinal shrinkage. In hardwood trees, reaction wood forms typically on the upper side of the stem and is termed tension wood, characterized by woolly surfaces when machined and greater than normal longitudinal shrinkage.

RED KNOT

See Intergrown Knot.

RELATIVE HUMIDITY

The ratio of the amount of water vapor present in the air to that which the air would hold at saturation at the same temperature. Usually expressed as a percent. See also Absolute Humidity.

RESIN

Material secreted into resin canals of softwood trees. Also, a term applied to certain synthetic organic products (as used in glues and finishes) similar to natural resins. See also Pitch.

RESIN CANAL

Tubular passageways containing resin in the wood of certain softwood trees.

RIBBON FIGURE (RIBBON GRAIN. STRIPE FIGURE)

Figure apparent on an edge-grain surface of wood with interlocked grain, characterized by vertical bands of varying luster and vessel markings. See also Broken Stripe.

RIFT CRACK

See Heart Shake.

RIFT GRAIN (COMB GRAIN. NEEDLE-POINT GRAIN)

The surface or figure produced by a longitudinal plane of cut which is at approximately 45° to both rays and growth rings. The term is used especially for white oak with its large rays. The term comb grain is used where the vessel lines are parallel to the board edge and the rays produce a uniform pencil stripe.

RING-POROUS WOOD

Hardwood having relatively large pores concentrated in earlywood and distinctly smaller pores in latewood. See also Diffuse-Porous Wood.

RING SHAKE (RING FAILURE. SHELL SHAKE)

A separation of wood structure parallel to the growth rings, often in the first layer(s) of earlywood, usually occurring in the standing tree.

RIPPLE MARKS

Fine striations perpendicular to the grain, most apparent on a tangential surface, produced in wood with storied rays.

ROE FIGURE (ROEY GRAIN)

The appearance of a radial surface when stripes less than 1 ft. long are formed by irregular interlocked grain.

ROT

See Decay.

ROTARY-CUT VENEER (PEELED VENEER)

Veneer cut on a lathe by rotating a log against a fixed knife, which produces a continuous veneer sheet.

ROUND-EDGE LUMBER

Lumber having bark along both edges.

ROUND KNOT

The round or oval exposed section of a knot cut more or less crosswise to the limb axis. See also Spike Knot.

The water in a tree, including any dissolved nutrients and extractives.

SAPSTAIN

See Blue Stain.

SAPWOOD

The physiologically active wood comprising one to many outermost growth rings, usually lighter in color than heartwood.

SEASONING (CURING)

The process of drying wood.

SECOND GROWTH

Timber that has grown in an area following harvest or destruction of previous timber.

SELECT

In softwood lumber, the highest appearance grades are Select grades, usually separated as B and better, C, and D Select grades. In hardwood factory lumber, Selects is one specific grade, placing in quality below Firsts and Seconds, but higher than Common grades.

SEMI-DIFFUSE POROUS WOOD (SEMI-RING-POROUS WOOD)

Hardwood having fairly evenly distributed pores of gradually decreasing size from earlywood to latewood portions of the growth ring.

SHAKE

See Ring Shake, Heart Shake. Also, a hand-split shingle.

SHARPNESS ANGLE

The angle between the face and back of a cutting edge, usually designated by the Greek letter B.

SHEAR

A condition of stress (and resulting strain) acting to cause portions of an object to move or slide in parallel but opposite direction from one another.

SHELL

The outer portion of a board, equivalent to one-quarter the thickness. See also Core.

SHELLED GRAIN

See Loosened Grain.

SHELL SHAKE

See Ring Shake.

SHORT GRAIN

See Cross Grain.

SHORT IN THE GRAIN

Term sometimes used to describe brittle fractures in wood.

SHRINKAGE

Change in dimension due to loss of moisture below the fiber saturation point, expressed numerically as a percentage of green dimension.

SIDE GRAIN (SIDE CUT)

Same as Flatsawn. Also, any longitudinal surface, as opposed to end grain.

SILVER GRAIN

Figure produced by showy or lustrous ray fleck on a quartered surface.

SLAB

A broad, flat, thick piece of wood. Also, a surface cut from a log with bark on one side.

SLASH GRAIN (SLASH SAWN)

Same as Flatsawn.

SLICED VENEER

Veneer produced by moving a log or flitch vertically against a fixed veneer knife.

SLOPE OF GRAIN (GRAIN SLOPE)

A measurement of cross grain taken as the amount of grain deviation across a board in a measured distance along its length, expressed as a ratio such as 1 in. in 12 in., or 1 in 12. or simply 1:12.

SOFT ROT

A type of decay that develops under very wet conditions, as in docks or boat timbers, caused by fungi that attack the interior of the secondary cell wall.

SOFTWOOD (CONIFEROUS WOOD)

Wood produced by coniferous trees in the botanical group referred to as gymnosperms. Since these woods lack vessels, they are sometimes referred to as nonporous woods. (The term softwood does not necessarily refer to the actual hardness of the wood.)

SOLID PILING (BULK PILING)

Close stacking of lumber or other products, without separation of layers with stickers, as in open piling.

SOLITARY PORE

Pores that do not touch other pores but are surrounded completely by other types of cells as seen in cross section.

SOUND KNOT

A knot that is solid throughout and shows no sign of decay.

SOUND WOOD

Wood having no decay.

SPALTED WOOD

Partially decayed wood characterized by irregular discolorations appearing as dark zone lines on the surface.

SPECIFIC GRAVITY

The ratio of the weight of a body to the weight of an equal volume of water; relative density.

SPIKE KNOT

A knot cut more or less parallel to its long axis so that the exposed section is definitely elongated. See also Round Knot.

SPIRAL GRAIN

Cross grain indicated by grain deviation from the edge of a tangential surface, resulting naturally from helical grain direction in a tree or artificially by misaligned sawing.

SPRINGWOOD

Same as Earlywood.

STAIN

A discoloration in wood caused by stain fungi, metals, or chemicals. Also, a finishing material used intentionally to change the color of wood.

STAR SHAKE (STAR CHECK)

Multiple heart shake, having a more or less star effect.

STARVED JOINT

A poorly bonded glue joint, due to insufficient glue.

STATIC BENDING

Bending under a constant load or a slowly applied load.

STEEP GRAIN

Rather severe cross grain.

STICKERS

Wooden strips used to separate layers of lumber to permit air circulation.

STORIED RAYS

Rays whose arrangement (as viewed on a tangential section) is in horizontal rows. See also Ripple Marks.

STRAIGHT BANDS

Internal plies of plywood, other than the core ply, having grain direction parallel to that of the face plies.

STRAIGHT GRAIN

Indicating grain direction parallel to the axis or edges of a piece.

STRAIN

Unit deformation resulting from applied stress.

STRENGTH

The ability of wood to resist applied load.

STRESS

The force or load per unit area resulting from external loads as in a structure, or internal conditions as in drying.

STRIPE FIGURE (STRIPE GRAIN)

Same as Ribbon Figure.

SUMMERWOOD

See Latewood.

SUNKEN JOINT

A depression at a glue joint resulting from surfacing edge-glued material too soon after gluing.

SURFACE CHECKS

Checks that develop on a side-grain surface and penetrate the interior to some extent.

SWELLING

Increase in the dimensions of wood due to increase in moisture content.

T~

Symbol for tangential section or surface.

TANGENTIAL

Describing surfaces and sections of wood perpendicular to the rays and more or less parallel to the growth ring.

TANGENTIAL CUT

See Flatsawn.

TENSION WOOD

See Reaction Wood.

TERMINAL PARENCHYMA

Parenchyma cells located at the end of the growth ring, sometimes forming a conspicuous light line delineating the growth ring, as in yellow-poplar.

TEXTURE

Relative cell size indicated by adjectives from fine to coarse; in softwoods, determined by relative tracheid diameter; in hardwoods, determined by relative pore diameter. Also, sometimes used to indicate evenness of grain, e.g., "uniform texture" and uniformity in size and distribution of pores, e.g., even texture. See also Coarse Texture, Fine Texture.

THERMAL CONDUCTIVITY

The transfer of heat through a material by conduction: the K factor indicates the relative rate of thermal conductivity. The lower the K factor, the better the insulating properties and the poorer the conducting properties.

THERMAL EXPANSION

The increase in dimension of a material in response to increase in temperature.

TIGER GRAIN

Same as Curly Figure.

TIGHT KNOT

Same as Intergrown Knot.

TIGHT SIDE

Same as Closed Side.

TIMBER

Wood in standing trees having potential for lumber.

TISSUE

A group or mass of cells having similar function or a common origin.

TORN GRAIN

Same as Chipped Grain. Also, in plywood or veneer, a growth ring separation.

TRACHEIDS

Elongated conductive cells comprising more than 90% of softwood tissue; also found in some hardwoods.

TRANSVERSE SECTION (TRANSVERSE SURFACE)

Same as Cross Section.

TRUNK

The main stem of a tree. See also Bole.

TWIST

A form of warp in which the four corners of a flat face are no longer in the same plane.

TYLOSES

Bubblelike structures that form in the vessels of certain hardwoods, usually in conjunction with heartwood formation.

TYLOSIDS

Bubblelike structures that form in the resin canals of certain softwoods.

UNEVEN GRAIN

Wood with growth rings exhibiting pronounced difference in appearance between earlywood and latewood, as in southern yellow pine or white ash.

VASICENTRIC PARENCHYMA

Parenchyma that forms a complete sheath one to many cells thick around a vessel.

VENEER

Wood cut by slicing, peeling, or sawing into sheets $\frac{1}{8}$ in. or less in thickness.

VERTICAL GRAIN

Same as Edge Grain.

VESSEL

A conductive tube in hardwoods formed by end-to-end arrangement of cells whose end walls are open. The cross section of a vessel is called a pore.

VESSEL LINES

In hardwoods with fairly large diameter vessels, the visible lines produced on longitudinal surfaces wherever the plane of cut opens vessels lengthwise.

VIRGIN TIMBER (VIRGIN GROWTH)

Same as Old Growth.

WAFERBOARD

A panel product made of wafer-type flakes and having equal properties in all directions parallel to the surface of the panel.

WANE

Bark, or lack of wood from any cause, on the edge or corner of a piece of lumber.

WARP

Distortion of the intended shape of a piece of wood. See also Bow, Crook, Cup, Diamonding, Kink, and Twist.

WAVY BANDS OF PORES

Pores arranged in undulating bands approximately parallel to the growth rings, as in the latewood of elm and hackberry.

WAVY GRAIN (CURLY GRAIN)

Undulations of the grain direction creating horizontal corrugations on a radially (and sometimes tangentially) split surface.

WEATHERING

Discoloration and disintegration of wood surfaces due to environmental influences such as wind and dust, abrasion, light, and variations in precipitation and humidity.

WET-BULB DEPRESSION

The difference between dry-bulb and wet-bulb temperatures.

WET-BULB TEMPERATURE

The temperature as measured by a thermometer whose bulb is covered by water-saturated cloth, the evaporation from which lowers the temperature in relation to the relative humidity of the air.

WHITE ROT

Decay caused by a type of fungus that leaves a whitish spongy or stringy residue. See also Brown Rot.

WHORL

In coniferous trees, a group of branches that occurs at regular intervals or nodes along the main stem.

WITH THE GRAIN

Reference to cutting direction, as in planing a board surface, such that splitting ahead of the cutter follows the grain direction upward and out of the projected surface. See also Against the Grain.

WOOD (XYLEM)

The cellular tissue of the tree (exclusive of pith) inside the cambium.

WOOD SUBSTANCE

The solid material of which wood is composed, principally cellulose and lignin, exclusive of extractives and sap.

WOOLLY GRAIN (WOOLLINESS, FUZZY GRAIN)

Wood surfaces having wood fibers frayed loose, rather than severed cleanly, at the surface; commonly encountered in machining tension wood.

WORKING LIFE (POT LIFE)

The period of time after mixing during which an adhesive remains usable.

X

Symbol for cross section or cross-sectional surface.

XYLEM

Same as Wood.

ZONE LINES

See Spalted Wood.

BIBLIOGRAPHY

- Alexander, John D., Jr. *Make a Chair from a Tree: An Introduction to Working Green Wood*. Mendhara, NJ: Astragal Press, 1994. A lively and informative introduction to the old ways of splitting and shaping wood straight from the tree to make a light and beautiful, yet rugged chair. Alexander combines traditional methods with his own tested techniques to guide the reader through every step of this satisfying craft.
- Constantine, Albert, Jr. *Know Your Woods*. New York: Charles Scribner's Sons, 1975. Describes more than 300 species of wood, including source, tree and wood features, workability, and uses. Gives information on general tree structure, wood anatomy, and characteristics. Other chapters discuss edible tree products, poisonous trees, drugs from trees, official state trees, and woods of the Bible.
- Core, H. A., W. A. Cote, and A. C. Day. *Wood Structure and Identification*, second edition. Syracuse, NY: Syracuse University Press, 1979. Wood structure presented at gross, microscopic, and ultrastructural levels. Features outstanding photomicrographs and electron micrographs. Gives individual anatomical analysis for commercially important American species. Identification keys are based on hand-lens and microscopic features. Useful to wood identification students and to woodworkers as well.
- Elias, Thomas S. *The Complete Trees of North America: Field Guide and Natural History*. New York: Van Nostrand Reinhold Company. Outdoor Life/Nature Books, 1980. A comprehensive field identification guide based on both winter and summer keys and written in nontechnical language. Covers 652 native and 100 introduced species, and includes range maps and commentary on wood use that are of interest to anyone involved with wood.
- Fine Woodworking on Bending Wood. Newtown, CT: The Taunton Press, Inc., 1985. A compilation of 37 articles on the subject of bending wood, covering basic techniques and fixtures used in bending both cold and heated wood, plus specific instructions for making a variety of bentwood items from simple trays, boxes, baskets, and fishnet frames to furniture, instruments, and boats.
- Harrar, Ellwood S. *Hough's Encyclopaedia of American Woods*. Vols. I-XIII. New York: Robert Speller & Sons, 1957. A treasured classic, in limited supply. Each two-part volume covers 25 species. Part One is a ring binder containing transverse, radial, and tangential slices (1.6 in. by 3.7 in. by 0.01 in.) of actual wood tissue. Part Two is a bound edition of species descriptions.
- Haygreen, John G., and Jim L. Bowyer. *Forest Products and Wood Science*, third edition. Ames, IA: Iowa State University Press, 1996. Combines in one volume wood structure and properties as well as the technology of major wood and wood fiber products. Presented in four parts: *The Nature of Wood: Wood Properties and Modification of Quality*; *The Technology of Major Forest Products: and Wood as a Fuel and Industrial Raw Material*.
- Hoadley, R. Bruce. *Identifying Wood: Accurate Results with Simple Tools*. Newtown, CT: The Taunton Press, Inc., 1990. A practical guide to identifying 180 common woods. Physical features and properties of wood used in identification are explained in detail, followed by illustrated chapters on hardwoods, softwoods, and tropical woods. Identification is based on hand-lens inspection, with microscopic features provided as needed to confirm identification of more difficult woods.
- James, William L. *Electric Moisture Meters for Wood*. U.S.D.A., Forest Products Laboratory Gen. Tech. Rpt. FPL-6. Washington, D.C.: U.S. Govt. Printing Office, 1975. Reviews pertinent electrical properties of wood and the design, accuracy, operation, and maintenance of resistance and dielectric moisture meters. A list of commercial suppliers is also included. Electrical resistance values for wood are tabulated.
- Jewitt, Jeff. *Great Wood Finishes: A Step-by-Step Guide to Beautiful Results*. Newtown, CT: The Taunton Press, Inc., 2000. Detailed instructions on all aspects of finishing wood. Chapters on tools, finishing materials, and wood preparation are followed by step-by-step instructions for coloring wood, filling, glazing, applying finishes, rubbing out, and maintenance of finishes. A final section covers a variety of specialty finishes.
- Koch, Peter. *Utilization of Hardwoods Growing on Southern Pine Sites*. Volumes I, II, and III. U.S.D.A. Forest Service Agr. Handb. No. 605. Washington, D.C.: U.S. Govt. Printing Office, 1985. A companion to *Utilization of the Southern Pines*, this ambitious undertaking covers 30 southern hardwood species. Volume I, *The Raw Material*, discusses trees and the anatomy of their woods. Volume II, *Processing*, covers all phases from harvesting through lumber manufacture. Volume III, *Products and Prospective*, reviews current products and considers future trends in the resource.
- Koch, Peter. *Utilization of the Southern Pines*. Volumes I and II. U.S.D.A. Agr. Handb. No. 420. Washington, D.C.: U.S. Govt. Printing Office, 1977. An exhaustive compilation on the 10 species of southern pine. Volume I, *The Raw Material*, discusses the trees and the anatomical, physical, and mechanical characteristics of their woods. Volume II, *Processing*, covers all phases of processing technology from machining to finishing.
- Koch, Peter. *Wood Machining Processes*. New York: The Ronald Press Company, 1964. This highly technical approach to all aspects of wood machining includes analyses of orthogonal cutting and peripheral milling. Woodworkers will be interested in the detailed discussions of sawing, jointing, planing, molding, shaping, turning, boring, routing, carving, mortising and tenoning, and abrasive machining.

- Kollmann, Franz F. P., and Wilfred A. Cote, Jr. *Principles of Wood Science and Technology*. Vol. I. New York: Springer-Verlag, 1968. Perhaps the most comprehensive work on wood science and technology ever written. Although much of the material is highly technical, fundamentals are also thoroughly covered. Includes chapters on anatomical structure, chemical composition, defects, biological deterioration, wood preservation, physical properties, strength properties, seasoning, and machining.
- Kollman, Franz F. P., Edward W. Kuenzi, and Alfred J. Stamm. *Principles of Wood Science and Technology*. Vol. II. New York: Springer-Verlag, 1975. A companion to Volume I. This equally thorough treatise covers modified woods in all forms. Although many fundamentals are presented, the emphasis is on commercial processing technology. The six chapters discuss adhesion and adhesives for wood, solid modified wood, veneer and plywood, sandwich composites, particleboard and fiberboard.
- Kribs, David A. *Commercial Foreign Woods on the American Market*. New York: Dover Publications, Inc., 1968. A most useful guide to foreign woods. Descriptions of more than 350 species (including general properties, anatomy, and uses) are accompanied by photographs of transverse (10x and 80x) and tangential (100x) sections. Contains an illustrated glossary, bibliographies, and identification keys.
- Lee, Leonard. *The Complete Guide to Sharpening*. Newtown, CT: The Taunton Press, Inc., 1995. The best work on the subject of sharpening I have seen. Covers topics from the meaning of sharpness and the physics of cutting to abrasives and equipment, followed by instructions for sharpening specific types of tools. A bonus in the Appendix is a section of macrophotography showing the cutting action of tool edges on wood tissue.
- Little, Elbert L., Jr. *Checklist of United States Trees /Native and Naturalized*. U.S.D.A. Agr. Handb. No. 541. Washington, D.C.: U.S. Govt. Printing Office, 1980. Contains a compilation of scientific names and current synonyms, approved common names and others in use, and the geographic ranges of native (679 species) and naturalized (69 species) trees of the United States (excluding Hawaii). A principal authority on scientific and common names.
- Marra, Alan A. *Technology of Wood Bonding*. New York: Van Nostrand Reinhold, 1992. An in-depth philosophical as well as highly technical approach to synthesizing products through the bonding together of wood elements. Includes fundamentals of bond formation, critical characteristics of wood and adhesives, process considerations in applying adhesive and bond consolidation, quality control and evaluation, and troubleshooting. For the advanced practitioner.
- Mitchell, H. L. *How PEG Helps the Hobbyist Who Works with Wood*. U.S.D.A. Forest Products Laboratory. Washington, D.C.: U.S. Govt. Printing Office, 1972. Polyethylene glycol-1000 (PEG) is introduced as an agent for dimensional stabilization of wood. This booklet gives instructions for mixing PEG solutions, preparing treating vats, and drying and gluing wood. This booklet also explains how to treat turnings, green wood carvings, gunstocks, and statuary, and how to preserve archeological specimens.
- Panshin, A. J., and Carl deZeeuw. *Textbook of Wood Technology*, fourth edition. New York: McGraw-Hill Book Company, 1980. A traditional college-level text used in teaching wood anatomy and identification, essentially two books in one. Part One discusses wood anatomy and common defects in wood; Part Two includes identification features and keys. For each of 75 domestic woods there are photomicrographs with descriptions of gross and minute features.
- Peck, Edward C. *Bending Solid Wood to Form*. U.S.D.A. Forest Service. Agr. Handb. No. 125. Washington, D.C.: U.S. Govt. Printing Office, 1957. A concise presentation of the principles and practice of steam bending wood. Presents a clear mathematical explanation of the mechanics of bending and a ranking of the woods best suited for bending. Guidelines on selecting, seasoning, and machining bending stock, as well as procedures for plasticizing the wood and bending to form.
- Princes Risborough Laboratory. *Handbook of Hardwoods*, second edition, revised by R. H. Farmer. London: Her Majesty's Stationery Office, 1972. Describes hardwoods from around the world to assist users in selecting timber. Information is conveniently arranged under headings such as weight, strength, working properties, veneer, defects, durability, preservation, and uses. Full descriptions of 117 species, brief descriptions of 103. no illustrations.
- Random Lengths Terms of the Trade. Eugene, OR: Random Lengths Publications, 1978. A handy book of terminology for woodworkers. Terms used in reference to wood, woodworking, and lumber comprise the main section of the book, with a second section of related abbreviations. A third section is "Useful Information," such as lumber profile patterns, tree characteristics, and lumber volume tables.
- Rendle, B. J. *World Timbers: Volume 1, Europe & Africa. Volume 2, North & South America. Volume 3, Asia & Australia & New Zealand*. London: Ernest Benn Ltd., and Toronto: University of Toronto Press, 1969. 1970. Reissued from a series that originally appeared in the journal *Wood*, this comprehensive work describes more than 200 timbers of the world, each illustrated by a color photograph. Properties and characteristics are presented with a minimum of technical terms.
- Shelton, Jay, and Andrew B. Shapiro. *The Woodburners Encyclopedia*. Waitsfield, VT: Vermont Crossroads Press, 1976. An informative, readable source of theory, practice, and equipment for anyone interested in wood for heating. Includes comprehensive and technical information on fuelwood, stoves, chimneys, installation and safety, plus data on commercial stoves and other products.
- Simpson, William T. (ed.). *Dry Kiln Operator's Manual*, revised. Madison, WI: Forest Products Society, 1991. A comprehensive text on dry-kiln technology, with focus on conventional methods involved in drying lumber in a standard steam-heated compartment kiln. Valuable drying schedules are given for commercial species in common thicknesses.
- Smulski, Stephen (ed.). *Engineered Wood Products*. Madison, WI: PFS Research Foundation, 1997. Useful and practical information, in plain language, for architects, contractors, building officials, and others who design, specify, build, or inspect structures. A separate chapter is dedicated to each category of today's structural engineered wood products, plus chapters related to uses, quality assurance, and building codes. Appendix has a directory of associations and manufacturers.

- Her Majesty's Stationery Office, 1970. Covers hand- and machine-bending of solid wood, laminated bending, and plywood bending. Also discusses selection of material, preparation, softening and setting of bends, and explores the theory of optimum bending restraint. Tables of bending properties for numerous species are invaluable.
- Tsoumis, George. *Wood as Raw Material*. New York: Pergamon Press, 1968. A well-written text describing wood in macroscopic, microscopic, physical, chemical, and ultrastructural terms. Wood formation and degradation are reviewed. Identification keys for North American and European woods are accompanied by useful photographs and instructions for microscopic study of wood.
- U.S. Forest Products Laboratory. *Wood Handbook: Wood As an Engineering Material*, revised. FPL-GTR-113. Madison, WI: U.S.D.A. Forest Service, Forest Products Laboratory. 1999. Summarizes a broad spectrum of valuable information on wood as an engineering material. Presents descriptions and properties of important domestic and foreign woods and wood-based products of particular interest to the architect and engineer. Includes discussion of designing with wood and wood-based products.
- Williston, Ed M. *Lumber Manufacturing*. San Francisco: Miller Freeman Publications, Inc., 1976. A discussion of sawmilling, in both practice and principle, from the raw material to sawing, sorting, drying, and planing. Also covers design and operation of all types and sizes of mills, as well as saw characteristics, filing, and maintenance.
- Press, Inc., 1998. A well-organized and clearly written book on the subject, adapted with appropriate technical depth to small-shop practices. Each of the major generic glue types are discussed, and recommended procedures for various types of gluing application-are explained and illustrated.
- Youngquist, W. G., and H. O. Fleischer. *Wood in American Life. 1776-2076*. Madison, WI: Forest Products Research Society, 1977. Written by a former director of the U.S. Forest Products Laboratory, this book looks at the role of wood and wood products in shaping our nation's past, present, and future, combining an experienced scientific and technical viewpoint with exhaustive historical research.

INDEX

Page references in bold indicate photos; page references in *italic* indicate illustrations.

A

Abnormal wood, 36-39
 Absolute humidity, 111, *111*, 112
 Acacia, 105
 Adhesive joints, 193-94, **194**
 Advanced decay, 40-41
 African mahogany, **70**
 Air-dried wood:
 common woods drying time, *156*
 described, 114, 115
 moisture absorption of, 129-30
 Alder, **63**, 194
 American basswood, **65**
 American beech, **51**, **63**
 American chestnut, **60**
 American elm, **60**
 American hornbeam, 50, **50**
 American Society for Testing and Materials:
 compression parallel to grain test, 80, **80**
 shear testing, 85, **86**, **86**
 standards of, 78
 static bending test, 87-88, **88**
 tension parallel to the grain testing, **85**
 tension perpendicular to the grain testing, 83, **83**
 Ammonia, plasticizing with, 179
 Angiosperms, 16
 Anisotropic properties, 75, 78
 Annual rings. *See* Growth rings
 APA Engineered Wood Association, 230, 230
 Apical meristems, 8
 Apple:
 stabilizing with PEG, 137
 Ash:
 black ash, **22**
 flat sawn figure of, **27**
 gluing properties of, 194
 moisture content of, 115
 steam bending, 178
 white ash, **13**, **61**, 114
 Aspen:
 fluorescence of, 105
 as oriented strandboard (OSB), 238
 quaking aspen, **66**
 sapwood of, 12
 Avodire, **72**
 Axial stress, 78

B

Balanced construction, 135, **135**
 Bald cypress, **59**
 Balsa:
 cell structure of, **97**
 macrophotograph of, **71**
 moisture content of, 114
 Banded parenchyma, 51
 Barberry, 105
 Bark, 8-9, **9**
 Basswood, 11, **65**, 155, 194
 Bastard grain, 14

Beams:

bending testing of, 87-90
 cantilever, 87, 92-93, **93**
 carrying capacity of, 90-94
 defined" 87
 mechanics of, described, 87-90, **88**, **88**, **89**, **89**
 stiffness of, 90-94, *90-91*
 types of, 87

Beech:

American beech, **51**, **63**
 gluing properties of, 194
 moisture content of, 115
 shrinkage in, 118
 stabilizing with PEG, 137
 steam bending, 178

Bending theory:

beam mechanics described, 87-90, **88**, **88**, **89**, **89**
 bending stresses, 87-90
 fiber stress at proportional limit (FSPL), 79, 87-90
 shear and, 93-94, **94**, **94**
 stiffness of beams and, 90-94, *90-91*

Bending wood:

ammonia plasticizing, 177-79
 green wood, 177
 steam bending, 177-79, **177**, *177*, 178

Bigleaf maple, 30

Birch:

Finnish birch plywood, 233
 gluing properties of, 194
 moisture content of, 114-15
 paper birch, **45**, **66**
 pores in, 51
 sapwood of, 12
 steam bending, 178
 white birch, **27**
 yellow birch, **65**

Bird's-eye figures, 30, **30**

Black ash, **22**

Black cherry:

cell structure of, **22**
 macrophotograph of, **64**
 ray fleck in, **47**

Black gum, **67**

Black locust, **62**, 105

Black tupelo, 12

Black walnut:

color of, 12
 macrophotograph of, **62**
 stabilizing with PEG, 137

Blister figures, 30

Blockboards, 241

Blue-stain fungi, 42

Board feet, 216, *217*

Bole, 7, 9

Bore holes, 44-45

Boring bits, 172-73, *172*, *173*

Bound water, 112

Bow warps, 123, *123*

Brashness, 99, 99-100

Broken stripe figures, 29

Brown rot, 41, **41**

Burls, 30-31, **31**

Burning of wood, 104-105

Butternut:

gluing properties of, 194
 growth rings of, **27**, 50, **50**
 macrophotograph of, **62**
 stabilizing with PEG, 137

C

Cambial cells, 8-9

Cambium:

cell development in, 8-10
 and growth rings, 10
 in tree internal system, 9

Cantilever beams. *See* Beams

Cap irons, 164, **164**

Carpenter ants, 45

Carved wood, fluorescence of, 106, **108**

Case-hardened wood:

described, 148-49
 kiln-drying and, **149**, 151

Catalpa:

and cracking, 126
 heartwood width of, **13**
 moisture content of, **116**
 northern catalpa, 12, **61**
 ring-porous features of, **21**
 shrinkage in, 118

CCA (chromated copper arsenate), 211

Cedar:

eastern red, 12, **13**, **58**, **107**
 knots in, 35
 northern white, **58**
 Spanish, **58**
 western red, **58**

Cells:

coniferous, *18*
 daughter, 9 . 1 0
 described, 8
 in hardwoods, *20*
 mahogany, **8**
 parenchyma, 1 0
 structure of, 17-18, 17
 tracheid, 18

Cellulose, 10

Cell walls, 8

Central American mahogany, **69**

Chairs, joint changes in, 127-28

Checks:

described, 98, 123
 honeycomb checks, 148-49, **149**
 and kiln drying, 151
 knife, 169, *169*, 170, 226-28
 and stacking lumber, 153-54
 and uneven drying, 130, **130**, 148-49, **148**, **149**
 in veneer, 226-28

Chemical salts, 157, *157*

Cherry:

black cherry, **22**, **47**, **64**
 and cracking, 126
 flatsawn figure of, **27**
 gluing properties of, 194, 195
 sapwood of, 12
 stabilizing with PEG, 137

- Chestnut:
 American chestnut, 72, **60**
 flatsawn figure of, **27**
 gluing properties of, 194
- Chip formation:
 described, 160-61, **160**, **161**
 machining wood, 160-61, **160**, 162-63, **163**
 types of chips, 162-64, **162**, **163**
- Chip marks, 168, **168**
- Chipping headrigs, 214-16
- Chromated copper arsenate (CCA), 211
- Circular saws, 171-72, **171**
- Clamps, woodworking, **196**, 197
- Clearance angles, 160, **160**
- Coating treatments, 205-206
- Coefficient of thermal linear expansion, 104
- Collapse, 148, **149**
- Color, wood:
 in heartwood, 11-12
 wood identification and, 52
- Comb grain, 14
- Combination finishing treatments, 207, **207**
- Combination saws, 172
- Composite panels:
 described, 235-37, **237**
 hardboard, 114, 237, 238-39, **238**, **239**
 insulation board, 237-39, **239**
 medium-density fiberboard (MDF), 236, 239, **239**
 oriented strandboard (OSB), 237-38, **237**, **245**, **256**
 particleboard, 94, 114, 235-37, 236, **237**
 waferboards, 237-38, **237**
- Compression:
 and grain, 97
 parallel to grain, **77**, 79-80, **80**, 101
 perpendicular to grain, 80-83, **81**, **81**, **83**, 101
 properties of common woods, 79
- Compression failures, 99, **99**
- Compression set, 82, **82**
- Compression stress, 78, **78**
- Compression wood, 37-38, **37**, **38**
- Cone cutting, 27
- Conifers, 16
- Conks, 42, **43**
- Continuous beams. *See* Beams
- Cords, 104
- Core layer of wood, 148
- Cottonwood:
 macrophotograph of, **66**
 moisture content of, 114
 stabilizing with PEG, 137
- Cracking:
 described, **124**, 125-27
 and size, 127
 tangential shrinkage and, 125-26, **125**, **126**
- Creep, 95
- Creosote, coal-tar, 210
- Crook warps:
 defined, 123, **123**
- Crossbands, plywood, 229, **232**
- Crosscut sawing:
 described, 170-73, **170**, **171**
- Cross grain:
 defined, 95-96
 and wood strength, 95-96, **96**, 96
- Cross-sectional planes. *See* Transverse planes
- Crotch figures, 27
- Crown, 9
 defined, 7
- Cup warps:
 defined, 123
 and drying lumber, 151-52
 and shrinkage, 124, **124**
- Curly figures, 27-28, **28**
- Curly grain, 27
- Cutting action:
 0°-90°. 169, 169-70, **170**, 171
 90°-0°. 162-65, 762, **163**, **164**, **164**
 90°-90°, **162**, 168-69, **168**, 169, 171
 described, 160-61, 760, **161**
 against the grain, 163-64, **164**
 with the grain, 163, 764
- Cypress, 41, **59**
- D
- Decay, wood strength and, 98-99
- Deciduous trees:
 defined, 16
- Decorative laminates, 114
- Defects, wood strength and, 98-99
- Deliquescent tree forms, 16
- Dendritic tree forms, 16, **16**
- Density:
 defined, 14-15
 and wood identification, 52
 wood strength and, 97-98, **97**
- Density index. *See* Specific gravity
- Design, dimensional changes and, 139-41, 740
- Destructive distillation, 104
- Dew points, 112
- Diagonal grain, 96
- Diamonding warps, 723, 124
- Dielectric meters, 144, **144**
- Diffuse-porous woods, 21-22, **22**
- Dimensional changes:
 chemicals for, 136-39
 design and, 139-41, 740
 and joint grain direction, **182**, 183, 184-85
 mechanical restraints for, 134-36
 mitered joints and, 127, **127**
 moisture control and, 133-34
 moisture monitoring for, 141-45
 mortise-and-tenon joints and, 127-29, **128**, **129**
 preshrinking and, 133
 tangential shrinkage, 1 16, 776, 777
 total shrinkage formula, 116
- Dimpling figures, 29-30, **30**
- Douglas fir:
 density of, 97
 earlywood of, **19**, **48**
 and laminated veneer lumber, 243, **243**
 macrophotograph of, **56**
 and parallel strand lumber, **243**, 244
 plywood, 230
 pores in, 51
 quartersawn, **26**
 shrinkage of plywood, 135
- Dovetail joints, 186
- Dowel joints:
 described, 187-88, **187**, **188**
 dimensional changes in, 127-29, **128**, **129**
- Drying wood:
 described, **147**, 148-19, **148**, **149**
 dry kiln process, 149-51, 150, **150**
 and end-drying, 152
 importance of, 147
 in small quantities, 151-55
 stacking for, 152-54, 153, **154**, 754
 weight monitoring for, 155, 755
- Dry kilns:
 described, 149-50, **150**
 kiln schedule for, 150-51
- E
- Earlywood:
 in growth rings, 10, 50
 staining, **19**
 tracheid cells in, 18
- vessel elements of, 21
 wood strength of, 97
- Eastern hemlock, **57**
- Eastern hophornbeam, **96**, 118
- Eastern red cedar:
 color of, 12
 fluorescence of, **107**
 heartwood width of, **13**
 macrophotograph of, **58**
- Eastern spruce, **27**, **57**
- Eastern white pine:
 cell structure of, **20**
 as fuel, 105
 macrophotograph of, **55**
 resin canals of, **51**
 sapwood of, 12
 shrinkage in, 118
 uneven grain in, **11**
- Ebony, **73**
- Edge grain:
 described, 13
 growth rings and, **14**
 lumber production and, 215, 216
- Elm:
 American elm, **60**
 gluing properties of, 194
 pores in, 51
 stabilizing with PEG, 137
 steam bending, 178
- Encased knots, 33, **33**
- End-coating wood, 152
- End-grain surfaces, 13, 168-69, 168, 769
- Engineered wood:
 described, 241
 finger-jointed lumber, 241, **242**
 glulam, 241, 242-43, **242**
 I-joists, 244-45, **245**
 laminated strand lumber, 244, **244**
 laminated veneer lumber, 243-44, **243**, **245**
 parallel strand lumber, **243**, 244
 structural composite lumber, 243, **243**
- Equilibrium moisture content:
 described, 112-14
 and relative humidity, 112-14, 773
- Equilibrium relative humidity, 114
- Even grain:
 described, 11
- Excurrent tree forms, 16, **16**
- Extractives, 11, 12, **12**, 194
- F
- Face cords, 104
- Faces, plywood, 229, 231, 232, 233
- Fastened joints, 188-91
- Fibers, 21
- Fiber saturation points, 112
- Fiber stress at proportional limit (FSPL), 79, 87-90
- Fiddleback figures, 28, **29**
- Figures:
 bird's-eye, 30, **30**
 blister, 30
 broken stripe, 29
 burls, 30-31, 31
 crotch, 27
 curly, 27-28, **28**
 defined, 25
 dimpling, 29-30, **30**
 fiddleback, 28, **29**
 moonshine crotch, 27
 mottled, 29
 pigment, 31, **31**
 of quartersawn lumber, 26, **26**
 quilted, 30
 ribbon, 28-29, **29**

roe, 29
swirl crotch, 27

Finger-jointed lumber, 241. **242**

Finishes:
coating treatments, 205-206
combination, 207. **207**
evaluation of, 209, **209**
and moisture, 207, 208, 209
and PEG treated wood, 139
penetrating treatments, 206-207. **206**
preservative treatments, 209-211. **210**
staining uneven grain, 18, 19
and surface preparation, 199-202, **200**, 207, **201**
untreated wood, 202-205, **203**, **204**
water-based, 204

Finnish birch, 233

Fir, Western (true), **57**

Fixed-end beams. *See* Beams

Flat-grain, 14, 14

Flatsawn boards:
characteristics of, 26, 27, **27**
described, 14
growth rings and, **14**
and uneven grain, 18

Flexure formula, 87

Fluorescence:
carved wood and, 106, 108
of common woods, 105-107. **107**
defined, 105-107

Forest management, 254-56

Free water, 112

Freshly cut wood, 115

FSPL (fiber stress at proportional limit), 79, 87-90

Fungal resistance, heartwood, 12

Fungi, wood-inhabiting:
described, 40-43, **40**, **41**, **42**, **43**
and preservative treatments, 209-211
and wood strength, 98-99

G

Ginkgo, 16

Glues:
adhesive joints, 193-94, 194
common woods and gluing properties, 194
described, 193-97, 194, 197
glue properties, 194-97. **197**
and PEG treated wood, 137
shear test for, 87, **87**, **87**
and woodworking clamps, 196, 197

Glulam, 241. 242-43, **242**

Grain:
bastard grain, 14
comb grain, 14
cross grain, 95-96, **96**, **96**
cutting action and, 160. 162-64. 163, 764
described, 10-11. 13
diagonal grain, 96
edge grain, 13, **14**, 215-16
end grain surfaces, 13. **168**, 168-69. 769
even grain, **11**
flat grain, 14, 74
lash grain, 14
mixed grain, 14
and peripheral milling, 167, **167**
quarter grain, 13
radial grain, 13
roey grain, 29
sawing effects on, 25-26, **25**
shelled grain, 167
side grain, 13, 14
straight-grained wood, 95
and thermal conductivity, 104
ton, 163-64

uneven grain, **11**, 18
vertical grain, 13
and wood strength, 95-98. **96**. **96**. **97**
woodworking usage of, 11
See also Compression: Figures: Grain direction

Grain direction:
described, 10-11. 27
and joints, 181. 7S2. 183. 184-85
rays and, 96
and temperature, 104

Greenheart, 118

Green wood:
defined, 115
measuring moisture in, 144-45
and PEG treatments, 138

Growth rings:
described, 8, 10, 10
fluted, 27. **27**
lumber face orientation and, 13-14
number in common hardwoods, 12
structural arrangement of, 12-14
and wood identification, 50. **50**

Gymnosperms, 16

H

Hackberry, 51, 178

Handplanes, 162. **162**. **164**. 165

Hardboard:
described, 237. 238-39. **238**. **239**
moisture content of, 114

Hardness, wood identification and, 52

Hardwood Plywood & Veneer Association (HPVA), 233

Hardwoods:
cell structure of, 17
characteristics of, 20-23
grading associations, 227
lumber grades of, 218-21. 279. **220**. **221**
lumber production of, 216
moisture content of, 114-15. **115**
penetration treatments of common, 270
and plant classification, 16-17
plywood, 231. 232-33. **232**
and resin, 19
wood strength of, 97. **98**

Heartwoods:
and cracking, 125-26. **125**, **126**. 131
decay resistance of, 44
described, 11-12. **12**
fluorescence of, 105
fungal resistance of, 12
moisture content of, 114-15
width of, 12. **13**
and wood identification, 50
wood strength of, 98

Heating with wood, 105, 254

Hemlock, **57**, **243**, 244

Hickory:
as fuel, 105
gluing properties of, 194
pores in, 51
shagbark hickory, **61**, 129
shrinkage in, 118
stabilizing with PEG, 137
steam bending, 178

Hollow grinding, 176, 776

Holly, 105

Homosote, 239

Honeycomb checks, 148-49, **149**

Honey locust, 105

Hooke's Law, 76-77

Horizontal shear, 93, 94-95, **94**. **94**

HPVA (Hardwood Plywood & Veneer Association), 233

Humidity. *See* Relative humidity

Hygrometers, 141-12, **142**, **143**, **144**, 145, **145**

Hyphae, 42, 43

Hysteresis, 113

I

Idaho white pine, 222

Identification, wood:
cutting for, 49-50, **49**, **50**, **50**
described, 47
macrophotographs of common species, **55-73**
macroscopic, 48, **49**
microscopic examination, 47-48, **47**, **48**, **49**
and structural properties, 50-52
techniques for, 52-54

I-joists, 244-45, **245**

Incipient decay, 40

Indian rosewood, **68**

Inner bark, 7

Insect damage to wood, 44-45

Insulation boards, 237-39. **239**

Insulation properties, 104

Intergrown knots, 33

J

Jelutong, **71**

Joints:
adhesive, 193-94, 194, 794
dovetail, 186, 786
dowel, 187-88, **187**, **188**
elements of, 181-83
fastened, 188-91
miter, 186, **187**
nails and, 189-90, **190**, **190**
woodscrews and, 191, 797
worked, 183
See also Dimensional changes; Mortise-and-tenon joints

Juvenile wood, 36, **36**, 38

K

Kentucky coffeetree, 105

Keys, wood identification, 52-53, 53

Kiln-dried wood:
described, 114
and moisture content, 115-16
and resin, 19, **19**
stress sections, **149**, **150**, 151

Kink warps, 123, **123**

Knife checks:
described, 169, 769, 170
and veneer production, 226-28

Knotholes, 33, **33**

Knots:
described, 32-35, **32**
encased, 33, **33**
intergrown, 33
knotholes, 33, **33**
locating, 34-35, 35
and lumber production, 214
pin, **34**, 98
round, **34**
sawing and, 34
spike, **33**, **34**, 98
value of, 34-35
and wood strength, 98

L

Lacewood, **26**

Lacquers, 204

Laminated strand lumber, 244, **244**

Laminated veneer lumber, 243-44, **243**, **245**

Lash grain, 14

Lateral meristems, 8

- Latewood, 10, 18, 50
 Lignin, 10
 Lignum vitae, **73**
 Load, time under, 79, 95
 Locust, 12, **62**, 105
 Longitudinal cells:
 defined, 8
 and grain, 10-11
 in hardwoods, 21-22
 Longitudinal shrinkage, moisture content vs., 118
 Longitudinal splines, 188, **188**
 Longitudinal surfaces, 13
 Lumber:
 chipping headrig, 214-16
 classification, 218, **218**
 commercial names for common species, 257
 common terms abbreviations, **214**
 edge grain, 215-16
 face orientation, 13-14
 finger-jointed, 241, **242**
 grading of, 218-23, **218**, **219**, **220**, **221**, **222**, **223**
 grain and, 12-14
 hardwood grading, 218-21, **219**, **220**, **221**
 knots in, 214
 laminated strand, 244, **244**
 laminated veneer, 243-14, **243**, **245**
 measure of, 216, **217**, **222**
 parallel strand, **243**, **244**
 production process of, 213-16, **215**, 216
 quartersawn, 13, **14**, 26, **26**, 214-16, **215**
 sawing patterns of, 213, **213**, 214
 stacking, 153-54
 standard American sizes of, 217
 storage of, 156-57
 structural composite, 243, **243**
 types of, 213
 See also Engineered wood
 Luster, 52
- Machine planing. See Peripheral milling
 Machine stress grading, 101
 Machining wood:
 chip formation, 160-61, **160**, 162-63, **163**
 cutting action types, 161-73, **161**, **162**, **163**, **164**, **164**, **165**, **165**, **166**, **166**, **167**, **168**, **168**, **169**, **170**, **171**, **172**, **173**
 described, 159-60
 tools for, 160, **160**
 tool sharpness, 174-76, **174**, **174**, **175**, **176**, **176**
- Macrophotographs of common species, **55-73**
 Macroscopic identification of wood, 48, **49**
 Mahogany:
 African mahogany, **70**
 cells of, **8**
 Central American mahogany, **69**
 figures in, **29-30**
 gluing, 194
 shrinkage in, **118**
- Mansonia, **72**
 Maple:
 bigleaf, 30
 gluing properties of, 194
 rays of, **51**
 red maple, **64**, **96**
 sapwood of, 12
 silver maple, **64**
 soft maple, 137, 194
 tiger, 28
 See also Sugar maple
 Masonite, 238
 Medium-density fiberboard (MDF), 236, 239, **239**
- Medullary spots, 44, **45**
 Meristematic tissue, 8
 Meristems, 8
 Microllam, 243
 Microsharpening, 175-76, **175**
 Mitered joints, dimensional changes and, 127, **127**
 Miter joints, 186, **187**
 Mixed grain, 14
 Modulus of elasticity:
 described, 77-78
 wood strength properties and, 101
 Moisture:
 finishes and, **208**
 and strain limits, 84
 and wood fungi, 42
 and wood strength, 95, **95**
 Moisture content:
 averages of, **134**, **135**
 of common wood species (green), **115**
 defined, 111
 and home building, 121, 122-23, **122**
 and kiln-dried wood, 114
 measuring for, 142-45, **144**, **145**
 and shrinkage, 119-23, **119**
 and steam bending, 178
 values, **116**
 of wood products, 114
 Moisture control:
 mechanical restraints for, 134-36
 need for, 133-34
 using chemicals, 136-39, **137**, **138**
 Moisture gradient, 149
 Moisture meters, 142-45, **144**, **145**
 Moonshine crotch figures, 27
 Mortise-and-tenon joints:
 and compression, 82, **82**, 129, **129**
 described, 183-86, **184**, **185**, **186**
 dimensional changes in, 127-29, **128**, **129**
 Mottled figures, 29
 Mycelium, 42, **43**
- N
 Nails, 189-90, **190**, **190**
 Neutral axis, 87
 Nonporous woods, 21
 Northern catalpa, 12, **61**
 Northern red oak, **126**, **130**
 Northern white cedar, 12
 shrinkage in, 118
- Oak:
 gluing properties of, 194, 195
 northern red oak, **126**
 overcup, 118
 rays of, **8**
 shrinkage in, 118
 stabilizing with PEG, 137
 white oak, **60**, 137, 178
 See also Red oak
 Obeche, **71**
 Odor, wood identification and, 52
 Oriented strandboards (OSB), 237-38, **237**, **245**, 256
 Orthogonal cutting:
 defined, 161
 types of, 161-70, **162**, **173**
 Osage-orange, 194
 OSB (oriented strandboard), 237-38, **237**, **245**, 256
 Oven-dried wood, 142
 Overcup oak, 118
 Overlays, plywood, 229
 Oxygen, wood fungi and, 42
- P
 Padauk, **68**
 Paper birch, **45**, **66**
 Parallam, 244
 Parallel strand lumber, **243**, 244
 Parallel to the grain shear, 85, 85-87, **86**, **86**, **87**, **87**, 101
 Paratracheal vasicentric parenchyma, 51
 Parenchyma, 10, 51
 Particleboards:
 described, 235-37, **236**, **237**
 future of, 256
 horizontal shear and, 94
 moisture content of, 114
 Pecan, 194
 Pecky cypress, 41
 PEG (polyethylene glycol):
 safety of, 138
 stabilization using, 136-39, **137**, **138**
 Penetrating treatments, 206-207, **206**
 Peripheral milling:
 cutting action of, 165, **165**, 765
 defined, 161
 knife jointing in, 166-67, **166**, 766
 and raised grain, 167, **167**
 Permanent tissue, 8
 Perpendicular to the grain shear, 85
 Persimmon, 194
 Photosynthesis, 8
 Pigment figures, 31
 Pine:
 drying of, 155
 knotty, 35
 moisture content of, 114
 ponderosa pine, 211
 stabilizing with PEG, 137
 sugar pine, **55**
 See also Eastern white pine; Red pine; Southern yellow pine; Western white pine; White pine
 Pin knots, 34, **34**, 98
 Pitch, products from, 20
 Pitch pockets, **19**
 Pith, 8, 151
 Pith flecks, 44, **45**
 Plain grain, 14
 Planing, end-grain surfaces, 168-69, 768, 769
 Planing, machine. See Peripheral milling
 Planing across the grain. See Cutting action
 Plant kingdom, classification system described, 16-17
 Plasticizing wood. See Steam bending
 Plastic-resin glues, 194
 Plywood:
 classes of, 230-33, **230**, **231**
 described, 229, 229, 237
 future of, 256
 grades of, 232-33, **233**
 horizontal shear and, 94-95
 and shrinkage, 135
 Polyethylene glycol (PEG):
 safety of, 138
 stabilization using, 136-39, 737, **138**
 Polymerization, 139
 Polyurethane glues, 194
 Polyvinyl acetate emulsions (PVA), 194
 Ponderosa pine, 211
 Poplar, 194
 See also Yellow poplar
 Pores, wood identification and, 51
 Porous woods, 21
 Powder-post beetles, 44-45
 Preservative treatments, 209-211, 270
 Preshrinkage of wood, 133

- Proportional limit:
 and compression strength. 80-81
 and stress, 76-77
 wood strength properties and. 101
 Prosenchyma, 10
 Psychological properties of wood, 107-109
 Purpleheart, **68**, 105
 PVA (polyvinyl acetate emulsions), 194
 Pyrolysis, 104
- Q
 Quaking aspen, **66**
 Quarter-grain, 13
 Quartersawn lumber:
 defined. 13
 and figure, 26, **26**
 growth rings and, 14
 production of, 214-16, 215
 Quilted figures, 30
- R
 Radial grain, 13
 Radial planes, 12-13, **13,17**
 Radial shrinkage:
 along the grain, **118**
 of common woods, 117
 described, 118
 and growth rings, 124-25, 725
 vs. moisture content, 118
 vs. tangential shrinkage, 124-25, **124, 125, 725**
 Rake angles, 160, 160
 Raker teeth, 171, 777, 172
 Ramin, **72**
 Ray flecks:
 described, 23, **23**
 sawing effects on, 26, **26**
 Rays:
 defined, 8, **8**
 and grain direction, 96
 in hardwoods, 20, **21**, 22-23
 in softwoods, **20**
 and wood identification, **51, 51**
 Reaction wood:
 described, 36-37, **36, 39**
 and shrinkage, 130-31, **131**
 Red alder, **63**
 Red knots, 33
 Red maple, **64, 96**
 Red oak:
 burls in, **31**
 cell structure of, **21**
 knots in, **35**
 macrophotograph of, **59**
 shrinkage in, **118**
 stabilizing with PEG, 137
 structure of, **7, 49**
 Red pine:
 cracking in, **126**
 structure of, **7**
 tangential shrinkage in, 125-26, **125**
 Redwood:
 finishing, 205
 macrophotograph of, **58**
 shrinkage in, 118
 stabilizing with PEG, 137
 Relative humidity:
 defined, 111-12
 and equilibrium moisture content, 112-14, 773
 indoors, 114, 156-57, 157
 measurement of, 141-42, **142, 143, 143**
 and shrinkage, 779
 using chemical salts, 157, 757
- Resin canals:
 described, 18-20, **19**
 and wood identification, 51, **51**
 Resistance, strength and, 76
 Resistance meters, 142-44, **144**
 Ribbon figures, 28-29, **29, 30**
 Rift-cut boards, 26, **26**
 Rift grain, 14
 Ring checks, 98
 Ring-porous woods, 21, **22**
 Ripsawing:
 cell structures and, **170**
 as 90°-90° cutting action, 168, 769
 Roe figures, 29
 Roey grain, 29
 Rolling shear, 86
 Root system, tree, 9
 Rosewood:
 cell structure of, **97**
 color of, 12
 drying of, 155
 figure in, 31
 gluing, 194
 Indian rosewood, **68**
 Rot, 40-42, **41, 42**
 Round knots, 34, **34**
- S
 Sanding wood, 200-202, **200, 201**, 207
 Sap, 8, 10, 112
 Sapstains:
 described, 40, **40**
 Sapwoods:
 and cracking, 125-26, **125, 126**, 131
 described, 10, 11, 12
 fluorescence of, 106
 fungal resistance of, 12
 moisture content of, 114-15, 775
 preservative treatments and, 211
 width of, 12, 12, **13**
 Satinwood, **73**
 Sawing wood:
 and circular saws, 171-72, **171**
 and combination saws, 172
 and grain appearance, 25-26, 25
 at lumber mills, 213-14, 275
 ripsawing, 168, 769, **170**
 setting a saw, 168, 769
 and table saws, 169, 169
 Scratcher teeth, 171, 171
 Secondary walls, cell, 10
 Semi-ring porous woods, 22
 Shagbark hickory, **61**, 129
 Shakes, 98
 Sharpness, tool, 174-76, **174, 174, 175, 176, 776**
 Sharpness angles, 160, 760, 174, **174, 174**
 Shear:
 horizontal, 93, 94-95, **94, 94**
 parallel to the grain, 85-87, 85, **86, 86, 87, 87**, 101
 perpendicular to the grain, 85
 properties of common woods, 79, 101
 rolling, 86
 stress, 78, 78
 wood adhesives and, 87, **87, 87**
 Shell, 148
 Shellacs, 204
 Shelled grain, 167
 Shrinkage:
 chemicals to stabilize, 136-39, 137, **138**
 and cup warping, 124, **124**
 described, 116
 diamonding warps and, 124
 estimating, 118-23, 119, 120, 121, 122
 vs. moisture content, 778
- of particleboard, 237
 of plywood, 135, 237
 radial, 117, 118, 118, **118**, 124-25, **124, 725**
 and reaction wood, 130-31, **131**
 tangential, 116, 117, 118, **118**, 124-25, **124, 725**
 tangential to radial ratio, 117, 118, **125**
 total shrinkage formula, 116
 transverse, 118
 uneven, 123-31, **130**
 Side grain, 13, 14
 Silver grain, 26
 Silver maple, 12
 Simple beams. *See* Beams
 Sitka spruce, **27**
 Slash grain, 14
 Slicewood, 225
 Sling psychrometers, 142, **143**
 Slope of grain, 96, **96**
 Soft maple, 137, 194
 Softwoods:
 cell structure of, **17**
 grading associations, 227
 lumber grades of, 221-22, **223**
 lumber production of, 216
 penetration treatments of common, 270
 and plant classification, 16
 plywood, 226, 230-32
 and resin, 18-19, **19**
 resin canals in, 19
 spheres in, **22**
 wood strength of, 97, 98, **98**
 Southern yellow pine:
 flatsawn figure of, **27**
 growth rings in, **10**
 and laminated veneer lumber, 243, **243**
 macrophotograph of, **56**
 and parallel strand lumber, **243, 244**
 uneven grain in, **11**
 wood strength properties for, 101
 Spalted wood, 42
 Spanish cedar, **69**
 Specific gravity, 14-15, 74, 232
 Spermatophytes, 16
 Spiked knots, **33**, 34, 98
 Spiral grain, 96, **96**
 Splits, 98
 Springwood. *See* Earlywood
 Spruce:
 color of, 12
 eastern spruce, **27, 57**
 knots in, 35
 pitch pockets in, **19**
 sitka spruce, **27**
 stabilizing with PEG, 137
 white spruce, 113, 113
 Staghorn sumac, 106, **107**
 Staining, uneven grain and, 18, **19**
 Standard cords, 104
 Static bending properties of common woods, 79, 101
 Steam bending, 177-79, **177, 777, 778**
 Stems. *See* Trunks
 Stickers, 152, **153**
 Straight-grained wood, 95
 Strain:
 defined, 75
 tension parallel to the grain, 84-85, 85
 Strength, wood:
 bending theory, 87-90, 88, **88, 89, 89, 90-97**
 brashness, 99-100, **99**
 calculating, 76
 compression failures, 99, **99**
 compression parallel to grain, **77, 79-80, 80**
 compression perpendicular to grain, 80-83, 81,
81, 83

- compression test and, 76
 defined, 75-78
 elasticity of wood and, 77, 83-84, 84
 factors affecting, 94-99, 95, **96**, 96, **97**, **98**
 Hooke's Law and, 76-77
 properties of common woods, 79
 shear parallel to the grain, 85-87, 85, **86**, 86,
87, 87
 shear perpendicular to the grain, 85
 stress-strain curve, 78, 78
 structural grades and, 100-101
 and temperature, 104
 tension parallel to the grain, 84-85, 85
 tension perpendicular to the grain, 83-84, **83**, 84
 types of, 78
 and Young's Modulus, 77-78
- Stress, and drying wood, 148-49, **149**, 151
 Stress ratings, 100-101
 Stress sections, **149**, **150**, 151
 Stress shear, 78, 78
 Stress-strain curve, 78, 78
 Stropping cutting edges, 175, 176
 Structural composite lumber, 243, **243**
 Structural grades, 100-101
 Sugar maple:
 bird's eye figure in, **29-30**
 curly figure of, **28**
 macrophotograph of, **64**
 stabilizing with PEG, 137
 white rot in, **42**
- Sugar pine, **55**
 Summerwood, 10, 18
 Surface preparations, 199-202, **200**, **201**, **201**
 Sweetgum:
 figure in, 31, **31**
 gluing properties of, 194
 macrophotograph of, **67**
- Swelling:
 and compression shrinkage, 82, 83
 and elastic limit strain, 82, 82
 and temperature change, 104
- Swirl crotch figures, 27
- Sycamore:
 macrophotograph of, **63**
 ray fleck of, **23**
 rays of, **51**
- Table saws, cutting action of, 169, 169
 Tack rags, 202
 Tamarack, **56**
 Tangential-grained lumber, 14
 Tangential planes, 12-13, **13**, **17**
 Tangential shrinkage:
 along the grain, **118**
 of common woods, 117
 cracking and, 125-26, **125**, **126**, 127
 described, 116, 116
 and growth rings, 124-25, 125
 and joints, 184
 vs. moisture content, 118
 vs. radial shrinkage, 124-25, **124**, **125**, 125
- Teak:
 gluing, 194
 macrophotographs of, **69**
 shrinkage in, 118
- Temperature:
 effect on wood, 104-105
 and equilibrium moisture content, 113
 and wood burning, 104-105
 and wood strength, 95
- Tensile stress, 78, 78
 Tension parallel to the grain, 84-85, 85
 Tension perpendicular to the grain, 83-84, **83**, 84
- Tension properties of common woods, 79
 Tension wood, 38, **39**
 Terminal parenchyma, 51
 Termites, 45
 Thermal conductivity, 103-104
 Thermal linear expansion, coefficient of, 104
 Thermal properties of various materials, 103-104
 Tiger maple, 28
 Tight knots, 33
 Tissue, 8
 Tracheid cells, 18
 Transpiration, 8
 Transverse planes, 12-13, **13**, **17**
 Transverse shrinkage, 118
 Tree internal system, 9
 Trees, 7, 9
 Trunks:
 and abnormal wood, 36-38, **36**
 described, 7-8
 in tree's internal system, 9
- Tung oil, 207
 Tupelo, **67**
 Twist drills, 173, 173
 Twist warps:
 defined, 123, 123
 in reaction wood, 130-31, **131**
- Tyloses:
 described, 22, 23
 and wood identification, 51
- U**
- Uneven drying, shrinkage caused by, 130, **130**
 Uneven grain:
 in conifers, 18, **19**
 described, 11, 11
 staining of, 18, **19**
- U.S. Forest Products Laboratory, 138, 207, 208, 209
 Untreated wood, 202-205, **203**, **204**
- V**
- Variability, wood strength and, 97-98, **97**, **98**
 Varnishes, 204-206
 Veneer:
 cutting action and, 169-70, 169, **170**
 described, 225
 knife checks in, 226-28
 production process, 225-28, 226, **227**, 227, **228**
- Vertical grain, 13
 Vessel elements, 21, 22
- W**
- Waferboards, 237-38, **237**
 Walnut, **31**, 178, 194, 195
 black walnut, 12, **62**, 137
- Warp:
 in common woods, 123
 defined, 123, 723
 shrinkage and, 124, **124**
 types of, 123, 725, 124, **124**, 130-31, **131**, 151-52
- Weathering, wood, 204-205, **204**
 Western fir (true), **57**
 Western hemlock, **243**, 244
 Western red cedar, **58**
 Western white pine, 222
 White ash:
 heartwood width of, **13**
 macrophotograph of, **61**
 moisture content of, 114
 White birch, **27**
 White lauan, **70**
 White oak:
 macrophotograph of, **60**
 stabilizing with PEG, 137
 steam bending, 178
- White pine:
 Idaho white pine, 222
 sapstain fungi in, **40**
 stabilizing with PEG, 137
 western white pine, 222
 See also Eastern white pine
- White rot, **41**, 41-42, **42**
 White speck, 41, **41**
 White spruce, 113, 773
 Willow, 137
 Wood:
 described, 8
 freshly cut, 115
 future of, 254-56
 historical uses of, 254-55
 supply of, 254-56
- Wood adhesives. See Glues
 Wood-plastic composites (WPC), 139
 Wood preservatives, 209-11
 Woodscrews, joints and, 191, 191
 Wood sources:
 industrial arts teachers, 253
 Internet, 253
 local sawmills, 250-51, **250**
 lumbermen, 253
 lumberyards, 251-52, **251**, **252**
 magazines, 253
 recycled wood, 249-50
 retail, 252-53
 for specialty woods, 253
 trees, 247-49, **247**, **248**, **249**
 Yellow Pages, 253
- Wood tissue, 8
 Woolly grain, 167, **168**
 Worked joints, 183
 WPC (wood-plastic composites), 139
- Y**
- Yellow birch, **65**
 Yellow glues, 194
 Yellow meranti, **70**
 Yellow-poplar:
 macrophotograph of, **65**
 and parallel strand lumber, **243**, 244
 ray fleck in, **47**
 stabilizing with PEG, 137
- Yucca, 105
- Z**
- Zebra wood, 31
 Zone lines, 42

UNDERSTANDING WOOD

A CRAFTSMAN'S GUIDE TO
WOOD TECHNOLOGY

Praise for the first edition

"Not 1 craftsman in 100 could know a quarter of the information Hoadley has collected in this handsomely illustrated volume. All of it will likely grip the attention of the woodworker as firmly as a bench vise."

—*American Forests*

"The truly serious woodworker needs a knowledge of his material and the best place to get it is in Bruce Hoadley's *Understanding Wood*."

—UPI wire and *Chicago Sun-Times*

"Hoadley has done an excellent job of culling and pulling together in a practical way a vast amount of information."

—*Library Journal*

